

---

**[Not translated]**

Characterization of bulk materials - Determination of a sizeweighted fine fraction and crystalline silica content - Part 3: Calculation method

Charakterisierung von Schüttgütern - Bestimmung einer größenengewichteten Feinfraktion und des Anteils an kristallinem Quarz - Teil 3: Berechnungsverfahren

**Ta slovenski standard je istoveten z: prEN 17289-3**

---

**ICS:**

13.040.30	Kakovost zraka na delovnem mestu	Workplace atmospheres
-----------	----------------------------------	-----------------------

**oSIST prEN 17289-3:2019****en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/39789009-ea41-42c4-9f83-64edc81f1621/osist-pr-n-17289-3-2019>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 17289-3**

January 2019

ICS 13.040.30

English Version

## Characterization of bulk materials - Determination of a sizeweighted fine fraction and crystalline silica content - Part 3: Calculation method

Charakterisierung von Schüttgütern - Bestimmung  
einer größengewichteten Feinfraktion und des Anteils  
an kristallinem Quarz - Teil 3: Berechnungsverfahren

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 137.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning :** This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	6
Introduction .....	7
1 Scope .....	9
2 Normative references .....	9
3 Terms and definitions .....	9
4 Symbols and abbreviations .....	9
5 Assumptions.....	10
6 Determination of SWFF and SWFF <sub>cs</sub> by sedimentation .....	11
6.1 Determination of sedimentation time .....	11
6.2 Selection of sedimentation liquid .....	12
6.3 Sample preparation, sedimentation and SWFF determination.....	12
6.4 Use of a dispersant or deflocculant .....	13
6.5 Determination of the SWFF and SWFF <sub>cs</sub> of mixtures of phases with different densities....	14
6.6 SWFF of mixtures .....	14
6.7 SWFF <sub>cs</sub> of mixtures of homogeneous particles .....	14
6.8 SWFF <sub>cs</sub> of mixtures of heterogeneous particles .....	14
Annex A (informative) Separation of the SWFF by sedimentation.....	16
A.1 Derivation for calculating the sedimentation parameters .....	16
A.1.1 General.....	16
A.1.2 Integral of $R(D)$ .....	17
A.1.3 Integral of $S(D)$ .....	17
A.2 Calculation of the SWFF after sedimentation.....	19
Annex B (informative) Determination and isolation of the size-weighted fine fraction (SWFF) of kaolins and kaolinitic clays by sedimentation.....	21
B.1 General.....	21
B.2 Application range.....	21
B.3 Equipment and consumables.....	21
B.3.1 Beakers, (preferably glass) or similar containers to hold, about 3 l by volume .....	22
B.3.2 Buchner vacuum flask, (preferably glass) of more than 2 l volume with implosion protection .....	22
B.3.3 Water bath, with temperature control to $\pm 1^\circ\text{C}$ to accommodate the 3-l-glass beakers (a bath that holds three to four beakers gives a good compromise between taking up too much bench space and adversely affecting sample throughput).....	22
B.3.4 Siphon tube, as described and shown in Figures B.1 to B.3 (alternatively, a curved glass-siphon can be used as well).....	22
B.3.5 Demineralized (deionised) water .....	22
B.3.6 Analytical balance, capable for weighing with an accuracy of 0,001 g .....	22

B.3.7	Ultrasonic bath or shaker .....	22
B.3.8	Dessicator .....	22
B.3.9	Oven, with temperature control to maintain at temperature of $(105 \pm 5) ^\circ\text{C}$ .....	22
B.3.10	Buchner filter assembly, flask and funnel for filtering fine fraction .....	22
B.3.11	Filter papers, with slow speed and hardened high retention (fine crystalline) .....	22
B.3.12	Filter assembly, suitable for use with mixed cellulose ester filter membranes .....	22
B.3.13	Filter membranes, $0,8 \mu\text{m}$ (or finer) mixed cellulose ester filter membranes .....	22
B.3.14	Evaporating basins .....	22
B.3.15	Dispersant, e.g. sodium hexametaphosphate (calgon), sodium polyacrylate .....	22
B.3.16	Sodium carbonate solution, diluted, about 10 % volume concentration, for pH adjustment .....	22
B.3.17	Sulphuric acid, diluted, about 10 % volume concentration, for pH adjustment .....	22
B.4	Method .....	22
B.4.1	Step 1 .....	22
B.4.2	Step 2 .....	22
B.4.3	Step 3 .....	23
B.4.4	Step 4 .....	23
B.4.5	Step 5 .....	23
B.4.6	Step 6 .....	23
B.4.7	Step 7 .....	23
B.4.8	Step 8 .....	24
B.5	Figures .....	24
Annex C (informative)	Other minerals which can be treated in a similar way to kaolins/kaolinitic clays for SWFF and SWFF <sub>CS</sub> determination .....	27
C.1	General .....	27
C.2	Andalusite .....	27
C.2.1	General .....	27
C.2.2	Sedimentation procedure .....	27
C.2.2.1	Steps .....	27
C.2.2.2	Example .....	28
C.3	Mica .....	28
C.4	Vermiculite .....	28
C.5	Talc .....	29
C.5.1	General .....	29
C.5.2	Surfactant/Dispersant preparation .....	29
C.5.3	Sedimentation procedure .....	29

<b>Annex D (informative) Determination of the size weighted fine fraction (SWFF) and SWFF<sub>CS</sub> of Diatomaceous Earth (DE) by sedimentation .....</b>	<b>30</b>
<b>D.1 General.....</b>	<b>30</b>
<b>D.2 Categories of diatomaceous earth.....</b>	<b>30</b>
<b>D.3 Equipment and consumables.....</b>	<b>30</b>
<b>D.3.1 Mercury porosimeter.....</b>	<b>30</b>
<b>D.3.2 Mercury of high purity, hexadistilled .....</b>	<b>30</b>
<b>D.3.3 Analytical balance, capable of weighing with an accuracy of 0,001 g .....</b>	<b>30</b>
<b>D.3.4 Gas pycnometer .....</b>	<b>30</b>
<b>D.3.5 Helium gas, quality class 2-1°A .....</b>	<b>30</b>
<b>D.4 Method .....</b>	<b>30</b>
<b>D.4.1 Determination of the skeletal density .....</b>	<b>30</b>
<b>D.4.2 Determination of the intra-particle pore volume and intra-particle porosity .....</b>	<b>30</b>
<b>D.4.3 Calculation of the effective density.....</b>	<b>31</b>
<b>D.5 Determination of SWFF by sedimentation.....</b>	<b>31</b>
<b>D.5.1 Preparation of the sample .....</b>	<b>31</b>
<b>D.5.2 Determination of sedimentation time.....</b>	<b>31</b>
<b>D.6 Determination of SWFF<sub>CS</sub>.....</b>	<b>31</b>
<b>D.7 Example .....</b>	<b>31</b>
<b>Annex E (informative) Determination of the size weighted fine fraction (SWFF) of feldspar products by sedimentation.....</b>	<b>33</b>
<b>E.1 General.....</b>	<b>33</b>
<b>E.2 Application range.....</b>	<b>33</b>
<b>E.3 Consumables.....</b>	<b>33</b>
<b>E.3.1 Measuring cylinders, of 250 ml volume or equivalent height .....</b>	<b>33</b>
<b>E.3.2 Demineralized (deionised) water .....</b>	<b>33</b>
<b>E.3.3 Sodium hexametaphosphate Na(PO<sub>3</sub>)<sub>6</sub>, 0,05 % or 50 g/l .....</b>	<b>33</b>
<b>E.3.4 Analytical balance, capable of weighing with an accuracy of 0,001 g .....</b>	<b>33</b>
<b>E.3.5 Ultrasonic bath or shaker .....</b>	<b>33</b>
<b>E.3.6 Desiccator .....</b>	<b>33</b>
<b>E.3.7 Oven with an automatic temperature control set to (103 ± 5) °C.....</b>	<b>33</b>
<b>E.3.8 Sedimentation Excel sheet for calculations of sedimentation time.....</b>	<b>33</b>
<b>E.4 Method .....</b>	<b>33</b>
<b>E.4.1 General.....</b>	<b>33</b>
<b>E.4.2 Step1 .....</b>	<b>34</b>
<b>E.4.3 Step 2 .....</b>	<b>34</b>
<b>E.4.4 Step 3 .....</b>	<b>34</b>

E.4.5	Step 4.....	35
E.4.6	Step 5.....	35
E.4.7	Step 6.....	35
Bibliography	.....	37

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/39789009-ea41-42c4-9f83-64edc81f1621/osist-pre-n-17289-3-2019>

**prEN 17289-3:2019 (E)****European foreword**

This document (prEN 17289-3:2019) has been prepared by Technical Committee CEN/TC 137 “Assessment of workplace exposure to chemical and biological agents”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/39789009-ea41-42c4-9f83-64edc81f1621/osist-pre-n-17289-3-2019>



## Introduction

A method was developed in the industrial minerals industry for the purpose of determining the “size weighted relevant fine fraction” within the bulk material. This method provides the necessary information to the users and allows them to compare bulk materials, by measuring the fine fraction, in order for them to select the safest materials. It has been used in the industry and by institutes previously under the acronym SWeRF. EN 17289 (all parts) is based on that industrial method and describes the analytical methods to determine the difference between materials with coarse quartz and fine quartz, e.g. sands versus flour.

As further activities with the material (intentional or otherwise) might change the particle size distribution, the size weighted fine fraction might also change. Therefore, the method reports (in terms of the mass percentages in the bulk material) both, the total CS and the estimated size weighted fine fraction of CS.

Conventions as described in EN 481 can be used as input for this document. However, the output of this document is not related to the respirable fraction and cannot be used for workplace exposure measurements.

EN 17289 (all parts) describes two procedures that can be used to estimate the size weighted fine fraction (SWFF) in bulk materials. It also describes how the SWFF, once separated, can be further analysed to measure the content of crystalline silica (SWFF<sub>cs</sub>). The method can be used for comparing the fine fraction in different bulk samples. EN 17289 (all parts) uses the term fine fraction to indicate that it does not analyse airborne particles, but it evaluates the proportion of particles in a bulk material that, based on their particle size, have a potential to be respirable if they were to become airborne.

EN 17289 (all parts) also allows for the size weighted fine fraction of crystalline silica (SWFF<sub>cs</sub>) particles in bulk materials to be evaluated in terms of mass fraction in percent, if the fraction separated is subsequently analysed by a suitable method.

In a comparison of similar bulk materials, in which the particle size distribution is the only variable, the SWFF can provide useful information to guide material selection. For example, leaving all other factors aside, a bulk material with a lower SWFF value can pose less of a risk in terms of potential occupational exposure. For the actual exposure at the workplace, the handling etc of the material, will play a major role.

Concentrations of respirable dust, or respirable crystalline silica (RCS), in the workplace air, resulting from processing and handling of bulk materials, will depend on a wide variety of factors and these concentrations cannot be estimated using SWFF or SWFF<sub>cs</sub> values. SWFF and SWFF<sub>cs</sub> values are not to be used for occupational exposure assessments as they have no relationship with occupational exposure.

The evaluation of bulk materials using SWFF is complementary to determining the dustiness according to EN 15051-1 [1].

The difference between EN 17289 (all parts) and EN 15051-1 is that SWFF quantifies the fine fraction in a bulk material while dustiness quantifies the respirable, thoracic and inhalable dust made airborne from the bulk material after a specific activity (it characterizes the material with relation to the workplace atmosphere when working with the bulk material).

**prEN 17289-3:2019 (E)**

EN 17289 *Characterization of bulk materials — Determination of a size-weighted fine fraction and crystalline silica content* consists of the following parts:

- Part 1: *General information and choice of test methods*;
- Part 2: *Calculation method*;
- Part 3: *Sedimentation method*.

Part 1 gives information on how to choose the most appropriate method as well as a guideline for the determination of crystalline silica. A calculation method based on particle size distribution is described in Part 2. Part 3 describes a method using sedimentation.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/39789009-ea41-42e4-9f83-64edc81f1621/osist-pr-en-17289-3-2019>

## 1 Scope

This document specifies the determination of the size weighted fine fraction (SWFF) and the size weighted fine fraction of crystalline silica (SWFF<sub>CS</sub>) in bulk materials by means of a sedimentation method using a liquid sedimentation technique.

The purpose of this document is to allow users to evaluate bulk materials with regard to their size-weighted fine fraction and crystalline silica content.

For preparation of the sample and determination of crystalline silica by XRD and FT-IR see prEN 17289-1:2018.

Annex A to Annex E describe specific methods for the evaluation of SWFF for specific bulk materials.

This document is applicable for bulk materials which have been fully investigated and validated. The criteria for the materials are described in this document and prEN 17289-2:2018. This includes industrial minerals which can contain crystalline silica such as quartz, clay, kaolin, talc, feldspar, mica, cristobalite, vermiculite, diatomaceous earth, barite, andalusite, iron ore, chromite etc.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies..

EN 1540, *Workplace exposure - Terminology*

EN 481, *Workplace atmospheres - Size fraction definitions for measurement of airborne particles*

prEN 17289-1:2019, *Characterization of bulk materials – Determination of a size-weighted fine fraction and crystalline silica content — Part 1: General information and choice of test methods*

prEN 17289-2:2019, *Characterization of bulk materials – Determination of a size-weighted fine fraction and crystalline silica content — Part 2: Calculation method*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in in EN 1540 and prEN17289-1:2019 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Symbols and abbreviations

CS	Crystalline Silica
PSD	Particle Size Distribution
PSCD	Particle Size Cumulative Distribution
SWFF	Size Weighted Fine Fraction
SWFF <sub>CS</sub>	Size Weighted Fine Fraction of crystalline silica