



SLOVENSKI STANDARD
SIST EN 1534:2020

01-marec-2020

Nadomešča:
SIST EN 1534:2011

**Lesene talne obloge in parket - Ugotavljanje odpornosti proti vtiskovanju -
Preskusna metoda**

Wood flooring and parquet - Determination of resistance to indentation - Test method

Holzfußböden und Parkett - Bestimmung des Eindruckwiderstands - Prüfmethode

iTeh STANDARD PREVIEW

Planchers en bois et parquets - (Détermination de la résistance au poinçonnement -
Méthode d'essai)

[SIST EN 1534:2020](https://standards.iteh.ai/catalog/standards/sist/b2e7136e-aed3-451c-8ef6-7c43445bc8b0/sist-en-1534-2020)

Ta slovenski standard je istoveten z: EN 1534:2020

ICS:

79.080	Polizdelki iz lesa	Semi-manufactures of timber
97.150	Talne obloge	Floor coverings

SIST EN 1534:2020

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1534:2020

<https://standards.iteh.ai/catalog/standards/sist/b2e7136e-aed3-451c-8ef6-7e45445bc8b0/sist-en-1534-2020>

EUROPEAN STANDARD

EN 1534

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2020

ICS 79.080; 91.060.30

Supersedes EN 1534:2010

English Version

Wood flooring and parquet - Determination of resistance to indentation - Test method

Planchers en bois - Détermination de la résistance au poinçonnement - Méthode d'essai

Holzfußböden und Parkett - Bestimmung des Eindruckwiderstands - Prüfmethode

This European Standard was approved by CEN on 11 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/b2e7136e-aed3-451c-8efb-7e45445bc8b0/sist-en-1534-2020>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	5
5 Apparatus.....	5
6 Test specimens.....	5
6.1 Dimensions	5
6.2 Sampling.....	5
6.3 Conditioning.....	6
6.4 Preparation prior to testing	6
7 Test method.....	6
7.1 Accuracy.....	6
7.2 Application of load.....	6
7.3 Measurement of residual indentation	6
8 Expression of results.....	6
8.1 Hardness for each indentation.....	6
8.2 Calculation values of hardness.....	7
8.2.1 General	7
8.2.2 Characteristic value.....	7
9 Test report	8
Annex A (informative) Brinell hardness of typical wood species.....	9

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1534:2020](#)

[/catalog/standards/sist/b2e7136e-aed3-451c-8eff-](#)

[5445bc8b0/sist-en-1534-2020](#)

European foreword

This document (EN 1534:2020) has been prepared by Technical Committee CEN/TC 175 “Round and sawn timber”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2020, and conflicting national standards shall be withdrawn at the latest by July 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1534:2010.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1534:2020](https://standards.iteh.ai/catalog/standards/sist/b2e7136e-aed3-451c-8ef6-7e45445bc8b0/sist-en-1534-2020)

<https://standards.iteh.ai/catalog/standards/sist/b2e7136e-aed3-451c-8ef6-7e45445bc8b0/sist-en-1534-2020>

EN 1534:2020 (E)**1 Scope**

This document specifies a method, derived from the test, for determining the resistance to indentation of wood flooring.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13756, *Wood flooring and parquet - Terminology*

EN 14762, *Wood flooring - Sampling procedures for evaluation of conformity*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13756, EN 14762 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1**indentation**

concave deformation of the surface of a test specimen from the action of an indenter

Note 1 to entry: An indentation consists of a plastic and elastic part of deformation.

3.2**indentation under action**

momentary indentation when the indenter is applied

Note 1 to entry: indentation consists of a plastic and elastic part of deformation.

3.3**residual indentation**

indentation after the time of recovery

Note 1 to entry: The time of recovery is specified in 7.3.

Note 2 to entry: An indentation consists of a plastic and elastic part of deformation.

3.4**test specimen**

element or square test piece cut from an element

3.5**hardness HB**

Brinell hardness in newtons per square millimetre

Note 1 to entry: Annex A contains a list of typical species and their Brinell hardness.

4 Principle

The resistance to indentation is determined by applying a loaded indenter to the face of the test specimen. The diameter of the residual indentation is used to evaluate the resistance to indentation of the test specimen. After the loading the unloaded specimen is left to recover.

5 Apparatus

5.1 Indenter, i.e. a hardened steel spherical body with contact diameter of $(10 \pm 0,01)$ mm.

5.2 Measurement rig, i.e. a device capable of measuring the diameter of the residual indentation on the face of the test specimen to an accuracy of $\pm 0,1$ mm.

5.3 Loading head, i.e. a device with a load cell accurate to ± 2 % of the maximum applied loads, moving perpendicular to a flat rigid table.

The load and the rate of head movement of the loading head shall be adjustable within specified limits.

6 Test specimens

6.1 Dimensions

The test shall be carried out on test specimens that may be elements or square test pieces, cut from elements that preferably have sides approximately 50 mm long.

6.2 Sampling

Indentation test shall be carried out on each element; the minimum number of tests to be carried out depends on the element length according to Table 1.

Table 1 — Minimum number of test according to the element length

Element length (mm)	Minimum number of test on one element	Minimum number of elements to be tested
≤ 200	1	60
201 to 500	2	30
501 to 1 000	4	15
1 001 to 2 000	6	10
$> 2 001$	10	6

Indentations shall be carried out either in the central area of test pieces or distributed all over the area of the face of the element.

The distance from the centre of the indentation to any edge of a test piece or an element or to a knot shall not be less than 20 mm. However, if the width of the test specimen is less than 40 mm, the indentation shall be placed along its longitudinal axis.

Within the above defined limits, the indentation points shall be distributed at random, representing the whole element length.

Test specimens shall be selected at random.

EN 1534:2020 (E)**6.3 Conditioning**

The test shall be carried out on test specimens conditioned in a relative humidity of $(65 \pm 5) \%$ and a temperature of $(20 \pm 2) ^\circ\text{C}$.

6.4 Preparation prior to testing

The test specimen shall be free of any material that could interfere with the results.

If the test specimens are fitted with a soft or brittle material on the back, this shall be removed to prevent any displacement during the test.

7 Test method**7.1 Accuracy**

All the measurements shall be carried out to the limits of accuracy specified for the instruments as defined in Clause 5.

7.2 Application of load

Set the test specimen on the table of the loading head. Lower the indenter to the surface of the test specimen. Apply a force increasing at such rate that the nominal value of 1 kN is reached after (15 ± 3) s. Maintain the force at this value for (25 ± 5) s. Withdraw the indenter completely.

Throughout the test, the machinery shall be vibration and shock free, to ensure that the sample is rigidly held.

7.3 Measurement of residual indentation

After withdrawal of the indenter, wait (let recover) for at least 3 min. Measure with the measurement rig two diameters of the residual indentation at right angles to each other: one along the grain d_1 , another across the grain d_2 , with an accuracy of $\pm 0,2$ mm.

Contrast on the edge of the indentation can be improved with appropriate lighting and/or application of graphite lead.

8 Expression of results**8.1 Hardness for each indentation**

The hardness Brinell HB is calculated to two significant digits, according to the following formula:

$$HB = \frac{2F}{\pi \cdot D \cdot \left[D - \sqrt{D^2 - d^2} \right]} \quad (1)$$

where

HB is the Brinell hardness in newtons per square millimetre;

π is the "pi" constant;

F is the maximum load applied force, in newtons;

D is the diameter of the ball, in millimetres,

d is the diameter of the residual indentation, in millimetres (average of d_1 and d_2).

The diameter of the residual indentation d is calculated from the measurements taken in accordance with 7.3, using the formula:

$$d = \frac{d_1 + d_2}{2} \quad (2)$$

8.2 Calculation values of hardness

8.2.1 General

A normal distribution is assumed.

The mean value (m), the standard deviation (s) and the characteristic value of the hardness Brinell shall be calculated. The mean value shall be expressed as the whole number.

8.2.2 Characteristic value

A characteristic value is defined as the fifth percentile of the assumed normal distribution.

A characteristic value is given by the following formula:

$$X_k = m - (t_{05} \times s) \quad (3)$$

where

X_k is the characteristic value;

t_{05} is the Student coefficient for a one sided 5 % probability.

Table 2 gives the Student coefficient for a range of values of n .

Table 2 — Student coefficient for a range of values of n

Number of indentations n	Student coefficient t_{05}
6	2,02
7	1,94
8	1,90
9	1,86
10	1,83
11	1,81
12	1,80
13	1,78
14	1,77
15	1,76
16	1,75
17	1,75
18	1,74
19	1,73
20	1,73
21	1,72
22	1,72
23	1,72
24	1,71