

**SLOVENSKI STANDARD**  
**oSIST prEN ISO 23153-1:2019**  
**01-april-2019**

---

**Polimerni materiali - Materiali na osnovi polietereeterketona (PEEK) za oblikovanje in ekstrudiranje - 1. del: Sistem označevanja in podlage za specifikacije (ISO/DIS 23153-1:2019)**

Plastics - Polyetheretherketone (PEEK) moulding and extrusion materials - Part 1: Designation system and basis for specifications (ISO/DIS 23153-1:2019)

Kunststoffe - Polyetheretherketone (PEEK)-Werkstoffe - Teil 1: Bezeichnungssystem und Basis für Spezifikationen (ISO/DIS 23153-1:2019)

Plastiques - Matériaux à base de polyétheréthercétone (PEEK) pour moulage et extrusion - Partie 1: Système de désignation et base de spécification (ISO/DIS 23153-1:2019)

**Ta slovenski standard je istoveten z: prEN ISO 23153-1**

---

**ICS:**

83.080.20	Plastomeri	Thermoplastic materials
-----------	------------	-------------------------

<b>oSIST prEN ISO 23153-1:2019</b>	<b>en,fr,de</b>
------------------------------------	-----------------



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 23153-1

ISO/TC 61/SC 9

Secretariat: KATS

Voting begins on:  
2019-01-21Voting terminates on:  
2019-04-15

### Plastics — Polyetheretherketone (PEEK) moulding and extrusion materials —

Part 1:

### Designation system and basis for specifications

*Plastiques — Polyétheréthercétone (PEEK) pour moulage et extrusion —**Partie 1: Partie 1: Système de désignation et base de spécification*

ICS: 83.080.20

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 23153-1:2020

<https://standards.iteh.ai/catalog/standards/sist/cde90367-128b-481b-a5f1-19f265af667d/sist-en-iso-23153-1-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

### ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 23153-1:2019(E)

© ISO 2019

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 23153-1:2020

<https://standards.iteh.ai/catalog/standards/sist/cde90367-128b-481b-a5f1-19f265af667d/sist-en-iso-23153-1-2020>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Designation and specification system</b> .....	<b>2</b>
4.1 General .....	2
4.2 Data block 1 .....	3
4.3 Data block 2 .....	3
4.4 Data block 3 .....	4
4.5 Data block 4 .....	4
4.5.1 General .....	4
4.5.2 Melt viscosity and melt volume-flow rate .....	5
4.5.3 Tensile modulus .....	5
4.5.4 Tensile strength .....	5
4.6 Data block 5 .....	6
<b>5 Examples of designation</b> .....	<b>6</b>
5.1 Example 1 .....	6
5.2 Example 2 .....	6

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 23153-1:2020

<https://standards.iteh.ai/catalog/standards/sist/cde90367-128b-481b-a5f1-19f265af667d/sist-en-iso-23153-1-2020>

## ISO/DIS 23153-1:2019(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

A list of all parts in the ISO xxxxx series can be found on the ISO website.

<https://standards.iteh.ai/catalog/standards/sist/cde90367-128b-481b-a5f1-19f265af667d/sist-en-iso-23153-1-2020>

# Plastics — Polyetheretherketone (PEEK) moulding and extrusion materials —

## Part 1: Designation system and basis for specifications

### 1 Scope

**1.1** This document establishes a system of designation for polyetheretherketone (PEEK) moulding and extrusion materials which may be used as the basis for specifications. Polyetheretherketone polymer chains are composed of phenylene rings linked in (1,4) position by a sequence of two ether groups followed by one ketone group.

**1.2** The grades of PEEK plastics are differentiated from each other by a classification system based on appropriate levels of the designatory properties

- a) melt viscosity or melt volume-flow rate,
- b) tensile modulus,
- c) tensile strength

and on information about the intended application and/or method of processing, important properties, additives, colorants, fillers and reinforcing materials.

**1.3** The designation system is applicable to all polyetheretherketones.

It applies to materials ready for normal use in the form of powder, granules or pellets, unmodified or modified by colourants, fillers, reinforcements or other additives.

**1.4** It is not intended to imply that materials having the same designation necessarily give the same performance. This document does not provide engineering data, performance data or data on processing conditions which may be required to specify a material for a particular application and/or method of processing.

If such additional properties are required, they shall be determined in accordance with the test methods specified in ISO 23153-2, if suitable.

**1.5** In order to specify a thermoplastic material for a particular application or to ensure reproducible processing, additional requirements may be given in data block 5 (see [Clause 4.1](#)).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

## ISO/DIS 23153-1:2019(E)

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 1043-2, *Plastics — Symbols and abbreviated terms — Part 2: Fillers and reinforcing materials*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

ISO 11443, *Plastics — Determination of the fluidity of plastics using capillary and slit-die rheometers*

ISO 23153-2, *Plastics — Polyetheretherketone (PEEK) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Designation and specification system

#### 4.1 General

The designation and specification system for thermoplastics is based on the following standardised pattern:

Designation						
Description block (optional)	Identity block					
	International Standard Num- ber block	Individual-item block				
		Data block 1	Data block 2	Data block 3	Data block 4	Data block 5

The designation consists of an optional description block, reading “Thermoplastics”, and an identity block comprising the International Standard number and an individual-item block. For unambiguous designation, the individual-item block is subdivided into five data blocks comprising the following information:

Data block 1: Identification of the plastic by its abbreviated term PEEK in accordance with ISO 1043-1 (see 4.2).

Data block 2: Fillers or reinforcing materials and their nominal content (see 4.3).

Data block 3: Position 1: Intended application or method of processing (see 4.4).

Positions 2 to 8: Important properties, additives and supplementary information (see 4.4).

Data block 4: Designatory properties (see 4.5).

Data block 5: For the purpose of specifications, a fifth data block may be added containing additional information.

The first character of the individual-item block shall be a hyphen. The data blocks shall be separated from each other by commas.

If a data block is not used, this shall be indicated by doubling the separation sign, i.e. by two commas (,,).



## 4.2 Data block 1

In this data block, after the hyphen, the polyetheretherketone plastic is identified by its abbreviated term PEEK in accordance with ISO 1043-1.

## 4.3 Data block 2

In this data block, the type of filler and/or reinforcing material is represented by a single code-letter in position 1 and its physical form by a second code-letter in position 2. The code-letters listed in Table 2 being as specified in ISO 1043-2. Subsequently (without a space), the mass content may be given by a 2-figure number in positions 3 and 4.

**NOTE** In accordance with ISO 1043-2 there are exceptions where additional code letters may be required for unanimous designation of material and/or form of fillers.

**Table 2 — Code-letters used for fillers and reinforcing materials in data block 2**

Code-letter	Material (Position 1)	Code-letter	Form (Position 2)
<b>A</b>	Aramid		
<b>B</b>	Borona <sup>a</sup>	<b>B</b>	Beads, spheres, balls
<b>C</b>	Carbona <sup>a</sup>	<b>Cc</b>	Chips, cuttings
		<b>Cm</b>	Chopped-strand mat
		<b>D</b>	Fines, powder
		<b>F</b>	Fibre
		<b>Fl</b>	Long fibres
<b>G</b>	Glass	<b>G</b>	Ground
		<b>H</b>	Whiskers
		<b>K</b>	Knitted fabric
		<b>L</b>	Layer, laminate
<b>Mi, Me</b>	Mineral <sup>a</sup> , metal <sup>a</sup>	<b>M</b>	Mat (thick)
		<b>Mc</b>	Continuous (endless) strand mat
		<b>N</b>	Non-woven (fabric, thin)
		<b>Nf</b>	Nano fibres
		<b>Nt</b>	Nano tubes
<b>P</b>	Mica <sup>a</sup>	<b>P</b>	Paper
<b>Q</b>	Silica		
		<b>R</b>	Roving
<b>S</b>	Synthetic, organica <sup>a</sup>	<b>S</b>	Scales, flakes
<b>T</b>	Talc	<b>T</b>	Twisted or braided fabric, cord, tube
		<b>W</b>	Woven fabric
<b>X</b>	Not specified	<b>X</b>	Not specified
		<b>Y</b>	Yarn
<b>Z</b>	Others <sup>a</sup>	<b>Z</b>	Others <sup>a</sup>

<sup>a</sup> These materials may be further defined by their chemical symbol or composition, special form, or additional specifiers as defined in the relevant International Standard. In the case of metals (M), it is essential to indicate the type of metal by means of its chemical symbol or alloy.

Mixtures of materials and/or forms may be indicated by combining the relevant codes using the sign “+” and placing the whole between parentheses. For example, a mixture of 25 % glass fibres (GF) and 10 % mineral powder (MD) would be indicated by (GF25+MD10).

## ISO/DIS 23153-1:2019(E)

#### 4.4 Data block 3

In this data block, information about the intended application and/or method of processing is given in position 1 and information about important properties, additives and colour in positions 2 to 8. The code-letters used are specified in [Table 3](#).

If a material can be used for more than one application and/or method of processing the most important shall be given in position 1.

If information is presented in positions 2 to 8 and no specific information is given in position 1, the letter X shall be inserted in position 1.

**Table 3 — Code-letters used in data block 3**

Code letter	Position 1	Code letter	Position 2 to 8
		<b>A</b>	Processing stabilized
<b>B</b>	Blow moulding	<b>B</b>	Antiblocking
		<b>C</b>	Coloured
		<b>D</b>	Powder
<b>E</b>	Extrusion of pipes, profiles and sheets		
<b>F</b>	Extrusion of films	<b>F</b>	Special burning characteristics
<b>G</b>	General use	<b>G</b>	Granules, pellets
<b>H</b>	Coating	<b>H</b>	Heat ageing stabilised
<b>J</b>	Cable and wire insulating	<b>J</b>	Elevated heat performance
<b>K</b>	Cable and wire sheathing		
<b>L</b>	Monofilament extrusion	<b>L</b>	Light or weather stabilized
<b>M</b>	Injection moulding	<b>M</b>	Nucleated
		<b>N</b>	Natural (no colour added)
<b>P</b>	Compounding	<b>P</b>	Impact modified
<b>Q</b>	Compression moulding		
<b>R</b>	Rotational moulding	<b>R</b>	Mould release agent
<b>S</b>	Sintering	<b>S</b>	Lubricated
<b>T</b>	Tape manufacture	<b>T</b>	Transparent
		<b>W</b>	Wear resistant, low friction
<b>X</b>	No indication	<b>X</b>	Crosslinkable
		<b>Y</b>	Increased electrical conductivity
		<b>Z</b>	Antistatic

#### 4.5 Data block 4

##### 4.5.1 General

In this data block, the melt viscosity (MV) or melt volume-flow rate (MVR) is represented by a combination of a single code-character representing test conditions and a single code-number representing value ranges (see [4.5.2](#)), the tensile modulus by a 2-figure code-number (see [4.5.3](#)), and the tensile strength by a 3-figure code-number (see [4.5.3](#)). The three codes are separated from each other by hyphens.

If a property value falls on or near a range limit for a particular product, the manufacturer of that product shall state which range will designate that product. If test values for subsequent lots of that