



# SLOVENSKI STANDARD

## oSIST prEN ISO 7233:2020

01-marec-2020

---

### Gumene in polimerne cevi ter cevni priključki - Ugotavljanje odpornosti proti vakuumu (ISO/DIS 7233:2020)

Rubber and plastics hoses and hose assemblies - Determination of resistance to vacuum (ISO/DIS 7233:2020)

Gummi- und Kunststoffschläuche und -schlauchleitungen - Bestimmung der Beständigkeit gegen Vakuum (ISO/DIS 7233:2020)

Tuyaux et flexibles en caoutchouc et en plastique - Détermination de la résistance à l'aspiration (ISO/DIS 7233:2020)

[kSIST FprEN ISO 7233:2021](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-7d6e62b3899/ksist-pr-en-iso-7233-2020)

[https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-7d6e62b3899/ksist-pr-en-iso-7233-2020)

Ta slovenski standard je istoveten z: **prEN ISO 7233**

---

#### **ICS:**

23.040.70      Gumene cevi in armature      Hoses and hose assemblies

**oSIST prEN ISO 7233:2020**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[kSIST FprEN ISO 7233:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021>

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 7233

ISO/TC 45/SC 1

Secretariat: DIN

Voting begins on:  
2020-01-24Voting terminates on:  
2020-04-17

---

---

## Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum

*Tuyaux et flexibles en caoutchouc et en plastique — Détermination de la résistance à l'aspiration*

ICS: 23.040.70

### iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 7233:2021](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021)<https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 7233:2020(E)

© ISO 2020

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 7233:2021  
https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021)



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
Introduction .....	v
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>1</b>
<b>6 Test pieces</b> .....	<b>2</b>
<b>7 Conditioning of test pieces</b> .....	<b>2</b>
<b>8 Test pressure</b> .....	<b>2</b>
<b>9 Procedures</b> .....	<b>2</b>
9.1 Method A .....	2
9.2 Method B .....	2
9.3 Method C .....	3
<b>10 Test report</b> .....	<b>4</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 7233:2021](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021)  
<https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021>

## ISO/DIS 7233:2020(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

This fifth edition cancels and replaces the fourth edition (ISO 7233:2016), which has been technically revised.

The main changes compared to the previous edition are as follows:

- Hose assembly has been added in the text
- A statement regarding change in length, as mentioned in Method C, has been added.

A list of all parts in the ISO 7233 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

Vacuum testing is applied to hoses or hose assemblies to determine whether they will withstand the differential pressure encountered in service resulting from reduced pressure within the hose or hose assembly.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 7233:2021](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021)

<https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[kSIST FprEN ISO 7233:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021>



# Rubber and plastics hoses and hose assemblies — Determination of resistance to vacuum

## 1 Scope

This document specifies three methods for determining the resistance to vacuum of hoses and hose assemblies manufactured from plastic or rubber. Applicable dimensions of hoses for each method are as follows:

- method A for hoses and hose assemblies of nominal size up to and including 80 ;
- method B for hoses of nominal size greater than 80 ;
- method C for hoses of all dimensions.

Methods A and B can also be used to check the adhesion of the lining to the reinforcement (delamination) in a length of hard-wall hose or hose assembly.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Principle

The test methodology for determining the resistance to vacuum of plastic and rubber hoses and hose assemblies consists of reducing the internal pressure in a length of hose by means of a vacuum pump and gauge, while examining the hose for any signs of deformation or delamination of reinforcement or lining.

## 5 Apparatus

**5.1 Vacuum pump**, provided with a gauge and capable of reducing the internal pressure in the hose within 60 s to the pressure specified in the product standard for the hose under test and maintaining it at that pressure for a minimum of 10 min.

## ISO/DIS 7233:2020(E)

**5.2 Smooth, solid ball (for method A)**, with a diameter equal to 0,9 times the bore of the hose under test, rounded down to the nearest whole millimetre.

**5.3 Two transparent airtight plates (for method B)**, for sealing each end of the hose. One of the plates shall permit attachment of the vacuum pump to the hose, while allowing internal visual inspection of the hose during the test.

## 6 Test pieces

If the complete hose or hose assembly is more than 1 m long, each test piece shall consist of a minimum length of hose, clear of the end fittings, of 1 m. If the complete hose or hose assembly is less than 1 m long, the complete length shall be used.

## 7 Conditioning of test pieces

No tests shall be carried out within 24 h of manufacture. Test pieces shall be conditioned at the appropriate temperature in accordance with ISO 23529 for at least 3 h before testing.

This 3 h period may form part of the minimum period of 24 h between manufacture and testing.

## 8 Test pressure

The internal pressure to which the hose or hose assembly is subjected to for the duration of the test shall be that stated in the product standard for the hose or hose assembly under test as being the minimum internal pressure which the hose or hose assembly is required to withstand.

## 9 Procedures

[kSIST FprEN ISO 7233:2021  
https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021](https://standards.iteh.ai/catalog/standards/sist/c87ee794-75e3-43a5-a6e6-2d6ec62b3899/ksist-fpren-iso-7233-2021)

### 9.1 Method A

Lay out the hose as straight as possible on a flat surface and blank off one end to form an airtight seal. Insert into the hose a smooth, solid ball (5.2) before assembling the hose and then connect the open end of the hose or hose assembly to a vacuum pump and gauge. Reduce the pressure in the hose or hose assembly within 60 s to the required test pressure and maintain this pressure for the required period, which shall not be less than 10 min.

While the test pressure is being maintained, examine the hose externally for any signs of indentation or collapse and then tilt the hose to permit the solid ball to traverse the full length of the hose or hose assembly to check for any obstructions caused by internal deformation or delamination.

### 9.2 Method B

Lay out the hose or hose assembly as straight as possible on a flat surface and fit transparent airtight plates (5.3) to both ends of the hose or hose assembly, one of which shall then be connected to a vacuum pump and gauge. Reduce the pressure in the hose or hose assembly within 60 s to the required test pressure and maintain this pressure for the required period, which shall not be less than 10 min.

While the test pressure is being maintained, examine the interior of the hose or hose assembly through one of the transparent plates by means of illumination supplied through the transparent plate at the other end of the hose for signs of delamination or blistering of the lining. Also examine the exterior of the hose or hose assembly for signs of indentation or collapse.