
**Rolling bearings — Load ratings for
hybrid bearings with rolling elements
made of ceramic —**

**Part 2:
Static load ratings**

iTeh STANDARD PREVIEW
*Roulements — Charges de base pour roulements hybrides avec
éléments roulants en céramique —
Partie 2: Charges statiques*
(standards.iteh.ai)

ISO 20056-2:2017

<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20056-2:2017

<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	2
5 Static load rating	3
5.1 General.....	3
5.2 Basic static radial load rating of radial ball bearings.....	3
5.3 Basic static axial load rating of thrust ball bearings.....	4
5.4 Basic static radial load rating of radial roller bearings.....	5
5.5 Basic static axial load rating of thrust roller bearings.....	5
5.6 Discontinuities in load ratings.....	5
5.7 Consideration of special material properties.....	5
6 Static equivalent load	5
6.1 General.....	5
6.2 Radial ball bearings.....	5
6.3 Thrust ball bearings.....	5
6.4 Radial roller bearings.....	5
6.5 Thrust roller bearings.....	5
7 Static safety factor	6
Annex A (informative) Calculation of the Hertzian parameters for point contact	7
Annex B (informative) Guide values of the factor f_0 for ball bearings	8
Annex C (informative) Discontinuities in the calculation of basic static load ratings	10
Annex D (informative) Material properties and material classification	11
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 4, *Rolling bearings*, Subcommittee SC 8, *Load ratings and life*. ISO 20056-2:2017

<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c->

A list of all the parts in the ISO 20056 series can be found on the ISO website. <https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c->

Introduction

Hybrid bearings are rolling bearings with raceways consisting of commonly used rolling bearing steel and rolling elements made from silicon nitride (for definitions, see ISO 5593). Due to the higher modulus of elasticity of the ceramic rolling elements, hybrid bearings have a noticeably smaller contact ellipse at the same load than rolling bearings with rolling elements made of rolling bearing steel. This will lead to higher contact stresses at the same load.

Since the second edition of ISO 76 in 1987, the static capacity of rolling bearings is defined by a permissible Hertzian contact stress in the highest loaded contact. In rolling bearings made of steel, this contact stress will lead to a permanent plastic deformation at raceway and rolling element of approximately 1/10 000th of the rolling element diameter. In hybrid bearings, no significant plastic deformation will occur at the rolling element, resulting in a smaller total plastic deformation in the rolling contact. Therefore, in accordance with industrial practice, slightly higher permissible Hertzian stresses are defined for hybrid bearings. The guideline values of the static safety factor, S_0 , have been increased accordingly to maintain the same overall safety for the raceway.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 20056-2:2017](https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017)

<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20056-2:2017

<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017>

Rolling bearings — Load ratings for hybrid bearings with rolling elements made of ceramic —

Part 2: Static load ratings

1 Scope

This document specifies methods of calculating the static load ratings for hybrid bearings with bearing rings made of contemporary, commonly used, high quality hardened bearing steel, in accordance with good manufacturing practice, and a full set of rolling elements made of silicon nitride (Si_3N_4) in contemporary, commonly used material and manufacturing quality. For balls, ISO 26602,^[4] together with ISO 3290-2,^[1] is applicable. For rollers, ISO 12297-2^[2] is applicable, and ISO 26602^[4] is applicable in an analogous way.

For applications where hybrid bearings are used, guideline values of the static safety factor, S_0 , according to [Table 1](#) and [Table 2](#) are observed.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-30471569ca24/iso-20056-2-2017>
ISO 76:2006, *Rolling bearings — Static load ratings*

ISO 5593, *Rolling bearings — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5593 and ISO 76, and the following, apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 basic static radial load rating

C_{0r}

radial load which corresponds to a calculated contact stress at the centre of the most heavily loaded rolling element/raceway contact of

- 4 600 MPa for all radial ball bearings including radial self-aligning ball bearings, and
- 4 200 MPa for all radial roller bearings

Note 1 to entry: In the case of a single-row angular contact bearing, the radial load rating refers to the radial component of that load which causes a purely radial displacement of the bearing rings in relation to each other.

Note 2 to entry: The contact stress limits given in this subclause are only valid for rolling elements made of silicon nitride with a modulus of elasticity of 300 000 MPa or higher. For rolling elements made of ceramics with a lower modulus of elasticity, the contact stress limits per ISO 76 should be applied.

3.2 basic static axial load rating

C_{0a}
static centric axial load which corresponds to a calculated contact stress at the centre of the most heavily loaded rolling element/raceway contact of

- 4 600 MPa for all thrust ball bearings, and
- 4 200 MPa for all thrust roller bearings

Note 1 to entry: For a tapered roller, the applicable diameter is equal to the mean value of the diameters at the imaginary sharp corners at the large end and at the small end of the roller.

Note 2 to entry: For an asymmetrical convex roller, the applicable diameter is an approximation of the diameter at the point of contact between the roller and the ribless raceway at zero load.

Note 3 to entry: The contact stress limits given are only valid for rolling elements made of silicon nitride with a modulus of elasticity of 300 000 MPa or higher. For rolling elements made of ceramics with a lower modulus of elasticity, the contact stress limits according to ISO 76 should be applied.

4 Symbols

C_0	basic static load rating, in N
C_{0a}	basic static axial load rating, in N
C_{0r}	basic static radial load rating, in N
D_{pw}	pitch diameter of ball or roller set, in mm
D_w	nominal ball diameter, in mm
D_{we}	roller diameter applicable in the calculation of load ratings, in mm
E_{Ce}	modulus of elasticity of ceramic rolling elements, in MPa ($E_{Ce} = 300\ 000$ MPa)
E_{St}	modulus of elasticity of rolling bearing steel, in MPa ($E_{St} = 207\ 000$ MPa, according to ISO 76)
$E(\chi)$	complete elliptic integral of the second kind
F_a	bearing axial load (axial component of actual bearing load), in N
F_r	bearing radial load (radial component of actual bearing load), in N
$F(\rho)$	relative curvature difference
f_0	factor for calculation of basic static load rating
i	number of rows of rolling elements
$K(\chi)$	complete elliptic integral of the first kind
L_{we}	effective roller length applicable in the calculation of load ratings, in mm
P_{0a}	static equivalent axial load, in N
P_{0r}	static equivalent radial load, in N

r_e	cross-sectional raceway groove radius of outer ring or housing washer, in mm
r_i	cross-sectional raceway groove radius of inner ring or shaft washer, in mm
S_0	static safety factor
w	correction factor for different material combinations
X_0	static radial load factor
Y_0	static axial load factor
Z	number of rolling elements in a single-row bearing; number of rolling elements per row of a multi-row bearing with the same number of rolling elements per row
α	nominal contact angle, in degrees
γ	auxiliary parameter, $\gamma = D_w \times \cos \alpha / D_{pw}$
ν_{Ce}	Poisson's ratio of ceramic rolling elements ($\nu_{Ce} = 0,26$)
ν_{St}	Poisson's ratio of bearing steel ($\nu_{St} = 0,30$, according to ISO 76)
$\sum \rho$	curvature sum, in mm^{-1}
ϕ	angular position of rolling element, in degrees
χ	ratio of semi major to semi minor axis of the contact ellipse

iTech STANDARD PREVIEW
(standards.itoh.ai)

5 Static load rating

ISO 20056-2:2017

<https://standards.itoh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017>

5.1 General

The static load ratings for hybrid bearings are calculated using [Formulae \(1\) to \(12\)](#). These formulae and the contact stress limits given in [3.1](#) and [3.2](#) are only valid for rolling elements made of silicon nitride with a modulus of elasticity of 300 000 MPa or higher. For rolling elements made of ceramics with a lower modulus of elasticity, the contact stress limits according to ISO 76 should be applied.

5.2 Basic static radial load rating of radial ball bearings

The basic static radial load rating for a radial ball bearing with a ceramic ball set is given by [Formula \(1\)](#):

$$C_{0r} = f_0 \times i \times Z \times D_w^2 \times \cos \alpha \tag{1}$$

with [Formula \(2\)](#):

$$f_0 = \min \{ f_{0,i}, f_{0,e} \} \tag{2}$$

and [Formulae \(3\) and \(4\)](#):

$$f_{0,i} = 2,295\,96 \times \chi_i \times \left(\frac{E(\chi_i)}{2 + \frac{\gamma}{1-\gamma} - \frac{D_w}{2 \times r_i}} \right)^2 \tag{3}$$

$$f_{0,e} = 2,295\,96 \times \chi_e \times \left(\frac{E(\chi_e)}{2 - \frac{\gamma}{1+\gamma} - \frac{D_w}{2 \times r_e}} \right)^2 \quad (4)$$

The calculation of the Hertzian parameters χ and $E(\chi)$ is described in [Annex A](#). Guide values of the factor f_0 are given in [Annex B, Table B.1](#).

The basic static radial load rating for a radial self-aligning ball bearing with a ceramic ball set is given by [Formula \(5\)](#):

$$C_{0r} = f_0 \times i \times Z \times D_w^2 \times \cos \alpha \quad (5)$$

with [Formula \(6\)](#):

$$f_0 = 2,295\,96 \times \left[\frac{\pi}{4} \times (1 + \gamma) \right]^2 \quad (6)$$

Guide values of the factor f_0 are given in [Annex B, Table B.1](#).

5.3 Basic static axial load rating of thrust ball bearings

The basic static axial load rating for a thrust ball bearing with a ceramic ball set is given by [Formula \(7\)](#):

$$C_{0a} = f_0 \times Z \times D_w^2 \times \sin \alpha \quad (7)$$

with [Formula \(8\)](#):

$$f_0 = \min\{f_{0,i}, f_{0,e}\} \quad (8)$$

ISO 20056-2:2017
<https://standards.iteh.ai/catalog/standards/sist/6a5644f7-c464-466c-af7c-0e4725839ea2/iso-20056-2-2017>

and [Formulae \(9\)](#) and [\(10\)](#):

$$f_{0,i} = 11,479\,8 \times \chi_i \times \left(\frac{E(\chi_i)}{2 + \frac{\gamma}{1-\gamma} - \frac{D_w}{2 \times r_i}} \right)^2 \quad (9)$$

$$f_{0,e} = 11,479\,8 \times \chi_e \times \left(\frac{E(\chi_e)}{2 - \frac{\gamma}{1+\gamma} - \frac{D_w}{2 \times r_e}} \right)^2 \quad (10)$$

where

Z is the number of balls carrying load in one direction.

The calculation of the Hertzian parameters χ and $E(\chi)$ is described in [Annex A](#). Guide values of the factor f_0 are given in [Annex B, Table B.1](#).

5.4 Basic static radial load rating of radial roller bearings

The basic static radial load rating for a radial roller bearing with a ceramic roller set is given by [Formula \(11\)](#):

$$C_{0r} = 41,586 2 \times \left(1 - \frac{D_{we} \times \cos \alpha}{D_{pw}} \right) \times i \times Z \times L_{we} \times D_{we} \times \cos \alpha \quad (11)$$

5.5 Basic static axial load rating of thrust roller bearings

The basic static axial load rating for a thrust roller bearing with a ceramic roller set is given by [Formula \(12\)](#):

$$C_{0a} = 207,931 \times \left(1 - \frac{D_{we} \times \cos \alpha}{D_{pw}} \right) \times Z \times L_{we} \times D_{we} \times \sin \alpha \quad (12)$$

where

Z is the number of rollers carrying load in one direction.

5.6 Discontinuities in load ratings

For information for discontinuities in load ratings, see [Annex C](#).

5.7 Consideration of special material properties

For information on consideration of special material properties, see [Annex D](#).

6 Static equivalent load

6.1 General

The derivation of the static radial load factor, X_0 , and the static axial load factor, Y_0 , is described in ISO/TR 10657:1991[5], Clause 4. The equation set used there is almost independent of the modulus of elasticity and Poisson's ratio of rolling elements and raceways, therefore the values obtained by this derivation is valid also for hybrid bearings with ceramic rolling elements.

6.2 Radial ball bearings

For the calculation of the static equivalent load, the factors and formulae given in ISO 76:2006, 5.2 apply.

6.3 Thrust ball bearings

For the calculation of the static equivalent load, the factors and formulae given in ISO 76:2006, 6.2 apply.

6.4 Radial roller bearings

For the calculation of the static equivalent load, the factors and formulae given in ISO 76:2006, 7.2 apply.

6.5 Thrust roller bearings

For the calculation of the static equivalent load, the factors and formulae given in ISO 76:2006, 8.2 apply.