



SLOVENSKI STANDARD
oSIST prEN ISO 23208:2018
01-november-2018

Kriogene posode - Čistoča za obratovanje v kriogenem področju (ISO 23208:2017)

Cryogenic vessels - Cleanliness for cryogenic service (ISO 23208:2017)

Kryo-Behälter - Reinheit für den tiefkalten Betrieb (ISO 23208:2017)

Réipients cryogéniques - Propreté en service cryogénique (ISO 23208:2017)

Ta slovenski standard je istoveten z: prEN ISO 23208

<https://standards.iteh.ai/catalog/standards/sist/e794b586-7be1-4aa0-a258-70507dbb230f/sist-en-iso-23208-2019>

ICS:

23.020.40 Proti mrazu odporne posode Cryogenic vessels
(kriogenske posode)

oSIST prEN ISO 23208:2018

en,fr,de

INTERNATIONAL STANDARD

**ISO
23208**

Second edition
2017-04

Cryogenic vessels — Cleanliness for cryogenic service

Réipients cryogéniques — Propreté en service cryogénique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 23208:2019

<https://standards.iteh.ai/catalog/standards/sist/e794b586-7be1-4aa0-a258-70507dbb230f/sist-en-iso-23208-2019>



Reference number
ISO 23208:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 23208:2019

<https://standards.iteh.ai/catalog/standards/sist/e794b586-7be1-4aa0-a258-70507dbb230f/sist-en-iso-23208-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	1
4.1 General requirements	1
4.2 Additional requirements for oxygen and oxidizing fluids	2
5 Cleaning procedure	2
6 Cleanliness evaluation	2
7 Post-cleaning protection	2
8 Identification	3
Annex A (informative) Inspection methods	4
Bibliography	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 23208:2019

<https://standards.iteh.ai/catalog/standards/sist/e794b586-7be1-4aa0-a258-70507dbb230f/sist-en-iso-23208-2019>

ISO 23208:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 220, *Cryogenic vessels*.

This second edition cancels and replaces the first edition (ISO 23208:2005), which has been technically revised. The main changes are in 4.1.

Cryogenic vessels — Cleanliness for cryogenic service

1 Scope

This document specifies the minimum requirements for the cleanliness of all surfaces of cryogenic vessels and associated accessories that are in contact with the cryogenic fluid at any expected operating conditions.

This document defines the acceptable level of surface and particle contamination to minimize the risk of malfunction of equipment and ensure safety against ignition when in contact with oxygen or oxidizing fluids (see ISO 10156).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 21010, *Cryogenic vessels — Gas/materials compatibility*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

cryogenic fluid

gas which is partially liquid because of its low temperature

Note 1 to entry: It includes totally evaporated liquids and supercritical fluids.

Note 2 to entry: In the context of this document, refrigerated but non-toxic gases and mixtures of them are referred to as cryogenic fluids.

Note 3 to entry: See also ISO 21029-1, ISO 20421-1 and/or ISO 21009-1.

3.2

oxidizing fluid

cryogenic fluid (3.1) with oxidizing properties

Note 1 to entry: This is in accordance with ISO 10156.

4 Requirements

4.1 General requirements

Foreign matter such as chips, oxide scale and weld spatter are not acceptable.

ISO 23208:2017(E)

Particles visible under daylight or white light without magnification are not acceptable. Depending upon the design of the system, more stringent requirements for particle size may be required to avoid malfunction of equipment.

The root pass of pipe welds shall be protected by forming gas, or another suitable method, to avoid gross porosity.

Free water shall not be detectable by visual examination.

4.2 Additional requirements for oxygen and oxidizing fluids

For oxygen and oxidizing fluids, hydrocarbon contamination, paint, adhesives, sealants and protective coating shall not be detectable by visual examination using white light unless they are oxygen compatible in accordance with ISO 21010.

The maximum acceptable hydrocarbon contamination (oil, grease, etc.) is 500 mg/m².

NOTE The value 500 mg/m² is taken from CGA G-4.1[5]. The quoted figure should be considered as guidance only. A lower figure could be requested depending on the specific application (type and state of fluid, temperature, pressure, flow, velocity, product purity), or effects like migration (see also EIGA Doc 33/06 [2]).

5 Cleaning procedure

Any cleaning procedure may be used, provided the requirements of 4.1 and 4.2, if relevant, are met. If solvent or cleaning agents are used, they shall be compatible with all materials to be cleaned, in particular, plastics. Special care shall be taken to remove any non-oxygen-compatible agents (see ISO 21010) from equipment cleaned for oxygen or oxidizing fluid service.

6 Cleanliness evaluation

An inspection and sampling method shall be selected to ensure that the requirements of 4.1 and 4.2, if relevant, are met. It shall take into account the cleaning procedure to be used, the equipment to be cleaned and its level of contamination. Cleanliness evaluation methods may include those listed in Annex A.

The method of inspection shall not itself result in contamination levels greater than those specified in 4.1 and 4.2.

The cleanliness evaluation method shall be documented and the results obtained shall be recorded.

7 Post-cleaning protection

After cleaning, items shall be protected to maintain their clean condition until used. To reduce the risk of condensing any atmospheric moisture during storage, consideration shall be given to purging and sealing the equipment.

Any packaging, plugs, etc. that can contact the clean surfaces shall be clean and removable without leaving any residue. Any packaging material shall be strong enough to resist the expected handling and storage conditions and be able to be sealed and waterproof.

Any protective gas used shall be dry and oil-free and dust-free.

Any pressurizing gas shall be kept at low pressure compatible with the strength of the packaging and have a warning tag if purge pressures exceed 0,5 bar.

8 Identification

Evidence of conformity with the requirements of this document shall be documented by either

- a certificate accompanying the equipment/item, or
- a label fixed to the protective packaging or equipment/item.

The certificate or label shall indicate

- a) “ISO 23208 – cleaned oxygen” when cleaned for oxygen or oxidizing fluids, and
- b) “ISO 23208” when cleaned for other cryogenic fluids only.

If a protective gas is used, the type of gas and its pressure shall be legibly indicated.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 23208:2019

<https://standards.iteh.ai/catalog/standards/sist/e794b586-7be1-4aa0-a258-70507dbb230f/sist-en-iso-23208-2019>

Annex A **(informative)**

Inspection methods

A.1 General

Various methods exist for determining the cleanliness acceptance of equipment and it is necessary that the method selected complements the cleaning method used. This annex covers the most practical and effective methods available. It is necessary that competent persons with the necessary training and relevant industrial experience perform this inspection.

All parts being checked by solvent flushing or immersion should be able to drain freely to empty the solvent. If an area is identified which cannot freely drain, a method should be developed to remove completely the solvent without leaving contamination.

For parts that are inaccessible for inspection after assembly, it may be necessary to disassemble or inspect parts prior to assembly. Consideration should be given to any contamination which may occur during the assembly of inspected components.

If an inspection reveals the presence of any contaminants, the item should be partially or totally re-cleaned. Persistent rejection requires a re-evaluation of the cleaning methods and quality control provisions before re-acceptance.

A.2 Direct visual examination with daylight or white light

This is the most common inspection method used to detect the presence of contaminants on equipment with easily accessible surfaces. This method will, without magnification, detect very small particulate matter and moisture, oils, grease, etc. in relatively small amounts.

The effectiveness of this method is dependent on the roughness of the inspected surface. The method can be used for sandblasted or mechanically cleaned steel surfaces.

Magnifying glasses are not necessary, but it is important to have a sufficiently bright level of daylight or artificial white light.

Visual examination of the surfaces is appropriate for detecting

- moisture (free water),
- cleaning agents,
- flux residues from brazing, soldering or welding,
- rust and loose scale, weld spatters, particles, fibres or other foreign matter, and
- organic material such as oil, grease and paint.

This direct visual examination method enables detection of the maximum acceptable hydrocarbon contamination level as specified in [4.2](#).

A.3 Direct visual examination method with ultraviolet light

Ultraviolet (UV) light causes many common, but not all, hydrocarbon or organic oils to fluoresce. A UV light with a wavelength of about 370 nm used in dark or near darkness at a distance of about 10 cm to