

# **SLOVENSKI STANDARD**

## **SIST EN ISO 17640:2019**

**01-marec-2019**

**Nadomešča:**

**SIST EN ISO 17640:2018**

---

**Neporušitveno preskušanje zvarnih spojev - Ultrazvočno preskušanje - Tehnike, stopnje preskušanja in ocenjevanje (ISO 17640:2018)**

Non-destructive testing of welds - Ultrasonic testing - Techniques, testing levels, and assessment (ISO 17640:2018)

Zerstörungsfreie Prüfung von Schweißverbindungen - Ultraschallprüfung - Techniken, Prüfklassen und Bewertung (ISO 17640:2018)

Essais non destructifs des assemblages soudés - Contrôle par ultrasons - Techniques, niveaux d'essai et évaluation (ISO 17640:2018)

**Ta slovenski standard je istoveten z: EN ISO 17640:2018**

---

**ICS:**

25.160.40	Varjeni spoji in vari	Welded joints and welds
-----------	-----------------------	-------------------------

**SIST EN ISO 17640:2019**

**en,fr**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 17640:2019

<https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN ISO 17640**

November 2018

ICS 25.160.40

Supersedes EN ISO 17640:2017

English Version

**Non-destructive testing of welds - Ultrasonic testing -  
Techniques, testing levels, and assessment (ISO  
17640:2018)**

Essais non destructifs des assemblages soudés -  
Contrôle par ultrasons - Techniques, niveaux d'essai et  
évaluation (ISO 17640:2018)

This European Standard was approved by CEN on 11 October 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

**iTeh STANDARD PREVIEW**

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

Contents	Page
European foreword.....	3

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 17640:2019  
<https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019>

## European foreword

This document (EN ISO 17640:2018) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2019, and conflicting national standards shall be withdrawn at the latest by May 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17640:2017.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**iTeh STANDARD PREVIEW**  
**Endorsement notice**  
**(standards.iteh.ai)**

The text of ISO 17640:2018 has been approved by CEN as EN ISO 17640:2018 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 17640:2019

<https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019>

# INTERNATIONAL STANDARD

**ISO**  
**17640**

Fourth edition  
2018-10

---

---

## Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment

*Essais non destructifs des assemblages soudés — Contrôle par  
ultrasons — Techniques, niveaux d'essai et évaluation*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 17640:2019](https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019)

[https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-  
212c51ee0cae/sist-en-iso-17640-2019](https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019)



Reference number  
ISO 17640:2018(E)

© ISO 2018

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 17640:2019

<https://standards.iteh.ai/catalog/standards/sist/7a9dbaf6-090d-41f3-b16a-212c51ee0cae/sist-en-iso-17640-2019>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland



# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>2</b>
<b>4 Symbols</b>	<b>2</b>
<b>5 General</b>	<b>3</b>
<b>6 Information required prior to testing</b>	<b>3</b>
6.1 Items to be specified	3
6.2 Specific information required before testing	4
6.3 Written test procedure	4
<b>7 Requirements for personnel and equipment</b>	<b>4</b>
7.1 Personnel qualifications	4
7.2 Test equipment	4
7.3 Probe parameters	5
7.3.1 Test frequency	5
7.3.2 Angles of incidence	5
7.3.3 Transducer size	5
7.3.4 Adaptation of probes to curved scanning surfaces	5
7.3.5 Coupling media	6
<b>8 Testing volume</b>	<b>6</b>
<b>9 Preparation of scanning surfaces</b>	<b>6</b>
<b>10 Parent metal testing</b>	<b>6</b>
<b>11 Range and sensitivity setting</b>	<b>7</b>
11.1 General	7
11.2 Reference for sensitivity setting	8
11.3 Evaluation levels	9
11.4 Transfer correction	9
11.5 Signal-to-noise ratio	9
<b>12 Testing levels</b>	<b>9</b>
<b>13 Testing techniques</b>	<b>10</b>
13.1 General	10
13.2 Manual scan path	10
13.3 Testing for imperfections perpendicular to the testing surface	10
13.4 Location of discontinuities	10
13.5 Evaluation of indications	10
13.5.1 General	10
13.5.2 Maximum echo amplitude	10
13.5.3 Discontinuity length	10
13.5.4 Discontinuity height	10
13.5.5 Characterization of discontinuities	10
<b>14 Test report</b>	<b>11</b>
<b>Annex A (normative) Testing levels for various types of welded joints</b>	<b>13</b>
<b>Bibliography</b>	<b>30</b>

## ISO 17640:2018(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

Any feedback, question or request for official interpretation related to any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 5 via your national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html). Official interpretations, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

This fourth edition cancels and replaces the third edition (ISO 17640:2017), which has been technically revised. The main change compared to the previous edition is that Figure A.4 a) and b) has been corrected.

# Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment

## 1 Scope

This document specifies techniques for the manual ultrasonic testing of fusion-welded joints in metallic materials of thickness  $\geq 8$  mm which exhibit low ultrasonic attenuation (especially that due to scatter) at object temperatures from 0 °C to 60 °C. It is primarily intended for use on full penetration welded joints where both the welded and parent material are ferritic.

Where material-dependent ultrasonic values are specified in this document, they are based on steels having an ultrasonic sound velocity of  $(5\,920 \pm 50)$  m/s for longitudinal waves and  $(3\,255 \pm 30)$  m/s for transverse waves.

This document specifies four testing levels, each corresponding to a different probability of detection of imperfections. Guidance on the selection of testing levels A, B, and C is given in [Annex A](#).

This document specifies that the requirements of testing level D, which is intended for special applications, be in accordance with general requirements. Testing level D can only be used when defined by specification. This includes tests of metals other than ferritic steel, tests on partial penetration welds, tests with automated equipment, and tests at object temperatures outside the range 0 °C to 60 °C.

This document can be used for the assessment of discontinuities, for acceptance purposes, by either of the following techniques:

- a) evaluation based primarily on length and echo amplitude of the discontinuity;
- b) evaluation based on characterization and sizing of the discontinuity by probe movement techniques.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5577, *Non-destructive testing — Ultrasonic testing — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 11666, *Non-destructive testing of welds — Ultrasonic testing — Acceptance levels*

ISO 16810, *Non-destructive testing — Ultrasonic testing — General principles*

ISO 16811, *Non-destructive testing — Ultrasonic testing — Sensitivity and range setting*

ISO 16826, *Non-destructive testing — Ultrasonic testing — Examination for discontinuities perpendicular to the surface*

ISO 17635, *Non-destructive testing of welds — General rules for metallic materials*

ISO 23279, *Non-destructive testing of welds — Ultrasonic testing — Characterization of discontinuities in welds*

EN 12668 (all parts), *Non-destructive testing — Characterization and verification of ultrasonic examination equipment*

## ISO 17640:2018(E)

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5577 and ISO 17635 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>


### 4 Symbols

The symbols in [Table 1](#) apply.

**Table 1 — Symbols**

Symbol	Definition	Unit
AL	acceptance level	—
$D_{\text{DSR}}$	diameter of the disk-shaped reflector (flat-bottomed hole)	mm
$h$	extension of the discontinuity in depth direction	mm
$l$	length of the discontinuity	mm
$l_x$	projected length of the discontinuity in the x-direction	mm
$l_y$	projected length of the discontinuity in the y-direction	mm
$p$	full skip distance	mm
$t$	thickness of parent material <sup>a</sup>	mm
$x$	position of the discontinuity in the longitudinal direction	mm
$y$	position of the discontinuity in the transverse direction	mm
$z$	position of the discontinuity in the depth direction	mm
<sup>a</sup> If the joined parts are not of equal thickness, $t$ represents the smallest thickness.		

Indications shall be considered to be originating from either longitudinal or transverse discontinuities, depending on the direction of their major dimension with respect to the weld axis,  $x$ , in accordance with [Figure 1](#).

**Key**

1 origin

**Figure 1 — Coordinate system for defining the location of discontinuities****5 General**

The purpose of this document is to describe general techniques of ultrasonic weld testing, using standard criteria, for the most commonly used welded joints at object temperatures in the range 0 °C to 60 °C. The specific requirements of this document cover the test equipment, preparation, performance of testing, and reporting. The parameters specified, in particular those for the probes, are compatible with the requirements of ISO 11666 and ISO 23279.

If the joined parts are not of equal thickness, the smallest thickness shall be considered.

The techniques used shall be specified.

**6 Information required prior to testing****6.1 Items to be specified**

These include:

- a) method for setting the reference level;
- b) method to be used for the evaluation of discontinuities;
- c) acceptance levels;
- d) testing level;
- e) manufacturing and operation stage(s) at which the testing is to be carried out;
- f) qualification of personnel;
- g) extent of the testing for transverse discontinuities;
- h) requirements for additional tandem testing (according to ISO 16826);