



SLOVENSKI STANDARD
oSIST prEN ISO 10993-12:2019
01-julij-2019

Biološko ovrednotenje medicinskih pripomočkov - 12. del: Priprava vzorcev in referenčni materiali (ISO/DIS 10993-12:2019)

Biological evaluation of medical devices - Part 12: Sample preparation and reference materials (ISO/DIS 10993-12:2019)

Biologische Beurteilung von Medizinprodukten - Teil 12: Probenvorbereitung und Referenzmaterialien (ISO/DIS 10993-12:2019)

Évaluation biologique des dispositifs médicaux - Partie 12: Préparation des échantillons et matériaux de référence (ISO/DIS 10993-12:2019)

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e1648e807da1/osist-pr-en-iso-10993-12-2019>

Ta slovenski standard je istoveten z: prEN ISO 10993-12

ICS:

11.100.20	Biološko ovrednotenje medicinskih pripomočkov	Biological evaluation of medical devices
-----------	---	--

oSIST prEN ISO 10993-12:2019 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 10993-12:2019](https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019)

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 10993-12

ISO/TC 194

Secretariat: DIN

Voting begins on:
2019-05-08Voting terminates on:
2019-07-31

Biological evaluation of medical devices —

Part 12:

Sample preparation and reference materials

*Évaluation biologique des dispositifs médicaux —**Partie 12: Préparation des échantillons et matériaux de référence*

ICS: 11.100.20

iTeh STANDARD PREVIEW

(standards.iteh.ai)

[oSIST prEN ISO 10993-12:2019](https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019)<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 10993-12:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 General requirements.....	3
5 Reference materials (RMs).....	4
5.1 General.....	4
5.2 Certification of RMs for biological safety testing.....	4
6 Use of RMs as experimental controls.....	4
7 Test sample selection.....	5
8 Test sample and RM preparation.....	5
9 Selection of representative portions from a medical device.....	6
10 Preparation of extracts of samples.....	6
10.1 General.....	6
10.2 Containers for extraction.....	6
10.3 Extraction conditions and methods.....	7
10.4 Extraction conditions for materials that polymerize <i>in situ</i>	10
11 Records.....	10
Annex A (informative) Experimental controls.....	11
Annex B (informative) General principles on, and practices of, test sample preparation and sample selection.....	13
Annex C (informative) Principles of test sample extraction.....	15
Annex D (informative) Exhaustive extraction of polymeric materials for biological evaluation.....	18
Annex ZA (informative) Relationship between this European Standard and the essential requirements of Directive 93/42/EEC [1993 OJ L 169] aimed to be covered.....	20
Annex ZB (informative) Relationship between this European Standard and the essential requirements of Directive 90/385/EEC [1990 OJ L 189] aimed to be covered.....	22
Annex ZC (informative) Relationship between this European standard and the General Safety and Performance Requirements of Regulation (EU) 2017/745 aimed to be covered.....	24
Bibliography.....	26

ISO/DIS 10993-12:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 194, *Biological and clinical evaluation of medical devices*.

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-1c618a7e4f10993-12-2019>

This fifth edition cancels and replaces the fourth edition (ISO 10993-12:2012), which has been technically revised.

The main changes compared to the previous edition are as follows:

- change of scope to cover extractions only for biological evaluation tests,
- harmonization of definitions with ISO 10993-18,
- revision of [10.3.1](#) extraction condition table and [Annex D](#) regarding exhaustive extraction.

A list of all parts in the ISO 10993- series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

It is important that sample preparation methods be appropriate for both the biological evaluation methods and the materials being evaluated. Each biological test method requires the selection of materials, extraction solvents and conditions.

This document is based on existing national and international specifications, regulations and standards wherever possible.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 10993-12:2019](https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019)

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 10993-12:2019](https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019)

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-e16d8a807da1/osist-pren-iso-10993-12-2019>

Biological evaluation of medical devices —

Part 12:

Sample preparation and reference materials

1 Scope

This document specifies requirements and gives guidance on the procedures to be followed in the preparation of samples and the selection of reference materials for medical device testing in biological test systems only in accordance with one or more parts of ISO 10993. Specifically, this document addresses the following:

- test sample selection;
- selection of representative portions from a medical device;
- test sample preparation;
- experimental controls;
- selection of, and requirements, for reference materials;
- preparation of extracts.

This document is not applicable to live cells, but can be relevant to the material or medical device components of combination products containing live cells.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

blank

extraction vehicle not containing the test material, which is exposed to identical vessels and conditions as the test sample during extraction

Note 1 to entry: The purpose of the blank is to evaluate possible confounding effects due to the extraction vessel, extraction vehicle and extraction process.

ISO/DIS 10993-12:2019(E)

3.2

certified reference material**CRM**

reference material (RM) characterized by a metrologically valid procedure for one or more specified properties, accompanied by an RM certificate that provides the value of the specified property, its associated uncertainty, and a statement of metrological traceability

Note 1 to entry: The concept of value includes a nominal property or a qualitative attribute such as identity or sequence. Uncertainties for such attributes may be expressed as probabilities or levels of confidence.

Note 2 to entry: Metrologically valid procedures for the production and certification of RMs are given in, among others, ISO Guide 34 and ISO Guide 35.

Note 3 to entry: ISO Guide 31 gives guidance on the contents of RM certificates.

Note 4 to entry: ISO/IEC Guide 99:2007 has an analogous definition (5.14).

[SOURCE: ISO Guide 30:2015, 2.1.2]

3.3

exaggerated extraction

extraction that is intended to result in a greater amount of a chemical constituent being released as compared to the amount generated under the simulated conditions of use

Note 1 to entry: It is important to ensure that the exaggerated extraction does not result in a chemical change of the material.

3.4

exhaustive extraction

extraction conducted until the amount of extractable material in a subsequent extraction is less than 10 % by gravimetric analysis (or that achieved by other means) of that detected in the initial extraction

Note 1 to entry: As it is not possible to demonstrate the exhaustive nature of residual recovery, the definition of exhaustive extraction adopted is as above. See also [Annex C](#).

3.5

experimental control

substance with well-characterized responses, which is used in a specific test system to assist in evaluating if the test system has responded in a reproducible and appropriate manner

3.6

extract

liquid that results from extraction of the test sample or control

3.7

extractables

substances that can be released from a medical device or material using extraction solvents and/or extraction conditions that are expected to be at least as aggressive as the conditions of clinical use

3.8

homogeneous

property of a material and its relationship to a biological endpoint, meaning that it is of uniform composition, and chemical/physical characteristics thereby producing a consistent test result

Note 1 to entry: A reference material is said to be homogeneous if the biological response to a specific test is found to lie within the specified uncertainty limits of the test, irrespective of the batch or lot of material from which the test sample is extracted.

3.9

leachables

substances that can be released from a medical device or material during clinical use

iTeh STANDARD PREVIEW
(standards.iteh.ai)

oSIST prEN ISO 10993-12:2019

<https://standards.iteh.ai/catalog/standards/sist/97e0edca-9977-47ec-8532-a1c18a817da/osis-pr-en-iso-10993-12-2019>

3.10**negative control**

any well-characterized material and/or substance, which, when tested by a specific procedure, demonstrates the suitability of the procedure to yield a reproducible, appropriately negative, non-reactive or minimal response in the test system

Note 1 to entry: In practice, negative controls are reference materials but can include blanks and extraction vehicles/solvents.

3.11**positive control**

any well-characterized material and/or substance, which, when evaluated by a specific test method, demonstrates the suitability of the test system to yield a reproducible, appropriately positive or reactive response in the test system

3.12**reference material****RM**

material, sufficiently homogeneous and stable with respect to one or more specified properties, which has been established to be fit for its intended use in a measurement process

Note 1 to entry: RM is a generic term.

Note 2 to entry: Properties can be quantitative or qualitative, e.g. identity of substances or species.

Note 3 to entry: Uses may include the calibration of a measurement system, assessment of a measurement procedure, assigning values to other materials, and quality control.

Note 4 to entry: ISO/IEC Guide 99:2007 has an analogous definition (5.13), but restricts the term “measurement” to apply to quantitative values. However, Note 3 of ISO/IEC Guide 99:2007, 5.13 (VIM), specifically includes qualitative properties, called “nominal properties”

[SOURCE: ISO Guide 30:2015, 2.1.1]

3.13**simulated-use extraction**

extraction performed using a method that simulates product use

Note 1 to entry: The laboratory is to demonstrate that the simulated-use extraction is carried out under conditions that provide an appropriate representation of intended use. Product-use simulation is carried out assuming the medical device is assigned to the most stringent category possible for the duration of exposure and takes into consideration both the tissue(s) exposed and the temperature of exposure.

3.14**stability**

characteristic of a material, when stored under specified conditions, to maintain a specified property value within specified limits for a specified period of time

Note 1 to entry: See also the IUPAC Compendium of Analytical Nomenclature^[5].

3.15**test sample**

medical device, component or material (or a representative sample thereof, manufactured and processed by equivalent methods), or an extract or portion thereof that is subjected to biological evaluation testing

4 General requirements

When identifying hazards and estimating risk in relation to medical devices, hazards that arise from changes in the manufacturing process, or insufficient control of the manufacturing process, shall be considered in the design and preparation of test samples, as described in ISO 14971. Particular attention

ISO/DIS 10993-12:2019(E)

shall be given to material additives, unintentional base material impurities and manufacturing process residues, e.g. trace elements, and cleaning and disinfection agents.

The ISO 10993- series describes many different biological assay systems. Therefore, the individual parts shall be consulted to ascertain whether these are appropriate for specific test systems.

Experimental controls shall be used in biological evaluations carried out in order to validate a test procedure and/or to compare the results between materials. Depending on the specifications of a particular test, negative controls, blanks and/or positive controls shall be used.

NOTE The same type of control can be applicable to different tests and can allow cross-reference to other established materials and test methods. Additional guidance on the selection of experimental controls is given in [Annex A](#). Use of positive controls for *in vivo* testing might be affected by animal welfare regulations.

5 Reference materials (RMs)

5.1 General

RMs are established by individual laboratories. The extent of chemical, physical and biological characterization is determined by the individual laboratory. Commercially available articles may be used as RM.

NOTE 1 See also ISO Guide 35.

CRMs are selected for their high purity, critical characteristics, suitability for the intended purpose and general availability. The critical chemical, physical and biological characteristics shall be determined by collaborative testing in three or more laboratories, and made available to the investigator by the distributor.

NOTE 2 It is desirable for users to obtain a commitment from suppliers of RMs or CRMs stating that these materials will be available to the user for at least five years. A second but less desirable option is for the source of the RM or CRM to publish an "open formulation" for the material, i.e. publication of the source materials and details of the processing needed to ensure uniform batches of the RM.

5.2 Certification of RMs for biological safety testing

Qualification of an RM is a procedure that establishes the numerical or qualitative value of the biological response of the material under specified test conditions, ensuring reproducibility of the response within and/or between laboratories. The range of biological responses associated with the material shall be established through laboratory tests.

NOTE See also ISO 17034.

Suppliers of RMs shall certify the materials. The supplier determines the extent of chemical and physical characterization that is performed. The individual laboratories that use the RM shall identify the biological characterization necessary to qualify a RM for a specific test or procedure. Commercially available materials may be used as RM, provided they are certified and qualified.

Certification of a RM is a procedure that establishes the numerical or qualitative value of the biological response of the material under the specified test conditions. This process serves to validate the testing of the material for that particular response and results in the issuance of a certificate. The biological response of the material shall be established through interlaboratory tests.

6 Use of RMs as experimental controls

RMs or CRMs shall be used in biological tests as control materials to demonstrate the suitability of a procedure to yield a reproducible response, i.e. positive and/or negative. Any material used in this way shall be characterized with each biological test procedure for which the use of the material is desired. A