



Designation: C1681 – 09

Standard Test Method for Evaluating the Tear Resistance of a Sealant Under Constant Strain¹

This standard is issued under the fixed designation C1681; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method evaluates the impact of an induced tear on a sealant specimen that is dimensioned, cured according to the guidelines in Test Method C719 and then subjected to a constant strain. It is effective in differentiating between sealants that are used in dynamic joints subject to abrasion, punctures, tears, or combination thereof.

1.2 Since this test method is for the evaluation of tear propagation, an adhesive failure to the substrates provides no usable data regarding tear propagation. This would be considered a failed test and that data would be discarded, or at least separated from the other data from specimens that did not experience an adhesive failure.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 The committee with jurisdiction over this standard is not aware of any comparable standards published by other organizations.

2. Referenced Documents

2.1 *ASTM Standards:*²

C719 Test Method for Adhesion and Cohesion of Elastomeric Joint Sealants Under Cyclic Movement (Hockman Cycle)

3. Terminology

3.1 *Definitions:*

3.1.1 *casting spacers*—rigid spacers made of an anti-adherent material used in the fabrication of joints to maintain the joint dimension during the extrusion, tooling and curing of the sealant material.

¹ This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.20 on General Test Methods.

Current edition approved Jan. 1, 2009. Published February 2009. DOI: 10.1520/C1681-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.1.2 *separators*—rigid spacers used to maintain a constant strain on the joint specimens during the testing period while maintaining parallel bond surfaces.

4. Summary of Test Method

4.1 Test specimens are fabricated and cured in accordance with Test Method C719. At the end of the 21-day cure period, an induced tear is created in the specimens by making a cut with a sharp blade in the midpoint of the joint. The specimens are then extended to a specified strain at both standard conditions and at $-26 \pm 2^\circ\text{C}$ ($-15 \pm 3^\circ\text{F}$). Propagation of the induced tear is measured at 0, 24 and 168 h.

5. Significance and Use

5.1 This test method is intended to determine if a joint that is subjected to a mechanically induced cut will resist tear propagation during normal joint movement. A sealant with a high resistance to tear propagation will typically perform better than a sealant with a low resistance to tear propagation.

6. Apparatus

6.1 A device capable of extending the test specimens to the specified strain.

6.2 *Freezer*, to maintain a constant temperature of -26°C .

6.3 A suitable measuring device such as calipers able to measure the induced tears to 0.01 mm.

6.4 *#17 Knife Blade*, 9 mm ($\frac{3}{8}$ in.) wide.

7. Reagents and Materials

7.1 *Spatulas*, for use in applying the sealant.

7.2 *Caulking Gun*, for extruding sealant from cartridges when applicable.

7.3 *Glass Substrates*—twelve substrates, with minimum dimensions of 25 by 75 mm (1 by 3 in.) of the same finish are required for each test specimen. Glass is the default substrate, however as mentioned in the scope, this is not an adhesion test, therefore the sealant must exhibit excellent adhesion to the substrate. Other rigid substrates in the above noted dimension are indeed acceptable.

7.4 *Casting Spacers*—Made from polytetrafluoroethylene (PTFE) or a suitable rigid material shall be used with each test

specimen to which the test sealant will not bond and will provide the appropriate joint dimensions and configurations. These spacers are machined to provide exact joint dimensions of 12.7 by 12.7 by 50.8 mm ($\frac{1}{2}$ by $\frac{1}{2}$ by 2 in.). See Fig. 5 in Test Method C719.

7.5 *Separators*, to provide a constant strain on the specimen while maintaining parallel bond surfaces.

7.6 *Substrate Cleaning Material*.

7.7 *Primer*, if required on the substrates.

7.8 A suitable measuring device, such as calipers, capable of measuring the induced cut in the sealant and additional changes in the cut to 0.01 mm.

7.9 *Marker*, to identify the exact placement of the induced cut.

7.10 A device which holds a #17 knife blade 9 mm ($\frac{3}{8}$ in.) wide to induce the cut into the test specimens. See Fig. 1.

8. Conditioning

8.1 *Multicomponent Sealants*—Prepare six test specimens for each type of substrate that is to be used in the test. After maintaining the unopened sample for at least 24 h at standard conditions, mix thoroughly for 5 min at least 250 g of base compound with the appropriate amount of curing agent. Extrude the sealant 12.7 by 12.7 by 50.8 mm ($\frac{1}{2}$ by $\frac{1}{2}$ by 2 in.) between parallel 25.4 by 76.2 mm (1 by 3 in.) faces of similar blocks or plates. Use appropriate casting spacer blocks to form the proper size of the bead. Apply polyethylene adhesive tape or any other suitable inert release agent to the inside surfaces of the spacers to prevent adhesion of the spacers to the sealant after cure. Use adhesive tape, rubber bands, or clamps to hold the test assembly together before and after filling it with the compound. In the case of a pourable-type compound, use masking or any other suitable tape to retain the compound.

8.2 Clean the test substrates using the methods suggested in Test Method C719. Fabricate the joints using the casting

spacers. Mask off the top of the substrate edges, extrude the test sealant into the cavity taking care to fill in the all of the corners, tool the top surface flat, and remove the masking tape.

8.3 *Single-Component Sealants*—Prepare six test specimens as described in 8.1 except that no mixing of components is required. Condition the sealed cartridge or bulk container at standard conditions at least 24 h before use.

8.4 Cure specimens made with multicomponent sealants for 14 days at standard conditions. During the second week of the curing period, free the compound from the spacer blocks at the ends and bottom without damaging the sealant bead.

8.5 Cure specimens made with single-component sealants for a total of 21 days at standard conditions. See 8.6.1.

8.6 Separate the casting spacers from the sealant as soon as practical during the curing period without damaging the sealant. Fourteen days is typically necessary.

8.6.1 The producer may request conditions other than those specified in 8.5 for the curing period of single-component sealants provided they meet the following requirements: (1) The curing period shall extend for 21 days; and (2) The temperature during the curing period shall not exceed 50°C (122°F).

9. Procedure

9.1 Within 8 h after the cure period (14 days for multicomponent or 21 days for single component products), mark the exact location for the induced cut with a permanent marker and then induce a cut, 9 mm ($\frac{3}{8}$ in.) in length, and 12.7 mm ($\frac{1}{2}$ in.) deep with the #17 knife blade. See Fig. 2. Make the cut as parallel as possible to the long direction of the sample, located directly on the midpoint and go perpendicularly through thickness of the sealant.

9.2 Extend all specimens until the separation between the substrates provides the desired/specified extension (in the absence of a specified strain, the sealant shall be strained to its Test Method C719 movement capability). Apply this strain at a minimum rate of 3 mm per hour ($\frac{1}{8}$ in. per hour). See Appendix X2.

9.3 When the specimens have reached their specified extension, block the specimens with the appropriate separator and remove from the extension device/machine. Do not remove separators for the duration of test.

9.4 Measure and record the length and width of the induced cut, immediately after the joints have been blocked at the specified strain. This is the 0 hour data.

9.5 Place three specimens in the freezer at $-26 \pm 2^\circ\text{C}$.

9.6 Place three specimens at room temperature laboratory conditions.

9.7 After 24 and 168 h, measure and record the length and width of the induced cut on the top of the joint and record the observed character of the tearing on the X and Y axis as noted in Fig. 3 (i.e., clean versus jagged, direction of the tear propagation, propagation of the tear at one or both ends of the induced cut, etc.).



FIG. 1 #17 Blade