



Standard Specification for Cured-In-Place Thermosetting Resin Sewer Piping Systems¹

This standard is issued under the fixed designation D 5813; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers cured-in-place thermosetting resin pipe (CIPP), 4 through 132-in. (100 through 3353-mm) equivalent diameter, for use in gravity flow systems for conveying sanitary sewage, storm water, and certain industrial wastes. This specification is suited for the evaluation and testing of materials used in the rehabilitation of existing pipes by the installation and cure of a resin-impregnated fabric liner.

1.2 This specification can also be extended to cover manholes, pump stations, wetwells, vaults, storage tanks, and other similar structures where a cured in place liner using thermosetting resin is applicable.

~~1.3 The values given in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.~~

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

NOTE 1—There are no ISO standards covering the primary subject matter of this specification.

1.4 The following safety hazards caveat pertains only to the test methods portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D 543 ~~Test Method~~ Practices for Evaluating the Resistance of Plastics to Chemical Reagents

D 638 Test Method for Tensile Properties of Plastics

D 695 Test Method for Compressive Properties of Rigid Plastics

D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D 883 Terminology Relating to Plastics

D 1600 Terminology for Abbreviated Terms Relating to Plastics

~~D 1682 Test Methods of Test for Breaking Load and Elongation of Textile Fabrics~~ ³ c6d4c87e6/astm-d5813-042008

D 3039/D 3039M ~~Test Method for Tensile Properties of Fiber-Resin Composites~~ Test Method for Tensile Properties of Polymer Matrix Composite Materials

D 3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings

D 3681 ~~Test Method for Chemical Resistance of “Fiberglass” (Glass-Fiber-Fiberglass (GlassFiberReinforced Thermosetting-Resin) Pipe in a Deflected Condition~~

D 4814 Specification for Automotive Spark—Ignition Engine Fuel

F 412 Terminology Relating to Plastic Piping Systems

F 1216 Practice for Rehabilitation of Existing Pipelines and Conduits by the Inversion and Curing of a Resin-Impregnated Tube

F 1743 Practice for Rehabilitation of Existing Existing Pipelines and Conduits by Pulled-in-Place Installation of Cured-in-Place Thermosetting Resin Pipe (CIPP)

F 2019 ~~Practice for Rehabilitation of Existing Existing Pipelines and Conduits by Pulled-in-Place~~ the Pulled in Place Installation of Glass Reinforced Plastic (GRP) Cured-in-Place Thermosetting Resin Pipe (CIPP)

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is under the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping Systems and Chemical Equipment.

~~Current edition approved Mar. 1, 2004. Published March 2004.~~

~~Originally approved in 1995. Last previous edition approved in 1995 as D5813-95.~~

~~Current edition approved Dec. 15, 2008. Published February 2009. Originally approved in 1995. Last previous edition approved in 2004 as D 5813-04.~~

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

3. Terminology

3.1 *General*—Definitions are in accordance with Terminologies D 883 and F 412. Abbreviations are in accordance with Terminology D 1600, unless otherwise indicated.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *cured-in-place pipe (CIPP)*—hollow cylinder or shape consisting of a fabric with cured (cross-linked) thermoset resin; interior or exterior plastic tube coatings, or both, may be included; this pipe is formed within and takes the shape of an existing conduit or structure.

3.2.2 *delamination*—separation of coating or layers of the CIPP, or both.

3.2.3 *dry spot*—a fabric area of the finished CIPP which is deficient or devoid of resin.

3.2.4 *fabric tube*—a flexible material formed into a tubular shape which during the installation process is saturated with resin and holds the resin in place during the cure.

3.2.5 *fully deteriorated pipe*—the original pipe is not structurally sound and cannot support soil and live loads or is expected to reach this condition over the design life of the rehabilitated pipe.

3.2.6 *lift*—a portion of the CIPP that has pulled away from the existing conduit wall and formed a reverse (inward) curvature of the CIPP relative to the existing conduit.

3.2.7 *partially deteriorated pipe*—the original pipe can support the soil and live loads throughout the design life of the rehabilitated pipe. The soil adjacent to the existing pipe must provide adequate side support. The pipe may have longitudinal cracks and some distortion of the diameter.

3.2.8 *qualification test*—one or more tests used to prove the design of a product; not a routine quality control test.

3.2.9 *quality assurance test*—one or more tests used to verify the physical properties of the CIPP.

3.2.10 *quality control test*—one or more tests used by the manufacturer of the tube during manufacture or assembly.

3.2.11 *tube coating*—a plastic coating on the outside or inside surface, or both, of the fabric tube.

4. Classification

4.1 *Types of CIPP:*

4.1.1 *Type I*—Designed to provide chemical resistance and prevent exfiltration.

4.1.2 *Type II*—Installed in a partially deteriorated existing pipe or structure and is designed to provide chemical resistance, prevent exfiltration and infiltration, and support the external hydrostatic loads due to groundwater only (and internal vacuum, where applicable), since the soil and live loads can be supported by the original conduit or structure.

4.1.3 *Type III*—Installed in a fully deteriorated existing pipe or structure and designed to provide chemical resistance, prevent exfiltration and infiltration, and support all external hydraulic, soil, and live loads acting on the original conduit or structure.

4.2 *Grades of CIPP:*

4.2.1 *Grade 1*—Thermosetting polyester resin.

4.2.2 *Grade 2*—Thermosetting polyester resin. [ASTM D5813-04\(2008\)](#)

4.2.3 *Grade 3*—Thermosetting epoxy resin. [https://standards.iteh.ai/catalog/standards/sist/d3411806-c21e-4ff7-8e15-065c6d4c87e6/astm-d5813-042008](#)

NOTE 2—For the purposes of this specification, polyester includes vinyl ester resins.

NOTE 3—The purchaser should determine or consult the manufacturer for the proper type and grade CIPP to be used under the installation and operation conditions that will exist for the project in which the pipe/structure is to be used.

5. Materials and Manufacture

5.1 *General*—The resins, fabric tube, tube coatings, fillers, and other materials, when combined as a composite structure, shall produce a pipe/structure that meets the requirements of this specification.

5.2 *CIPP Wall Composition*—The wall shall consist of a fabric tube and tube coating filled with a thermosetting (cross-linked) resin, and if used, a filler.

5.2.1 *Resin*—A thermosetting polyester or epoxy resin.

5.2.2 *Fabric Tube*—This tube shall consist of one or more layers of fabric that are compatible with the resin system used and are capable of supporting and carrying resin. The tube should be capable of withstanding installation procedures and curing temperatures. Longitudinal and circumferential joints between multiple layers of a tube should be staggered to not overlap. The tube shall be fabricated to fit its final in-place position in the original conduit, with allowance for stretch as recommended by the tube manufacturer.

5.2.2.1 *Tube Coating*—The inside or outside surface, or both, of the fabric tube may be coated with a plastic flexible material that is compatible with the tube and the resin system used. The coating shall allow visual inspection of the proper impregnation of the tube fabric with resin.

5.2.3 *Filler*—An additive which alters the thixotropic or physical properties, or both, of a resin, and when incorporated into the CIPP will not detrimentally affect its ability to meet the requirements of this specification.

~~6. Requirements~~ Requirements

6. Requirements

6.1 *Fabric Tube Strength*—The fabric tube, as a quality control test, when tested in accordance with 8.4 shall have a minimum