



Designation: ~~D3514-05~~ Designation: D 3514 – 09

Standard Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Elastomeric Pad¹

This standard is issued under the fixed designation D 3514; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the resistance to the formation of pills and other surface distortions such as fuzzing of textile fabrics. The method utilizes the Stoll Quartermaster Universal Wear Tester with the frosting attachment. The procedure is generally applicable to all types of woven and knitted fabrics.

NOTE 1—For other current test methods of testing the pilling resistance of textiles, refer to Test Methods D 3511, D 3512, and D 4970.

1.2 The fabric may be laundered or dry cleaned before testing.

1.3 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 123 [Terminology Relating to Textiles](#)

D 3511 [Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Brush Pilling Tester](#)

D 3512 [Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Random Tumble Pilling Tester](#)

D 4848 [Terminology Related to Force, Deformation and Related Properties of Textiles](#)

D 4850 [Terminology Relating to Fabrics and Fabric Test Methods](#)

D 4970 [Test Method for Pilling Resistance and Other Related Surface Changes of Textile Fabrics \(Martindale Pressure Fabrics: Martindale Tester Method\)](#)

2.2 *ASTM Adjuncts:*

ADJD3514 [Three Sets of Five Photographic Standards for Elastomeric Pad Pilling Test](#)³

3. Terminology

3.1 *Definitions:*

3.1.1 *fuzz, n*—untangled fiber ends that protrude from the surface of a yarn or fabric.

3.1.2 *pilling resistance, n*—resistance to the formation of pills on the surface of a textile fabric.

3.1.3 *pills, n*—bunches or balls of tangled fibers which are held to the surface of a fabric by one or more fibers.

3.1.4 For definitions of other textile terms used in this test method, refer to Terminology D 123.

3.1 For all terminology relating to D 13.59, Fabric Test Methods, General, refer to Terminology D 4850.

3.2 For all terminology relating to Force, Deformation and Related Properties in Textiles, refer to Terminology D 4848.

3.2.1 The following terms are relevant to this standard: fuzz, pilling resistance, pills.

3.3 For all other terminology related to textiles, refer to Terminology D 123.

4. Summary of Test Method

4.1 Pilling and other changes in surface appearance that occur in normal wear are simulated on a laboratory testing machine. Fabric samples are washed or drycleaned, depending on expected refurbishment, followed by controlled rubbing against an

¹ This test method is under the jurisdiction of ASTM Committee D13 on ~~Textiles~~; Textiles and is the direct responsibility of Subcommittee D13.60 on Fabric Test Methods, Specific.

Current edition approved Sept. 1, 2005-Jan. 15, 2009. Published October 2005-February 2009. Originally approved in 1976. Discontinued November 1995 and reinstated as D 3514 – 99. Last previous edition approved in 20022005 as D 3514 – 025

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from ASTM International Headquarters. Order Adjunct No. ADJD3514.

elastomeric pad having specifically selected mechanical properties. The degree of fabric pilling is evaluated by comparison of the tested specimens with visual standards that may be actual fabrics, or photographs of fabrics, showing a range of pilling resistance. The observed resistance to pilling is reported using an arbitrary rating scale.

5. Significance and Use

5.1 *Acceptance Testing*—This method of testing fabrics for resistance to pilling is not recommended for acceptance testing. If it is used for acceptance testing, it should be used with caution because interlaboratory data are not available. In some cases the purchaser and the supplier may have to test a commercial shipment of one or more specific materials by the best available method, even though the method has not been recommended for acceptance testing.

5.1.1 If there is a disagreement arising from differences in values reported by the purchaser and the supplier when using Test Method D 3514 for acceptance testing, the statistical bias, if any, between the laboratory of the purchaser and the laboratory of the supplier should be determined based on testing specimens randomly drawn from one sample of material of the type being evaluated. Competent statistical assistance is recommended for the investigation of bias. A minimum of two parties should take a group of test specimens which are as homogeneous as possible and which are from a lot of material of the type in question. The test specimens should then be randomly assigned in equal numbers to each laboratory for testing. The average test results from the two laboratories should be compared using an acceptable statistical protocol and probability level chosen by the two parties before the testing begins. Appropriate statistical disciplines for comparing data must be used when the purchaser and supplier cannot agree. If a bias is found, either its cause must be found and corrected, or the purchaser and the supplier must agree to interpret future test results with consideration for the known bias.

5.2 The pilling of textile fabrics is a very complex property because it is affected by many factors which may include type of fiber or blends, fiber dimensions, yarn and fabric construction, and fabric finishing treatments. The pilling resistance of a specific fabric in actual wear varies more with general conditions of use and individual wearers than in replicate fabric specimens subjected to controlled laboratory tests. This experience should be borne in mind when adopting levels of acceptability for any series of standards.

5.3 Finishes and fabric surface changes may exert a large effect on pilling. It is recommended that fabrics be tested after laundering or drycleaning, or both. Testing before refurbishing may also be advisable. Prior agreement between interested parties should determine the state of test.

5.4 Pills vary appreciably in size and appearance and depend on the presence of lint and degree of color contrast. These factors are not evaluated when pilling is rated solely on the number of pills. The development of pills may be accompanied by other surface phenomena such as loss of cover, color change, or the development of fuzz. Since the overall acceptability of a specific fabric is dependent on both the characteristics of the pills and the other factors affecting surface appearance, it is suggested that fabrics tested in the laboratory be evaluated subjectively with regard to their acceptability and not rated solely on the number of pills developed. A series of standards, based on graduated degrees of surface change of the fabric type being tested, may be set up to provide a basis for subjective ratings. The visual standards are most advantageous when the laboratory test specimens correlate closely in appearance with worn fabrics and show a similar ratio of pills to fuzz. Counting the pills and weighting their number with respect to their size and contrast, as a combined measure of pilling resistance, is not recommended because of the excessive time required for counting, sizing, and calculation.

5.5 The degree of fabric pilling is evaluated by comparing the tested specimens with visual standards, which may be actual fabrics or photographs of fabrics, showing a range of pilling resistance. The observed resistance to pilling is reported on an arbitrary scale ranging from 5 (no pilling) to 1 (very severe pilling).

5.6 This test method is applicable to a wide variety of woven and knitted fabrics that vary in pilling propensity as a result of variations in fiber, yarn and fabric structure, and finish. The applicability of the test method to non-woven fabrics has not been determined.

6. Apparatus and Materials

6.1 *Stoll Quartermaster Universal Wear Tester*,⁴ with frosting attachment.

6.2 *Elastomeric Friction Pad*,⁴ mounted on the bottom side of the tester pressure plate. This is a pad made especially for this test. It is attached to the pressure plate by means of side clamps, and secured at the front by a strip of tape.

6.2.1 *Elastomeric Base Pad*,⁴ attached to the specimen holder of the frosting attachment. This pad is made especially for this test.

6.3 *Twill Fabric*, 65/35 polyester/cotton, approximately 166.5 g/m² (5.0 oz/yd²) with moderately coarse weave, for preparation of friction pad.

6.4 *Emery Paper*, 150-grit, for preparation of the base pad.

6.5 *Rubber Ring*,⁴ 50 ± 1 mm (2 ± 0.1 in.) inside diameter and 61 ± 1 mm (2.44 ± 0.1 in.) outside diameter, to secure the specimen to the holder.

⁴ Available from Atlas Electric Devices Co., 4114 Ravenswood Ave., Chicago, IL 60613.

⁴ For additional information on obtaining apparatus, equipment, or supplies that may be suitable for use in this standard, please visit the ASTM Manufacturers' Equipment Directory at www.astm.org.