

---

---

**Imaging materials — Photo books —  
Test methods for permanence and  
durability**

*Matériaux pour l'image — Albums photos — Méthodes d'essai de  
permanence et de durabilité*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 18948:2018

<https://standards.iteh.ai/catalog/standards/sist/b7c81027-9318-44f2-b637-8998258056e5/iso-18948-2018>



## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 18948:2018

<https://standards.iteh.ai/catalog/standards/sist/b7c81027-9318-44f2-b637-8998258056e5/iso-18948-2018>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>v</b>
<b>Introduction</b>	<b>vi</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>2</b>
<b>4 Image permanence tests for covers and pages</b>	<b>4</b>
4.1 General	4
4.2 Sample preparation	4
4.3 Thermal stability during long-term dark storage	5
4.3.1 General	5
4.3.2 Procedures	5
4.3.3 Reporting	5
4.4 Light stability	6
4.4.1 General	6
4.4.2 Covers	6
4.4.3 Pages	6
4.4.4 Reporting	6
4.5 Ozone stability	6
4.5.1 General	6
4.5.2 Covers	6
4.5.3 Pages	7
4.5.4 Reporting	7
4.6 Humidity stability	7
4.6.1 General	7
4.6.2 Covers and pages	7
4.6.3 Reporting	7
<b>5 Book integrity tests</b>	<b>8</b>
5.1 General	8
5.2 Ageing conditions	8
5.3 Page pull test	8
5.3.1 General	8
5.3.2 Test procedure	9
5.3.3 Alternate test procedure	9
5.3.4 Calculation of the binding strength	10
5.4 Peeling and lamination durability	10
5.4.1 General	10
5.4.2 Resistance to delamination	11
5.4.3 Assessment of age related lamination and binding strength	11
5.4.4 Peeling resistance and lamination bond strength for protective laminate	11
5.4.5 Internal bond strength for glued single side sheets	11
5.4.6 Test sample preparation, results assessment and reporting	12
5.5 Book block attachment to the cover (heat durability)	12
5.5.1 General	12
5.5.2 Book binding strength (heat durability)	12
5.5.3 Opening and closing durability	12
<b>6 Book blocking</b>	<b>13</b>
6.1 General	13
6.2 Test conditions	13
6.3 Test target design	14
6.4 Conditioning of test specimen	15
6.5 Test methods	15
6.5.1 General	15

6.5.2	Equipment and calibration .....	16
6.5.3	Test environment control .....	16
6.5.4	Long term storage (hot/dry) test .....	17
6.5.5	Long term storage (warm/humid) test .....	17
6.5.6	Short term transport test .....	17
6.6	Evaluation .....	17
6.6.1	General considerations .....	17
6.6.2	Reporting .....	17
6.6.3	Additional evaluations .....	18
<b>7</b>	<b>Deformation caused by humidity .....</b>	<b>18</b>
7.1	Page deformation of a photo book (waviness) .....	18
7.1.1	General .....	18
7.1.2	Procedure .....	18
7.1.3	Reporting .....	19
7.2	Cover deformation of a photo book (warp) .....	20
7.2.1	General .....	20
7.2.2	Procedure .....	20
7.2.3	Reporting .....	21
<b>Annex A (informative) Guidelines for data interpretation .....</b>		<b>22</b>
<b>Annex B (informative) Abrasion .....</b>		<b>24</b>
<b>Annex C (informative) Extreme photo book tests .....</b>		<b>26</b>
<b>Annex D (informative) Sandwich thermal test method .....</b>		<b>29</b>
<b>Annex E (normative) Lamination and delamination testing procedures .....</b>		<b>31</b>
<b>Bibliography .....</b>		<b>34</b>

<https://standards.iteh.ai/catalog/standards/sist/b7c81027-9318-44f2-b637-8998258056e5/iso-18948-2018>  
 ISO 18948:2018

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 42, *Photography*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

Photo books are bound books with printed pages comprised of integrated photos, along with artwork and text, designed by and usually dedicated to a limited group of people.

Like photographic prints, photo books are produced on the widest available spectrum of production, from large run commercial facilities to one-off home kits. Their expected permanence and durability can cover a similarly broad range. Careful consideration should be given to the materials used in the construction of photo books to insure high permanence of the printed images<sup>[32]</sup> and of the books themselves<sup>[33]</sup>.

Photo books are typically stored in a closed condition, either in a stack or on a book shelf; consequently environmental factors that may adversely affect displayed prints, such as light and ozone, may not be applicable to the preservation of the inside pages of a photo book. The user is cautioned that these factors may become relevant if the photo book is displayed or otherwise exposed to light or other environmental factors for an extended period of time. ISO 18937 and ISO 18941 provide guidelines on testing for the effect of light and ozone on photo books.

The test methods included in this document assume that the photo book will be stored and used in environments that may or may not be climate controlled. For this reason, it includes test conditions designed to assess the adverse effects of humidity and temperature that may be outside of recommended long-term and medium-term storage conditions as described in ISO 18920. It also includes test conditions intended to simulate short duration exposure of photo books to the interior of a hot vehicle.

This document contains many specific tests for various binding systems and printing processes. It is not the intention of this document to require that all possible combinations be tested. Testing all combinations of sizes, cover materials, binding options and printing processes is not possible due to the large number of combinations. However, testing representative combinations of materials is encouraged.

[ISO 18948:2018](https://standards.iteh.ai/catalog/standards/sist/b7c81027-9318-44f2-b637-8998258056e5/iso-18948-2018)

<https://standards.iteh.ai/catalog/standards/sist/b7c81027-9318-44f2-b637-8998258056e5/iso-18948-2018>

# Imaging materials — Photo books — Test methods for permanence and durability

## 1 Scope

This document specifies test methods to assess the permanence and durability of photo books, including cover and pages.

This document is applicable to photo books which contain reflection colour prints made with colour hardcopy materials of all types, including those from either traditional analogue printing or modern digital printing processes. The same performance test methods apply, regardless of the printing process. Because of the large number of combinations of sizes, cover materials, binding options and printing processes, testing of all possible combinations is not within the scope of this document. Instead, a representative selection of printed pages, cover materials and binding options that are used in the makeup of the photo book are tested.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets*

ISO 11800:1998, *Information and documentation — Requirements for binding materials and methods used in the manufacture of books*

ISO 18913, *Imaging materials — Permanence — Vocabulary*

ISO 18924, *Imaging materials — Test method for Arrhenius-type predictions*

ISO 18931, *Imaging materials — Recommendations for humidity measurement and control*

ISO 18936, *Imaging materials — Processed colour photographs — Methods for measuring thermal stability*

ISO 18937, *Imaging materials — Photographic reflection prints — Methods for measuring indoor light stability*

ISO 18941:2017, *Imaging materials — Colour reflection prints — Test method for ozone gas fading stability*

ISO 18946, *Imaging materials — Reflection colour photographic prints — Method for testing humidity fastness*

ISO 18949<sup>1)</sup>, *Imaging Materials — Reflection colour photographic prints — Method for testing stability under low humidity conditions*

ISO 19594, *Graphic technology — Test method for the determination of the binding strength for perfect-bound products — Page-pull test working upwards*

ASTM F904, *Standard Test Method for Comparison of Bond Strength or Ply Adhesion of Similar Laminates Made from Flexible Materials*

1) Under preparation. Stage at the time of publication: ISO/DIS 18949:2018.

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18913 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **photo book**

bound book with printed pages comprised of integrated personal photos along with artwork and text, designed by and usually dedicated to a limited group of people

#### 3.2

##### **cover**

protective covering on the front, back, and spine of a book, including any associated adhesives, binding boards, liners, and laminates

#### 3.3

##### **blister**

localized delamination of a multilayer assembly that looks like a bubble

#### 3.4

##### **delamination**

separation of a laminated assembly into its constituent layers, either in whole or in part

#### 3.5

##### **laminate**

layer of material that goes over one or both sides of a printed page

Note 1 to entry: Usually the laminate layer provides moisture barrier and abrasion resistance, as well as UV shielding, to add protection to the photo images from physical damage and colour fading.

#### 3.6

##### **lamine**

<film> clear polymeric layer applied using thermosetting or pressure-sensitive adhesive to one or both surfaces of a print to improve durability

#### 3.7

##### **lamine**

<liquid coating> water-based, solvent-based, or UV-curable liquid protective coating applied to one or both surfaces of a print to improve durability

#### 3.8

##### **laminated assembly**

multilayer structure typically comprising a paper support, one or more barrier layers, an imaging layer, and a protective laminate top layer

Note 1 to entry: Laminated assemblies include films or coatings adhered to the surface of pages or covers, prints adhered back-to-back to each other forming a completed page.

#### 3.9

##### **lay-flat**

binding that allows for an uninterrupted image across the binding, either by using flexible, hinged pages or by adhering the front and reverse sides of each page together



**3.10****sandwich sample holder**

metal fixture intended to hold three components in a flattened, pressed-together position so that airflow to the printed areas of the middle component is restricted as a function of the permeability of the two outer components

Note 1 to entry: This type of sample holder is suitable for sandwich thermal test method written in [Annex D](#).

**3.11****sample sandwich thermal test method**

thermal stability test method that complies with ISO 18936 except that the sandwich sample holder is used in place of the free hanging sample holding method

**3.12****blocking**

undesired adhesion between sheets of printed material that occurs under moderate pressure, high temperature, or high humidity, while in storage or in use that leads to undesirable effects such as delamination, paper splitting, tearing, ferrotyping, colourant transfer, or edge deformation

**3.13****sticking**

temporary adhesion of prints in a stack or pages in a photo book but without physical damage when adjacent prints or pages are separated

**3.14****ferrotyping**

changes in surface gloss resulting from intimate contact with another surface, often associated with high humidity

Note 1 to entry: The term ferrotyping is derived from a historical term associated with silver halide photography. It is a process used to produce a very high gloss surface on a gelatine silver halide print in which a damp print is placed in contact with a highly polished surface, such as chromium-plated steel, and dried under conditions of elevated temperature and pressure.

**3.15****bleeding**

lateral migration of colourant

**3.16****colourant transfer**

transfer of colourant from one sheet to the other sheet, when both sheets are placed in direct contact

**3.17****curling**

physical deformation of a page, a cover, a stack of prints or a bound photo book resulting in departure from physical flatness with the tendency to curve into a concave or convex shape

**3.18****wrinkling**

physical deformation of a page or a cover of a photo book resulting in departure from physical flatness with the tendency to make furrows, crinkles, folds, ridges or creases

**3.19****warp**

distortion of the front and/or back covers of a bound book, so that the covers do not lie flat against the book block

**3.20****book block**

text block, including the endpapers and other materials added by the binder, before casing in

### 3.21

#### **waviness**

physical deformation of a page or a cover of a photo book resulting in departure from physical flatness with the tendency to curve alternately in opposite directions, resembling or suggesting waves

### 3.23

#### **cockle**

planar distortion in flat materials, especially paper or vellum, that is characterized by puckering, waves, or rippling

### 3.24

#### **edge fluting**

wave-shaped deformation along the edges of cut sheets and may be caused by an expansion of the edge of the material, which is exposed to greater variations in temperature and humidity than the centre

## 4 Image permanence tests for covers and pages

### 4.1 General

Although the individual pages of most photo books are not typically exposed to light and pollutants in the ambient environment for long periods of time, it is useful to know how stable the printed pages are if the book were to be left open to the environment for extended periods of time. Therefore, the tests described in this clause are intended to be carried out on individual printed sheets or pages of a photo book. In addition, these tests are also intended for photo book covers. Different use profiles are addressed in specification documents.

Thermal stability, light stability, ozone resistance and humidity resistance of printed sheets and covers may be evaluated according to the test methods given in ISO 18936, ISO 18937 (indoor home lighting condition), ISO 18941, and ISO 18946, respectively.

Light stability and ozone resistance, as measured according to ISO 18937 and ISO 18941 will reflect the performance that can be expected for a cover that contains pictures or for the underlying printed sheets, if a cover has a window opening that shows the first page, or if the book is displayed or otherwise left in an open state for long periods of time. However the most important issue regarding image permanence of photo books is generally dark storage.

NOTE Information regarding physical abrasion testing is provided in [Annex B](#).

### 4.2 Sample preparation

The samples shall consist of the parts of a photo book, including pages, liner and end sheets, and covers, separated into individual page size components. Printable components, including a printable cover — if applicable — shall be printed with a test target. These parts are then bound in the same process (time and machine settings) as the book for which the test is intended. At least two replicate samples are recommended. Alternatively, test specimens shall be cut off from the book. For general testing purposes, users of this document are free to choose whatever target patches and starting densities they feel are appropriate for their testing needs. An example of such a target is included in ISO 18944 along with requirements and recommendations for sample preparation. Applicable International Standard(s) for specification of print life may require the use of specific targets. If a protective lamination film or varnish coating is applied to the photo book, either on the book cover or in its inner sheets, the same protective film or varnish coating shall be applied on the test samples. The photo book components shall be conditioned at 23 °C and 50 % RH for 24 h prior to testing.

NOTE Be aware that different starting densities of the test prints may yield different test results in terms of fading rate. Once a test sample density is chosen, it is important to be consistent across all test samples for comparison. If testing is being done according to a standard that uses specific starting densities those densities need to be adhered to.

At least two replicate samples of each photo book component part are required, both printed and unprinted. Replicates of each photo book component part shall be located in different regions of the respective test chambers (light, ozone, etc.).

The measurement and sample holding conditions and measurement procedures given in ISO 18936 shall be followed. In particular, care shall be taken to use consistent ambient light levels and hold times in each iteration of the sample holding and measurement process. Density shall be measured for printed patch areas, and colorimetric values shall be measured in the  $D_{\min}$  (minimum density) patch areas of the printable components and in the centre, of each unprinted component. Density and colorimetric values from the replicate samples shall be averaged before calculations are performed.

### 4.3 Thermal stability during long-term dark storage

#### 4.3.1 General

Long term stability shall be evaluated in accordance with ISO 18936, the test method, and ISO 18924, the Arrhenius analysis. It should be noted that the test results of the short term high temperature test may not correspond to the long term stability.

#### 4.3.2 Procedures

The sealed bag method, as detailed in ISO 18936, shall be used to test individual pages or covers. In addition to the required sealed bag method, the 'free hanging' method, also detailed in ISO 18936, may be used to minimize page or cover interactions; it does not, however, reflect the actual storage conditions of the photo book. The 'free hanging' test does not simulate interactions between components that may be present in a photo book, such as between the cover and the first page. To simulate those interactions the user may conduct a "sandwich" type thermal ageing test as described in [Annex D](#).

During actual storage of photo books the temperature and humidity will fluctuate, including potentially large fluctuations depending on the differences in seasons. The testing shall be done at a relative humidity (RH) of 50 %. However, because the effects of humidity on image stability can differ markedly from one product to another, it is useful to evaluate its effect. This is done by means of a temperature test series carried out at different relative humidity. If the relative humidity during storage is expected to be significantly lower than 50 % RH, such as when stored in accordance with some conditions specified in ISO 18911, ISO 18920 or in an arid climate, or significantly higher, as in a tropical climate, the relative humidity selected for the test should correspond to the storage conditions. Such tests are often conducted at conditions of various % RH levels, such 20 % RH to pick up low humidity effects and 70 % RH to pick up high humidity effects. In order to make use of the Arrhenius method in ISO 18924, the temperatures used shall span a minimum range of 20 °C.

#### 4.3.3 Reporting

Reporting shall comply with the reporting requirements of ISO 18936. The results of these tests are reported as temperatures and time for thermal testing to reach the observed losses in optical densities, together with the percentage of optical density losses, or the amount of densitometric and/or colorimetric change observed for a given temperature and time. Reporting shall include results for each tested photo book component, printed and unprinted. For each photo book component, reporting shall also include the presence or absence of physical and biological changes including, but not limited to, delamination, adhesive failure, mould growth, and blocking. In particular, if a sample photo book component held in the interior of a three layer sandwich in the sandwich sample holder adheres to or transfers colourant to the materials comprising the outer layers of the three layer sandwich, this failure shall be reported. In addition, visible edge yellowing, differentiating the component edge region from the interior shall be reported.

## 4.4 Light stability

### 4.4.1 General

The test method for “simulated indoor daylight typical home display” according to ISO 18937, shall be used. For general testing purposes, users of this document are free to choose whatever target patches and starting densities they feel are appropriate for their testing needs. An example of such a target is included in ISO 18944 along with requirements and recommendations for sample preparation.

NOTE Be aware that different starting densities of the test prints can yield different test results in terms of fading rate. Once a test sample density is chosen, it is important to be consistent across all test samples for comparison. If testing is being done according to a standard that uses specific starting densities those densities need to be adhered to.

### 4.4.2 Covers

The total cumulative exposure shall be 20 Mlx·h. Data may also be collected at lower and higher cumulative exposures if applicable to the usage case.

### 4.4.3 Pages

The total cumulative exposure shall be 2 Mlx·h. Data may also be collected at lower and higher cumulative exposures if applicable to the usage case.

NOTE The total cumulative exposure of 20 Mlx·h corresponds to 25 y exposure assuming that 12 h a day at a light level of 200 lx. 200 lx is the light level for book shelves at library which is described in ISO 8995. The pages are typically not exposed to as much light as the covers, and it is estimated to be less than ten percent of the cover value.

### 4.4.4 Reporting

Reporting shall comply with the reporting requirements of ISO 18937. The results of these tests are reported as the amount of densitometric or colorimetric change observed for a given cumulative exposure (lx·h) together with the percentage losses in optical densities. If multiple exposures are used, the results are reported as the cumulative exposure to reach the observed densitometric or colorimetric change together with the percentage losses in optical densities.

## 4.5 Ozone stability

### 4.5.1 General

The test method described in ISO 18941 shall be used. For general testing purposes, users of this document are free to choose whatever target patches and starting densities they feel are appropriate for their testing needs. An example of such a target is included in ISO 18944 along with requirements and recommendations for sample preparation.

NOTE Be aware that different starting densities of the test prints can yield different test results in terms of fading rate. Once a test sample density is chosen, it is important to be consistent across all test samples for comparison. If testing is being done according to a standard that uses specific starting densities those densities need to be adhered to.

### 4.5.2 Covers

The total cumulative exposure shall be 1 450 µl/l·h. Data may also be collected at lower and higher cumulative exposures if applicable to the usage case. Unless otherwise specified, the test shall be carried out at 1,0 µl/l, with an operational uniformity of ±0,1 µl/l ozone as specified in ISO 18941:2017, 9.4. Other optional concentrations, such as 0,5 µl/l or 5,0 µl/l, may be useful for testing. If concentrations other than 1,0 µl/l are used, the operational uniformity tolerances shall be ±10 % of aim or the best achievable with the test equipment. If greater than ±10 %, the actual tolerance shall be reported. If optional concentrations are used, the tester should evaluate the materials for ozone reciprocity

behaviour before making any comparative conclusions. For testing at ozone concentrations greater than 1,0 µl/l, reciprocity testing shall be conducted at an ozone concentration of 1,0 µl/l or lower (as discussed in ISO 18941:2017, Annex B).

NOTE 1 µl/l = 1 ppm ( $1 \times 10^{-6}$ ) and is measured in terms of volume.

#### 4.5.3 Pages

The total cumulative exposure shall be 145 µl/l·h. Data may also be collected at lower and higher cumulative exposures if applicable to the usage case. Unless otherwise specified, the test shall be carried out at 1,0 µl/l, with an operational uniformity of  $\pm 0,1$  µl/l ozone as specified in ISO 18941:2017, 9.4. Other optional concentrations, such as 0,5 µl/l or 5,0 µl/l, may be useful for testing. If concentrations other than 1,0 µl/l are used, the operational uniformity tolerances shall be  $\pm 10$  % of aim or the best achievable with the test equipment. If greater than  $\pm 10$  %, the actual tolerance shall be reported. If optional concentrations are used, the tester should evaluate the materials for ozone reciprocity behaviour before making any comparative conclusions. For testing at ozone concentrations greater than 1,0 µl/l, reciprocity testing shall be conducted at an ozone concentration of 1,0 µl/l or lower (as discussed in ISO 18941:2017, Annex B).

NOTE The total cumulative exposure of 1 450 µl/l·h corresponds to 25 y exposure to ozone gas of 6,6 nl/l concentration. Median ambient indoor ozone concentrations of 9 nl/l and 4,5 nl/l were determined for different regions worldwide. The 6,6 nl/l is the half point of the discussion. The pages are typically not exposed to as much ozone as the covers, and it is estimated to be less than ten percent of the cover value.

#### 4.5.4 Reporting

Reporting shall comply with the reporting requirements of ISO 18941:2017, Clause 10. The results of these tests are reported as the amount of densitometric or colorimetric change observed for a given cumulative exposure (µl/l·h) together with the percentage losses in optical densities. If multiple exposures are used, the results are reported as the cumulative exposure to reach the observed densitometric or colorimetric change together with the percentage losses in optical densities.

### 4.6 Humidity stability

#### 4.6.1 General

The test method and target patches described in ISO 18946 and ISO 18949 shall be used.

#### 4.6.2 Covers and pages

The tests of Method A of ISO 18946 (high humidity) and ISO 18949 (low humidity) shall be run and results reported as described in ISO 18946 and ISO 18949.

#### 4.6.3 Reporting

Reporting shall comply with the reporting requirements of ISO 18946 and ISO 18949. Reporting the specific humidity fastness test result (Method A of ISO 18946 and ISO 18949) shall include reporting of the humidity (% RH) and temperature test conditions, the test time duration and the delta E resulting over the test duration. For each photo book component, reporting shall also include the presence or absence of physical and biological changes including, but not limited to, delamination, adhesive failure, mould growth, and blocking.