
Vpliv cementnih proizvodov na pitno vodo - Preskusne metode - 1. del: Vpliv industrijsko izdelanih cementnih proizvodov na organoleptične parametre

Influence of cementitious products on water intended for human consumption - Test methods - Part 1: Influence of factory made cementitious products on organoleptic parameters

Einfluss von zementgebundenen Produkten auf Wasser für den menschlichen Gebrauch - Prüfverfahren - Teil 1: Einfluss fabrikmäßig hergestellter zementgebundener Produkte auf organoleptische Parameter (standards.iteh.ai)

Influence des produits à base de ciment sur l'eau destinée à la consommation humaine - Méthode d'essai - Partie 1: Influence des produits à base de ciment fabriqués en usine sur les paramètres organoleptiques

Ta slovenski standard je istoveten z: prEN 14944-1

ICS:

13.060.20	Pitna voda	Drinking water
67.250	Materiali in predmeti v stiku z živili	Materials and articles in contact with foodstuffs

oSIST prEN 14944-1:2021**en,fr,de**

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 14944-1:2021](https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 14944-1

September 2021

ICS 13.060.20; 67.250

Will supersede EN 14944-1:2006

English Version

**Influence of cementitious products on water intended for
human consumption - Test methods - Part 1: Influence of
factory made cementitious products on organoleptic
parameters**

Influence des produits à base de ciment sur l'eau
destinée à la consommation humaine - Méthode d'essai
- Partie 1: Influence des produits à base de ciment
fabriqués en usine sur les paramètres organoleptiques

Einfluss von zementgebundenen Produkten auf Wasser
für den menschlichen Gebrauch - Prüfverfahren - Teil
1: Einfluss fabrikmäßig hergestellter
zementgebundener Produkte auf organoleptische
Parameter

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 164.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	5
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	8
4 Principle	12
5 Reagents	12
6 Apparatus	14
7 Samples and test pieces	16
8 Pre-treatment of samples (curing and preconditioning)	18
9 Test procedure.....	19
10 Determination of odour as TON and flavour as TFN	20
11 Determination of colour and turbidity	20
12 Determination of TOC and calculation of test results	20
13 Expression of results	22
14 Test report.....	22
Annex A (normative) Additional procedures for testing factory-made pipes (cement mortar lined and concrete)	25
A.1 Sampling, test piece preparation and storage.....	25
A.2 Surface area to volume (S/V) ratio	29
A.3 Preconditioning of test pieces.....	29
A.4 Test procedure.....	29
A.5 Expression of results	29
A.6 Reporting	29
Annex B (normative) Additional procedures for testing factory-made fittings (cement mortar lined and concrete)	30
B.1 Sampling, test piece preparation and storage.....	30
B.2 Surface area to volume (S/V) ratio	34
B.3 Preconditioning of test pieces)	34
B.4 Test procedure.....	34
B.5 Expression of results	35
B.6 Reporting	35

Annex C (normative) Additional procedures for testing factory-made storage systems (cement mortar, cement mortar lined and concrete)	36
C.1 Sampling, test piece preparation and storage	36
C.2 Surface area to volume (S/V) ratio.....	40
C.3 Preconditioning of test pieces.....	40
C.4 Test procedure	40
C.5 Expression of results	40
C.6 Reporting.....	40
Annex D (informative) Examples of typical test pieces and test conditions as a function of S/V ratio	41
D.1 General	41
D.2 Pipes and fittings	41
D.3 Test pieces to which a cylinder of stainless steel or glass is to be attached.....	42
D.4 Square test plates coated with mortar.....	43
D.5 Moulded test pieces where all faces are exposed to test water	43
Annex E (informative) Test arrangements for testing factory-made cement based products	46
Annex F (normative) Additional procedures for testing factory-made cement based products at elevated temperature.....	53
F.1 General	53
F.2 Test procedure at elevated temperature.....	53
F.3 Control samples (blank test)	53
F.4 Expression of results	54
F.5 Reporting.....	54
Annex G (informative) Discrimination between porous and non-porous coatings on factory-made products	55
G.1 Principle.....	55
G.2 Apparatus	55
G.3 Materials and reagents.....	55
G.4 Test procedure	55
G.5 Determination of pH.....	57
G.6 Expression of results	57
G.7 Classification criteria	57
Annex H (informative) Schematic description of the test procedure	58
H.1 Preconditioning.....	58
H.2 Production of migration water for organoleptic assessment at 23 °C	58
H.3 Typical Schedule	60
Bibliography	61

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 14944-1:2021](https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

European foreword

This document (prEN 14944-1:2021) has been prepared by Technical Committee CEN/TC 164 “Water Supply”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 14944-1:2006.

In comparison with EN 14944-1:2006, the following changes have been made:

- provisions for testing the influence of materials on the migration of organic substances (TOC) have been added,
- the test method for TON /TFN according to EN 1622 has been specified according to the revised EN 1420,
- requirements for disinfection (preconditioning with 50 mg/L Chlorine) have been removed,
- a procedure for extending the number of migration periods has been included.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 14944-1:2021](https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021)
<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

Introduction

This document describes a test method to determine the influence(s) of factory-made cement based products on organoleptic parameters and the migration of organic substances (TOC) in water intended for human consumption.

This European Standard will result in one of a series of standards that support standards for the approval of products and materials in contact with water intended for human consumption.

This European Standard is part of a series dealing with the influence of cement based and associated non-cement based products/materials on water intended for human consumption, including:

- *Part 1: Influence of factory-made cement based products on organoleptic parameters and migration of organic substances (TOC)*
- *Part 2: Influence of site-applied cement based materials and associated non-cement based products/materials on organoleptic parameters and migration of organic substances (TOC)*
- *Part 3: Migration of substances from factory-made cement based products.*
- *Part 4: Migration of substances from site-applied cement based materials and associated non-cement based products/materials.*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 14944-1:2021](https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

1 Scope

This document specifies a method to determine the influence of factory-made cement based products on the odour, flavour, colour, turbidity and total organic carbon (TOC) of test waters after contact with the products.

This document is applicable to factory-made cement based products, e.g. cement mortar linings to metallic pipes, tanks, concrete pipes, etc. intended to be used for the transport and storage of water for human consumption, including raw water used for the production of drinking water.

NOTE Tests with the specified test water will not necessarily be representative of materials used in different kinds of waters and especially very soft waters.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1, *Methods of testing cement - Part 1: Determination of strength*

EN 1420:2016, *Influence of organic materials on water intended for human consumption - Determination of odour and flavour assessment of water in piping systems*

EN 1484, *Water analysis - Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC)*

EN 1622:2006, *Water quality - Determination of the threshold odour number (TON) and threshold flavour number (TFN)*

EN 1015-2, *Methods of test for mortar for masonry - Part 2: Bulk sampling of mortars and preparation of test mortars*

EN 1015-11, *Methods of test for mortar for masonry - Part 11: Determination of flexural and compressive strength of hardened mortar*

EN 10088-1:2014, *Stainless steels - Part 1: List of stainless steels*

EN 12350-1, *Testing fresh concrete - Part 1: Sampling and common apparatus*

EN 12390-1, *Testing hardened concrete - Part 1: Shape, dimensions and other requirements for specimens and moulds*

EN 12390-2, *Testing hardened concrete - Part 2: Making and curing specimens for strength tests*

EN 27888, *Water quality - Determination of electrical conductivity (ISO 7888)*

EN ISO 3696:1995, *Water for analytical laboratory use - Specification and test methods (ISO 3696:1987)*

EN ISO 7027:1999, *Water quality - Determination of turbidity (ISO 7027:1999)*

EN ISO 7393-1, *Water quality - Determination of free chlorine and total chlorine - Part 1: Titrimetric method using N, N-diethyl-1,4-phenylenediamine (ISO 7393-1)*

prEN 14944-1:2021 (E)

EN ISO 7393-2, *Water quality - Determination of free chlorine and total chlorine - Part 2: Colorimetric method using N,N-dialkyl-1,4-phenylenediamine, for routine control purposes (ISO 7393-2)*

EN ISO 7887:2011, *Water quality - Examination and determination of colour (ISO 7887:2011)*

EN ISO 9963-2, *Water quality - Determination of alkalinity - Part 2: Determination of carbonate alkalinity (ISO 9963-2)*

EN ISO 16264, *Water quality - Determination of soluble silicates by flow analysis (FIA and CFA) and photometric detection (ISO 16264)*

ISO 6058, *Water quality — Determination of calcium content — EDTA titrimetric method*

EN ISO 10523, *Water quality - Determination of pH*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

appropriate body

certification body, inspection body or test laboratory, as relevant to a particular requirement

3.2

cement based product

factory-made product containing a cement based material supplied in the hardened state with a formed surface prior to its incorporation into the construction works

3.3

cement based material

material that contains a hydraulic cement in sufficient proportion to act as the main binder by forming a hydrate structure which governs the performance of the material

3.4

associated non-cement based product

product which is applied to the surface of a cement based product, directly or indirectly, during manufacture (or construction) and which either provides a porous seal to the product or which remains as a residue in contact with water, e.g. porous seal coats, formwork release agents and curing compounds

3.5**porous seal coat**

polymeric (usually organic) materials applied in a thin (25 µm – 200 µm thickness) surface layer to a cement mortar lining in order to restrict (but not prevent) interactions between the mortar and conveyed water

Note 1 to entry: See ISO 16132:2004, 3.6 [1].

3.6**proxy sample**

sample of fresh mortar or fresh concrete taken from material to be used for the production of a factory-made product, either applied to one face of a stainless steel plate (6.2.1.1) using the same process of application used in the factory (mortar only) or cast into a mould (mortar or concrete) of appropriate dimensions (e.g. standard cube, cylinder or prism, etc.) and compacted (where appropriate), cured and hardened under conditions representative of those intended for the product

3.7**fresh concrete**

concrete that is fully mixed and still in a condition capable of being compacted by the chosen method

3.8**fresh mortar**

cement mortar that is fully mixed and still in a condition of being applied by the chosen method

3.9**odour**

sensation perceived by means of the olfactory organ in sniffing certain volatile substances

SOURCE:

ISO 5492:2008, 3.18

[oSIST prEN 14944-1:2021](https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

3.10**flavour**

complex combination of the olfactory, gustatory, and trigeminal sensations perceived during tasting

Note 1 to entry: The flavour may be influenced by tactile, thermal, painful and/or kinaesthetic effects.

SOURCE:

ISO 5492:2008, 3.20 [2]

3.11**colour of water**

optical property that causes the changing of the spectral composition of transmitted visible light measured at three wavelengths

SOURCE:

EN ISO 7887:2011, 3.2

3.12**turbidity**

reduction of transparency of a water due to the presence of undissolved matter

Note 1 to entry: See EN ISO 7027:1999, 3.1.

prEN 14944-1:2021 (E)**3.13****threshold odour number****TON**

dilution ratio of the migration water with the reference water at the same temperature, beyond which this diluted sample does not have any perceptible odour

Note 1 to entry: See EN 1622.

3.14**threshold flavour number****TFN**

dilution ratio of the migration water with the reference water at the same temperature, beyond which this diluted sample does not have any perceptible flavour

Note 1 to entry: See EN 1622.

3.15**total organic carbon****TOC**

sum of organically bound carbon present in water, bonded to dissolved or suspended matter, including cyanate, elemental carbon and thiocyanate

SOURCE: EN 1484:1997, 3.3, modified

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.16**testing panel**

group of people meeting the relevant requirements of EN 1622

3.17**test**

technical operation that consists of the determination of one or more characteristics of a given product

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

3.18**test procedure**

specified technical method for performing a test

3.19**sample**

one or more units, or a specified quantity, drawn from a batch or lot, selected at random for inspection, e.g. at the factory or in a laboratory

3.20**test piece**

sample or portion which is to be conditioned, treated or otherwise prepared to be tested to obtain a single test result

3.21**nominal diameter****DN/ID****DN/OD**

numerical designation of the size of a component, which is a whole number approximately equal to the actual dimensions in millimetres

Note 1 to entry: This applies to either the internal diameter (DN/ID) or the external diameter (DN/OD).

3.22**preconditioning**

succession of contact periods of a test piece with the preconditioning water (3.23) before contact with the test water

3.23**preconditioning water**

water used for preconditioning

Note 1 to entry: prepared as described in 5.3.1

3.24**reference water**

water described as without odour, flavour, colour and turbidity

Note 1 to entry: conforming to the requirements in 5.3.2

3.25**test water**

water used for testing purposes

Note 1 to entry: prepared as described in 5.3.3 and 5.3.4

3.26**migration water:**

test water which has been in contact with a test piece under specified conditions

[SOURCE: EN 1622:2006, 3.13]

3.27**blank water**

test water which has been kept at the same specified conditions as migration water but without contact with the test piece

3.28**tap water**

drinking water distributed by a public supplier

Note 1 to entry: Tap water is used as a lubricant/coolant for the sawing and coring operations used to obtain test pieces generally from products of large dimensions. See Annexes A, B and C.

3.29**demineralized water**

water conforming to the requirements in EN ISO 3696:1995 for Grade 3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

oSIST prEN 14944-1:2021
http://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021

4 Principle

Each test piece is subjected to a specified preconditioning procedure where the surface which, in practice will be exposed to water intended for human consumption, is brought into contact with preconditioning water during five sequential periods: three periods of 24 h, 1 period of 72 h and a final period of 24 h.

The preconditioned test piece is then brought into contact with test water, chlorinated and/or chlorine-free during three sequential migration periods. A migration period is either:

- a) 72 h at (23 ± 2) °C for products intended to come into contact with chlorinated or chlorine-free cold water;
- b) 24 h at a specified elevated temperature for products intended to come into contact with warm or hot chlorine-free water.

After each contact period, each migration water is assessed for odour, flavour, colour, turbidity and TOC.

NOTE: The selection of:

- a) the appropriate test water, chlorinated and/or chlorine-free, from those made available in this European Standard,
- b) the temperature of the test water,
- c) the need for chlorination during preconditioning

is specified in product or system standards or in national or European regulations, as appropriate.

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

5 Reagents

<https://standards.iteh.ai/catalog/standards/sist/a7489ebc-9a3a-4300-82ad-390d7ad76540/osist-pren-14944-1-2021>

5.1 Chlorine neutralization reagents

5.1.1 Ascorbic acid solution, prepared by dissolving $(4,0 \pm 0,1)$ g of ascorbic acid in one litre of reference water (5.3.2).

This ascorbic acid solution shall be replaced on a monthly basis.

5.1.2 Sodium thiosulfate solution, comprising a solution of 3,5 g/l of sodium thiosulfate pentahydrate ($\text{Na}_2\text{S}_2\text{O}_3 \cdot 5 \text{H}_2\text{O}$) and stored in the absence of light at a temperature below 10 °C, for a maximum of 4 months.

Sodium hypochlorite solution, prepared from a commercial solution of sodium hypochlorite (NaOCl) and have a known concentration of $\pm 0,1$ % by mass of free chlorine determined in accordance with either EN ISO 7393-1 or EN ISO 7393-2.

This sodium hypochlorite solution is unstable and shall be prepared on the day of use.

5.2 Sodium hypochlorite solution, prepared from a commercial solution of sodium hypochlorite (NaOCl) and have a known concentration of about 0,1 % by mass of free chlorine determined in accordance with either EN ISO 7393-1 or EN ISO 7393-2.

This sodium hypochlorite solution is unstable and shall be prepared on the day of use.

5.3 Waters to be used for testing

5.3.1 Preconditioning water prepared by dissolving (222 ± 2) mg anhydrous calcium chloride (CaCl_2) and (336 ± 2) mg sodium hydrogen-carbonate (NaHCO_3) in one litre of demineralized water (3.29). The pH is determined in accordance with EN ISO 10523 and adjusted to $7,4 \pm 0,1$ by bubbling air and/or CO_2 into the solution.

NOTE The target total hardness is 200 mg/l as CaCO_3 and the target alkalinity is 244 mg/l as HCO_3 .

5.3.2 Reference water, a natural water without gas and with parameters that conform to the requirements given in Table 1.

When the reference water is chlorinated to 1,0 mg/l free chlorine and then dechlorinated after 72 h with either the ascorbic acid solution (5.1.1) or the sodium thiosulfate solution (5.1.2), its organoleptic parameters, odour, flavour colour and turbidity shall conform to the requirements given in Table 1.

When the reference water is prepared from demineralised water, dissolve (222 ± 2) mg anhydrous calcium chloride (CaCl_2), (482 ± 2) mg sodium hydrogencarbonate (NaHCO_3) and (71 ± 1) mg sodium silicate ($\text{Na}_2\text{SiO}_3 \cdot 9 \cdot \text{H}_2\text{O}$) in 1 l of demineralised water (3.29). The pH is determined in accordance with EN ISO 10523 and adjusted to $7,4 \pm 0,1$ by bubbling air and/or CO_2 into the solution.

Table 1 — Reference water

Parameter	Test method ^a	Requirement	Unit
Conductivity	EN 27888	500 ± 50	$\mu\text{S}/\text{cm}$
pH	EN ISO 10523	$7,3 \pm 0,2$	pH unit
Calcium	ISO 6058	80 ± 10	mg Ca/l
Alkalinity	EN ISO 9963-2	350 ± 50	mg HCO_3^-/l
Silica	EN ISO 16264	15 ± 5	mg SiO_2/l
Odour	EN 1622	< 2	TON
Flavour	EN 1622	< 2	TFN
Colour	EN ISO 7887 ^b	$< 0,1$	m^{-1}
Turbidity	EN ISO 7027 ^c	$< 0,1$	FNU
TOC	EN 1484	$< 0,2$	mg C/l
^a Alternative methods, either calibrated against the reference methods or which have proven comparable analytical performance, may be used. ^b See Clause 5. ^c See Clause 6.			

5.3.3 Test water without chlorine content (chlorine-free), shall consist of a batch of reference water (5.3.2) used for contact with test pieces and preparation of the blank water (3.27).

5.3.4 Test water with chlorine content (chlorinated), consisting of reference water (see 5.3.2) with a free chlorine content of $(1,0 \pm 0,2)$ mg/l as Cl_2 , determined in accordance with either EN ISO 7393-1 or EN ISO 7393-2, after addition of sodium hypochlorite solution (5.2).