INTERNATIONAL STANDARD

ISO 15115

First edition 2019-08

Leather — **Vocabulary**

Cuir — Vocabulaire

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 15115:2019 https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-1025eb741bfd/iso-15115-2019



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 15115:2019 https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-1025eb741bfd/iso-15115-2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

ii

Contents		
Forev	word	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
Bibliography		12
Indox	v	12

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 15115:2019 https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-1025eb741bfd/iso-15115-2019

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html. (Standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 120, *Leather*.

Any feedback or questions on this document should be directed to the diser's national standards body. A complete listing of these bodies can be found at www.iso.org/inembers.html.

Leather — Vocabulary

1 Scope

This document defines terms used in the leather industry.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

iTeh STANDARD PREVIEW 3.1

abrasion resistance

frictional forces

ISO 15115:2019

3.2

https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-

aniline leather 1025eb741bfd/iso-15115-2019

<material> leather whose natural grain (3.46) is clearly visible either without a surface coating or with a non-pigmented surface coating

Note 1 to entry: The thickness of non-pigmented surface coating is usually less than or equal to 0,01 mm.

3.3

barkometer

<equipment> type of hydrometer used in tanneries

Note 1 to entry: The correlation between specific gravity and barkometer reading (Bk) is as follows:

Specific gravity	°Bk
1,0	0
1,020	20
1,120	120

3.4

basicity of chromium

<chemical characteristics> number of hydroxyl groups borne by a chromium unit as a percentage fraction of the same present in chromic hydroxide

3.5

basification

Treating the mineral tanned stock with a view to forming a large aggregate of metallic compounds and enabling reactive groups of *skin* (3.88) to complex with tanning material.

ISO 15115:2019(E)

3.6

bate

<material> enzymes mixed with an inert carrier used to selectively remove unwanted constituents of *hides* (3.48) and *skins* (3.88)

3.6.1

acid bate

bate (3.6) that has optimum activity in the pH range of 3 to 5

3.6.2

alkaline bate

bate (3.6) that has optimum activity in the pH range of 8 to 8,5

3.7

bating

3.8

baume

<physical characteristic> liquid density measurement which can be converted to specific gravity

Note 1 to entry: Typically used to calculate the concentration of the process solution, for example salt solution, using the following formulae:

- for liquids heavier than water, specific gravity = $\frac{145}{(145 n)}$ at $\frac{15 \circ C}{(60 \circ F)}$.
- for liquids lighter than water, specific gravity = 140/(130 + n) at 15 °C (60 °F).

where *n* is the reading on the baume scale abbreviated as °Be.

Note 2 to entry: Be is equivalent to 6,9 °barkometer (3.3) reading, Bk.

https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-

1025eb741bfd/iso-15115-2019

3.9 beam

<equipment> convex wooden slab sloping downward from about waist height over which a *hide* (3.48) is placed for unhairing, trimming off excess flesh and ragged edges, and *scudding* (3.78) by hand knife

3.10

binder

<material> film-forming material, usually polymeric, used to adhere pigment particles and additives for coating the surface of the leather

3.11

bleaching

3.12

bleaching of vegetable-tanned leather

cess> removing oxidized tannins and insoluble materials from the surface layers of leather, in
order to prevent cracking of the grain (3.46) and to lighten the colour

3.13

boil test

<performance> test of a piece of fully hydrated leather to check whether there is any shrinkage after
placing in boiling water for 2 min to 3 min

Note 1 to entry: When the leather retains the original area, chrome tanning is considered complete.

3.14

box calf leather

<material> full chrome tanned calf leather, black or coloured, smooth or boarded, with a proteinic finish(3.39)

3.15

break of leather

<performance> surface wrinkles formed when the leather is bent, grain (3.46) inward

Note 1 to entry: Adjectives commonly used to describe this characteristic are "tight", "fine", "loose", "coarse", "pipey" and "flanky". Generally, the finer the wrinkles or grain break, the better the quality of the leather.

3.16

buffing

abrasive mechanical treatment to the grain (3.46) or flesh surface of the leather

Note 1 to entry: See also *snuffing* (3.90).

3.17

burnishable leather

<material> leather which will develop a shiny darkening appearance on rubbing or polishing

3.18

burst strength

<performance> force required to completely rupture the full thickness of the leather test piece

[SOURCE: ISO 3379:2015] eh STANDARD PREVIEW

3.19

(standards.iteh.ai)

chamois

<material> leather made from the *flesh split* (3.93.2) of sheepskin or lamb *skin* (3.88), or from sheepskin or lamb *skin* (3.88) from which the *grain* (3.46) has been removed by frizzing, and tanned by processes involving the oxidation of marine oils in the skin using solely such oils (full-oil chamois) or first an aldehyde and then such oils (combination chamois)

Note 1 to entry: Also leather made from the skin of a mountain antelope or chamois, but such leather is rare.

Note 2 to entry: In German language this term is also used to define chamois for clothing made out of deer skin.

Note 3 to entry: Chamois are also made out of goatskins.

3.20

chrome-free leather

<material> hide (3.48) or skin (3.88) converted to leather by a tanning agent free of chromium salts, where the total content of chromium in the tanned leather is less than or equal to 0,1% (mass of chromium/total dry weight of leather)

3.21

chrome-tanned leather

<material> hide (3.48) or skin (3.88) converted to leather either by treatment solely with chromium salts or with chromium salts together with a small amount of some other tanning agent, used merely to assist the chromium tanning process, and not in sufficient amount to alter the essential chromium tanned character of the leather

3.22

coated and coated split leather

<material> leather and *split leather* (3.93) where the surface coating, applied to the outer side, does not exceed one third of the total thickness of the product but is in excess of 0,15 mm

ISO 15115:2019(E)

3.23

cold crack resistance

<performance> resistance of leather finish (3.39) to crack and peel when subject to bending/flexing under a temperature not exceeding -5 °C

3.24

corrected grain leather

<material> leather in which the grain (3.46) has been partially removed by buffing (3.16) or any similar mechanical treatment, and enhanced by a *finishing* (3.40) treatment

Note 1 to entry: The original pattern is generally identifiable except for heavily corrected grains.

3.25

crocking

<performance> transfer of colourant to the contact fabric when dry rubbed or wet rubbed

3.26

curing

3.27

degreasing

s removing natural fat from the hide (3.48) or skin (3.88) by emulsification in an aqueous media and/or using a solvent media

3.28

iTeh STANDARD PREVIEW degree of tannage

<chemical characteristics> amount of fixed organic matter in 100 g of collagen

Note 1 to entry: Applicable to mineral-free leathers.

ISO 15115:2019

3.29 deliming

https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-

1025eb741bfd/iso-15115-2019

3.30

double face

<material> double-sided leather made from lamb or sheep skins (3.88) or other animals with wool, dressed, tanned, softened and dyed for desired properties

3.31

drawn grain

<physical characteristics> unwanted distorted grain (3.46) appearance

3.32

drum

<equipment> cylindrical vessel with baffles inside and capable of rotation about its own axis, used for mechanical agitation in leather processing

3.33

dry drumming

dry tumbling for leather with or without additives in a revolving drum (3.32) to soften the structure and improve the nap (3.58)

Note 1 to entry: Also referred to as dry milling.

3.34

dry salting

3.35

dyed crust leather

<material> leather tanned, dyed, fatliquored and dried, before *finishing* (3.40)

3.36

E.I. leather

East India leather

<material> vegetable-tanned leather (3.100) with characteristic light beige or pale golden yellow colour manufactured by a process specific to a geographical location

Note 1 to entry: Registered Indian geographical indication number 95.

3.37

fatliquor

<material> natural or synthetic oil-based formulation that can be an emulsion, solution or dispersion used to lubricate leather fibres

3.38

fatliquoring

application of fatliquors (3.37) for lubricating and softening leathers

3.39

finish

<material> coating on a leather surface

3.40 iTeh STANDARD PREVIEW

finishing

3.41 ISO 15115:2019

flexural endurancetps://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c1-

<performance> ability of finished leather to endure the stress applied due to repeated bending

3.42

fog resistance

<performance> resistance to the release of semi-volatile and low-volatile substances present in the
leather at high ambient temperature

3.43

full grain leather

<material> leather having kept its entire *grain* (3.46), with none of the surface removed by any corrective mechanical treatment

3.44

fur dressing

cess> finishing (3.40) fur leather

Note 1 to entry: When dressing the furs, they are sheared (or trimmed), bleached (optional), dyed, combed and finally plush wheeled.

3.45

glazing

cess> operation of producing a bright, glossy or glasslike finish (3.39) on the grain (3.46) surface
of leather

3.46

grain

<material> outer side of the leather once the hair or wool and epidermis have been removed, characterized by follicles from hair or wool, feather follicles or scales, specific to each animal species

ISO 15115:2019(E)

3.47

grain crack resistance

<performance> resistance of the grain (3.46) surface of the leather to rupture when subjected to

3.48

hide

<material> raw skin (3.88) of a mature or fully-grown animal of the larger kind

Cattle and buffalo. **EXAMPLE**

3.49

hide powder

<material> powder from well-washed, dried, delimed pelt (3.67) disintegrated using a grinding mill

3.50

hide substance

<material> amount of collagenous substance in 100 g of dry leather

3.51

laminated leather

<material> leather where a foil (polymeric film) layer, not exceeding one third of the total thickness, is applied by a transfer coating process

Note 1 to entry: Other methods of applying a foil (polymeric film) are plating, embossing and ironing.

3.52

iTeh STANDARD PREVIEW

leather

<material> hide (3.48) or skin (3.88) with its original fibrous structure more or less intact, tanned to be imputrescible, where the hair or wool may or may not have been removed, whether or not the hide (3.48) or skin (3.88) has been split into layers or segmented either before or after tanning (3.97) and where any surface coating lon surface layer, however applied is not thicker than 0.15 mm

1025eb741bfd/iso-15115-2019

Note 1 to entry: If the tanned hide or skin is disintegrated mechanically and/or chemically into fibrous particles, small pieces or powders, and is then, with or without the combination of a binding agent, made into sheets or other forms, such sheets or forms are not leather.

Note 2 to entry: If the grain layer has been completely removed, the term leather is not to be used without further qualification, e.g. *split leather* (3.93), suede leather.

Note 3 to entry: The material shall be of animal origin.

3.53

lime blast

<material> formation of patches of insoluble calcium carbonate by the reaction of atmospheric carbon dioxide with the lime present in the pelts (3.67) when they are exposed to the atmosphere

3.54

liming

s treating raw hides (3.72) and skins (3.88) with lime liquor with a view to plumping and/or unhairing

3.55

loose grain

<physical characteristics> grain (3.46) whose attachment to corium has been eroded, giving rise to pronounced wrinkles when leather is bent, grain inside

3.56

masking agent

<material> weak acids and their salts added during mineral tanning (3.97) to prevent precipitation of tanning salts

3.57

metal-free leather

<material> hide (3.48) or skin (3.88) converted to leather, where the total content of all tanning metals (Cr, Al, Ti, Zr, Fe) in the leather is less than or equal to 0,1 % (mass of all metals/total dry weight of leather)

3.58

nap

<material> vertical and fine fibres cut short enough to produce a velvety two-tone effect when a two-way stroke is applied by hand

3.59

nappa

<material> soft *full grain leather* (3.43), through dyed and lightly finished

3.60

nappalan

<material> wool-on sheepskin, finished by coating on the reverse side

3.61

nappalan finish

<physical characteristic> finishing (3.40) on the flesh side of hides (3.48) and skins (3.88)

3.62

neutralization

3.63

(standards.iteh.ai)

nubuck

<material> leather snuffed (buffed) to give velvety effect, where the original *grain* (3.46) pattern is still visible https://standards.iteh.ai/catalog/standards/sist/fa6d5b69-d771-41ac-b1c11025eb741bfd/iso-15115-2019

3.64

organic-tanned leather

<material> hide (3.48) or skin (3.88) converted to leather by natural or synthetic organic tanning agents, where the total content of tanning metals (Cr, Al, Ti, Zr, Fe) is less than or equal to 0,3 % (mass of all metals/total dry weight of leather)

3.65

parchment

<material> dry, translucent or opaque untanned hide (3.48) or skin (3.88) material

3.66

patent leather

<material> leather with generally a mirror-like effect, obtained by application of a layer of pigmented or non-pigmented varnishes, or synthetic resins, whose thickness does not exceed one third of the total thickness of the product

Note 1 to entry: The term patent *split leather* (3.93) also exists.

Note 2 to entry: Varnishes and lacquers are usually based on linseed oil, nitrocellulose, polyurethane and/or other synthetic resins.

3.67

pelt

<material> hide (3.48) or skin (3.88) prepared for tanning (3.97) by removal of the hair or the wool, epidermis and flesh

Note 1 to entry: The term pelt can also be used for the skin of an animal with fur or hair still on it.