
**Magnesium lithium alloys —
Determination of lithium —
Inductively coupled plasma optical
emission spectrometric method**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 20258:2018](https://standards.iteh.ai/catalog/standards/sist/4fc72939-17f1-4192-9ecd-7f00891283d2/iso-20258-2018)

<https://standards.iteh.ai/catalog/standards/sist/4fc72939-17f1-4192-9ecd-7f00891283d2/iso-20258-2018>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20258:2018

<https://standards.iteh.ai/catalog/standards/sist/4fc72939-17f1-4192-9ecd-7f00891283d2/iso-20258-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	2
6 Apparatus	2
7 Sampling and sample preparation	3
8 Procedure	3
8.1 General.....	3
8.2 Test portion.....	4
8.3 Determination.....	4
8.3.1 Preparation of the test solution.....	4
8.3.2 Preparation of the calibration solutions.....	4
8.4 Adjustment of the apparatus.....	4
8.5 Measurement of the calibration solutions.....	4
8.6 Calibration curve.....	5
8.7 Measurements of the test solution.....	5
9 Expression of results	5
9.1 Method of calculation.....	5
9.2 Precision.....	5
10 Test report	6
Annex A (normative) Inductively coupled plasma optical emission spectrometer — Performance criteria to be checked	7
Annex B (informative) Information on the precision test	9
Annex C (informative) Graphical representation of precision data	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 5, *Magnesium and alloys of cast or wrought magnesium*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Magnesium lithium alloys are the lightest metallic materials in the world and show several advantageous properties such as: excellent rigidity, high electric and thermal conductivity, good damping, electromagnetic, shielding, welding, matching and cold forming performances. Lithium is the most important element in magnesium lithium alloys, and can improve the deformation capability of alloys with further a decrease in weight. With the increasing demands of the world today for lightweight materials, energy saving, environmental protection and sustainable development, magnesium lithium alloys show broad application prospects in the fields of materials, transportation, electronics, medical products and so on.

Chemical compositions of magnesium and its alloys are widely standardized from major to trace contents in international and other national standards. However, there is no standard dealing with the determination of lithium content in magnesium lithium alloys.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 20258:2018](https://standards.iteh.ai/catalog/standards/sist/4fc72939-17f1-4192-9ecd-7f00891283d2/iso-20258-2018)

<https://standards.iteh.ai/catalog/standards/sist/4fc72939-17f1-4192-9ecd-7f00891283d2/iso-20258-2018>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20258:2018

<https://standards.iteh.ai/catalog/standards/sist/4fc72939-17f1-4192-9ecd-7f00891283d2/iso-20258-2018>

Magnesium lithium alloys — Determination of lithium — Inductively coupled plasma optical emission spectrometric method

1 Scope

This document specifies a method for the determination of lithium contents in magnesium lithium alloys by inductively coupled plasma (ICP) optical emission spectrometry.

The method is applicable to the determination of lithium content between 3,0 % and 16,0 % (mass fraction) in magnesium lithium alloys.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

Dissolution of a test portion in hydrochloric acid. Nebulization of the solution into an ICP optical emission spectrometer and measurement of the intensity of the emitted light from lithium.

Calibration based on a very close matrix matching of the calibration solutions to the sample shall be carried out. The advantage with this procedure is that all possible interferences from the matrix will be compensated, which will result in high accuracy. This is important to spectral interferences, which can be severe in highly alloyed matrixes.

All spectral interferences shall be kept at a minimum level. Therefore, it is essential to select the appropriate wavelengths. The wavelengths generally used for lithium are shown in [Table 1](#) together with the possible interferences. Depending on the performance of each spectrometer, other wavelengths may be used, provided that interferences, sensitivity, resolution and linearity criteria have been carefully investigated.

5 Reagents

During the analysis, use only reagents of recognized analytical grade and only grade 2 water as specified in ISO 3696, or water of equivalent purity.

- 5.1 **Pure magnesium**, purity $\geq 99,99$ % (mass fraction), free from lithium.
- 5.2 **Lithium carbonate**, purity $\geq 99,99$ % (mass fraction).
- 5.3 **Hydrochloric acid**, ρ about 1,19 g/ml.
- 5.4 **Hydrochloric acid solution 1 + 1**, add 500 ml of hydrochloric acid (5.3) to 500 ml of water.
- 5.5 **Hydrogen peroxide**, ρ about 1,13 g/ml.
- 5.6 **Magnesium base solution**, corresponding to 2,5 g of magnesium per litre.

Weigh, to the nearest of 1 mg, 0,5 g of pure magnesium (5.1) and transfer into a 300 ml glass beaker. Add about 50 ml of water and, in small portions, 25 ml of hydrochloric acid (5.4). Cover with a watch-glass and, if necessary, heat gently to complete the dissolution. Add a few drops of hydrogen peroxide (5.5) and boil for 5 min. Cool and transfer quantitatively into a 200 ml one-mark volumetric flask. Dilute to the mark with water and mix.

1 ml of this solution contains 2,5 mg of magnesium.

- 5.7 **Magnesium base solution**, corresponding to 0,25 g of magnesium per litre.

Transfer 10 ml of the solution (5.6) to a 100 ml one-mark volumetric flask. Add 10 ml of hydrochloric acid (5.4). Dilute to the mark with water and mix.

1 ml of this solution contains 0,25 mg of magnesium.

- 5.8 **Lithium standard solution**, corresponding to 1,0 g of lithium per litre.

Dry several grams of lithium carbonate (5.2) in an oven at $100\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$ for at least 1 h and cool to room temperature in a desiccator. Weigh, to the nearest 0,1 mg, 5,322 8 g of the dried lithium carbonate, transfer into a 500 ml glass beaker, add 60 ml of hydrochloric acid (5.4), cover with a watch-glass and, if necessary, heat gently to complete the dissolution. Cool and transfer quantitatively into a 1 000 ml one-mark volumetric flask. Dilute to the mark with water and mix.

1 ml of this solution contains 1,0 mg of lithium.

- 5.9 **Lithium standard solution**, corresponding to 0,1 g of lithium per litre.

Transfer 10,00 ml of the lithium standard solution (5.8) to a one-mark 100 ml volumetric flask. Add 10 ml of hydrochloric acid (5.4). Dilute to the mark with water and mix.

1 ml of this solution contains 0,1 mg of lithium.

6 Apparatus

All volumetric glassware shall be class A and calibrated in accordance with ISO 648 or ISO 1042, as appropriate.

6.1 Inductively coupled plasma optical emission spectrometer.

6.1.1 General

The instrument used will be satisfactory if, after optimizing in accordance with the manufacturer's instructions, it meets the performance criteria given in 6.1.3 to 6.1.5.

6.1.2 Wavelengths

This method does not specify any particular emission line. It is mandatory that each laboratory carefully investigates the wavelengths available on its own equipment to find the most suitable one regarding sensitivity and absence of interferences.

In Table 1, however, several suggestions are given together with possible interferences. These wavelengths have been carefully investigated. It is recommended to use Li 670,784 nm or Li 610,362 nm because of their high sensitivity.

Table 1 — Examples of wavelengths for lithium determination

Element	Wavelength nm	Possible interferences
Li	670,784	V, Ti, Sc
	610,362	Ca, Fe

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6.1.3 Minimum resolution of the spectrometer

Calculate the bandwidth, according to A.1, for the wavelength used. The bandwidth shall be less than 0,030 nm.

ISO 20258:2018

<https://standards.iteh.ai/catalog/standards/sist/4fc72939-17fl-4192-9ecd-7f00691283d2/iso-20258-2018>

6.1.4 Minimum short-term precision

Calculate the short-term precision according to A.2. The relative standard deviation (RSD) should not exceed 1 %.

6.1.5 Linearity of the calibration curve

The linearity of the calibration curve is checked by calculating the corresponding correlation coefficient. This coefficient shall be higher than 0,999.

7 Sampling and sample preparation

Sampling shall be carried out in accordance with an appropriate national standard for magnesium. If it is suspected that the laboratory sample is contaminated with oil or grease from the milling or drilling process, it shall be cleaned with ethanol or acetone and then dried in air. The sample shall be in the form of fine drillings, chips or millings with a maximum thickness of 1 mm. Sampling position shall be selected so as to be representative of the sample. In order to avoid oxidation of the surface, the chips shall be taken from the inner portion of a bulk sample just before starting an analytical procedure.

8 Procedure

8.1 General

For each set of determinations, all reagents, including water, calibration and test solutions, shall be from the same batch.