



SLOVENSKI STANDARD
oSIST prEN ISO 18417:2019
01-januar-2019

Jodni ogljeni sorbenti za jedrske objekte - Metoda za določanje indeksa sorpcijske zmogljivosti (ISO 18417:2017)

Iodine charcoal sorbents for nuclear facilities - Method for defining sorption capacity index (ISO 18417:2017)

Jodkohlenstoffsorptionsmittel für kerntechnische Anlagen - Verfahren zur Bestimmung des Sorptionsvermögensindex (ISO 18417:2017)

Pièges à iode pour installations nucléaires - Méthode pour définir la capacité de rétention (ISO 18417:2017)

Ta slovenski standard je istoveten z: prEN ISO 18417

ICS:

13.280 Varstvo pred sevanjem Radiation protection

oSIST prEN ISO 18417:2019 **en,fr,de**

INTERNATIONAL
STANDARD

ISO
18417

First edition
2017-03

**Iodine charcoal sorbents for nuclear
facilities — Method for defining
sorption capacity index**

*Pièges à iode pour installations nucléaires — Méthode pour définir la
capacité de rétention*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 18417:2019

<https://standards.iteh.ai/catalog/standards/sist/9d0fd964-1fac-439e-89c9-7f9392f29a90/sist-en-iso-18417-2019>



Reference number
ISO 18417:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 18417:2019

<https://standards.iteh.ai/catalog/standards/sist/9d0fd964-1fac-439e-89c9-7f9392f29a90/sist-en-iso-18417-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principles of the method	2
5 Preparation of the test	4
5.1 General.....	4
5.2 Removal of air impurity and humidity into the installation.....	4
5.3 Radioactive methyl iodide used for sorbent testing.....	5
5.4 Preparation of sorbent samples.....	5
5.5 Measuring devices.....	6
5.6 Conditions for achieving equilibrium during the test.....	6
5.7 Safe conditions for workers and members of the public.....	6
6 Test conditions	7
7 Sorbent testing	7
8 Test performance	9
9 Determination of the sorption capacity index	10
9.1 Sorption capacity index determination.....	10
9.2 Calculating sorption capacity index.....	11
9.3 Uncertainties of measurements.....	12
10 Documenting test results	13
Annex A (normative) Format of test report (for the customer)	14
Annex B (normative) Format of internal test report	15
Annex C (normative) Measurements results	16
Annex D (informative) Example of expected results for sorption capacity index	17
Bibliography	19

ISO 18417:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 85, *Nuclear energy, nuclear technologies, and radiological protection*, Subcommittee SC 2, *Radiological protection*.

<https://standards.iteh.ai/catalog/standards/sist/9d0fd964-1fac-439e-89c9-7f9392f29a90/sist-en-iso-18417-2019>

Introduction

Iodine sorbents are extensively used in nuclear facilities to remove radioiodine from gases and air in off-gas cleaning systems and ventilation installations. The sorbents are very important for protection of the members of the public and environment from iodine radionuclides radiation.

In the normal operation of nuclear installations, the main hazard comes from radioactive isotopes of iodine; as examples, for reactors ^{131}I and a minor extent ^{133}I , for fuel processing facilities ^{129}I , etc. Iodine is one of the main contributors of the radiation impact on the environment. Under abnormal and accident conditions, some other isotopes ^{132}I , ^{134}I and ^{135}I have also some significant effects on the total iodine dose (thyroid dose)^[3].

The volatile radioiodine forms can occur in the gaseous radioactive wastes as elemental iodine, the simplest organic compound methyl iodide, and some others such as hydrogen iodide under reducing conditions.

Radioactive iodine can create a serious danger to the members of the public and workers in abnormal and accident conditions at nuclear facilities as far as the exposure in these conditions could be much higher than the exposure due to the natural background radiation.

The need to prevent widespread dispersal of gaseous radioiodine from nuclear facilities is a major purpose of iodine sorbents. It is universally recognized that radioactive methyl iodide is the less readily removable radioiodine form. The removal of radioactive iodine from gaseous radioactive wastes at nuclear facilities is almost always performed with the help of impregnated activated charcoals that have become often accepted as the preferred iodine sorbents used in these facilities. Impregnated charcoals require a high efficiency especially from humid gases containing iodine in order to trap all the iodine gaseous compounds.

Two types of tests are considered^{[2][4]}: laboratory and *in situ* tests.

- Laboratory tests are done to establish the performance characteristics of the charcoal to be used in retention systems under specified operating conditions.
- *In situ* tests are done to obtain a measure of the performance of retention systems under appropriate operational conditions.

This document concerns only the laboratory tests. Laboratory tests of representative samples of charcoal (e.g. new charcoal, aged charcoal from iodine absorbers, etc.) are performed to establish their efficiency for a given test agent under specified conditions.

The quality of sorbents and its potential application at nuclear facilities can be estimated by means of a criterion that defines specifically the sorption capacity of the sorbent. Such criterion is called in this document the sorption capacity index.

The index is defined by the result of a laboratory test on the basis of radioiodine activity distribution inside the sorbent. This index characterizes the total kinetic sorption process for established test conditions and show whether the sorbent can be used as iodine filters for nuclear facilities. One example of criteria is given in [Annex D](#).

This document provides a method to determine the quantitative quality of a sorbent and also to compare the performance of different iodine sorbents at the specified conditions. It is useful for users of iodine sorbents (filter or sorbent manufacturers as well as operators).

Iodine charcoal sorbents for nuclear facilities — Method for defining sorption capacity index

1 Scope

The scope of this document covers

- iodine sorbents for nuclear power plants, nuclear facilities, research and other nuclear reactors,
- iodine sorbents for laboratories, including nuclear medicine, and
- iodine sorbents for sampling equipment on sample lines.

This document applies to iodine sorbents manufacturers and operators in order to measure the actual performance of these sorbents and their sorption capacity for radioiodine.

This document applies to granulated and crushed iodine sorbents based on activated charcoal (hereinafter referred to as “sorbents”) used for trapping gaseous radioiodine and its compounds. This document establishes the method and conditions for defining sorption capacity index in a laboratory.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

gaseous radioactive wastes

wastes that contain radioactive material in gas form for which no further use is foreseen and have radionuclides at concentrations or activities greater than clearance levels as established by a regulatory body

3.2

discharge

planned and controlled release of (gas or liquid) radioactive material to the environment

3.3

mass transfer zone

defined zone (range) of sorbent volume in which the phenomena of substance mass transfer from gas to solid phases takes place

3.4

iodine sorbent

sorbent intended for trapping radioiodine in gaseous radioactive wastes

ISO 18417:2017(E)**3.5****free volume**

void between grains or crushed grains of the sorbent inside the whole volume containing the sorbent

Note 1 to entry: The free volume can be expressed as in [Formula \(1\)](#):

$$V_{\text{fr}} = \chi \cdot V_{\text{sorb}} \quad (1)$$

where

V_{fr} free volume;

χ fraction free volume in sorbent volume;

V_{sorb} sorbent volume.

3.6**contact time**

gas flow transit time through sorbent layer

Note 1 to entry: Contact time τ is expressed using [Formula \(2\)](#):

$$\tau = \frac{V_{\text{fr}}}{Q_{\text{col}}} \quad (2)$$

where

Q_{col} the volumetric gas flow rate in the inlet sectional column.

Note 2 to entry: The contact time defined here does not consider the geometric volume of the sample, but only its free volume.

3.7**bulk density**

ρ_{sorb}

ratio between granulated or crushed grains sorbent mass (definite granulation) and the total volume containing the sorbent

3.8**sorption capacity index**

ξ

criterion indicating the degree of reduction of gaseous radioiodine in the gas flowing through the sorbent under specified test conditions

Note 1 to entry: The index is valid only for a specific chemical form of the radioactive gas. In this document, the index has been calculated for radioactive methyl iodide. The index can also be calculated with other gaseous species, such as radioactive iodine, but the results cannot be compared with the ones obtained with radioactive methyl iodide.

4 Principles of the method

The main rationale for the method defined in this document are the following:

- radioactive methyl iodide ($\text{CH}_3^{131}\text{I}$) is the most difficult form of radioiodine to trap in nuclear facilities discharges;
- the distribution of radioactive methyl iodide along sorbent layer is exponential;
- there is an active mass transfer zone in the sorbent layer;

- the amount of sorbed radioactive methyl iodide depends on the contact time between the gas and sorbent.

The sorption capacity index indicates the degree by which radioactive methyl iodide concentration in gas phase is reduced during the contact of the gas flow with the sorbent.

The principle of the method is the following:

- indoor laboratory air is used as carrier gas;
- air is transferred in the test plant by means of extraction device (fan, vacuum pump, etc.);
- in order to remove indoor laboratory air pollutants, aerosols and humidity, air flow passes through an aerosol filter, an air conditioning system used for humidity (e.g. zeolite or dehumidifier) and volatile compounds removal (e.g. activated charcoal);
- the humidity level shall be maintained to a specified value and be controlled. One example for this humidity control is to split the total air flow and pass one of the flows through a second air condition system (e.g. humidifier);
- the air temperature and air flow are regulated and measured before introduction in the sample to test (e.g. the air temperature is control by heat insulation of the sectional column or to place it in a vessel with controlled temperature);
- radioactive methyl iodide is injected into the carrier gas from a generator and then it is trapped in the sectional columns containing the sorbent to be tested;
- before discharging the test gas, the air is passed through a protection column for radiation protection issues and for control of the penetration radioiodine and to ensure a low level of iodine active species in discharged air;
- each section test column is monitored for radioiodine content via gamma monitors (0,364 MeV for ^{131}I);
- the sorption capacity index is calculated using the formula given in [Clause 9](#).

[Figure 1](#) presents the principle of an example scheme of the test plant used for the method presented in this document.