
**Optics and photonics —
Environmental test methods —
Part 17:
Combined contamination, solar
radiation**

iTeh STANDARD PREVIEW
*Optique et photonique — Méthodes d'essais d'environnement —
Partie 17: Essai combiné contamination-rayonnement solaire*
(standards.iteh.ai)

ISO 9022-17:2015

<https://standards.iteh.ai/catalog/standards/sist/5874d145-f6b7-4953-9e7d-b86d660fa834/iso-9022-17-2015>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9022-17:2015

<https://standards.iteh.ai/catalog/standards/sist/5874d145-f6b7-4953-9e7d-b86d660fa834/iso-9022-17-2015>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	vi
1 Scope	1
2 Normative references	1
3 General information and test conditions	1
3.1 General.....	1
3.2 Specimens	2
4 Conditioning	2
4.1 Conditioning method 90: Basic cosmetic substances and artificial hand sweat, combined with solar radiation	2
4.2 Conditioning method 91: Fuels and other resources for aircraft, naval vessels, and land vehicles, combined with solar radiation	2
5 Procedure	2
5.1 General.....	2
5.2 Preconditioning, recovery, evaluation, and general level for acceptance.....	2
6 Environmental test code	4
7 Specification	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9022-17:2015

<https://standards.iteh.ai/catalog/standards/sist/5874d145-f6b7-4953-9e7d-b86d660fa834/iso-9022-17-2015>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information \(standards.iteh.ai\)](http://Foreword - Supplementary information (standards.iteh.ai))

The committee responsible for this document is ISO/TC 172, *Optics and photonics*, Subcommittee SC 1, *Fundamental standards*.

This second edition cancels and replaces the first edition (ISO 9022-17:1994), of which it constitutes a minor revision.

ISO 9022 consists of the following parts, under the general title *Optics and photonics — Environmental test methods*:

- *Part 1: Definitions, extent of testing*
- *Part 2: Cold, heat and humidity*
- *Part 3: Mechanical stress*
- *Part 4: Salt mist*
- *Part 6: Dust*
- *Part 7: Resistance to drip or rain*
- *Part 8: High internal pressure, low internal pressure, immersion*
- *Part 9: Solar radiation and weathering*
- *Part 11: Mould growth*
- *Part 12: Contamination*
- *Part 14: Dew, hoarfrost, ice*
- *Part 17: Combined contamination, solar radiation*
- *Part 20: Humid atmosphere containing sulfur dioxide or hydrogen sulfide*

- *Part 22: Combined cold, dry heat or temperature change with bump or random vibration*
- *Part 23: Low pressure combined with cold, ambient temperature and dry and damp heat*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9022-17:2015

<https://standards.iteh.ai/catalog/standards/sist/5874d145-f6b7-4953-9e7d-b86d660fa834/iso-9022-17-2015>

Introduction

Optical instruments are affected during their use by a number of different environmental parameters which they are required to resist without significant reduction in performance and to remain within defined specifications.

The type and severity of these parameters depend on the conditions of use of the instrument (for example, in the laboratory or workshop) and on its geographical location. The environmental effects on optical instrument performance in the tropics and subtropics are totally different from those found when they are used in arctic regions. Individual parameters cause a variety of different and overlapping effects on instrument performance.

The manufacturer attempts to ensure, and the user naturally expects, that instruments will resist the likely rigours of their environment throughout their life. This expectation can be assessed by exposure of the instrument to a range of simulated environmental parameters under controlled laboratory conditions. The severity of these conditions is often increased to obtain meaningful results in a relatively short period of time.

In order to allow assessment and comparison of the response of optical instruments to appropriate environmental conditions, ISO 9022 contains details of a number of laboratory tests which reliably simulate a variety of different environments. The tests are based largely on IEC standards, modified where necessary to take into account features special to optical instruments.

As a result of continuous progress in all fields, optical instruments are no longer only precision-engineered optical products, but, depending on their range of application, also contain additional assemblies from other fields. For this reason, the principal function of the instrument is to be assessed to determine which International Standard should be used for testing. If the optical function is of primary importance, then ISO 9022 is applicable, but if other functions take precedence then the appropriate International Standard in the field concerned should be applied. Cases can arise where application of both ISO 9022 and other appropriate International Standards will be necessary.

Optics and photonics — Environmental test methods —

Part 17:

Combined contamination, solar radiation

1 Scope

This part of ISO 9022 specifies the methods relating to the environmental tests of optical instruments and including additional assemblies from other fields (e.g. mechanical, chemical, and electronic devices) under equivalent conditions, for their ability to resist the influence of combined contamination and solar radiation. “Contamination”, as used in this part of ISO 9022, means the contact of optical instruments with corrosive chemical substances (hereafter called test agents).

Complete instruments or assemblies are, however, not be tested to this part of ISO 9022 except for special reasons (refer to ISO 9022-12). As a rule, representative substrates are used as specimens.

The tests described in this part of ISO 9022 are designed for the selection of materials and components for instruments likely to be subjected to combined contamination and solar radiation during service life, rather than for regular production control.

The purpose of testing is to investigate the resistance of an instrument, and in particular, of instrument surfaces, coatings, or synthetic materials to a short-time exposure to the test agents combined with solar radiation.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9022-1, *Optics and photonics — Environmental test methods — Part 1: Definitions, extent of testing*

ISO 9022-9, *Optics and photonics — Environmental test methods — Part 9: Solar radiation and weathering*

ISO 9022-12, *Optics and photonics — Environmental test methods — Part 12: Contamination*

3 General information and test conditions

3.1 General

Exposure of the specimen to the combined stress conditions renders the test much more severe than separate exposure to any of the conditions cited.

The test shall be conducted in ambient atmospheric conditions in accordance with ISO 9022-1.

The test agents listed in [Tables 1](#) and 2 were selected from ISO 9022-12, conditioning methods 86 and 89.

The test shall be conducted in accordance with the requirements of ISO 9022-9 and ISO 9022-12.

The surface of the specimens shall be orientated so that the test agents do not flow away during testing. If liquid test agents are used, enough drops shall be deposited in one place on the surface to form a circular spot of approximately 10 mm diameter. During the test, the test agents may not flow into each other. In the case of spreading liquids, several specimens should be used if necessary. Viscous or paste

liquids shall be spread evenly and thinly in the form of the spot described above (thickness approximately 0,1 mm). It should be noted that heating of the test agents can cause them to spread during the test. Test agents which evaporate during the test shall not be replaced.

The relevant specification might require testing of a complete instrument or assembly if such instrument or assembly would be likely to encounter, during its service life, complete flooding rather than partial contamination only. After having preconditioned such specimens as described in ISO 9022-12, the surface shall be completely and copiously sprayed, by means of an atomizer, with a test agent specified in the relevant specification. Any test agent evaporating during exposure shall not be replaced.

3.2 Specimens

For specimens, see ISO 9022-12.

4 Conditioning

[Tables 1](#) and [2](#) show combinations of degrees of severity from ISO 9022-9 and test agents from ISO 9022-12, conditioning methods 86 and 89.

4.1 Conditioning method 90: Basic cosmetic substances and artificial hand sweat, combined with solar radiation

See [Table 1](#).

4.2 Conditioning method 91: Fuels and other resources for aircraft, naval vessels, and land vehicles, combined with solar radiation

See [Table 2](#).

5 Procedure

5.1 General

The test shall be conducted in accordance with the requirements of the relevant specifications and the reference documents.

5.2 Preconditioning, recovery, evaluation, and general level for acceptance

For preconditioning, recovery, evaluation, and general level for acceptance, see ISO 9022-12.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/5874d145-f6b7-4953-9e7d-b86d660fa834/iso-9022-17-2015>
ISO 9022-17:2015

Table 1 — Degrees of severity for conditioning method 90: Basic cosmetic substances and artificial hand sweat, combined with solar radiation

Degree of severity		01	02	03 ^a	04 ^a
Temperature limits within test chamber	°C $\frac{t_2}{t_1}$	55 ± 2	55 ± 2	40 ± 2	55 ± 2
		25 ± 2			
Relative humidity	%	<40			
Recirculating air speed	m/s	1,5 to 3			
Irradiance	kW/m ²	1 ± 0,1	0 to 1,0 ^b	1 ± 0,1	1 ± 0,1
Total exposure time ^c	days	3	5	4	10
Irradiation ^c	kWh/m ²	24	45	96	240
Test sequence ^c		Figure 1	Figure 2	Figure 3	Figure 3
Number of cycles		5	5	1	
Test agents		Paraffin oil, high purity Glycerine, high purity Vaseline, white Lanoline (unguentum molle) Cold cream (unguentum leniens) Artificial hand sweat ^d			
State of operation		1			

^a For testing representative specimens only.

^b Tolerance for intermediate irradiance levels and upper limit ±0,1 kW.

^c Refer to ISO 9022-9, Figures 1 to 3.

^d High purity composition:

4,0 g sodium chloride

1,0 g urea

3,5 g ammonium chloride

3,0 ml lactic acid

0,5 ml acetic acid

0,5 ml pyruvic acid

1,0 ml butyric acid

Add sufficient distilled water to make 1 000 ml of solution.

Table 2 — Degrees of severity for conditioning method 91: Fuels and other resources for aircraft, naval vessels, and land vehicles, combined with solar radiation

Degree of severity		01 ^a	02 ^a
Temperatures limits within test chamber	$^{\circ}\text{C} \frac{t_2}{t_1}$	40 ± 2	55 ± 2
		25 ± 2	
Relative humidity	%	<40	
Recirculating air speed	m/s	1,5 to 3	
Irradiance	kW/m ²	$1 \pm 0,1$	$1 \pm 0,1$
Total exposure time ^b	days	4	10
Irradiation ^b	kWh/m ²	96	240
Test sequence ^b		Figure 3	Figure 3