
**Implants for surgery — Wear of
total intervertebral spinal disc
prostheses —**

Part 3:

**Impingement-wear testing and
corresponding environmental
conditions for test of lumbar
prostheses under adverse kinematic
conditions**

[https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-](https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-211111111111)

*Implants chirurgicaux — Usure des prothèses totales de
remplacement des disques intervertébraux lombaires —*

*Partie 3: Essai d'incidence d'usure et conditions environnementales
correspondantes pour l'essai de prothèses lombaires sous conditions
cinématiques défavorables*



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18192-3:2017

<https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reagents and materials	2
6 Apparatus	3
7 Impingement wear testing methods	5
7.1 General	5
7.2 Example of development of load and displacement profiles for extension impingement protocol	6
7.3 Procedure	7
8 Test report	8
9 Disposal of test specimen	9
Annex A (normative) Wear of spinal disc prostheses — Gravimetric measurement method	10
Annex B (informative) Justification of the test method	13
Bibliography	15

iTeh STANDARD PREVIEW

(standards.iteh.ai)

ISO 18192-3:2017

<https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 5, *Osteosynthesis and spinal devices*. [ISO 18192-3:2017](https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254de2f64b21/iso-18192-3-2017)

A list of all parts in the ISO 18192 series can be found on the ISO website.

Implants for surgery — Wear of total intervertebral spinal disc prostheses —

Part 3:

Impingement-wear testing and corresponding environmental conditions for test of lumbar prostheses under adverse kinematic conditions

1 Scope

This document defines a test procedure to simulate and evaluate lumbar spinal disc prostheses wear under adverse impingement conditions.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4965-1, *Metallic materials — Dynamic force calibration for uniaxial fatigue testing — Part 1: Testing systems*

ISO 18192-3:2017

ISO 18192-1, *Implants for surgery — Wear of total intervertebral spinal disc prostheses — Part 1: Loading and displacement parameters for wear testing and corresponding environmental conditions for test*

ISO 23788, *Metallic materials — Verification of the alignment of fatigue testing machines*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18192-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

impingement

point at which two opposing components collide or restrict motion usually indicated by a sharp change in force or moment

3.2

range of motion

ROM

amount of angular displacement that a total disk replacement prosthesis can undergo from the device neutral position to the point at which impingement occurs around a defined global axis

Note 1 to entry: If an implant impinges at 15° from the implant neutral position in flexion and 20° from the implant neutral position in extension, the implant range of motion can be defined as +15°/-20° in flexion/extension.

3.3 distance between centre of rotation and point of impingement

DCI

distance between the point of impingement and the nominal centre of rotation for the flexion, extension or lateral bending motions

3.4 axial load during impingement

ALI

axial load applied to the device in newtons while the device is in an impinged condition

3.5 point of impingement

point of contact between two opposing components that results in impingement

4 Principle

Based on current clinical evidence, lumbar spinal disc prostheses have experienced impingement in extension/flexion, lateral bending, axial rotation and combinations thereof with extension being the most commonly reported mode for the lumbar spine.

Adverse impingement testing conditions are determined based on available clinical data, engineering analysis and other relevant information in the literature.

An axial load and a time-varying angular displacement are applied to the test specimens to simulate repeated contact between design features of the specimens.

Four possible individual impingement scenarios have been identified in the literature:

- a) flexion; [ISO 18192-3:2017](https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017)
- b) extension; <https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017>
- c) lateral bending;
- d) combined flexion and lateral bending.

In addition, combined axial rotation with any of the aforementioned motion modes should be considered, if necessary to achieve a clinically relevant impingement wear scar and/or worst case impingement scenario.

A load soak control specimen, if polymers are the object of investigation, is subjected to the same time-varying force to determine the creep of the test specimen and/or the amount of mass change due to fluid transfer. The test takes place in a controlled environment simulating physiological conditions.

5 Reagents and materials

5.1 Fluid test medium.

The fluid test medium consisting of calf serum diluted with de-ionized water (balance) to a concentration of $20 \text{ g} \pm 2 \text{ g}$ protein/l shall be prepared according to ISO 18192-1. If routine monitoring of the pH of the fluid test medium is undertaken, the values shall be included in the test report [see [Clause 8](#), m) 6)] as an increase in pH could indicate an increase in microbial activity^[1].

5.2 Test and control specimen.

Between the inferior and superior components shall be the articulating surface of the inferior and superior components, attached by its normal immediate backing (for example, bone cement or a machined replica of the inner surface of the backing), unless this is impractical due to physical features

of the implant system. If the component forming the articulating surface is fixed to the backing by a rim/snap-fit system, the machined replica shall provide the same fixation conditions.

If it is not practical to use the normal backing or cement fixation due to physical features of the implant system, the support system for the inferior and/or superior component should represent normal design features and conditions of use but should allow removal of the component for measurement of wear without destruction.

It is recommended that six specimens be tested for the impingement-wear test. If less than six specimens are tested, appropriate justification shall be given.

NOTE The number of specimens tested can be the subject of national legislation.

If polymers are the object of investigation, a load soak control specimen is to be subjected to the same axial load to determine the creep of the test specimen and/or the amount of mass change due to fluid transfer. The test should take place in a controlled environment of test medium to simulate physiological conditions (see 5.1).

In the test cases where surrounding fluid is not absorbed by the specimens, test specimens shall be weighed prior to testing with an instrument having a precision of 0,1 mg.

The tested implant size should be selected by an engineering analysis including theoretical, computational, or experimental methods. If computational methods are used, experimental verification that considers the point of impingement, the materials in contact and the range of motion of the specimens is recommended. The point of impingement and the centre of rotation of the bearing are detected in all testing directions. The combination of implant components with the highest contact stress in the tested direction is selected for the test. If the materials in contact during impingement change with size, then tests with different implant sizes should be considered. The number of test specimens of each size should not be less than three with no less than six test specimens in total.

[ISO 18192-3:2017](https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017)

6 Apparatus <https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017>

For the kinematical analysis the following testing configuration shall be applied. Deviation from this testing configuration shall be justified.

6.1 Test machine, in accordance with ISO 4965-1 and ISO 23788, as specified in ISO 18192-1 for lumbar prosthesis, and capable of associating and replacing the required corresponding angular displacements and forces (see [Clause 7](#)) for each specific protocol of movement.

6.2 Means of mounting and enclosing the test specimen, as specified in ISO 18192-1 for lumbar prosthesis.

6.3 Means of aligning and positioning, as specified in ISO 18192-1 for lumbar prosthesis.

6.4 Motion control system, capable of generating the required angular movements of the inferior component with an accuracy of $\pm 1^\circ$ at the maxima and minima of the motion and $\pm 5\%$ of cycle time phasing. For multi-station test systems, capabilities shall be assessed with all stations active.

6.5 Force control system, capable of generating a force in the z-direction (see [Figure 1](#)), which varies for each specific protocol of movement, and capable of maintaining the magnitude of the maxima and minima of this force cycle to a tolerance of $\pm 5\%$ of the maximum force value for the cycle and $\pm 5\%$ of the full cycle time for phasing. For multi-station test systems, capabilities shall be assessed with all stations active.

6.6 Lubrication system, as specified in ISO 18192-1 for lumbar prosthesis.

6.7 Temperature control system, as specified in ISO 18192-1.

6.8 Control station(s), capable of applying the loading regime for specific protocol of movement and incorporating the requirements given in [6.1](#), [6.2](#), [6.5](#), [6.6](#) and [6.7](#).

6.9 The origin of the fixed coordinate system of the test machine (which is consistent with the centre of rotation of the implant) shall be the intersection of the axis for lateral bending, flexion extension and axial rotation. The machine's former sequence shall be the Euler sequence used for coordinate transformation. The coordinate system of the test machine shall coincide with the coordinate system of the upper endplate. All other parts of the specimens shall move relative to this coordinate system (see [Figure 1](#)).

The axial load vector shall be perpendicular to the flexion (Y) and lateral bending (X) axis and shall coincide with axial rotation (Z) axis in a fixed coordinate system.


The superior endplate may translate along the Z axis and in the XY plane (to avoid shear forces). The inferior endplate may rotate around all three axis.

The intended movement shall be applied via the inferior endplate. The load shall be applied via the superior endplate.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 18192-3:2017](#)

<https://standards.iteh.ai/catalog/standards/sist/d1e2aac6-02e3-4cd0-89b9-254da2ea6d2c/iso-18192-3-2017>

**Key**

- 1 flexion/extension
- 2 lateral/bending
- 3 axial rotation

Figure 1 — Coordinate system of the test machine

7 Impingement wear testing methods

7.1 General

Extension, flexion, and lateral bending impingement boundary conditions shall be analysed to determine the worst case clinically relevant conditions to be tested. In addition, the manufacturer should consider combining axial rotation with any of the aforementioned motion modes, if necessary to achieve a clinically relevant impingement wear scar and worst case impingement wear or damage.

The nominal device centre of rotation in flexion, extension, lateral bending and axial rotation shall be determined.

The points of impingement in all testing directions shall be detected and the respective perpendicular distance between each point of impingement and the nominal centre of rotation (DCI) determined.

The load and displacement profile shall be developed prior to running the test.

During impingement testing, the device range of motion shall be exceeded by at least 2° in the impingement direction. In addition, the impingement region shall be offloaded completely each cycle.

The angular displacements applying flexion/extension, lateral bending and/or rotation should be sinusoidal.

Establish the pattern of load and movement for each selected movement protocol. An example of development of load and displacement profiles for extension impingement protocol is presented in 7.2.

7.2 Example of development of load and displacement profiles for extension impingement protocol

Figure 2 shows an example of an impingement load and displacement profile in extension that is based on applying a moment of 7,5 Nm to the device during impingement. In this example, the test starts with the device in the 0-point position and progresses 3° in flexion. Subsequently, the motion progresses back through the neutral position to 2° beyond the device range of motion in extension. In this example, lateral bending and axial rotation are held at neutral.

For some bearing combination, force overshoot can be observed at the point of impingement. Force overshoot should be minimized.

To apply a 7,5 Nm extension moment, the horizontal distance between the centre of the device and DCI should be measured. The ALI necessary to apply the 7,5 Nm impingement motion mode moment during impingement shall be determined by dividing 7,5 Nm by the DCI, expressed in metres (m).

NOTE 1 The extension moment value is justified in Reference [2].




Figure 2 — Example of load and displacement profile for a lumbar spine extension impingement wear test

The loading conditions for this example are as follows:

- a) sinusoidal axial loading is used except for the impingement loading interval;
- b) a minimum axial load of 300 N is used to engage the sample at the neutral position;

NOTE 2 The minimum axial load value in ISO 18192-1 is 600 N. In certain designs, a 600 N load will exceed the 7,5 Nm moment. Therefore, a 300 N minimum axial load force was selected for this example.

- c) the maximum ALI from all tested motions is used to define the non-impingement sinusoidal load profile;
- d) during impingement, the axial load is constant and equal to ALI as determined above.

NOTE 3 In the context of this example, to “offload” means changing the angular displacement to eliminate impingement,

7.3 Procedure

7.3.1 Prior to testing, clean the implant specimen and characterize the surface conditions with photographs using up to 10 times magnification. A typical ultrasonic cleaning regime is established in [A.2.4](#).

7.3.2 Mount the specimen in the testing machine, ensuring the required alignment.

7.3.3 Fill the test chamber such that the test specimen is fully immersed in the fluid test medium.

7.3.4 In accordance with accepted wear test procedures, replace the fluid test medium completely at least every 5×10^5 cycles, or every seven days, whichever is the shorter. If the objective of the test is to characterize particle or ion release, one volume of test medium may be used without changing the test medium until the protocol is complete.

7.3.5 Run the test with the load and displacement profiles developed for the protocol. See [7.2](#) and [Figure 2](#) for example load and displacement profiles. For any control specimens, run the test with the same load profile without displacement. Operating the testing machine at a frequency of 1 Hz is recommended. An accuracy of $\pm 0,1$ Hz is required.

7.3.6 Stop the machine after $1,25 \times 10^5$ cycles, $2,5 \times 10^5$ cycles, 5×10^5 cycles and 1×10^6 cycles. Remove the test specimen from the machine. Clean the specimen. Characterize the contact pattern with light microscopy with appropriate magnification.

NOTE Use of 50 times magnification has been used successfully in some laboratories for impingement wear characterization.

7.3.7 Gravimetric analyses of the specimen shall be performed at the beginning of the test and at each of the intervals defined in [7.3.6](#) according to [Annex A](#). Additionally, the fluid test medium may be analysed for wear particles and ion-concentration. If particle analysis is to be conducted, the fluid test medium should be frozen and stored.

7.3.8 In case larger deformations are observed during specimen inspection at the point of impingement which allow no further contact between implant components as intended for the test, the displacement waveform has to be adjusted to again run the specimen to 2° beyond the ROM.

7.3.9 Continue the test until one of the following occurs.

- a) Completion of the cycle limit. The cycle limit shall be 1×10^6 cycles unless the submitter of the specimen requests a different cycle limit, which may be used with appropriate justification.

NOTE 1 The number of cycles tested can be the subject of national legislation.