
**Thermal insulation for building
equipment and industrial
installations — Aluminosilicate wool
products — Specification**

*Isolation thermique pour les équipements du bâtiment et les
installations industrielles — Produits en laine d'aluminosilicate —
Spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20310:2018

<https://standards.iteh.ai/catalog/standards/sist/b3356548-51c7-4a69-be23-9f26fadedf0aa/iso-20310-2018>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 20310:2018

<https://standards.iteh.ai/catalog/standards/sist/b3356548-51c7-4a69-be23-9f26fadedf0aa/iso-20310-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
4.1 Symbols	2
4.2 Abbreviated terms	2
5 Requirements	2
5.1 General	2
5.2 Classification	3
5.3 Permanent linear change	3
5.4 Thermal conductivity	3
5.5 Dimensions	3
5.6 Apparent density	4
5.7 Shot content	4
5.8 Tensile strength	4
6 Test methods	5
6.1 Sampling	5
6.2 Conditioning	5
6.3 Testing	5
6.3.1 Test methods and specimen requirements	5
6.3.2 Thermal conductivity	6
7 Designation code	6
8 Product conformity	6
8.1 General	6
8.2 Initial type testing	7
8.3 Factory production control	7
9 Marking and labelling	7
Annex A (normative) Factory production control	8
Annex B (informative) Evaluation of conformity	9
Annex C (informative) Service temperature of aluminosilicate wool, ceramic wool and mineral wools	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 163, *Thermal performance and energy use in the built environment*, Subcommittee SC 3, *Thermal insulation products*.

<https://standards.iteh.ai/catalog/standards/sist/b3356548-51c7-4a69-be23-9f26fadedf0aa/iso-20310-2018>

Thermal insulation for building equipment and industrial installations — Aluminosilicate wool products — Specification

1 Scope

This document specifies the classification, requirements and test methods for factory-made aluminosilicate wool products which are used for thermal insulation of industrial installations and building equipment, for non-refractory applications. The products are delivered as blanket, module, felt, board, paper, textile and other forms.

This document describes product characteristics and testing methods, marking and labelling.

This document does not specify the required level of a given property to be achieved by a product to demonstrate fitness for purpose in a particular application.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 836, *Terminology for refractories*

ISO 8302, *Thermal insulation — Determination of steady-state thermal resistance and related properties — Guarded hot plate apparatus*

ISO 8894-1, *Refractory materials — Determination of thermal conductivity — Part 1: Hot-wire methods (cross-array and resistance thermometer)*

ISO 9229, *Thermal insulation — Vocabulary*

ISO 10635, *Refractory products — Methods of test for ceramic fibre products*

ISO 13787, *Thermal insulation products for building equipment and industrial installations — Determination of declared thermal conductivity*

ISO 29465, *Thermal insulating products for building applications — Determination of length and width*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9229, ISO 836 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1 aluminosilicate wool ASW

amorphous High Temperature Insulating Wool (HTIW) manufactured predominantly from molten raw minerals

Note 1 to entry: The main ingredients are Al_2O_3 and SiO_2 , and may contain ZrO_2 and Cr_2O_3 .

3.2 aluminosilicate module

aluminosilicate wool (3.1) blanket formed into thick sections by needling, stacking or folding sheets, compressed to a higher density and typically supplied with integral anchoring systems

3.3 aluminosilicate paper

thin and flexible insulating material formed on a paper-making machine

4 Symbols and abbreviated terms

4.1 Symbols

b	width	mm
d	thickness	mm
l	length	mm
d_N	nominal thickness of the product	mm
λ	thermal conductivity	$\text{W}/(\text{m} \cdot \text{K})$
λ_D	declared thermal conductivity	$\text{W}/(\text{m} \cdot \text{K})$
ρ_a	apparent density	kg/m^3
ρ_D	nominal apparent density	kg/m^3

4.2 Abbreviated terms

ITT	initial type test
FPC	factory production control

5 Requirements

5.1 General

Product properties shall be tested in accordance with [Clause 6](#). To comply with this document, products shall meet the requirements of [5.2](#) to [5.8](#), where applicable.

The test methods to be used for determination of each property are given in [Table 5](#), which also shows the required test specimen dimensions and the minimum number of test specimens required to give one test result.

One test result for a product property is the average of the measured values on the number of test specimens given in [Table 5](#).

For FPC, see [Annex A](#).

5.2 Classification

Products shall be classified into one of six types according to the classification temperature per [Table 1](#).

Table 1 — Type and classification temperature – unit: Celsius

Classification	Classification temperature ^a °C	Recommended service temperature ^b °C
Type I	1 000	800
Type II	1 200	1 000
Type III	1 250	1 100
Type IV	1 350	1 200
Type V	1 400	1 250
Type VI	1 500	1 350

^a The classification is determined by permanent linear change testing at the classification temperature.

^b Recommended service temperatures are recommended for long-term use. Generally they are 150 °C to 200 °C lower than classification temperatures, based on actual usage and specific conditions. Service temperature of aluminosilicate wool, ceramic wool and mineral wools are given in [Annex C](#).

5.3 Permanent linear change

Permanent linear change upon heating shall not be greater than 4,0 %. The test temperature shall be at the classification temperature as per [Table 1](#).

5.4 Thermal conductivity

The manufacturer shall make declaration for the thermal conductivity λ_D . The table or curve of conductivity versus temperature (from 200 °C up to 1 100 °C, where applicable) shall be given according to ISO 13787. Thermal conductivity shall be based upon measurements carried out in accordance with ISO 8302 up to 800°C and shall be in accordance with ISO 8894-1 or ISO 10635 for temperatures above 800 °C.

5.5 Dimensions

The length, l , and width, b , shall be determined in accordance with ISO 29465. The thickness, d , shall be determined in accordance with ISO 10635. No test result shall deviate from the nominal values by more than the tolerances given in [Table 2](#).

Table 2 — Board, blanket, felt and paper dimension tolerances

Product type	Length tolerance	Width tolerance	Thickness	
			Nominal	Tolerance
Board	±5 mm	±5 mm	—	+3 mm –2 mm
Blanket	+∞ –0	+15 mm –2 mm	10 mm < 20 mm	+4 mm – 2 mm
			≥20 mm	+8 mm –4 mm
Felt	±4 mm	±3 mm	<15 mm	+2 mm –2 mm
			≥15 mm	+3 mm –3 mm
Paper	+∞ –0	+∞ –0	< 2 mm	+0,3 mm –0,2 mm
			≥2 mm	+0,5 mm –0,5 mm

5.6 Apparent density

The tolerance of apparent density, ρ_D , from the nominal density, ρ_a , as measured by ISO 10635 shall not be more than ±10 %.

5.7 Shot content

The mass of the shot content, as measured by ISO 10635, with a diameter larger than 0,212 mm shall not be more than 20,0 % of the total mass.

5.8 Tensile strength

The tensile strength of the blanket and felt as measured by ISO 10635 shall be in accordance with the requirements in [Table 3](#).

Table 3 — Tensile strength for blanket and felt

Nominal density kg/m ³	Tensile strength kPa
<64	≥14
64 to 95	≥20
96 to 127	≥28
128 to 159	≥42
160 to 192	≥56
>192	≥70

The tensile strength of paper as measured by ISO 10635 shall be in accordance with the requirements in [Table 4](#).

Table 4 — Tensile strength of paper

Thickness mm	Tensile strength kPa
<2,0	≥250
2,0 to 2,9	≥200
3,0 to 3,9	≥150
≥4,0	≥100

6 Test methods

6.1 Sampling

Test specimens shall be taken from the same sample, with a total area not less than 1 m², and sufficient to cover the tests needed. The shorter side of the sample shall not be less than 300 mm or the full size of the product, whichever is the smaller.

6.2 Conditioning

The test specimens shall be dried at 110 °C until constant mass is reached.

The constant mass is reached when the change of mass between three consecutive weighings made 24 h apart is less than 0,1 % of the total mass (see ISO 12570). The conditioning should be noted on the test report.

6.3 Testing

6.3.1 Test methods and specimen requirements

[Table 5](#) provides the dimensions of the test specimens, the minimum number of measurements required to obtain one test result.

Testing may be performed on unfaced/uncoated product if the facing/coating is shown to have no relevance to the test result.

Table 5 — Test methods, test specimens and specific conditions

No.	Subclause Title	Test method	Test specimen length and width	Minimum number of measurements to get one test result
5.4	Thermal conductivity	ISO 8302, ISO 8894-1, or ISO 10635	ISO 8302, ISO 8894-1 or ISO 10635	1
5.5	Length and width	ISO 29465	Full-size	3
	Thickness	ISO 10635	Full-size	4
5.6	Apparent density	ISO 10635	Full-size	1
5.7	Shot content	ISO 10635	ISO 10635	3
5.3	Permanent linear change	ISO 10635	100 mm × 100 mm	2
5.8	Tensile strength	ISO 10635	230 mm × 75 mm	5