



## Standard Test Method for Extrudability of Oil- and Resin-Base Caulking Compounds<sup>1</sup>

This standard is issued under the fixed designation D 2452; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

~~<sup>ε1</sup>Note—An editorial change was made in 1.1 in February 1999.~~

### 1. Scope

1.1 This test method describes the laboratory procedure for determining the rate of extrusion of oil- and resin-base caulking compounds.

1.2 The values stated in metric (SI) units are to be regarded as the standard. The values given in parentheses are provided for information only.

~~1.3~~

~~1.3 The subcommittee with jurisdiction is not aware of any similar ISO standard.~~

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C 717 [Terminology of Building Seals and Sealants](#)

D 1475 [Test Method for Density of Paint, Varnish, Lacquer and Related Products](#) Test Method For Density of Liquid Coatings, Inks, and Related Products

### 3. Terminology

3.1 *Definitions*—Definitions of the following terms are found in Terminology C 717: caulking compound, compound, sealant.

### 4. Significance and Use

4.1 The rate of extrusion determined by this test may be correlated with the rate of gunning of the compound.

### 5. Apparatus

5.1 *Press-Flow Extrusion Rheometer* constructed in accordance with Fig. 1.

5.2 *Air Supply and Pressure Gage*, accurate to 6.9 kPa (1 psi).

5.3 *Clamps and Stand* to hold rheometer.

5.4 *Balance*, accurate to 0.01 g.

5.5 *Stop Watch*.

5.6 *Spatula (Steel)*.

5.7 *Weight-per-gallon Cup*, capacity 83.2 cm<sup>3</sup>.

### 6. Reagent

6.1 *Solvent*, such as methyl ethyl ketone.

<sup>1</sup>This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants, and is the direct responsibility of Subcommittee C24.20 on General Sealant Standards.

Current edition approved April 15, 1994. Published June 1994. Originally published as D2452-66 T. Last previous edition D2452-75(1993).

<sup>2</sup>This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.20 on General Test Methods.

Current edition approved Jan. 1, 2009. Published March 2009. Originally approved in 1966. Last previous edition approved in 2003 as D 2452 – 03.

<sup>3</sup>For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* Vol 04.07 volume information, refer to the standard's Document Summary page on the ASTM website.

