



SLOVENSKI STANDARD
kSIST prEN ISO 12625-11:2019
01-februar-2019

Tissue papir in proizvodi iz tissue papirja - 11. del: Ugotavljanje razpočne trdnosti s kroglico v mokrem (ISO/FDIS 12625-11)

Tissue paper and tissue products - Part 11: Determination of wet ball burst strength

Tissue-Papier und Tissue-Produkte - Teil 11: Bestimmung der Nass-Berstfestigkeit mit einem Durchstoßkörper

Papier tissue et produits tissues - Partie 11: Détermination de la résistance à l'éclatement à l'état humide, méthode à la balle

<https://standards.iteh.ai/catalog/standards/sist/77e14efd-3a90-4242-9886-8b8b063242b/sist-en-iso-12625-11-2019>

Ta slovenski standard je istoveten z: prEN ISO 12625-11

ICS:

85.080.20 Tissue papir

Tissue paper

kSIST prEN ISO 12625-11:2019

en,fr,de

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
12625-11

ISO/TC 6/SC 2

Secretariat: SIS

Voting begins on:
2018-11-27

Voting terminates on:
2019-02-19

Tissue paper and tissue products — Part 11: Determination of wet ball burst strength

Papier tissue et produits tissues —

*Partie 11: Détermination de la résistance à l'éclatement à l'état
humide, méthode à la balle*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 12625-11:2019

<https://standards.iteh.ai/catalog/standards/sist/77e14efd-3a90-4242-9886-8b8b0f63242b/sist-en-iso-12625-11-2019>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/FDIS 12625-11:2018(E)

© ISO 2018

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 12625-11:2019

<https://standards.iteh.ai/catalog/standards/sist/77e14efd-3a90-4242-9886-8b8b0f63242b/sist-en-iso-12625-11-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Reagents	2
6 Apparatus	2
6.1 General	2
6.2 Clamping system	2
6.3 Penetration system	3
6.4 Force measuring system	3
6.5 Drive mechanism	4
6.6 Water application system	4
7 Sampling	4
8 Conditioning	4
8.1 General	4
8.2 Rapid ageing (curing)	4
9 Preparation of test pieces	5
9.1 General	5
9.2 Preparation of test pieces	5
10 Procedure	5
11 Calculation	6
12 Test report	6
Annex A (informative) Precision	7
Annex B (informative) Adaptor	8
Bibliography	9

ISO/FDIS 12625-11:2018(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

This second edition cancels and replaces the first edition (ISO 12625-11:2012), of which it constitutes a minor revision.

The main changes compared to the previous edition are as follows:

- [Clause 12](#), addition of new "h)" stating "clamping ring diameter (89 mm or 50 mm)".

A list of all parts in the ISO 12625 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This part of ISO 12625 is applicable to tissue papers and tissue products. In principle, application to other types of paper is possible, but is not covered by this part of ISO 12625.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 12625-11:2019

<https://standards.iteh.ai/catalog/standards/sist/77e14efd-3a90-4242-9886-8b8b0f63242b/sist-en-iso-12625-11-2019>

Tissue paper and tissue products —

Part 11:

Determination of wet ball burst strength

1 Scope

This part of ISO 12625 specifies a test method for the determination of the resistance to mechanical penetration (ball burst strength procedure) of tissue paper and tissue products after wetting.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system*

ISO 12625-1, *Tissue paper and tissue products — Part 1: General guidance on terms*

ISO 12625-9, *Tissue paper and tissue products — Part 9: Determination of ball burst strength*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 12625-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

bursting force

F_D

maximum force, that a test piece of a tissue paper or tissue product can withstand under the test conditions, perpendicular to its surface

[SOURCE: ISO 12625-9:2015, 3.2, modified — right angle changed to perpendicular]

Note 1 to entry: The bursting force is expressed in newtons (N).

3.2

wet bursting force

maximum force, that a wetted test piece of a tissue paper or tissue product can withstand under the test conditions, applied perpendicular to its surface

Note 1 to entry: The wet bursting force is expressed in newtons (N).

ISO/FDIS 12625-11:2018(E)

3.3

wet burst index

wet bursting force of the tissue paper or tissue product divided by the grammage of the conditioned sample determined by the standard method of test

Note 1 to entry: The wet burst index is expressed in newton square metres per gram ($\text{N} \cdot \text{m}^2/\text{g}$).

3.4

wet burst retention

ratio, expressed as a percentage, of the burst strength of the wet tissue paper or wet tissue product to the burst strength of the same tissue paper or tissue product in the dry and conditioned state

Note 1 to entry: This definition is similar to the definition of wet tensile strength retention; see ISO 12625-5:2016, 3.2.

4 Principle

A test piece of tissue paper or tissue product is rigidly clamped at the periphery between two concentric annular rings, then wetted with deionized water and submitted to a perpendicular force until penetration, applied by a ball of a hard, non-deformable, material moving at a constant speed.

5 Reagents

5.1 Deionized water, with a conductivity $\leq 0,25 \text{ mS/m}$ at 25°C , in accordance with ISO 14487. The water temperature should be maintained during the test at the temperature used for conditioning and testing.

6 Apparatus

6.1 General

The apparatus shall be placed on a horizontal surface, free from externally induced vibrations.

6.2 Clamping system

The clamping system is designed to clamp the test piece firmly and uniformly between two concentric annular plane, parallel surfaces. The clamping rings can be activated mechanically or pneumatically.

The clamping pressure shall be sufficient to prevent slippage during the test, without damaging the test pieces.

The clamping surfaces of the clamping rings are coated with a commercial grade of a band made of rubber material, typically 1,0 mm to 2,0 mm thick, having an IRHD hardness (International Rubber Hardness Degree) of 70 IRHD to 85 IRHD. The inner edges of the coated band shall be coincident with the inner diameter of the clamping rings and be at least 12,5 mm wide. The internal diameter of the two concentric rings shall be $(50,0 \pm 0,2) \text{ mm}$. For an example of a pneumatic clamping system, see [Figure 1](#).