
Grey cast irons — Classification

Fontes à graphite lamellaire — Classification

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 185:2019](https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019)

<https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 185:2019

<https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Designation.....	2
5 Order information.....	2
6 Manufacture.....	2
7 Requirements.....	3
7.1 Mechanical properties.....	3
7.2 Tensile properties.....	3
7.2.1 General.....	3
7.2.2 Test pieces machined from cast samples.....	3
7.2.3 Test pieces cut from a casting.....	3
7.3 Hardness properties.....	5
7.4 Graphite structure.....	6
8 Sampling.....	6
8.1 General.....	6
8.2 Types of samples.....	7
8.3 Samples for tensile test.....	7
8.3.1 Size of cast samples.....	7
8.3.2 Frequency and number of test samples.....	7
8.3.3 Separately cast samples.....	7
8.3.4 Side-by-side cast samples.....	7
8.3.5 Cast-on samples.....	8
8.3.6 Samples cut from a casting.....	10
8.4 Samples for hardness test.....	11
9 Test methods.....	11
9.1 Tensile test.....	11
9.2 Brinell hardness test.....	13
9.3 Graphite structure.....	13
9.4 Alternative test procedures.....	13
10 Retests.....	13
10.1 Need for retests.....	13
10.2 Test validity.....	13
10.3 Nonconforming test results.....	14
10.4 Heat treatment of samples and castings.....	14
Annex A (informative) Information on mechanical and physical properties in addition to that given in Tables 1 and 2.....	15
Annex B (informative) Additional information on the relationship between hardness and tensile strength of grey cast irons.....	17
Annex C (informative) Additional information on the relationship between tensile strength, hardness and wall thickness of grey iron castings.....	20
Annex D (informative) Cross-references of ISO 185 grade designations to other standard grades of grey cast irons.....	24
Bibliography.....	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 25, *Cast irons and pig irons*.

This third edition cancels and replaces the second edition (ISO 185:2005), which has been technically revised. The main changes compared with the previous edition are as follows:

- terms and definitions have been added for “separately cast sample”, “side-by-side cast sample” and “cast-on sample”;
- [Table 1](#) has been revised to delete the column of anticipated minimum tensile strength values in castings; this information has been moved to [Annex C](#);
- [Table 1](#) has been revised to include side-by-side cast samples with the same tensile strength requirements as separately cast samples;
- [Table 1](#) has been revised to add a maximum tensile strength for each grade for separately cast samples and side-by-side cast samples;
- [Table 1](#) has been revised to revise minimum tensile strength values for some selected grades and relevant wall thicknesses of cast-on samples;
- [Annex C](#) has been revised to add [Table C.1](#), which shows anticipated values for tensile strength in grey iron castings based on relevant wall thickness; some values are slightly changed from those in [Table 1](#) of the previous edition;
- information in [Annex D](#) has been updated to include corresponding hardness grades from GB/T 9439;
- additional changes have been made for clarity of expression and improved consistency with ISO standards for other types of cast irons.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document deals with the classification of grey cast irons, subdivided into two groups:

- materials specified by their tensile strength;
- materials specified by their hardness.

It is also possible to specify grey cast irons by a combination of tensile strength and hardness.

NOTE This document does not cover technical delivery conditions for grey iron castings.

The properties of grey cast iron depend on the form and distribution of the graphite and on the structure of the matrix.

For many applications, tensile strength and hardness are not the only properties of interest to casting designers. Other mechanical or physical properties can be decisive for the use of grey iron. For example:

- the thermal capacity and the thermal diffusivity for disc brakes;
- the damping capacity for engine blocks or machine beds;
- the thermocycle fatigue for exhaust manifolds or ingot moulds.

Therefore, [Annex A](#) provides additional information of interest to casting designers.

Furthermore:

- [Annex B](#) contains additional information on the relationship between hardness and tensile strength;
- [Annex C](#) contains additional information on the relationship between tensile strength, hardness and wall thickness of grey iron castings;
- [Annex D](#) provides cross-references of ISO 185 grade designations to other standard grades of grey cast irons.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

ISO 185:2019

[https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-](https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9d42e0185185/ISO-185-2019)

9d42e0185185/ISO-185-2019

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 185:2019

<https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019>

Grey cast irons — Classification

1 Scope

This document specifies the properties of unalloyed and low-alloyed grey cast irons used for castings that have been manufactured in sand moulds or in moulds with comparable thermal behaviour.

This document specifies the characterizing properties of grey cast irons by any of the following:

- a) the tensile strength of cast samples;
- b) if agreed by the manufacturer and the purchaser, the tensile strength of samples cut from a casting;
- c) if agreed between the manufacturer and the purchaser, the hardness of the material determined on castings or on a cast-on knob.

If agreed by the manufacturer and the purchaser, the combination of tensile strength from option a) or option b) and plus hardness from option c) can be specified. Information on specifying a combination of tensile strength and hardness is given in [Annex B](#).

This document specifies eight grades of grey cast iron according to tensile strength (see [Table 1](#)) and six grades of grey cast iron according to Brinell hardness (see [Table 2](#)).

This document does not apply to grey cast irons used for pipes and pipe fittings and continuous cast products.

This document does not cover technical delivery conditions for grey iron castings.

NOTE General information on the engineering properties of grey cast irons is provided in ISO/TR 10809-1.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 945-1, *Microstructure of cast irons — Part 1: Graphite classification by visual analysis*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 grey cast iron
cast material, iron and carbon based, carbon being present mainly in the form of flake (lamellar) graphite particles

Note 1 to entry: Grey cast iron is also known as "flake graphite cast iron" and, less commonly, as "lamellar graphite cast iron".

Note 2 to entry: Graphite form, distribution and size are specified in ISO 945-1.

3.2 relevant wall thickness
section of the casting, agreed between the manufacturer and the purchaser, to which the determined mechanical properties apply

3.3 separately cast sample
sample cast in a separate sand mould under representative manufacturing conditions and material

3.4 side-by-side cast sample
sample cast in the mould alongside the casting, with a connected but separate running system

3.5 cast-on sample
sample attached directly to the casting

ITeH STANDARD PREVIEW
(standards.iteh.ai)

4 Designation

The material shall be designated as given in either [Table 1](#) or [Table 2](#). The designation system is given in ISO/TR 15931.

<https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019>

The number in position 3 of the designation in [Table 1](#) is the minimum tensile strength of the grade as determined by test pieces machined from standardized 30 mm test bars or from cast samples of corresponding relevant wall thickness.

The number in position 3 of the designation in [Table 2](#) is the maximum Brinell hardness value of the grade for relevant wall thickness > 40 mm to ≤ 80 mm.

5 Order information

The following information shall be supplied by the purchaser:

- a) the complete designation of the material;
- b) any special requirements that have to be agreed between the manufacturer and the purchaser.

All agreements between the manufacturer and the purchaser shall be made by the time of acceptance of the order.

6 Manufacture

Unless otherwise specified by the purchaser, the method of manufacture of grey cast irons, including their chemical composition, to obtain the specified mechanical properties shall be left to the discretion of the manufacturer.

The manufacturer shall ensure that the requirements of this document are met for the material grade specified in the order.

For grey cast irons to be used in special applications, the chemical composition and heat treatment may be the subject of an agreement between the manufacturer and the purchaser.

7 Requirements

7.1 Mechanical properties

The order shall specify, in an unambiguous manner, whether the characterizing property is tensile strength determined on cast samples or Brinell hardness determined on the casting, or both tensile strength and Brinell hardness.

If the order does not specify the characterizing property, then the manufacturer shall characterize the material according to tensile strength.

7.2 Tensile properties

7.2.1 General

The property values apply to grey cast irons cast in sand moulds or in moulds of comparable thermal behaviour. Subject to amendments to be agreed upon in the order, the property values may be applied to castings obtained by alternative methods.

Tensile properties are dependent upon wall thickness as shown in [Table 1](#). For process quality assurance purposes, standardized 30 mm test bars are commonly used.

NOTE Tensile testing requires sound test pieces in order to guarantee pure uniaxial stress during the test.

7.2.2 Test pieces machined from cast samples

The tensile properties of the eight grades of grey cast iron specified by tensile strength, when determined in accordance with [9.1](#) using test pieces machined from cast samples, shall conform to the requirements specified in [Table 1](#).

7.2.3 Test pieces cut from a casting

If test pieces are to be machined from samples cut from a casting, the manufacturer and the purchaser shall agree on:

- the locations on a casting where the samples shall be taken;
- the minimum value or the allowable range of values for the tensile properties, when determined in accordance with [9.1](#).

NOTE 1 The properties and the structure of castings are not uniform and depend on the complexity of the castings and their variation in section thickness.

NOTE 2 Tensile properties for test pieces machined from samples cut from a casting are affected not only by material properties (subject of this document) but also by the local casting soundness (not subject of this document).

Table 1 — Tensile strength of grey cast irons determined on test pieces machined from cast samples

Material designation	Relevant wall thickness t		Tensile strength R_m		
			in separately cast samples or side-by-side cast samples		in cast-on samples
	mm		MPa		MPa
	\geq	\leq	\geq	\leq	\geq
ISO 185/JL/100	5	40	100	200	—
ISO 185/JL/150	2,5	5	150	250	—
	5	10			—
	10	20			—
	20	40			125
	40	80			110
	80	150			100
ISO 185/JL/200	2,5	5	200	300	—
	5	10			—
	10	20			—
	20	40			170
	40	80			155
	80	150			140
ISO 185/JL/225	5	10	225	325	—
	10	20			—
	20	40			190
	40	80			170
	80	150			155
	150	300			145
ISO 185/JL/250	5	10	250	350	—
	10	20			—
	20	40			210
	40	80			190
	80	150			170
	150	300			160
ISO 185/JL/275	10	20	275	375	—
	20	40			230
	40	80			210
	80	150			190
	150	300			180
ISO 185/JL/300	10	20	300	400	—
	20	40			250
	40	80			225
	80	150			210
	150	300			190

Table 1 (continued)

Material designation	Relevant wall thickness t		Tensile strength R_m		
			in separately cast samples or side-by-side cast samples		in cast-on samples
	mm		MPa		MPa
	\geq	\leq	\geq	\leq	\geq
ISO 185/JL/350	10	20	350	450	—
	20	40			290
	40	80			260
	80	150			240
	150	300			220

For each grade, the figure in bold indicates the minimum tensile strength to which the material designation of the grade relates, based on separately cast or side-by-side cast 30 mm test samples.

Minimum and maximum tensile strength values are mandatory for separately cast samples and for side-by-side cast samples.

Tensile strength values are mandatory for cast-on samples representing the relevant wall thickness, which shall be agreed by the manufacturer and the purchaser.

For relevant wall thicknesses greater than 300 mm, the manufacturer and the purchaser shall agree on the type and size of the cast sample and on the minimum required tensile strength value.

If a particular type of sample is to be specified, a "/" is added to the designation, followed by a letter indicating the type of sample:

/S = separately cast sample or side-by-side cast sample;

/U = cast-on sample;

/C = sample cut from casting.

[ISO 185:2019](https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019)

<https://standards.iteh.ai/catalog/standards/sist/50f7f59e-6e81-4933-8ea9-9df2e0e4f111/iso-185-2019>

If tensile strength is specified as a characterizing property, the type of the sample should be stated in the order. If not stated in the order, the type of sample is left to the discretion of the manufacturer.

For high damping capacity and thermal conductivity, ISO 185/JL/100 is the most suitable material.

For each grade, Brinell hardness decreases with increasing wall thickness.

7.3 Hardness properties

Classification of grey iron castings by hardness is applicable principally where machinability or wear resistance are of importance.

The Brinell hardness values of the six grades of grey cast iron specified by hardness, when determined in accordance with 9.2, shall conform to the requirements specified in Table 2.

NOTE 1 Brinell hardness stated in HBW means under test conditions of 10/3000 unless different test conditions have been specified.

Minimum and maximum Brinell hardness values for the relevant wall thickness specified by the purchaser shall be mandatory for the castings covered by the order.

If a casting is ordered on the basis of hardness, the relevant wall thickness and the position of the test shall be agreed.

NOTE 2 For a relevant wall thickness $t > 80$ mm, grades are not classified by hardness.

If it is not possible to use the Brinell test method in accordance with ISO 6506-1, alternative test methods may be used, which shall have correlated values with Brinell hardness.

Table 2 — Brinell hardness of castings of grey cast iron

Material designation	Relevant wall thickness <i>t</i>		Brinell hardness	
	mm		HBW	
	>	≤	≥	≤
ISO 185/JL/HBW155	40	80	—	155
	20	40		160
	10	20		170
	5	10		185
	2,5	5		210
ISO 185/JL/HBW175	40	80	100	175
	20	40	110	185
	10	20	125	205
	5	10	140	225
	2,5	5	170	260
ISO 185/JL/HBW195	40	80	120	195
	20	40	135	210
	10	20	150	230
	5	10	170	260
ISO 185/JL/HBW215	40	80	145	215
	20	40	160	235
	10	20	180	255
	5	10	200	275
ISO 185/JL/HBW235	40	80	165	235
	20	40	180	255
	10	20	200	275
ISO 185/JL/HBW255	40	80	185	255
	20	40	200	275

For each grade, the figure in bold indicates the minimum and maximum Brinell hardness to which the material designation of the grade relates and the corresponding relevant wall thickness range limits.

Information on the relationship between Brinell hardness and tensile strength is given in [Annex B](#).

Information on the relationship between tensile strength, Brinell hardness and wall thickness is given in [Annex C](#).

By agreement between the manufacturer and the purchaser, a narrower Brinell hardness range, not less than 40 HBW, may be adopted at the agreed position on the casting. An example of such a circumstance is castings for long-series production.

For each grade, Brinell hardness decreases with increasing wall thickness.

7.4 Graphite structure

If the graphite structure is agreed upon, the test shall be carried out in accordance with 9.3.

8 Sampling

8.1 General

Samples shall be supplied in order to characterize the grade of the material.