
**Test methods for machine readable
travel documents (MRTD) and
associated devices —**

**Part 1:
Physical test methods for passport
books (durability)**

iTeh STANDARD PREVIEW

(standards.iteh.ai)
*Méthodes d'essais pour documents de voyage lisibles par machine et
dispositifs associés —*

*Partie 1: Méthodes d'essais physiques pour livrets de passeport
(durabilité)*

<https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debacec6eaa/iso-iec-18745-1-2018>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/IEC 18745-1:2018](https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debacec6eaa/iso-iec-18745-1-2018)

<https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debacec6eaa/iso-iec-18745-1-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO/IEC 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	vii
Introduction	viii
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Abbreviated terms	3
5 Methodology	3
6 Guidance to the tester	5
6.1 Number of samples	5
6.2 Preparation	5
6.3 Sampling	6
6.4 Storage	6
7 Common method information	6
7.1 Default environment	6
7.2 Climatic conditions	6
7.3 Tolerances	6
7.4 Default MRP holder	6
8 Stress methods	7
8.1 Conditioning stress method	7
8.1.1 General	7
8.1.2 Input Parameters	7
8.1.3 Apparatus	7
8.1.4 Method	7
8.2 Thermal cycling stress method	8
8.2.1 General	8
8.2.2 Input parameters	8
8.2.3 Apparatus	8
8.2.4 Method	8
8.3 Storage temperature stress method	9
8.3.1 General	9
8.3.2 Input parameters	9
8.3.3 Apparatus	9
8.3.4 Method	9
8.4 Operational climate stress method	9
8.4.1 General	9
8.4.2 Input Parameters	9
8.4.3 Apparatus	9
8.4.4 Method	9
8.5 Impact stress method	10
8.5.1 General	10
8.5.2 Input parameters	10
8.5.3 Output parameters	10
8.5.4 Apparatus	10
8.5.5 Method	12
8.5.6 Alternate method	13
8.6 Book bend stress method (back pocket)	13
8.6.1 General	13
8.6.2 Input parameters	13
8.6.3 Output parameters	13
8.6.4 Apparatus	13
8.6.5 Method	14

8.7	Dynamic bend stress method.....	15
8.7.1	General.....	15
8.7.2	Input parameters.....	15
8.7.3	Output parameters.....	15
8.7.4	Apparatus.....	15
8.7.5	Calibration of movement method.....	16
8.7.6	Method.....	17
8.8	Torsion stress method.....	18
8.8.1	General.....	18
8.8.2	Input parameters.....	18
8.8.3	Output parameters.....	18
8.8.4	Apparatus.....	18
8.8.5	Calibration.....	19
8.8.6	Method.....	19
8.9	Sheet turning stress method.....	19
8.9.1	General.....	19
8.9.2	Input parameters.....	19
8.9.3	Output parameters.....	19
8.9.4	Apparatus.....	19
8.9.5	Method.....	20
8.9.6	Bending parameters.....	21
8.10	Sheet pull stress method.....	21
8.10.1	General.....	21
8.10.2	Input parameters.....	21
8.10.3	Output parameters.....	21
8.10.4	Apparatus.....	21
8.10.5	Method.....	21
8.11	Abrasion stress method.....	22
8.11.1	General.....	22
8.11.2	Input parameters.....	22
8.11.3	Output parameters.....	22
8.11.4	Apparatus.....	22
8.11.5	Method.....	23
8.12	Pen stress method.....	23
8.12.1	General.....	23
8.12.2	Input parameters.....	23
8.12.3	Output parameters.....	23
8.12.4	Apparatus.....	23
8.12.5	Method.....	23
8.13	Resistance to chemicals stress method.....	24
8.13.1	General.....	24
8.13.2	Input parameters.....	25
8.13.3	Output parameters.....	25
8.13.4	Apparatus.....	25
8.13.5	Short term contamination test.....	25
8.13.6	Long term contamination test.....	26
8.14	Artificial daylight exposure stress method.....	26
8.14.1	General.....	26
8.14.2	Input parameters.....	27
8.14.3	Output parameters.....	27
8.14.4	Apparatus.....	27
8.14.5	Method.....	27
8.15	X-ray stress method.....	27
8.15.1	General.....	27
8.15.2	Input parameter.....	27
8.15.3	Output parameter.....	27
8.15.4	Apparatus.....	28
8.15.5	Method.....	28

iTech STANDARD PREVIEW
(standards.iteh.ai)

9	Evaluation methods	28
9.1	Functional PIC evaluation method	28
9.1.1	General	28
9.1.2	Input parameters	28
9.1.3	Output parameters	28
9.1.4	Apparatus	28
9.1.5	Method	28
9.2	Physical damage evaluation method	28
9.2.1	General	28
9.2.2	Input parameters	29
9.2.3	Output parameters	29
9.2.4	Apparatus	29
9.2.5	Method	29
9.3	Peel strength evaluation method	29
9.3.1	General	29
9.3.2	Input parameters	29
9.3.3	Output parameters	30
9.3.4	Apparatus	30
9.3.5	Method	30
9.4	Colour fastness evaluation method	30
9.4.1	General	30
9.4.2	Input parameters	30
9.4.3	Output parameters	31
9.4.4	Apparatus	31
9.4.5	Method	31
9.5	Datapage and cover warpage evaluation method	31
9.5.1	General	31
9.5.2	Input parameters	31
9.5.3	Output parameters	31
9.5.4	Apparatus	31
9.5.5	Method	31
9.6	Book warpage evaluation method	33
9.6.1	General	33
9.6.2	Input parameters	33
9.6.3	Output parameters	34
9.6.4	Apparatus	34
9.6.5	Method	34
10	Test sequences	35
10.1	General	35
10.2	Instructions for using the sequence table	35
10.3	Sheet binding sequence	35
10.3.1	General	35
10.3.2	Input parameters	35
10.3.3	Output parameters	35
10.3.4	Sequence	36
10.4	Storage climate sequence	36
10.4.1	General	36
10.4.2	Input parameters	36
10.4.3	Output parameters	36
10.4.4	Sequence	36
10.5	Operational climate sequence	36
10.5.1	General	36
10.5.2	Input parameters	37
10.5.3	Output parameters	37
10.5.4	Sequence	37
10.6	Impact sequence	37
10.6.1	General	37
10.6.2	Input parameters	37

10.6.3	Output parameters	37
10.6.4	Sequence	37
10.7	Back pocket sequence	38
10.7.1	General	38
10.7.2	Input parameters	38
10.7.3	Output parameters	38
10.7.4	Sequence	38
10.8	Torsion fatigue sequence	38
10.8.1	General	38
10.8.2	Input parameters	38
10.8.3	Output parameters	38
10.8.4	Sequence	39
10.9	Delamination sequence	39
10.9.1	General	39
10.9.2	Input parameters	39
10.9.3	Output parameters	39
10.9.4	Sequence	39
10.10	Bending fatigue sequence	39
10.10.1	General	39
10.10.2	Input parameters	39
10.10.3	Output parameters	40
10.10.4	Sequence	40
10.11	Thermal cycling sequence	40
10.11.1	General	40
10.11.2	Input parameters	40
10.11.3	Output parameters	40
10.11.4	Sequence	40
10.12	Colour fastness sequence	41
10.12.1	General	41
10.12.2	Input parameters	41
10.12.3	Output parameters	41
10.12.4	Sequence	41
10.13	Resistance to chemicals sequence	41
10.13.1	General	41
10.13.2	Input parameters	41
10.13.3	Output parameters	42
10.13.4	Sequence	42
10.14	Pen sequence	42
10.14.1	General	42
10.14.2	Input parameters	42
10.14.3	Output parameters	42
10.14.4	Sequence	42
10.15	Datapage abrasion sequence	42
10.15.1	General	42
10.15.2	Input parameters	43
10.15.3	Output parameters	43
10.15.4	Sequence	43
10.16	X-ray sequence	43
10.16.1	General	43
10.16.2	Input parameters	43
10.16.3	Output parameters	43
10.16.4	Sequence	43
11	Test plans	43
11.1	General	43
11.2	Minimum level test plan	44
	Bibliography	45

iTech STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2ebacce6caa/iso-iec-18745-1-2018>

Foreword

ISO (the International Organization for Standardization) and IEC (the International Electrotechnical Commission) form the specialized system for worldwide standardization. National bodies that are members of ISO or IEC participate in the development of International Standards through technical committees established by the respective organization to deal with particular fields of technical activity. ISO and IEC technical committees collaborate in fields of mutual interest. Other international organizations, governmental and non-governmental, in liaison with ISO and IEC, also take part in the work. In the field of information technology, ISO and IEC have established a joint technical committee, ISO/IEC JTC 1.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO and IEC shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/IEC JTC 1, *Information technology*, Subcommittee SC 17, *Cards and security devices for personal identification*.

This second edition cancels and replaces the first edition (ISO/IEC 18745-1:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- test definitions have been detailed;
- instructions to evaluate test results have been clarified;
- the definition of the foam to be used in 8.6.4 book bend stress method has been changed to enhance the accessibility to the foam needed;
- test sequences have been updated to create more realistic test results;
- references have been updated.

A list of all the parts in the ISO/IEC 18745 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

0.1 General

ICAO Doc 9303 provides the basic functional specification for Machine Readable Travel Documents (MRTDs) and, together with the Supplement, which is published from time to time, describes all relevant properties of MRTDs. Machine Readable Passports (MRPs) are a subset of all MRTDs. The publication of Part 1 of the 6th edition of Doc 9303 introduces the contactless integrated circuit to the MRP. Such a passport containing a contactless integrated circuit is commonly referred to as an e-Passport.

This document provides a set of instructions for the evaluation of MRPs which may incorporate contactless integrated circuits. This document is a companion to ICAO Doc 9303. It specifies the minimum criteria to be achieved in order to meet ICAO's expectations for durability of fully personalized MRPs. Therefore, by its existence, and endorsement by ICAO, this document implicitly defines additional requirements for passports above and beyond ICAO Doc 9303. Some of the tests described herein are also intended to serve as an instrument for the assessment of the ageing behaviour of the MRP and its components.

This document updates and replaces the document "ICAO Technical Report – Durability Of Machine Readable Passports" published by ICAO (International Civil Aviation Organization).

0.2 Future considerations

Where technologies or combinations of technologies are to be applied in an MRP, which are not covered by the test methods described below, it is recommended to define such test methods based on available methods described in ISO/IEC standards or any other accepted standards from other international standard organizations in cooperation with the suppliers of such technologies.

Today, there is no stable state of the art regarding the correlation between stress and ageing, neither for previously existing nor for oncoming types of MRPs. The tests that can be described at the present stage may contribute to improving such knowledge but need to be considered preliminary. It is important to notice that ultimately, reliable and predictably useful correlations can only be achieved by continuously comparing the ageing behaviour of documents in real use to the predictions made. Such predictions are based on assumptions that, in particular if novel and unusual technologies and components are used, they are in many cases unproven and preliminary in nature.

It is one of the aims of this document to help in the task of establishing sound correlations. This is done by providing tools for executing tests with comparable results for a multitude of acting parties. Comparable results are a prerequisite to encourage the execution of field surveys in quality related research and their use for a continuous improvement not only of this document but also of the quality of MRPs on a global basis.

0.3 Other uses for this document

The tests defined in this document may also be appropriate for other forms of MRTDs, however, they may require modification before use.

Where applicable, tests may be used to evaluate characteristics of non-personalized MRPs or materials used to make MRPs.

Type evaluation is usually a one-time exercise in the life cycle of a specific type of document. However the same test procedures may be useful for the proper definition of quality assurance procedures during the regular production of MRTDs. In the framework of the contractual relationship between a manufacturer and its customer(s) it is common practice to establish an expected quality level for the MRTDs in the delivery contract, and also to specify acceptance criteria for individual deliveries in executing the contract. On the other hand, it is good practice to leave it with the manufacturer to decide on the production quality measures to assure this quality level.

This document has been carefully designed to provide the user with a set of tools for evaluating MRPs, whether it be prototype evaluation, delivery acceptance or any other purpose.

Test methods for machine readable travel documents (MRTD) and associated devices —

Part 1: Physical test methods for passport books (durability)

1 Scope

This document provides a set of instructions for evaluation of MRPs which may incorporate contactless integrated circuits. This evaluation is an instrument to establish the ability in principle of a specific type of document to fulfil the requirements of use. It supplies a structured approach to evaluate MRPs by:

- defining reproducible stress methods to submit the document(s) under evaluation to specific stress or environmental conditions;
- defining reproducible evaluation methods to measure numerical values for specific document properties;
- defining test sequences that specify the order in which stress methods and evaluation methods are to be performed;
- defining test plans to link specific user requirements to test sequences and related parameters.

It specifies the minimum criteria to be achieved in order to meet ICAO's expectations for durability of fully personalized MRPs.

<https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debacec6eaa/iso-iec-18745-1-2018>

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-A02, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour*

ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test*

ISO 105-E04, *Textiles — Tests for colour fastness — Part E04: Colour fastness to perspiration*

ISO 2439:2008, *Flexible cellular polymeric materials — Determination of hardness (indentation technique)*

ISO/IEC 7810, *Identification cards — Physical characteristics*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO/IEC 10373-1:2006, *Identification cards — Test methods — Part 1: General characteristics*

ISO 12757-2, *Ball point pens and refills — Part 2: Documentary use (DOC)*

ISO/IEC 18745-2:2016, *Information technology — Test methods for machine readable travel documents (MRTD) and associated devices — Part 2: Test methods for the contactless interface*

ASTM E 832-81(Reapproved 2003), *Standard Specification for Laboratory Filter Papers*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1 chip sheet

sheet containing a chip

3.2 constant

fixed values that can be given to parameters (within methods) when defining a sequence or test plan

3.3 evaluation method

method to measure numerical values for specific document properties

3.4 evaluation result

all numerical values related to document properties measured upon performing a test sequence

3.5 method

instruction or set of instructions defining equipment and related tools and materials in an experimental setup, including general advice on their use in a specific test procedure

3.6 page

any single side of an individual sheet of the MRP

iTeh STANDARD PREVIEW

(standards.iteh.ai)

ISO/IEC 18745-1:2018

[https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-](https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debace66eaa/iso-iec-18745-1-2018)

[2debace66eaa/iso-iec-18745-1-2018](https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debace66eaa/iso-iec-18745-1-2018)

3.7 parameter

variable quantity within a test procedure that is not part of the instructions describing the procedure; in particular, experimental parameters that need to be controlled during the test sequence but whose values and/or tolerances are not explicitly defined in a specific stress or evaluation method or sequence

3.8 sheet

any structure having a free edge and an opposite edge attached to the spine making up the MRP including covers, datapage, visa pages, observation pages and chip sheet

Note 1 to entry: Each sheet has two pages.

3.9 stress method

experimental setup and procedure that may or may not deteriorate or destroy the document under examination

3.10 test instruction

distinct piece of information required within the framework of test execution

3.11 test plan

list of test sequences and their specific test parameters and expected evaluation results

3.12**test procedure**

set of instructions to be followed in order to obtain a test result

3.13**test sequence**

test procedure that comprises a number of different methods in a defined order of execution

3.14**type evaluation****type approval**

process of testing a design (type of documents produced while using a common material and component basis and the same manufacturing processes, including same production quality assurance process) to ensure it is compliant-in-principle with the specifications

4 Abbreviated terms

IC Integrated Circuit

ICAO International Civil Aviation Organization

MRP Machine Readable Passport

MRTD Machine Readable Travel Document

MRZ machine-readable zone

NSS Neutral Salt Spray

PCD Proximity Coupling Device [ISO/IEC 18745-1:2018](https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-1c4d41ec6eaa/iso-iec-18745-1-2018)

PIC Proximity Integrated Circuit <https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-1c4d41ec6eaa/iso-iec-18745-1-2018>

NOTE ICAO 9303 uses CIC (contactless integrated circuit) and PIC interchangeably.

RH relative humidity

VIZ Visual Inspection Zone

5 Methodology

The systemic approach used in this document provides three structural levels to define a complete test specification for MRPs.

The first level deals with methods to exert defined stresses to documents and to evaluate the results of such stresses. The second level deals with predefined sequences of stresses and related evaluations using the methods defined in level 1. The third level specifies the lists of test sequences and the individual quantities of test specimens to be subject to each sequence. The purpose is to include in such lists all sequences that are considered necessary to achieve type approval for a specific type of MRP with specific lifetime and usage expectations. This is referred to as a test plan.

This approach provides flexibility in creating individual test plans appropriate for varying user requirements and MRP specifications without increasing the variety of basic testing methods beyond a strict minimum. It also allows the use of a parameterized method description; parameters, which may be explicitly specified on the sequence and/or test, plan level.

In this way this document provides the entire toolset for prototype evaluation of MRPs.

Table 1 — Hierarchical approach for test methodology

Level	Subject	Description	Degree of variance	Clause
1	Stress methods	The purpose is to submit the document(s) under evaluation to specific stress or environmental conditions in a well-defined experimental setup that ensures reproducibility.	Parameters	Clause 8
1	Evaluation methods	The purpose is to measure numerical values for specific document properties using well-defined and reproducible experimental setups that may or may not deteriorate or destroy the document under examination.	Parameters	Clause 9
2	Test sequences	Sequence of use of the above methods in performing a complete test.	Constants and Parameters	Clause 10
3	Test plans	Scenarios which link the user requirements to specific test sequences and related parameters used for the tests on the one hand and to specific test results on the other.	Constants	Clause 11

Each sequence is composed of stress methods and evaluation methods executed in a specific order. A test plan is composed of one or more individual sequence(s) that is linked to a specific set of documents and user requirements. See [Figure 1](#).

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/IEC 18745-1:2018
<https://standards.iteh.ai/catalog/standards/sist/65a81b96-9726-4b79-a161-2debacc6eaa/iso-iec-18745-1-2018>




Figure 1 — Relationship between methods, sequences and test plans

6 Guidance to the tester

6.1 Number of samples

References are given to a single MRP. However, multiple MRP samples may be tested simultaneously depending on the size and construction of the test apparatus.

6.2 Preparation

Test samples shall be either finished MRPs or be prepared from finished MRPs having passed the entire production process including visual personalization with a dataset considered typical for the specific type of passport. Initialisation and personalization of the chip may be done in an arbitrary way as long as the chip is able to support the necessary tests within the intended test sequence.

MRPs shall be conditioned in accordance with 7.1.

Test pieces shall, as necessary, be prepared from the test samples in the particular form required by the test apparatus used.

6.3 Sampling

For testing samples may be taken from the base material before MRP manufacture if it can be demonstrated that no significant change in the property to be tested can arise during subsequent processing. The samples used to prepare a set of test pieces shall be taken from the same batch of MRP base materials.

6.4 Storage

Any test samples or test pieces retained for reference shall be stored under the environmental conditions specified in [7.1](#).

All such samples shall be clearly cross-referenced to the test report and any relevant supplementary documentation.

7 Common method information

7.1 Default environment

Unless otherwise specified, testing shall take place in an environment having a default temperature of $23\text{ °C} \pm 3\text{ °C}$ and 40 % RH to 60 % RH.

7.2 Climatic conditions

Climatic conditions defined in the test methods are the conditions within the chamber. The resulting temperature in the MRP is not specified or defined in the methods.

7.3 Tolerances

Unless otherwise specified, a tolerance of $\pm 5\%$ shall be applied to the quantity values given in this document.

7.4 Default MRP holder

A structure for holding the MRP while maximizing air space around the MRP during testing shall have the general construction as shown in [Figure 2](#). There are no size or quantity limitations for the holder rack, any number of MRP positions may be used. For the wire and the square rod use a non-corrosive material.




Figure 2 — MRP rack

8 Stress methods

Stress methods are designed to apply reproducible stresses to the travel document. Methods that describe how to measure the effect of these stresses are given in [Clause 9](#).

The fundamental philosophy behind all stress methods is to define conditions that mimic real daily use (as much as possible). In cases where the correlation between real life and the stress method is tenuous, every attempt has been made to define conditions that produce similar rates of deterioration.

8.1 Conditioning stress method

8.1.1 General

The MRPs to be tested shall be conditioned to the test environment as described below.

8.1.2 Input Parameters

t = time of conditioning. If t is not specified, assume 24 h.

8.1.3 Apparatus

8.1.3.1 Default MRP holder.

8.1.4 Method

- Remove MRP from any box and protective packaging.
- Place MRP in default MRP holder with spine up. MRP shall not be forced open but may open on its own. Minimum spacing between MRP and any other MRP shall be 10 mm in all directions.
- Expose MRP to a temperature of $23\text{ °C} \pm 3\text{ °C}$ and 40 % RH to 60 % RH for at least time t .