

---

**Specifikacije za posebne vrste navijalnih žic - 35. del: S poliuretanom emajlirana okrogla bakrena žica, za spajkanje, razred 155, s spajalno plastjo - Dopolnilo A1 (IEC 60317-35:2013/A1:2019)**

Specifications for particular types of winding wires - Part 35: Solderable polyurethane enamelled round copper wire, class 155, with a bonding layer (IEC 60317-35:2013/A1:2019)

Technische Lieferbedingungen für bestimmte Typen von Wickeldrähten - Teil 35: Runddrähte aus Kupfer, verzinnbar und verbackbar, lackisoliert mit Polyurethan, Klasse 155 (IEC 60317-35:2013/A1:2019)

[SIST EN 60317-35:2014/A1:2019](https://standards.itech.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019)

Spécifications pour types particuliers de fils de bobinage - Partie 35: Fil brasable de section circulaire en cuivre émaillé avec polyuréthane, classe 155, avec une couche adhérente (IEC 60317-35:2013/A1:2019)

**Ta slovenski standard je istoveten z: EN 60317-35:2014/A1:2019**

---

**ICS:**

29.060.10	Žice	Wires
77.150.30	Bakreni izdelki	Copper products

**SIST EN 60317-35:2014/A1:2019** en

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 60317-35:2014/A1:2019](https://standards.iteh.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019)

<https://standards.iteh.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019>

EUROPEAN STANDARD

**EN 60317-35:2014/A1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2019

ICS 29.060.10

English Version

Specifications for particular types of winding wires - Part 35:  
Solderable polyurethane enamelled round copper wire, class  
155, with a bonding layer  
(IEC 60317-35:2013/A1:2019)

Spécifications pour types particuliers de fils de bobinage -  
Partie 35: Fil brasable de section circulaire en cuivre  
émaillé avec polyuréthane, classe 155, avec une couche  
adhérente  
(IEC 60317-35:2013/A1:2019)

Technische Lieferbedingungen für bestimmte Typen von  
Wickeldrähten - Teil 35: Runddrähte aus Kupfer, verzinnbar  
und verbackbar, lackisoliert mit Polyurethan, Klasse 155  
(IEC 60317-35:2013/A1:2019)

This amendment A1 modifies the European Standard EN 60317-35:2014; it was approved by CENELEC on 2019-07-17. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this amendment the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This amendment exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN 60317-35:2014/A1:2019 (E)****European foreword**

The text of document 55/1691/CDV, future IEC 60317-35/A1, prepared by IEC/TC 55 "Winding wires" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60317-35:2014/A1:2019.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2020-04-17
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2022-07-17

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

**Endorsement notice**  
**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

The text of the International Standard IEC 60317-35:2013/A1:2019 was approved by CENELEC as a European Standard without any modification.

[SIST EN 60317-35:2014/A1:2019](https://standards.iteh.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019)  
<https://standards.iteh.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019>



IEC 60317-35

Edition 2.0 2019-06

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

AMENDMENT 1  
AMENDEMENT 1

**Specifications for particular types of winding wires –  
Part 35: Solderable polyurethane enamelled round copper wire, class 155, with a  
bonding layer**

**Spécifications pour types particuliers de fils de bobinage –  
Partie 35: Fil brasable de section circulaire en cuivre émaillé avec polyuréthane,  
classe 155, avec une couche adhérente**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 29.060.10

ISBN 978-2-8322-6964-0

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## FOREWORD

This amendment to International Standard IEC 60317-35 has been prepared by IEC technical committee 55: Winding wires.

The text of this amendment is based on the following documents:

CDV	Report on voting
55/1691/CDV	55/1741/RVC

Full information on the voting for the approval of this amendment can be found in the report on voting indicated in the above table.

The committee has decided that the contents of this amendment and the base publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 60317-35:2014/A1:2019](https://standards.iteh.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019)

<https://standards.iteh.ai/catalog/standards/sist/a7a611ff-9776-4b7c-be15-d34b78310f5d/sist-en-60317-35-2014-a1-2019>

## 17 Solderability

*Replace the content of this clause by the following:*

### 17.1 General

The temperature of the solder bath shall be  $(390 \pm 5)$  °C. The surface of the tinned wire shall be smooth and free from holes and enamel residues.

### 17.2 Nominal conductor diameters up to and including 0,100 mm

The maximum immersion time shall be 2 s.

### 17.3 Nominal conductor diameters over 0,100 mm

The maximum immersion time (in seconds) shall be the following multiple of the nominal conductor diameter (in millimetres) with a minimum of 2 s.

Grade 1B	Grade 2B
12 s/mm	16 s/mm