





# INTERNATIONAL STANDARD

# ISO 29863

Second edition  
2018-05

---

---

## Self adhesive tapes — Measurement of static shear adhesion

*Rubans auto-adhésifs — Mesurage de la résistance au cisaillement  
statique*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 29863:2019

<https://standards.iteh.ai/catalog/standards/sist/e22be015-6782-4f72-bd16-2ab4dc815bbf/sist-en-iso-29863-2019>



Reference number  
ISO 29863:2018(E)

© ISO 2018

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 29863:2019

<https://standards.iteh.ai/catalog/standards/sist/e22be015-6782-4f72-bd16-2ab4dc815bbf/sist-en-iso-29863-2019>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	v
Introduction.....	vi
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Significance and use.....</b>	<b>2</b>
<b>5 Method A: Measurement of shear adhesion to a vertical standard steel panel.....</b>	<b>2</b>
5.1 Principle.....	2
5.2 Materials.....	2
5.3 Apparatus.....	3
5.3.1 Typical shear adhesion tester.....	3
5.3.2 Test piece cutter.....	3
5.3.3 Stainless steel panels.....	3
5.3.4 Roller mechanically or hand operated.....	3
5.4 Test samples and test piece.....	4
5.5 Procedure.....	4
5.5.1 Standard test conditions.....	4
5.5.2 Preparation of the panel.....	4
5.5.3 Shear adhesion.....	4
5.6 Expression of results.....	5
5.7 Test report.....	5
<b>6 Method B: Measurement of shear adhesion to a vertical panel covered with NIST SRM 1810A standard fibreboard.....</b>	<b>6</b>
6.1 Principle.....	6
6.2 Materials.....	6
6.3 Apparatus.....	6
6.3.1 Test piece cutter.....	6
6.3.2 Suitable panels.....	6
6.3.3 Roller mechanically or hand operated.....	6
6.3.4 Test stands and ancillary apparatus.....	6
6.4 Test samples and test piece.....	6
6.5 Procedure.....	6
6.5.1 Standard test conditions.....	6
6.5.2 Preparation of the panel.....	6
6.5.3 Shear adhesion.....	7
6.6 Expression of results.....	7
6.7 Test report.....	7
<b>7 Method C: Measurement of shear adhesion to a vertical panel covered with a fibreboard agreed upon by the buyer and the seller.....</b>	<b>7</b>
7.1 Principle.....	7
7.2 Procedure.....	7
<b>8 Method D: Measurement of shear adhesion of filament reinforced tape applied to a horizontal standard steel panel.....</b>	<b>7</b>
8.1 Principle.....	7
8.2 Materials.....	7
8.3 Apparatus.....	8
8.3.1 Test piece cutter.....	8
8.3.2 Stainless steel panels.....	8
8.3.3 Roller mechanically or hand operated.....	8
8.3.4 Test stands and ancillary apparatus.....	8
8.4 Test samples and test piece.....	8

## ISO 29863:2018(E)

8.5	Procedure.....	8
8.5.1	Standard test conditions.....	8
8.5.2	Preparation of the panel.....	8
8.5.3	Shear adhesion.....	8
8.6	Expression of results.....	9
8.7	Test report.....	9
<b>9</b>	<b>Method E: Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with NIST SRM 1810A standard fibreboard.....</b>	<b>10</b>
9.1	Principle.....	10
9.2	Procedure.....	10
<b>10</b>	<b>Method F: Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with a fibreboard agreed upon by the buyer and the seller.....</b>	<b>10</b>
10.1	Principle.....	10
10.2	Procedure.....	10
<b>11</b>	<b>Method G: Measurement of shear adhesion to a vertical standard steel panel at an elevated temperature after 10 min dwell time.....</b>	<b>10</b>
11.1	Principle.....	10
11.2	Procedure.....	11
	<b>Bibliography.....</b>	<b>14</b>

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 29863:2019

<https://standards.iteh.ai/catalog/standards/sist/e22be015-6782-4f72-bd16-2ab4dc815bbf/sist-en-iso-29863-2019>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition cancels and replaces the first edition (ISO 29863:2007) of which it constitutes a minor revision.

The changes compared to the previous edition are as follows:

- the Introduction has been revised to remove outdated information;
- the normative references in [Clause 2](#) have been updated;
- the definition of “shear adhesion” has been revised and a definition has been added for “self adhesive tape” in [Clause 3](#);
- a Bibliography has been added;
- the text has been editorially revised to comply with the most recent editing rules.

ISO 29863:2018(E)

## Introduction

This document has been prepared in conjunction with AFERA (International Association for the Self Adhesive Tape Industry) in Europe and PSTC (Pressure Sensitive Tape Council) in USA.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 29863:2019

<https://standards.iteh.ai/catalog/standards/sist/e22be015-6782-4f72-bd16-2ab4dc815bbf/sist-en-iso-29863-2019>



# Self adhesive tapes — Measurement of static shear adhesion

## 1 Scope

This document specifies a series of methods for the determination of the ability of a pressure sensitive tape to remain adhered under a constant load applied parallel to the surfaces of the tape and substrate.

This document contains:

- method A: Self adhesive tapes – Measurement of shear adhesion to a vertical standard steel panel;
- method B: Self adhesive tapes – Measurement of shear adhesion to a vertical panel covered with NIST SRM 1810A<sup>1)</sup> standard fibreboard;
- method C: Self adhesive tapes – Measurement of shear adhesion to a vertical panel covered with a fibreboard agreed upon by the buyer and seller;
- method D: Self adhesive tapes – Measurement of shear adhesion of filament reinforced tape applied to a horizontal standard steel panel;
- method E: Self adhesive tapes – Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with NIST SRM 1810A<sup>1)</sup> standard fibreboard;
- method F: Self adhesive tapes – Measurement of shear adhesion of filament reinforced tape applied to a horizontal panel covered with a fibreboard agreed upon by the buyer and seller;
- method G: Self adhesive tapes – Measurement of shear adhesion to a vertical standard steel panel at elevated temperature after a 10 min dwell time.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12481, *Self adhesive tapes — Terminology*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12481 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

1) NIST SRM 1810A is National Institute of Standards and Technology – Standard Reference Material 1810A and is available from the Institute at Gaithersburg, Maryland MD 20899, USA.

## ISO 29863:2018(E)

**3.1 shear adhesion**  
resistance of the pressure sensitive adhesive against shear when static forces are exerted parallel to the bonding surface

Note 1 to entry: It is expressed as the time to failure under constant load.

**3.2 self adhesive tape**  
pressure sensitive adhesive adhesive which in a dry state is permanently tacky at room temperature and adheres readily to surfaces under brief and light pressure

## 4 Significance and use

These test methods are tools for quality control use. Given specific self adhesive tape and a requirement in terms of the minimum or maximum value expected for this tape, the data from the test can be used in conjunction with acceptance criteria.

These methods provide a means of assessing the uniformity of the adhesive of a given type of pressure-sensitive tape (an example are tapes used for packaging applications). The assessment may be within a roll of tape, between rolls or production lots.

Variations in the tape backing and adhesive affect the results, therefore, these methods cannot be used to pinpoint the specific cause(s) of non-uniformity.

These test methods may not provide design information as there is usually no direct relationship between shear adhesion and any functional requirement.

## 5 Method A: Measurement of shear adhesion to a vertical standard steel panel

### 5.1 Principle

Method A measures the shear adhesion of a self adhesive tape to a standard steel panel by its time to failure at 23 °C and 50 % relative humidity (RH) under constant load.

Shear adhesion to standard steel panel – A strip of tape is applied to a standard steel panel under controlled roll down. The panel is mounted vertically, a standard mass is attached to the free end of the tape and the time to failure is determined.

### 5.2 Materials

**5.2.1 Absorbent cleaning material**, surgical gauze, cotton wool or tissue. To be suitable, materials shall be lint free during use, absorbent, contain no additives that are soluble in the solvents listed in [5.2.2](#) and made exclusively from virgin materials.

#### 5.2.2 One or more of the following solvents:

- diacetone alcohol (4-hydroxy-4-methyl-2-pentanone) non-residual grade;
- methanol;
- methyl ethyl ketone;
- acetone;
- *n*-heptane;

- a mixture of *n*-heptane and a fluorinated hydrocarbon such as refrigerant (suitable when toxicity or flammability restrictions apply).

Solvents shall be of general purpose chemical grade and held in a suitable dispensing system.

## 5.3 Apparatus

### 5.3.1 Typical shear adhesion tester

See [Figure 1](#) for a typical shear adhesion tester.

### 5.3.2 Test piece cutter

A test piece cutter shall hold two single edge razor blades in parallel planes a precise distance apart, to form a cutter of exact specimen width; two cutters, 12 mm and 24 mm cutting width, shall be available or appropriate alternatives which will not cause edge damage. The precision of the razor blade separation shall be the nominal width  $\pm 0,1$  mm.

### 5.3.3 Stainless steel panels

These shall be perfectly flat, at least 125 mm long and 50 mm wide and at least 1,1 mm thick, stainless steel type 1.4301 in accordance with the 2 R quality defined in EN 10088-2, having a bright annealed finish with a surface roughness of  $50 \text{ nm} \pm 25 \text{ nm}$ . Panels showing stains, discoloration or many scratches are not acceptable. New panels shall be cleaned prior to use as described in [5.5.2](#) except with ten washes of the final solvent. Between uses the panel test surface shall be protected from scratches and contamination and the panels shall be stored in the conditions described in [5.5.2](#).

### 5.3.4 Roller mechanically or hand operated

**5.3.4.1** A steel roller  $85 \text{ mm} \pm 2,5 \text{ mm}$  in diameter and  $45 \text{ mm} \pm 1,5 \text{ mm}$  in width, covered with rubber approximately 6 mm in thickness, having a Shore A durometer hardness of  $80 \pm 5$ . The surface shall be a true cylinder, void of any convex or concave deviations. The mass of the roller shall be  $2 \text{ kg} \pm 0,1 \text{ kg}$ .

**5.3.4.2** No part of the apparatus shall increase the mass of the roller during use. The roller shall move either mechanically or by hand at the rate of  $10 \text{ mm/s} \pm 0,5 \text{ mm/s}$ .

### 5.3.5 Test stands and ancillary apparatus

#### 5.3.5.1 Test stand

A test stand that shall hold the test panel, with tape applied, at an angle between  $0^\circ$  and  $2^\circ$  from the vertical, so that when the mass is acting on the test specimen, no peel force will be exerted on the tape.

#### 5.3.5.2 Clamps

Clamps that will allow the attachment of the mass to the specimen, distributing the load equally across the tape specimen width.

#### 5.3.5.3 Test masses

The test mass shall be  $1\,000 \text{ g} \pm 5 \text{ g}$  or other mass as specified. The mass of the clamp described in [5.3.5.2](#) shall be included as part of the total mass.