

# DRAFT AMENDMENT ISO 7206-2:2011/DAM 1

ISO/TC 150/SC 4

Secretariat: BSI

Voting begins on:  
2016-02-03

Voting terminates on:  
2016-05-03

---

---

## Implants for surgery — Partial and total hip joint prostheses —

Part 2:

## Articulating surfaces made of metallic, ceramic and plastics materials

### AMENDMENT 1

*Implants chirurgicaux — Prothèses partielles et totales de l'articulation de la hanche —*

*Partie 2: Surfaces articulaires constituées de matériaux métalliques, céramiques et plastiques*

AMENDEMENT 1

ICS: 11.040.40

**ITeH STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/00e54c2-4dd4-4c16-bc75-a7f124add082/iso-7206-2-2011-dam-1-2016>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



Reference number  
ISO 7206-2:2011/DAM 1:2015(E)

© ISO 2015

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/c00e54c2-4dd4-4c16-bc75-a7f124add082/iso-7206-2-2011-amd-1-2016>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 7206-2:2011 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 4, *Bone and joint replacements*.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/c00e2262-4dd4-4c16-bc75-a7f124add082/iso-7206-2-2011-amd-1>  
2016

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/c00e54c2-4dd4-4c16-bc75-a7f124add082/iso-7206-2-2011-amd-1-2016>

# Implants for surgery — Partial and total hip joint prostheses —

## Part 2: Articulating surfaces made of metallic, ceramic and plastics materials

### AMENDMENT 1

#### Changes to Forward

Remove the following standard, once it was withdraw→

☒ *Part 8: Endurance performance of stemmed femoral components with application of torsion*

#### Changes to clause 4.1.1: General

*This subclause refers to spherical articulating surfaces of femoral components of total hip joint prostheses in accordance with classification c) of ISO 7206-1. → add to the existing text the following sentence (text in green):*

The principles for the surface finish measurements of hip joint prostheses components are given in ISO 4287. Surface finish measurements shall be performed according to the rules and procedures described in ISO 4288:1996

#### Changes to clause 4.1.3: Surface finish

☒ *Amend to read*

The spherical articulating surfaces of metallic and ceramic components shall have  $R_{max}$  values not greater than  $0,05 \mu\text{m}$  and  $0,02 \mu\text{m}$  respectively. Table 1 of ISO 4288:1996 requires using a cut-off value of  $0,25 \text{ mm}$  for the  $0,05 \mu\text{m}$  requirement and requires using a cut-off value of  $0,08 \text{ mm}$  for the  $0,02 \mu\text{m}$  requirement. The  $R_{tmax}$  value shall not be greater than  $1,0 \mu\text{m}$ . The cut-off value used to determine the  $R_t$  value shall be in accordance with table 2 of ISO 4288:1996.

The measurements shall be taken at five locations on the spherical surface. One measurement shall be taken in each of four quadrants approximately  $30^\circ$  from the spherical pole and one at the spherical pole. The following details shall be reported along with the  $R_{max}$  value:

- a) stylus tip radius;
- b) position of measurement on specimen;
- c) average  $R_a$ .

When examined by normal or corrected vision, the articulating surface shall be free from embedded particles and from scratches and score marks other than those arising from the finishing process.

#### Changes to clause 4.2.1: General

*This subclause refers to plastics acetabular components for total hip joint prostheses in accordance with classification c) of ISO 7206-1. → add to the existing text the following sentence (text in green):*

The principles for the surface finish measurements of hip joint prostheses components are given in ISO 4287. The measurements shall be performed according to the rules and procedures described in ISO 4288:1996.

### Changes to clause 4.2.3: Surface finish

Remove following sentence:

NOTE Although ISO 4288 requires a cut-off of 0,8 mm if the surface finish approaches 2  $\mu\text{m}$ , a cut-off value as long as that is not practical due to the curvature of the spherical surface.

☑ Amend to read

Following the requirements of table 1 of ISO 4288:1996, the spherical articulating surface of the implant shall have a  $R_{\text{max}}$  value not greater than 2  $\mu\text{m}$ , using a cut-off value of 0,8 mm.

The measurements shall be taken at five locations evenly distributed around the equator of the acetabular component on the spherical surface. The locations shall be at least 5 mm from the edge of the acetabular component and the measurement direction shall be oriented approximately perpendicular to any machining marks that are present.

The following details shall be reported along with the measured values:

- a) stylus tip radius;
- b) position of measurement on specimen;
- c) average  $R_a$ .

When examined by normal or corrected vision the articulating surface shall be free from embedded particles and from scratches and score marks other than those arising from the finishing process.

### Changes to clause 4.3.1: General

*This subclause refers to spherical articulating surfaces of femoral prosthesis for partial joint replacements in accordance with classification c) of ISO 7206-1. → add to the existing text the following sentence (text in green):*

The principles for the surface finish measurements of hip joint prostheses components are given in ISO 4287. The measurements shall be performed according to the rules and procedures described in ISO 4288:1996.

### Changes to clause 4.3.3: Surface finish

☑ Amend to read

The spherical articulating surface of the implant shall have an  $R_{\text{max}}$  value not greater than 0,5  $\mu\text{m}$  using a cut-off value of 0,8 mm. The  $R_{\text{tmax}}$  value shall not be greater than 1,0  $\mu\text{m}$ . The cut-off value used to determine the  $R_{\text{t}}$  value shall be in accordance with table 2 of ISO 4288:1996. The measurements shall be taken at five locations on the spherical surface. One measurement shall be taken in each of four quadrants approximately 30° from the spherical pole and one at the spherical pole.

The following details shall be reported along with the measured values:

- a) stylus tip radius;
- b) position of measurement on specimen.

When examined by normal or corrected vision, the articulating surface shall be free from embedded particles and from scratches and score marks other than those arising from the finishing process.

### New Sub clause

## 4.5 Metallic and ceramic acetabular components of total hip joint prostheses

#### 4.5.1 General

This subclause refers to spherical articulating surfaces of acetabular components of total hip joint prosthesis with classification c) of ISO 7206-1.

The principles for the surface finish measurements of hip joint prostheses components are given in ISO 4287. Surface finish measurements shall be performed according to the rules and procedures described in ISO 4288:1996

#### 4.5.2 Surface finish

The spherical articulating surfaces of metallic and ceramic components shall have  $R_{\text{max}}$  values not greater than  $0,05 \mu\text{m}$  (acknowledging to ASTM F2033). Table 1 of ISO 4288:1996 requires using a cut-off value of  $0,25 \text{ mm}$  for the  $0,05 \mu\text{m}$  requirement.

**ITeH STANDARD PREVIEW**  
(standards.iteh.ai)

Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/c00e54c2-4dd4-4c16-bc75-a7f124add082/iso-7206-2-2011-amd-1-2016>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/c00e54c2-4dd4-4c16-bc75-a7f124add082/iso-7206-2-2011-amd-1-2016>