



SLOVENSKI STANDARD
SIST EN 12697-34:2020

01-maj-2020

Nadomešča:
SIST EN 12697-34:2012

Bitumenske zmesi - Preskusne metode - 34. del: Preskus po Marshallu

Bituminous mixtures - Test methods - Part 34: Marshall test

Asphalt - Prüfverfahren - Teil 34: Marshall-Prüfung

Mélanges bitumineux - Méthodes d'essai - Partie 34 : Essai Marshall

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: EN 12697-34:2020

<https://standards.iteh.ai/catalog/standards/sist/1f85b7b1-09c5-49db-bccc-5e11c491479/sist-en-12697-34-2020>

ICS:

93.080.20 Materiali za gradnjo cest Road construction materials

SIST EN 12697-34:2020

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12697-34:2020

<https://standards.iteh.ai/catalog/standards/sist/1f85b7b1-09c5-49db-bcec-f5c11c491479/sist-en-12697-34-2020>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12697-34

February 2020

ICS 93.080.20

Supersedes EN 12697-34:2012

English Version

**Bituminous mixtures - Test methods - Part 34: Marshall
test**

Mélanges bitumineux - Méthodes d'essai - Partie 34 :
Essai Marshall

Asphalt - Prüfverfahren - Teil 34: Marshall-Prüfung

This European Standard was approved by CEN on 18 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/1f85b7b1-09c5-49db-bccc-f5c11c491479/sist-en-12697-34-2020>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 Principle	5
5 Apparatus.....	5
6 Procedure.....	6
6.1 Specimen preparation.....	6
6.2 Test procedure.....	6
7 Expression of results.....	7
8 Test report.....	7
9 Precision.....	8
Annex A (normative) Marshall stability and flow values.....	9
Annex B (normative) Testing head.....	10
Bibliography.....	11

[SIST EN 12697-34:2020](https://standards.iteh.ai/catalog/standards/sist/1f85b7b1-09c5-49db-bcec-f5c11c491479/sist-en-12697-34-2020)
<https://standards.iteh.ai/catalog/standards/sist/1f85b7b1-09c5-49db-bcec-f5c11c491479/sist-en-12697-34-2020>

European foreword

This document (EN 12697-34:2020) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2020, and conflicting national standards shall be withdrawn at the latest by August 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-34:2012.

The following is a list of significant technical changes since the previous edition:

- the title no longer makes the method exclusively for hot mix asphalt;
- [ge] editorial update according to current standard template;
- [Clause 2] titles for test methods EN 12697-series adjusted, reference EN ISO 7500-1:2018, Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500 1:2018) replaced by: EN ISO 7500-1:2018, Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Calibration and verification of the force-measuring system (ISO 7500-1:2018);
- [6.1.1 and 6.2.4] NOTES modified according to ISO/IEC Directives – Part 2:2016, 24.5;
- [7.1] correction of Formula (1). Factor v realigned as exponent;
- [Bibliography] EN 12697-35 deleted. Referred to in Clause 2 Normative references.

A list of all parts in the EN 12697 series can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 12697-34:2020 (E)**1 Scope**

This document specifies a test method for determining the stability, flow and the Marshall quotient values of specimens of bituminous mixtures mixed according to EN 12697-35 and prepared using the impact compactor method of test EN 12697-30. It is limited to dense graded asphalt concrete and hot rolled asphalt.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-6, *Bituminous mixtures — Test methods — Part 6: Determination of bulk density of bituminous specimens*

EN 12697-29, *Bituminous mixtures — Test method — Part 29: Determination of the dimensions of a bituminous specimen*

EN 12697-30, *Bituminous mixtures — Test methods — Part 30: Specimen preparation by impact compactor*

EN 12697-35, *Bituminous mixtures — Test methods — Part 35: Laboratory mixing*

EN ISO 7500-1:2018, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines* Calibration and verification of the force-measuring system (ISO 7500-1:2018)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/ui>

3.1 stability**S**

maximum load, in kilonewtons (kN), of a moulded asphalt specimen

3.2 flow**F**

deformation of the moulded specimen in millimetres (mm) at maximum load less the nominal deformation obtained by extrapolation of the tangent of the graph of load against deformation back to zero load (A to M' in Figure A.1)

3.3 tangential flow**F_t**

nominal deformation of the moulded specimen, in millimetres (mm) obtained by extrapolation of the tangent of the graph of load against deformation forward to the stability load less the nominal deformation obtained by extrapolation of the tangent back to zero load (A to B' in Figure A.1)

3.4 total flow F_T

deformation of the moulded specimen in millimetres (mm) at maximum load (0 to M' in Figure A.1)

3.5 Marshall quotient

ratio of the stability, S , to the flow, F , S/F

Note 1 to entry: See Annex A.

4 Principle

Marshall specimens are compacted in accordance with EN 12697-30. The Marshall stability, flow and quotient are subsequently determined on these specimens using defined procedures and reported along with the bulk density of the specimen.

5 Apparatus

5.1 Compression testing machine of Class 2 or better according to EN ISO 7500-1:2018, Clause 7, having a recommended minimum capacity of 28 kN and capable of applying loads to test specimens at a constant rate of deformation of (50 ± 2) mm/min after a transitory period less than 20 % of the loading time.

The rate of deformation is to be maintained.

5.2 Flow measuring device, capable of determining deformation to an accuracy of $\pm 0,1$ mm.

5.3 Graphical plotter, for evaluating the curve of force versus deformation, e.g. graphical plotter, strip recorder or software program.

A graphical plotter is required to obtain a test result by this test method. If dial gauges are used, they should be checked and zeroed prior to each measurement. In these cases, only the total flow can be recorded.

5.4 Testing head, comprised of upper and lower breaking heads with the dimensions given in Figure B.1.

5.5 Water bath, at least 150 mm deep and capable of thermostatically maintaining the water at a temperature of (60 ± 1) °C.

This bath shall have a perforated false bottom or shelf that can suspend the test specimens at least 25 mm above the bottom of the bath, and allow at least 25 mm depth of water above the specimens. The size of the bath shall allow specimens to be placed face down and not in contact with one another. A device to ensure continuous circulation of water shall also be fitted.

5.6 Thermometer, capable of measuring a temperature of 60 °C accurate to 0,5 °C.

5.7 Oven, capable of maintaining temperatures of (110 ± 5) °C.

EN 12697-34:2020 (E)

6 Procedure

6.1 Specimen preparation

6.1.1 Specimens shall be compacted in accordance with EN 12697-30, ensuring that 50 blows are applied to each side within the acceptable temperature range given.

NOTE A different number of blows can be selected; for example, 35 blows for light traffic and 75 blows for heavy duty pavements.

6.1.2 The compacted specimens shall be de-moulded, ensuring that they are cooled in air to avoid any danger of deformation and then tested in accordance with 6.1.1 and 6.1.3. After de-moulding, wait at least 4 h before further testing begins. All tests shall be completed within 32 h of de-moulding. Specimens shall not be stacked prior to testing.

Specimens of rolled asphalt may be left in the moulds and immersed in cold water to facilitate rapid cooling. The cooled specimens should be extruded from their moulds with the minimum of force and using an extractor of suitable design so that they are ejected without distortion or shock.

The bulk density of each specimen shall be determined in accordance with EN 12697-6.

6.1.3 The height of each specimen shall be measured in accordance with EN 12697-29; or the volume shall be calculated from the bulk density measurement.

6.1.4 Immerse the cylindrical specimens on their flat surface in the water bath for at least 40 min and not longer than 60 min. Maintain the temperature of the water in the bath at $(60 \pm 1) ^\circ\text{C}$.

6.2 Test procedure

6.2.1 Thoroughly clean the guide rods and the inside surfaces of the test heads. Lubricate the guide rods to ensure that the upper test head slides freely over them.

6.2.2 Prepare the test head by preheating for at least 30 min at $(60 \pm 1) ^\circ\text{C}$ in the water bath, or for 1 h in the oven.

This action shall be undertaken at the start of testing of a batch of specimens not greater than twelve in number. In the event of a delay of more than 3 min between the testing of each specimen, the test head shall be heated in a suitable oven or water-bath maintained at the specified test temperature. The minimum reheating period shall be the lesser of the delay encountered and 30 min when heated in a water bath, or double that when heated in an oven.

6.2.3 Remove the test specimen from the water bath and place it centrally on its side in the test head, ensuring good surface contact between the specimen and the test head. Place the complete assembly centrally on the testing machine.

Prior to testing each specimen, the test head shall be cleaned as required. An environmentally suitable solvent may be used for cleaning and a silicone spray applied to prevent specimens adhering to the test head.

6.2.4 Apply the load to the test specimen to achieve a constant rate of deformation of (50 ± 2) mm/min allowing for the transitory period. Continue the application of this load until the maximum reading is obtained on the load-measuring device. Record the load indicated. This section of the test shall be carried out within 40 s of removal of the test specimen from the water bath.

Measure the flow (see 7.2).

If dial gauges are used, record the movement of the top of the testing head from the instant of application of the load to the point when maximum load is reached (F_T).

Carry out the stability and flow tests on a set of four specimens.

7 Expression of results

7.1 The maximum load attained represents the stability of the mix only if the specimen height equals the required 63,5 mm. A corrected stability shall be reported by multiplying the maximum load with the correction factor calculated according to Formula (1) using the volume of the specimen as determined in accordance with 6.1:

$$c = 5,2 e^{-0,025 \cdot 9 h} = 5,2 e^{-3,2 \cdot 10^{-6} v} \quad (1)$$

where

- c is the correction factor;
- h is the height of the specimen (in millimetres);
- v is the volume of the specimen determined in 6.1 (in cubic millimetres).

The stability, S , is reported to the nearest 0,1 kN.

NOTE Corrections outside the range of specimen heights from 60,5 mm to 66,5 mm can lead to inaccurate results.

7.2 To obtain the flow value F measure on the graph of force versus deformation the distance from the intersection of the tangent and the base line, A , to the point where the maximum load is achieved, M . The flow values F_t and F_T are similarly obtained.

Record the flow values, F , F_t and F_T , to the nearest 0,1 mm.

7.3 Test results shall be considered reliable if both the variation in stability between specimens, V_S , is less than 15 % and the variation in flow between specimens, V_f , is less than 20 %. Reject the test specimen with the largest variation and obtain the average value of the other specimens if either:

- the stability value from one or more specimens differs from the average stability by more than 15 %, or
- the flow value from one or more specimens differs from the average flow by more than 20 %.

Furthermore, if any value differs from the new average by more than 15 % for stability or 20 % for flow, repeat the test.

7.4 The Marshall quotient shall be obtained by the calculation of S/F and reporting the value obtained to 0,1 kN/mm.

8 Test report

The test report shall include the following information:

- a) reference to this document;
- b) the average results F , F_t , F_T , S and Marshall quotient for each set of specimens;
- c) the average bulk density of the specimen set.