

SLOVENSKI STANDARD oSIST prEN 17417:2019

01-november-2019

Ugotavljanje dokončne biorazgradnje plastičnih materialov v vodnem sistemu pri anoksičnih (denitrifikacijskih) pogojih - Metoda z meritvijo zviševanja tlaka

Determination of the ultimate biodegradation of plastics materials in an aqueous system under anoxic (denitrifying) conditions - Method by measurement of pressure increase

Bestimmung der vollständigen Bioabbaubarkeit von Kunststoff-Materialien in wässriger Phase unter anoxischen (denitrifizierenden) Bedingungen - Verfahren mittels Messung der Druckzunahme

Détermination de la biodégradation ultime des matériaux plastiques dans un système aqueux dans des conditions anoxiques (dénitrifiantes) - Méthode par mesure de l'augmentation de pression

Ta slovenski standard je istoveten z: prEN 17417

ICS:

| 13.030.99 | Drugi standardi v zvezi z odpadki | Other standards related to wastes |
|-----------|--------------------------------------|-----------------------------------|
| 83.080.01 | Polimerni materiali na splošno | Plastics in general |

oSIST prEN 17417:2019

en,fr,de



iTeh STANDARD PREVIEW (standards.iteh.ai)



EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

DRAFT prEN 17417

August 2019

ICS 13.030.99; 83.080.01

English Version

Determination of the ultimate biodegradation of plastics materials in an aqueous system under anoxic (denitrifying) conditions - Method by measurement of pressure increase

Détermination de la biodégradation ultime des matériaux plastiques dans un système aqueux dans des conditions anoxiques (dénitrifiantes) - Méthode par mesure de l'augmentation de pression Bestimmung des endgültigen biologischen Abbaus von Kunststoffmaterialien in einem wässrigen System unter anoxischen (denitrifizierenden) Bedingungen -Verfahren durch Messung des Druckanstiegs

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 249.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2019 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. prEN 17417:2019 E

oSIST prEN 17417:2019

Page

prEN 17417:2019 (E)

Contents

| EUR | OPEAN FOREWORD | 5 |
|--------------|--|---------|
| INTR | ODUCTION | 6 |
| 1 | SCOPE | 7 |
| 2 | NORMATIVE REFERENCES | 7 |
| 3 | TERMS AND DEFINITIONS | 7 |
| 4 | PRINCIPLE | 9 |
| 5 | EQUIPMENT AND MATERIALS | 10 |
| 5. | 1 PRESSURE MEASUREMENT SYSTEM | .10 |
| FIGU (EXA | RE 1 — PRESSURE MEASUREMENT SYSTEM FOR MEASURING BIODEGRADATION UNDER ANOXIC CONDITIONS MPLE) | ; 11 |
| 5. | 2 STIRRING PLATFORM OR SINGLE MAGNETIC STIRRERS. | .11 |
| 5. | 3 ROOM OR INCUBATOR WITH A CONSTANT TEMPERATURE OF (20 ± 2) °C | .11 |
| 5. | 4 ARGON FOR THE ELIMINATION OF OXYGEN FROM THE MEDIUM AND THE GAS SPACE. | .11 |
| 5. | 5 Thermometer | .12 |
| 5. | 6 MEMBRANE FILTER | .12 |
| _ | 0101 11111,2021 | - |

5.7 5.8 5.9 5.10 5.11 5.12 5.13 5.14 6.1 6.2 6.3 6.3.1 6.3.2 6.3.3 634 64

| 7.1 | START OF TEST | 15 |
|------------|---|----|
| 7.2 7.2 | DETERMINATION OF THE INITIAL CONCENTRATIONS (ANALYTICAL SAMPLE) | |

7

6

| | 7.2.2 Determination of the suspended solids of the inoculum | 17 |
|----------------------|---|------------|
| | 7.2.3 Determination of ammonia-nitrogen, nitrite-nitrogen and nitrate-nitrogen (for a nitrogen balance) | 17 |
| | 7.2.4 Protein determination (for a nitrogen and carbon balance) | 17 |
| 7 | 7.2.5 Determination of DOC (for a carbon balance) | 17 |
| 7. | 3 INCUBATION PERIOD | 17 |
| 7. | 4 END OF LEST | 18 18 |
| - /. | | 10 |
| 8 | CALCULATION AND EVALUATION | 18 |
| 8. | 1 CALCULATION OF THE THEORETICAL N ₂ PRODUCTION | 18 |
| 8. | 2 CALCULATION OF THE PRESENT N ₂ PRODUCTION | 19 |
| 8. | 3 CALCULATION OF THE LEVEL OF DEGRADATION RELATED TO THE NITROGEN PRODUCTION | 20 |
| 8. | 4 GENERATION OF A NITROGEN BALANCE | 20 |
| TABI SUBS | LE 2 — EXAMPLE OF A NITROGEN BALANCE FOR TESTING THE ANOXIC DEGRADATION WITH PHB AS THE TEST STANCE (INITIAL MASS: <i>M</i> = 100 MG) | T 20 |
| 8. | 5 Evaluation and expression of results | 21 |
| 9 | VALIDITY OF RESULTS | |
| 5 | | |
| 10 | TEST REPORT | 21 |
| ANN SUBS | EX A (INFORMATIVE) TEST SCHEME — CALCULATION OF THE MAXIMUM PERMITTED INITIAL MASS OF THE STANCE AND THE MINIMUM NITRATE CONCENTRATION | TEST 23 |
| A.1 | GENERAL | 23 |
| A.2 | UPPER PRESSURE MEASUREMENT LIMIT SIST EN 17417:2021 | 23 |
| A.3 | SORPTION CAPACITY OF THE SORPTION SOLUTION (IF APPLICABLE) | 24 |
| A.4 | PH BUFFER CAPACITY OF THE MEDIUM | 24 |
| A.5 | MINIMUM NITRATE CONCENTRATION | 25 |
| ANN | EX B (INFORMATIVE) EXAMPLES OF DEGRADATION CURVES | 26 |
| FIGU (POL | IRE B.1 — PRESSURE INCREASE DURING A BIODEGRADATION TEST UNDER ANOXIC CONDITIONS WITH PHB Y- <i>B</i> -HYDROXYBUTYRIC ACID) AND BLANK VALUE | 27 |
| FIGU (PHE | IRE B.2 — PERCENTAGE BIODEGRADATION RELATED TO THE NITROGEN PRODUCTION OF A TEST SUBSTANCE IN THIS CASE) IN A DEGRADATION TEST UNDER ANOXIC CONDITIONS — SAME TEST AS IN FIGURE B.1 | 28 |
| ANN BAL | EX C (INFORMATIVE) CALCULATION OF THE PRODUCED INORGANIC CARBON AND PREPARATION OF A CAR | BON 29 |
| C.1 | CALCULATION OF THE PRODUCED INORGANIC CARBON | 29 |
| FIGU SORI (STA | IRE C.1 — EXAMPLES OF TITRATION CURVES OF THE ORIGINAL KOH (NEW, ORIGINAL, 25 MMOL) AND OF THI PTION SOLUTIONS OF A BLANK TEST AND A TEST WITH PHB (100 MG) AFTER COMPLETION OF THE TEST NDARD TEST CONDITIONS) | E 29 |
| C.2 | GENERATION OF A CARBON BALANCE | 30 |
| ТАВІ | LE 3 — EXAMPLE OF A CARBON BALANCE FOR PHB (INITIAL MASS: <i>M</i> = 100 MG) | 31 |

| C.3 | CALCULATION OF THE LEVEL OF BIODEGRADATION RELATED TO CARBON | 31 |
|--------|--|----|
| BIBLIO | GRAPHY | 32 |

iTeh STANDARD PREVIEW (standards.iteh.ai)

European foreword

This document (prEN 17417:2019) has been prepared by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This document is currently submitted to the CEN Enquiry.

iTeh STANDARD PREVIEW (standards.iteh.ai)

Introduction

Biodegradation of chemical substance strongly depends on environmental conditions. The presence or the absence of oxygen is significant for the metabolic pathway on which the degradation of bacteria can take place. At present, several test methods for the investigation of biodegradability of polymers under aerobic conditions, but only a few test methods for the investigation of biodegradability under anaerobic conditions exist. However, degradation under anoxic (denitrifying) conditions has barely been considered yet. The concept "anoxic" has been created by engineers and designates conditions under which denitrification can take place. This means that either a little amount of oxygen or no oxygen at all (< 0,1 mg/l) but nitrate (> 0,1 mg/l NO₃⁻-N) is present. During heterotrophic denitrification, e.g. inside the denitrification tank of a wastewater treatment plant, nitrate is reduced to nitrogen and at the same time organic substrate is oxidized to CO_2 . In nature, anoxic conditions can be present within the hypolimnion of eutrophic lakes or within the sediment at the transition zone between the aerobic and the anaerobic zone.

A way to use biodegradable polymers after intended service life would be their addition as additional carbon source to the denitrification unit of a wastewater treatment plant. In order to check if this way of disposing a polymer is possible, the biodegradability under anoxic (denitrifying) conditions shall be determined. Even if a substance shows good aerobic degradability, this does not necessarily apply under anoxic conditions.

Furthermore, a distinction shall be made between biodegradable polymers that are soluble in water and those not soluble in water.

Those biodegradable polymers that are soluble in water could be added systematically and continuously to the denitrification unit as a solid substrate, which is quickly converted and which can therefore replace the addition of an external liquid carbon source such as ethanol or acetic acid. Testing their aerobic degradability, their water solubility and, if necessary, their water dispersibility can be carried out in accordance with EN 14987. In addition to this, special testing regarding their use as a carbon source for denitrification is done according to this standard. As long as these biodegradable polymers are present as a solid substance, it shall be ensured that they remain in the denitrification tank in order to prevent operational failure during other phases of the wastewater treatment plant.

Those biodegradable polymers that are not soluble in water are discontinuously introduced as a solid substance into a specially designed denitrification reactor, where they substantially remain because of an appropriate process control. Induced by bacterial activity, they continuously release carbon for the purpose of denitrification during a process of anoxic degradation, the duration of which depends on their dimensions (surface/volume ratio). Special testing regarding their use as a water insoluble carbon source for denitrification is described in this standard.

1 Scope

This document specifies a method for the determination of the ultimate anoxic biodegradability of plastics made of organic compounds, where the amount of the produced nitrogen and carbon dioxide at the end of the test is measured.

The test substance is exposed to an inoculum stemming from the denitrification tank of a wastewater treatment plant. Testing is performed under defined laboratory conditions.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 872:2005, Water quality — Determination of suspended solids - Method by filtration through glass fibre filters

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <u>http://www.electropedia.org/</u>
- ISO Online browsing platform: available at <u>http://www.iso.org/obp</u>

3.1

ultimate anoxic biodegradation

degradation of an organic compound into carbon dioxide, water and mineral salts of any of the present elements (mineralization) as well as new biomass by means of microorganisms in the presence of oxidized nitrogen compounds (nitrate, nitrite) and in the absence of oxygen

3.2

suspended solids

solids removed by filtration under specified conditions

[SOURCE: EN 872:2005, 3.1]

3.3 dissolved inorganic carbon DIC

that part of the inorganic carbon in water which cannot be removed by specified phase separation, for example by centrifugation at 40 000 m s⁻² for 15 min or by membrane filtration using membranes with pores of 0,2 µm to 0,45 µm in diameter

[SOURCE: EN ISO 14852:2004, 3.4] [1]

3.4

lag phase

time, measured in days, from the start of a test until adaptation and/or selection of the degrading microorganisms is achieved and the level of biodegradation of a chemical compound or organic matter has increased to about 10 % of the maximum level of biodegradation

[SOURCE: EN ISO 14855-1:2013, 3.7] [2]

3.5

level of biodegradation related to the nitrogen production

measured level of biodegradation of a chemical compound or organic substance in a test, calculated from the amount of actually produced nitrogen divided by the theoretical maximum amount of nitrogen

Note 1 to entry: It is expressed as a percentage.

3.6

level of biodegradation related to carbon

measured level of biodegradation of a chemical compound or organic substance in a test, calculated from the final products of mineralization of the carbon fraction (amount of carbon from carbon dioxide and biomass) divided by the carbon fraction of the amount of the test substance used

Note 1 to entry: It is expressed as a percentage.

3.7

maximum level of biodegradation

measured level of biodegradation of a chemical compound or organic substance in a test, above which no further biodegradation takes places during the test

Note 1 to entry: It is expressed as a percentage.

[SOURCE: EN ISO 14855-1:2013, 3.8, modified — the unit "percentage" has been included in the Note] [2]

3.8

biodegradation phase

time from the end of the lag phase of a test until about 90 % of the maximum level of biodegradation has been reached

Note 1 to entry: It is expressed in days.

[SOURCE: EN ISO 14855-1:2013, 3.9, modified — the unit "days" has been included in the Note] [2]

3.9

plateau phase

time from the end of the biodegradation phase until the end of a test

Note 1 to entry: It is expressed in days.

[SOURCE: EN ISO 14855-1:2013, 3.10, modified — the unit "days" has been included in the Note] [2]

3.10

nitrogen recovery rate

sum of the mass concentrations of the nitrogen fractions of nitrate, nitrite, ammonium, protein and of elementary nitrogen at the end of the test divided by the sum of the corresponding mass concentrations at the beginning of the test

Note 1 to entry: It is expressed in percent.

3.11

carbon recovery rate

sum of the mass concentrations of the dissolved organic carbon (DOC), the carbon fractions of the test substance, of carbon dioxide and of biomass at the end of the test divided by the sum of the corresponding mass concentrations at the beginning of the test

Note 1 to entry: It is expressed in percent.

3.12 theoretical oxygen demand ThOD

theoretical maximum amount of oxygen required to completely oxidize a chemical compound

Note 1 to entry: It is calculated from the molecular formula of this compound and expressed in milligram of oxygen uptake per milligram of the test compound.

3.13 theoretical nitrogen production ThNP

theoretical maximum amount of nitrogen produced during biodegradation under denitrifying conditions

Note 1 to entry: It is calculated from the molecular formula of the test compound and the stoichiometry of the anoxic biodegradation of this compound (simplified, without biomass) and expressed in milligram of nitrogen produced per milligram of the test compound.

3.14 theoretical nitrate demand standards.iteh.ai) ThND

theoretical maximum amount of nitrate-nitrogen that is reduced during biodegradation under denitrifying conditions

Note 1 to entry: It is calculated from the molecular formula of the test compound and the stoichiometry of the anoxic biodegradation of this compound (simplified, without biomass) and is expressed in milligram of nitratenitrogen produced per milligram of the test compound.

3.15

preadaptation

pre-incubation of an inoculum in the presence of the chemical compound or organic substance under test, with the aim of enhancing the ability of the inoculum to biodegrade the test substance by adaptation and/or selection of the microorganisms

4 Principle

In order to investigate anoxic degradation, the nitrogen production (N_2) is monitored by means of pressure measurement in a closed system.

A mineral salt medium, free of oxygen and containing nitrate, with the test substance being the only carbon source, is placed in a pressure-tight bottle and inoculated with the inoculum from the denitrification tank of a waste water treatment plant; The gas space of the bottle shall be gassed with argon or nitrogen in order to prevent oxygen from entering. Subsequently, the vessel is closed by means of a pressure measuring head. The use of KOH or NaOH is favourable if the absorbed CO_2 is to be measured by means of titration in order to prepare a carbon balance.

Therefore, the pressure increase inside the bottle is proportional to the nitrogen that is produced during denitrification. Pressure measurement values of a sample are captured and recorded by pressure sensors

and can be transmitted to a personal computer any time. The analytical determination of the NO_3^- , NO_2^- ,

 NH_4^+ and protein content at the beginning and the end of the test allows a nitrogen balance which provides information about the plausibility of results and, in particular, about the leak-tightness of the system. Based on experience, the resulting concentrations of the metabolites NO and N₂O will be very low, which is why they can be neglected.

The level of biodegradation under anoxic conditions is expressed as a percentage and determined by comparison of the actual and the theoretical nitrogen production. The test result is the maximum level of biodegradation determined from the plateau phase of the biodegradation curve. Optionally, a carbon balance can be calculated in order to obtain additional information regarding biodegradation and to improve the evaluation of biodegradation (see C.2).

5 Equipment and materials

5.1 Pressure measurement system

The following example represents the principle of a system for measuring the produced nitrogen by means of pressure measurement.

The pressure measurement system ¹⁾ (see Figure 1) consists of:

- pressure measuring heads, a combination of a screw cap with integrated pressure sensor;
- bottles capable of being sealed pressure-tight for being used as reaction vessels, nominal volume:
 500 ml (or 1 000 ml) with side neck made of glass also capable of being sealed pressure-tight;
- sorption vessel for the purpose of CO₂ sorption in the reaction vessels.

¹⁾ The OxiTop Control system of WTW, Weilheim, Germany, consisting of "OxiTop[®]-C" pressure measuring heads, sorption vessels, adequate bottles and accessories, is an example of a suitable product available commercially. For this system, pressure measurement values of a sample are continuously recorded by the OxiTop heads. At the start of the test, the value is automatically set to ambient pressure (relative zero). The heads are controlled (e.g. mode, start, measurement duration, GLP monitoring, etc.) by means of a controller (OxiTop[®] OC110) using an infrared interface. The relevant pressure measurement values can be retrieved, displayed and further processed by a software programme any time. This information is given for the convenience of users of this standard and does not constitute an endorsement by CEN of the product named.