



SLOVENSKI STANDARD
oSIST prEN ISO 19403-6:2019
01-julij-2019

Barve in laki - Omočljivost - 6. del: Merjenje dinamičnega stičnega kota (ISO 19403-6:2017)

Paints and varnishes - Wettability - Part 6: Measurement of dynamic contact angle (ISO 19403-6:2017)

Beschichtungsstoffe - Benetzbarkeit - Teil 6: Messung des dynamischen Kontaktwinkels (ISO 19403-6:2017)

Peintures et vernis - Mouillabilité - Partie 6: Mesurage de l'angle de contact dynamique (ISO 19403-6:2017)

Ta slovenski standard je istoveten z: prEN ISO 19403-6

ICS:

87.040

Barve in laki

Paints and varnishes

oSIST prEN ISO 19403-6:2019

en,fr,de

INTERNATIONAL
STANDARD

ISO
19403-6

First edition
2017-06

**Paints and varnishes — Wettability —
Part 6:
Measurement of dynamic contact angle**

Peintures et vernis — Mouillabilité —

Partie 6: Mesurage de l'angle de contact dynamique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 19403-6:2020

<https://standards.iteh.ai/catalog/standards/sist/1e3e25db-269f-4e38-8e00-d51c96995843/sist-en-iso-19403-6-2020>



Reference number
ISO 19403-6:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 19403-6:2020

<https://standards.iteh.ai/catalog/standards/sist/1e3e25db-269f-4e38-8e00-d51c96995843/sist-en-iso-19403-6-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus and materials	2
6 Sampling	4
7 Procedure	4
7.1 General for measuring on the horizontal drop.....	4
7.1.1 Setting up the contact angle measuring system.....	4
7.1.2 Test conditions.....	4
7.1.3 Conditioning of the test panels.....	4
7.1.4 Conditioning of the test liquids.....	4
7.2 Measurement.....	4
7.2.1 General.....	4
7.2.2 Measuring method.....	5
7.2.3 Determination of the contact angle.....	5
8 Evaluation	5
9 Precision	8
10 Test report	8
Annex A (informative) Notes on sampling and treatment of test specimens	10
Bibliography	11

ISO 19403-6:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

A list of all parts in the ISO 19403 series can be found on the ISO website.

Introduction

Dynamic contact angles describe the processes on the interface liquid/solid during volume increase (advancing angle) or volume decrease (receding angle) of a drop in horizontal position. As an alternative to the static method (see ISO 19403-2), for the advancing angle always a surface area is wetted, which was previously unwetted. For the receding angle, the contact angle during dewetting is observed. The difference between advancing angle and receding angle is a sign of different chemical or physical homogeneity (morphology, topology) or roughness. The receding angle is not suitable for the determination of the surface energy.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 19403-6:2020](https://standards.iteh.ai/catalog/standards/sist/1e3e25db-269f-4e38-8e00-d51c96995843/sist-en-iso-19403-6-2020)

<https://standards.iteh.ai/catalog/standards/sist/1e3e25db-269f-4e38-8e00-d51c96995843/sist-en-iso-19403-6-2020>

Paints and varnishes — Wettability —

Part 6: Measurement of dynamic contact angle

1 Scope

This document specifies a method to measure the dynamic contact angle with an optical method. The advancing and the receding angles are determined.

By means of this defined measurement, the wetting and dewetting properties can be characterized. It can also be concluded on the morphological and chemical homogeneity of interfaces.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 19403-1, *Paints and varnishes — Wettability — Part 1: Terminology and general principles*

ISO 19403-2:2017, *Paints and varnishes — Wettability — Part 2: Determination of the free surface energy of solid surfaces by measuring the contact angle*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and ISO 19403-1, and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 dynamic contact angle

contact angle, which is measured during advancing or receding of the three-phase point

Note 1 to entry: For the definition of “contact angle”, see ISO 19403-1:2017, 3.1.9.

Note 2 to entry: The advancing or receding of the three-phase point can be achieved by changing the volume of the liquid drop to be measured, by relative movement (immersing and pulling out) of a solid body to an interface, or by moving the drop over the interface (e.g. rolling off).

ISO 19403-6:2017(E)

3.2 advancing angle

θ_a
contact angle, which is measured during advancing of the three-phase point

Note 1 to entry: Generally, the advancing angle is used for the determination of the interface energy, in which case, the measurement should be carried out close to the thermodynamic equilibrium. This is approximately reached if there is no influence of, for example, the dosing speed on the contact angle.

3.3 receding angle

θ_r
contact angle, which is measured during receding of the three-phase point

3.4 contact angle hysteresis

θ_{ar}
difference between *advancing angle* (3.2) and *receding angle* (3.3)

3.5 polynomial method

<contact angle> image-analysing evaluation method for the contact angle which can also be applied when the dosing needle is still inside the drop

4 Principle

At least three drops of the respective test liquids are dosed onto the flat surface of a test specimen. The volume of the respective drop is continuously increased (advancing angle) or decreased (receding angle). The contact angle is preferably determined by means of the polynomial method, synchronously with the dosing. If the polar and dispersive fraction of the surface free energy is to be determined according to ISO 19403-2, the advancing angle shall be used.

5 Apparatus and materials

Ordinary laboratory apparatus, together with the following.

5.1 Contact angle measuring system.

Any state-of-the-art contact angle measuring device, preferably systems with digital image capture and analysis for measuring the contact angle. [Figure 1](#) shows a schematic example of a contact angle measuring system.