INTERNATIONAL STANDARD

ISO 2398

Sixth edition 2016-11-01

Rubber hoses, textile-reinforced, for compressed air — Specification

Tuyaux en caoutchouc renforcés textile pour l'air comprimé — Spécifications

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 2398:2016 https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-59d5f50b37a6/iso-2398-2016



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 2398:2016 https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-59d5f50b37a6/iso-2398-2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Contents				
Fore	eword	iv		
1	Scope	1		
2	Normative references	1		
3	Terms and definitions	1		
4	Classification	2		
5	Materials and construction	2		
6	Dimensions 6.1 Inside diameters and tolerances 6.2 Concentricity 6.3 Tolerance on length 6.4 Minimum thickness of lining and cover			
7	Physical properties 7.1 Rubber compounds 7.2 Finished hose	4		
8	Frequency of testing	5		
9	Type testing	5		
10	Test report or certificate TANDARD PREVIEW	5		
11	1 Marking			
Ann	Marking ex A (normative) Type tests and routine tests iteh.ai)	6		
Ann	ex B (informative) Productions acceptance tests	7		
Bibl	liography https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-	8		

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 45, Rubber and rubber products, Subcommittee SC 1, Rubber and plastics hoses and hose assemblies.

This sixth edition cancels and replaces the fifth edition (ISO 2398:2006); which has been technically revised with the following main changes. 59d5f50b37a6/iso-2398-2016

- Clause 2 has been updated: ISO 1746 and ISO 4672 have been deleted and replaced by ISO 10619-1 and ISO 10619-2. ISO 7326:1991 has been replaced by ISO 7326:2006.
- New clauses (<u>Clause 8</u>, <u>Clause 9</u> and <u>Clause 10</u>) describing frequency of testing, routine tests, type tests and production acceptance tests have been added.
- Clause 8 has been renumbered as <u>Clause 11</u>; a), b), f) and the example have been amended.
- Annex A and Annex B have been introduced in accordance with ISO/TC 45/SC 1 Guide 976 Rev 7:2013.
- Clause 10, describing a test report or certificate supplied on request of the purchaser, has been added.

Rubber hoses, textile-reinforced, for compressed air — Specification

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate health and safety practices and to ensure compliance with any national regulatory conditions.

1 Scope

This document specifies the requirements for three types, three classes and two categories of textile-reinforced rubber hose for compressed air, up to a maximum working pressure of 25 bar with an operating-temperature range of -40 °C to +70 °C, depending on the type and category.

NOTE 1 bar = 0.1 MPa.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only/the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties

ISO 188, Rubber, vulcanized or thermoplastic—2: Accelerated ageing and heat resistance tests https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-

ISO 1307, Rubber and plastics hoses—SHose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses

ISO 1402, Rubber and plastics hoses and hose assemblies — Hydrostatic testing

ISO 1817:2015, Rubber, vulcanized or thermoplastic — Determination of the effect of liquids

ISO 4671, Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies

ISO 7326:2006, Rubber and plastics hoses — Assessment of ozone resistance under static conditions

ISO 8033, Rubber and plastics hoses — Determination of adhesion between components

ISO 10619-1, Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature

ISO 10619-2:2011, Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 2: Bending tests at sub-ambient temperatures

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

4 Classification

Hoses are designated as one of the following types, depending on their pressure rating.

Type 1: Low pressure — designed for a maximum working pressure of 1 MPa (10 bar)

Type 2: Medium pressure — designed for a maximum working pressure of 1,6 MPa (16 bar)

Type 3: High pressure — designed for a maximum working pressure of 2,5 MPa (25 bar)

These types can be subdivided into three classes depending on their oil resistance.

Class A: Non-oil-resistant

Class B: Normal oil resistance

Class C: Good oil resistance

The types and classes above can also be further subdivided into two categories, depending on their operating-temperature range.

Category N-T (normal temperature): -25 °C to +70 °C

Category L-T (low temperature): -40 °C to +70 °C

5 Materials and construction (standards.iteh.ai)

The hose shall consist of

— a rubber lining. <u>ISO 2398:2016</u>

https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-

- a reinforcement of natural or synthetic textile applied by any suitable technique, and
- a rubber cover.

The lining and cover shall be of uniform thickness, concentric to comply with the minimum thickness specified, and free from holes, porosity and other defects. The cover finish may be smooth or fabric-marked.

6 Dimensions

6.1 Inside diameters and tolerances

When measured in accordance with ISO 4671, the inside diameters and their tolerances shall conform to the values specified in Table 1.

Table 1 — Minimum and maximum inside diameters

Hose size	Minimum internal diameter mm	Maximum internal diameter mm
4	3,25	4,75
5	4,25	5,75
6,3	5,55	7,05
8	7,25	8,75
10	9,25	10,75
12,5	11,75	13,25
16	15,25	16,75
19	18,25	19,75
20	19,25	20,75
25	23,75	26,25
31,5	30,25	32,75
38	36,50	39,50
40	38,50	41,50
51	49,50	52,50
63	61,50	64,50
Teh %TA	ND 474,50) PR	77,50
80	78,00	82,00
10 0 Stal	ndar _{%,60} iteh.	al) 102,00
102	100,00	104,00

ISO 2398:2016

Concentricity Co 6.2 59d5f50b37a6/iso-2398-2016

When determined in accordance with ISO 4671, the concentricity, based on a total indicator reading between the inside diameter and the outside surface of the cover, shall be no greater than 1,0 mm for hoses of inside diameter up to and including 76 mm, and no greater than 1,5 mm for hoses of inside diameter greater than 76 mm.

6.3 Tolerance on length

The tolerance on cut lengths shall be as specified in ISO 1307, the length being measured in accordance with ISO 4671.

6.4 Minimum thickness of lining and cover

When measured in accordance with ISO 4671, the minimum thickness of the lining and cover shall be as follows.

Type 1: lining 1,0 mm

cover 1,5 mm

Type 2: lining 1,5 mm

cover 2,0 mm

Type 3: lining 2,0 mm

cover 2,5 mm

7 Physical properties

7.1 Rubber compounds

When determined by the methods listed in <u>Table 2</u>, the physical properties of the compounds used for the lining and cover shall conform to the values specified in <u>Table 2</u>.

Tests shall be carried out either on samples taken from the hose or from separately vulcanized sheets, 2 mm in thickness and vulcanized to the same cure state as the production hoses.

Table 2 — Physical properties of rubber compounds

Dwanautri	Requi	rement	Tost method	
Property	Lining	Cover	Test method	
Minimum tensile strength	7,0 MPa	7,0 MPa	ISO 37 (dumb-bell test piece)	
Minimum elongation at break	250 %	250 %	ISO 37 (dumb-bell test piece)	
Resistance to ageing				
Change in tensile strength from original value (max.)	±25 %	±25 %	ISO 188 (3 days at 100 °C ± 1 °C), air-oven method ISO 37 (dumb-bell test piece)	
Change in elongation at break from original value (max.)	±50 %	±50 %		
Resistance to liquids				
Increase in volume (class A)	iTeh ATAN	DARNA PRE	¥IEW	
Increase in volume (max.) (class B only)	115 % No shrinkage allowed		ISO 1817:2015 (72 h at 70 °C ± 2 °C In oil No. 3), gravimetric method	
Increase in volume (max.) (class C only)	30 % No shrinkage allowed	75 % No shrinkage allowed	ISO 1817:2015 (72 h at 70 °C \pm 2 °C in oil No. 3), gravimetric method	

https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-59d5f50b37a6/iso-2398-2016

7.2 Finished hose

When determined by the methods listed in $\underline{\text{Table 3}}$, the physical properties of the finished hose shall conform to the values specified in $\underline{\text{Table 3}}$.

Table 3 — Physical properties of finished hose

Property	Requirement			Test method
		МРа	bar	
Proof pressure	type 1	2	20	ISO 1402
Proof pressure	type 2	3,2	32	130 1402
	type 3	5	50	
Change in length at maximum working pressure	±5 %			ISO 1402
Change in diameter at maximum working pressure	±5 %			ISO 1402
		МРа	bar	
Minimum hurst prossure	type 1	4	40	ISO 1402
Minimum burst pressure	type 2	6,4	64	130 1402
	type 3	10	100	
Adhesion between components	2,0 kN/m (min.)			ISO 8033

Table 3 (continued)

Property	Requirement	Test method
Ozone resistance	No cracking observed under × 2 magnification	ISO 7326:2006 — method 1 (up to 25 mm id) — method 2 or 3 for other sizes
Flexibility at 23 °C	T/D not less than 0,8	ISO 10619-1
Low-temperature flexibility	No cracke and chall hace the proof	ISO 10619-2:2011 Category N-T at -25 °C ± 2 °C Category L-T at -40 °C ± 2 °C

8 Frequency of testing

The minimum frequency of testing (routine tests and type tests) shall conform to the schedule given in Annex A. The recommended frequency of production acceptance testing, carried out per batch, is given in Annex B and is for guidance only.

Routine tests are those tests carried out on each length of finished hose to verify that the hose design, materials and method of manufacture meet all the requirements of this document. Production acceptance tests are those tests, carried out per batch or per 10 batches, by the manufacturer to monitor the quality of his production.

9 Type testing iTeh STANDARD PREVIEW

Type tests are carried out by the manufacturer to confirm that all the materials, construction and test requirements of this document have been met by the method of manufacture and design. Type testing shall be repeated at a maximum of five years or whenever a change in the method of manufacture or materials occurs. Type testing shall be performed for all sizes and types except those of the same size and construction.

https://standards.iteh.ai/catalog/standards/sist/846d4fa4-153f-41c5-971b-59d5f50b37a6/iso-2398-2016

10 Test report or certificate

Upon the purchaser's request, the manufacturer shall supply a test report or certificate, positively identifying the hoses supplied to the purchaser.

11 Marking

The hose shall be continuously and durably marked with the following minimum information:

- a) the manufacturer's name or identification (XXXX);
- b) the number and year of publication of this document (ISO 2398:2016);
- c) the hose type and class;
- d) the category, if low-temperature (L-T);
- e) the inside diameter, in mm;
- f) the maximum working pressure, in MPa and bar, with units stated;
- g) the date of manufacture, by giving the quarter and year of manufacture or using another suitable date code.

EXAMPLE XXXX/ISO 2398:2016/2B/L-T/25 mm/1,6 MPa/16 bar/2Q16.