
Barve in laki - Omočljivost - 2. del: Določevanje proste površinske energije površin trdnih teles z merjenjem stičnega kota (ISO 19403-2:2017)

Paints and varnishes - Wettability - Part 2: Determination of the surface free energy of solid surfaces by measuring the contact angle (ISO 19403-2:2017)

Beschichtungsstoffe - Benetzbarkeit - Teil 2: Bestimmung der freien Oberflächenenergie fester Oberflächen durch Messung des Kontaktwinkels (ISO 19403-2:2017)

Peintures et vernis - Mouillabilité - Partie 2: Détermination de l'énergie libre de surface des surfaces solides par la mesure de l'angle de contact (ISO 19403-2:2017)

<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad01c1594/sist-en-iso-19403-2:2020>

Ta slovenski standard je istoveten z: EN ISO 19403-2:2020

ICS:

87.040

Barve in laki

Paints and varnishes

SIST EN ISO 19403-2:2020**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 19403-2:2020

<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020>

EUROPEAN STANDARD

EN ISO 19403-2

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2020

ICS 01.040.87

English Version

Paints and varnishes - Wettability - Part 2: Determination of the surface free energy of solid surfaces by measuring the contact angle (ISO 19403-2:2017)

Peintures et vernis - Mouillabilité - Partie 2:
Détermination de l'énergie libre de surface des
surfaces solides par la mesure de l'angle de contact
(ISO 19403-2:2017)

Beschichtungsstoffe - Benetzbarkeit - Teil 2:
Bestimmung der freien Oberflächenenergie fester
Oberflächen durch Messung des Kontaktwinkels (ISO
19403-2:2017)

This European Standard was approved by CEN on 4 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

| Contents | Page |
|------------------------|------|
| European foreword..... | 3 |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 19403-2:2020
<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020>

European foreword

The text of ISO 19403-2:2017 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 19403-2:2020 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2020, and conflicting national standards shall be withdrawn at the latest by August 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW Endorsement notice (standards.iteh.ai)

The text of ISO 19403-2:2017 has been approved by CEN as EN ISO 19403-2:2020 without any modification.

[SIST EN ISO 19403-2:2020](https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020)

<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 19403-2:2020

<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020>

INTERNATIONAL
STANDARD

ISO
19403-2

First edition
2017-06

**Paints and varnishes — Wettability —
Part 2:
Determination of the surface free
energy of solid surfaces by measuring
the contact angle**

iTeh STANDARD PREVIEW
*Peintures et vernis — Mouillabilité —
Partie 2: Détermination de l'énergie libre de surface des surfaces
solides par la mesure de l'angle de contact*

SIST EN ISO 19403-2:2020

<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020>



Reference number
ISO 19403-2:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 19403-2:2020

<https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8170-482ad0dc1594/sist-en-iso-19403-2-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

| | |
|--|-----------|
| Foreword | iv |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Principle | 1 |
| 5 Apparatus and materials | 2 |
| 6 Sampling | 3 |
| 7 Procedure | 4 |
| 7.1 General for measuring on the horizontal drop..... | 4 |
| 7.1.1 Setting up the contact angle measuring system..... | 4 |
| 7.1.2 Test conditions..... | 4 |
| 7.1.3 Conditioning of the test panels..... | 4 |
| 7.2 Measurement..... | 4 |
| 7.2.1 General..... | 4 |
| 7.2.2 Static method..... | 4 |
| 7.2.3 Dynamic method (progressive contact angle)..... | 5 |
| 7.2.4 Determination of the contact angle..... | 6 |
| 8 Evaluation | 6 |
| 8.1 General..... | 6 |
| 8.2 Owens-Wendt-Rabel-Kaelble method (OWRK method)..... | 6 |
| 8.3 Wu method..... | 7 |
| 9 Precision | 8 |
| 9.1 General..... | 8 |
| 9.2 Repeatability limit, r | 8 |
| 9.3 Reproducibility limit, R | 8 |
| 9.4 Calculation in accordance with Owens-Wendt-Rabel-Kaelble method (OWRK method)..... | 8 |
| 10 Test report | 9 |
| Annex A (informative) Notes on measuring practice | 10 |
| Bibliography | 14 |

ISO 19403-2:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

A list of all parts in the ISO 19403 series can be found on the ISO website.

Paints and varnishes — Wettability —

Part 2:

Determination of the surface free energy of solid surfaces by measuring the contact angle

1 Scope

This document specifies a test method to measure the contact angle for the determination of the surface free energy of a solid surface. The method can be applied for the characterization of substrates and coatings.

NOTE 1 For the determination of the surface free energy of polymers and coatings, either the method in accordance with Owens, Wendt, Rabel and Kaelble or the method in accordance with Wu is used preferably.

NOTE 2 The morphological and chemical homogeneity have an influence on the measuring results.

NOTE 3 The procedures indicated in this document are based on the state-of-the-art employing the drop projection method in penumbral shadow. Other methods are not excluded.

NOTE 4 Measuring the contact angle on powders is not part of this document. For further information, see the bibliography.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

2 Normative references

SIST EN ISO 19403-2:2020

[https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-](https://standards.iteh.ai/catalog/standards/sist/2d2172c4-0476-4511-8176-877d01414141/iso-19403-2:2017)

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 19403-1, *Paints and varnishes — Wettability — Part 1: Terminology and general principles*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and ISO 19403-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Principle

A minimum of three drops of at least two test liquids are dosed onto the flat surface of a test specimen. For every drop, the contact angle is measured. From the averaged contact angles of every liquid, their surface tensions, as well as their polar and dispersive fractions, the surface free energy of the solid is calculated by means of an appropriate model, divided into the polar and dispersive fractions.