
Gradbeni proizvodi - Ocenjevanje sproščanja nevarnih snovi - Določanje ostankov biocidov s tekočinsko kromatografijo in tandemsko masno spektrometrijo (LC-MS/MS)

Construction products - Assessment of release of dangerous substances - Determination of biocide residues using liquid chromatography with mass spectrometric detection (LC-MS/MS)

Bauprodukte - Bewertung der Freisetzung von gefährlichen Stoffen - Bestimmung von Biozid-Rückständen mittels LC-MS/MS

Produits de construction - Évaluation de l'émission de substances dangereuses - Détermination de la teneur en biocides par chromatographie en phase liquide et détection par spectrométrie de masse en tandem (LC-MS/MS)

<https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024>

Ta slovenski standard je istoveten z: EN 17845:2023

ICS:

13.020.99	Drugi standardi v zvezi z varstvom okolja	Other standards related to environmental protection
71.040.50	Fizikalnokemijske analitske metode	Physicochemical methods of analysis
91.100.01	Gradbeni materiali na splošno	Construction materials in general

SIST EN 17845:2024**en,fr,de**

EUROPEAN STANDARD

EN 17845

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2023

ICS 91.100.01

English Version

Construction products: Assessment of release of
dangerous substances - Determination of biocide residues
using liquid chromatography with mass spectrometric
detection (LC-MS/MS)

Produits de construction : Évaluation de l'émission de
substances dangereuses - Détermination de la teneur
en biocides par chromatographie en phase liquide et
détection par spectrométrie de masse en tandem (LC-
MS/MS)

Bauprodukte: Bewertung der Freisetzung von
gefährlichen Stoffen - Bestimmung von Biozid-
Rückständen mittels LC-MS/MS

This European Standard was approved by CEN on 14 August 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Abbreviations	8
5 Sample preparation.....	9
6 Principle	9
7 Reagents	9
8 Apparatus and equipment	11
9 Procedure.....	12
9.1 Preparation and storage of the samples.....	12
9.2 Preparation of eluates.....	12
9.3 Sample preparation for content analysis	13
9.4 Determination	14
9.5 Test for interference and recovery.....	14
10 Evaluation of results	14
10.1 Identification	14
10.2 Quantification.....	15
10.3 Quality assurance.....	15
11 Calculation of results	16
11.1 Calculation of biocide concentrations without standard addition	16
11.2 Calculation of biocide concentrations with standard addition	17
12 Test performance.....	20
13 Test report.....	21
Annex A (normative) LC-UV method for content analysis.....	22
A.1 Extraction and clean-up.....	22
A.2 HPLC analysis.....	22
A.3 Example of chromatographic conditions.....	22
A.4 Calibration	23
A.4.1 General.....	23
A.4.2 Calibration curve.....	23
A.5 Calculation of biocide content in the construction product	24
Annex B (informative) Solid phase extraction of eluates (example).....	25
Annex C (informative) Example conditions for suitable LC-MS/MS systems.....	26

Annex D (informative) Validation results for biocides in eluates from construction products	31
Bibliography	33

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 17845:2024](https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024)

<https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024>

EN 17845:2023 (E)**European foreword**

This document (EN 17845:2023) has been prepared by Technical Committee CEN/TC 351 “Construction products: Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2024, and conflicting national standards shall be withdrawn at the latest by May 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 17845:2024](https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024)

<https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024>

Introduction

This document deals with the determination of the content of biocides in construction products and eluates using liquid chromatography and tandem mass spectrometric detection (LC-MS/MS).

Following an extended evaluation of available methods for content and eluate analysis in construction products (CEN/TR 16045) and subsequent method evaluation in the robustness validation [Van De Weghe et al., 2018] it was concluded that eluate analysis and content analysis for biocides can be based on EN 15637 after some modifications.

This document is part of a modular horizontal approach and belongs to the analytical step. An overview of all modules which belong to a chain of measurement and the manner how modules are selected is given in CEN/TR 16220.

In the growing amount of product and sector-oriented test methods it was recognized that many steps in test procedures are or could be used in test procedures for many products, materials and sectors. It was supposed that, by careful determination of these steps and selection of specific questions within these steps, elements of the test procedure could be described in a way that can be used for all materials and products or for all materials and products with certain specifications.

In this context a horizontal modular approach is adopted in CEN/TC 351. "Horizontal" means that the methods can be used for a wide range of materials and products with certain properties. "Modular" means that a test standard developed in this approach concerns a specific step in assessing a property and not the whole "chain of measurement" (from sampling to analyses). A beneficial feature of this approach is that "modules" can be replaced by better ones without jeopardizing the standard "chain".

The use of modular horizontal standards implies the drawing of test schemes as well. Before executing a test on a certain material or product to determine certain characteristics, it is necessary to draw up a protocol in which the adequate modules are selected and together form the basis for the entire test procedure.

(<https://standards.iteh.ai>)

Document Preview

[SIST EN 17845:2024](https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024)

<https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024>

EN 17845:2023 (E)**1 Scope**

This document describes a method for the determination of the content of biocides in construction products, (either finished (dried) or in a ready-to-use state) and in eluates thereof, using liquid chromatography and tandem mass spectrometric detection (LC-MS/MS).

For content analysis liquid chromatography with UV-detection can also be used, if sufficient sensitivity and selectivity is ensured (see Annex A (normative)).

The method in this document is validated for the product types listed in Annex D (informative). For eluate analysis quantification limits of 0,1 µg/l can be achieved.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 16637-2, *Construction products: Assessment of release of dangerous substances — Part 2: Horizontal dynamic surface leaching test*

EN 16637-3, *Construction products: Assessment of release of dangerous substances — Part 3: Horizontal up-flow percolation test*

EN 16687:2023, *Construction products: Assessment of release of dangerous substances — Terminology*

EN 17087, *Construction products: Assessment of release of dangerous substances — Preparation of test portions from the laboratory sample for testing of release and analysis of content*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 16687:2023 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1**blank value**

test result obtained by carrying out the test procedure in the absence of a test portion

[SOURCE: EN 16687:2023, 3.3.1.10; modified – Note 1 to entry removed]

3.2**clean-up**

purification of a crude extract to remove interfering compounds

[SOURCE: EN 16687:2023, 3.2.2.27; modified – Note 1 to entry removed]

3.3**external standard**

known quantity of the target analytes that is measured in the same series as the solution to be measured and is used for identification and quantification

[SOURCE: EN 16687:2023, 3.2.2.20]

3.4**extract**

solution resulting from extraction of a sample with a solvent

[SOURCE: EN 16687:2023, 3.2.2.13]

3.5**extraction**

dissolution of substances in a solvent for subsequent chemical analysis

[SOURCE: EN 16687:2023, 3.2.2.14; modified – Note 1 to entry removed]

3.6**final extract**

solution that is obtained after clean-up of the Soxhlet extract through a purification stage

[SOURCE: EN 16687:2023, 3.2.2.18]

3.7**internal standard**

known quantity of a substance (where applicable deuterated) not present in the sample, which is added to the analysis sample in order to determine the recovery

[SOURCE: EN 16687:2023, 3.3.2.10]

3.8**laboratory sample**

sample or subsample(s) sent to or received by the laboratory

[SOURCE: EN 16687:2023, 3.2.2.1; modified – Notes to entry removed]

3.9**method detection limit****MDL**

lowest analyte concentration that can be detected with a specified analytical method including sample preparation with a defined statistical probability

[SOURCE: EN 16687:2023, 3.3.1.12; modified – Note 1 to entry removed]

3.10**product matrix**

main composition of the product dictating the manner of sample preparation and the type of digestion or extraction for later chemical analysis

[SOURCE: EN 16687:2023, 3.1.1.2; modified – Note 1 to entry removed]

EN 17845:2023 (E)**3.11****sample**

portion of material selected from a larger quantity of material

[SOURCE: EN 16687:2023, 3.2.1.5; modified – Notes to entry removed]

3.12**Soxhlet extract**

solution that is obtained after extraction of a solid subsample by the Soxhlet technique for determining organic compounds

[SOURCE: EN 16687:2023, 3.2.2.17]

3.13**Soxhlet extraction**

chemical pre-treatment of a solid subsample, where the organic compounds to be determined are dissolved by the Soxhlet technique

[SOURCE: EN 16687:2023, 3.2.2.16]

3.14**test portion**

analytical portion

amount of the test sample taken for testing/analysis purposes, usually of known dimension, mass or volume

[SOURCE: EN 16687:2023, 3.2.2.3; modified – Examples removed]

3.15**test sample**

analytical sample

sample, prepared from the laboratory sample, from which test portions are removed for testing or for analysis

[SIST EN 17845:2024](https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024)

<https://standards.iteh.ai/catalog/standards/sist/80aa00b1-7708-4715-9226-f4111b8103d0/sist-en-17845-2024>

[SOURCE: EN 16687:2023, 3.2.2.2]

4 Abbreviations

For the purposes of this document, the following abbreviations apply.

a.u.	Arbitrary units
DTL	Detection limit
HPLC	High performance liquid chromatography
	NOTE High pressure liquid chromatography is an (outdated) synonym.
ISTD	Internal standard solution
LC	Liquid chromatography
LOD	Limit of detection
MQL	Method quantification limit
MRL	Maximum residue limit

MRM	Multiple reaction monitoring
MS	Mass spectrometry; Mass selective detection
PTFE	Polytetrafluoroethylene
SPE	Solid phase extraction

5 Sample preparation

To obtain test samples for extraction (and analysis) guidance on sample preparation as specified in EN 17087 shall be applied.

Precautions shall be taken before and during transport of the laboratory sample as well as during the time in which the samples are preserved in the laboratory before being analysed, to avoid alteration of the sample (see CEN/TR 16220).

Extracts are susceptible to change due to physical or chemical reactions which can take place between the time of extraction and the analysis.

It is therefore essential to take the necessary precautions to minimize these reactions and in the case of many parameters to analyse the extract with a minimum of delay. The maximum delay is given in the respective analytical standards.

6 Principle

Quantification of biocides is performed by liquid chromatography with tandem mass spectrometric detection (LC-MS/MS), using electrospray ionization. Eluates are injected directly into the LC-MS/MS system.

Solid and pasty samples are extracted with methanol or a methanol/water mixture. Clean-up may be applied when necessary by solid phase supported liquid-liquid extraction.

To achieve the required selectivity the mass spectrometer is operated in the MRM mode.

7 Reagents

Use reagents of recognized analytical grade, unless otherwise specified. Take every precaution to avoid possible contamination of water, solvents, inorganic salts, etc.

7.1 Additive for LC-eluent depending on method used, e.g. ammonium formate, formic acid, acetic acid.

7.2 Water, HPLC quality.

7.3 Dichloromethane, for biocide analysis.

7.4 Methanol, LC-MS/MS quality.

7.5 Internal standard (ISTD) solutions in methanol, mass concentration $\rho = 10 \mu\text{g/ml}$ to $50 \mu\text{g/ml}^1$.

Use as much as possible isotope labelled internal standards, if available and obtainable at reasonable price. The internal standard solution should be added at the extraction step and to standard solutions.

If no isotope labelled internal standards are used, it is recommended to check whether matrix compounds are co-eluting with the ISTD to ensure reliable results. Losses of the ISTD during clean-up will result in an overestimation of analyte concentration. Such losses should thus be minimal.