



**SLOVENSKI STANDARD**  
**oSIST prEN 6052:2021**  
**01-januar-2021**

---

**Aeronavtika - Sistem zakovic, aluminijeva zlitina, strižni tip, palčne mere -  
Tehnična specifikacija**

Aerospace series - Rivet-collar-system, aluminium alloy, shear type, inch series -  
Technical Specification

Luft- und Raumfahrt - Passniet-Schließring-System aus Aluminiumlegierung für  
Scherbeanspruchung, Zöllige Reihe - Technische Lieferbedingungen

Série aérospatiale - Rivet-bague-système, alliage d'aluminium, type cisaillement, série  
en inches - Specification Technique

<https://standards.iteh.ai/catalog/standards/sist/3e2935f0-d8cb-47d9-a390-232531ac595/osist-pr-en-6052-2021>

**Ta slovenski standard je istoveten z: prEN 6052**

---

**ICS:**

49.025.20	Aluminij	Aluminium
49.030.60	Kovice	Rivets

**oSIST prEN 6052:2021**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[oSIST prEN 6052:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/3e2935f0-d8cb-47d9-a390-2225f31ac595/osist-pren-6052-2021>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**DRAFT**  
**prEN 6052**

November 2020

ICS 49.030.60

English Version

## Aerospace series - Rivet-collar-system, aluminium alloy, shear type, inch series - Technical Specification

Série aérospatiale - Rivet-bague-système, alliage  
d'aluminium, type cisaillement, série en inches -  
Specification Technique

Luft- und Raumfahrt - Passniet-Schließring-System aus  
Aluminiumlegierung für Scherbeanspruchung, Zöllige  
Reihe - Technische Lieferbedingungen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ASD-STAN.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

**Warning** : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## Contents

	Page
European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions.....	5
4 General requirements.....	5
5 Requirements for pins in aluminium alloy 7050T73.....	5
6 Requirements for collars in aluminium alloy 3003 and 6061.....	10
7 Certification and quality assurance.....	12
7.1 Qualification tests.....	12
7.2 Quality conformance inspection.....	12
7.3 Quality control records.....	12
7.4 Lot.....	12
8 Delivery.....	22
8.1 Unit type containers.....	22
8.2 Unit packages.....	22
9 Quality management system.....	22
Annex A (informative) Record of revisions.....	23
Bibliography.....	24

iTech STANDARD PREVIEW

(standards.iteh.ai)

oSIST prEN 6052:2021

[https://standards.iteh.ai/catalog/standards/sist/5c2995f0-d8cb-47d9-a390-](https://standards.iteh.ai/catalog/standards/sist/5c2995f0-d8cb-47d9-a390-2225b1ac595/osist-pren-6052-2021)

2225B1ac595/osist-pren-6052-2021

## European foreword

This document (prEN 6052:2020) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This document is currently submitted to the CEN Enquiry.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 6052:2021](https://standards.iteh.ai/catalog/standards/sist/3e2935f0-d8cb-47d9-a390-2225b1ac595/osist-pren-6052-2021)

<https://standards.iteh.ai/catalog/standards/sist/3e2935f0-d8cb-47d9-a390-2225b1ac595/osist-pren-6052-2021>

**prEN 6052:2020 (E)****1 Scope**

This document defines the requirements for qualification, acceptance, delivery and inspection of 100° countersunk head, 100° countersunk reduced head and protruding head close tolerance pins, shear type in aluminium alloy 7050T73 and collars of aluminium alloy 3003 and of aluminium alloy 6061T7 for use as permanent fasteners in aerospace applications.

**2 Normative references**

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3115, *Aerospace series — Aluminium alloy 7050-T73 — Wire for solid rivets —  $D \leq 10$  mm*

ANSI/ASQC-Z1.4<sup>1</sup>, *Sampling procedures and Tables for Inspection by Attributes*

ASME-B46.1<sup>1</sup>, *Surface texture (Surface Roughness, Waviness, and Lay)*

ASTM-B193<sup>2</sup>, *Standard Test Method for Resistivity of Electrical Conductor Materials*

ASTM-E1417<sup>2</sup>, *Standard Practice for Liquid Penetrant Testing*

ASTM-E8<sup>2</sup>, *Standard Test Method for Tension Testing of Metallic Materials*

ASTM-E92<sup>2</sup>, *Standard Test Methods for Vickers Hardness and Knoop Hardness of Metallic Materials*

ASTM-G-110<sup>2</sup>, *Standard Practice for Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminum Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution*

NASM1312<sup>3</sup>, *Fastener Test Methods*

QQ-A-430<sup>4</sup>, *Aluminium Alloy Rod and Wire, for Rivets and Cold Heading*

SAE AMS2644<sup>5</sup>, *Inspection Material, Penetrant*

---

<sup>1</sup> Published by: Department of Defense (DoD), the Pentagon, Washington, D.C., 20307, USA.

<sup>2</sup> Published by: American Society for Testing and Materials, 100 Barr Harbor Dr., West Conshohocken, P.A., 19428, USA.

<sup>3</sup> Published by: Aerospace Industries Association of America Inc. (AIA), 1250 Eye Street, N.W., Washington, D.C., 20005 3924, USA.

<sup>4</sup> Published by: Superintendent of documents, US Government Printing House, Washington, D.C., 20402, USA.

<sup>5</sup> Published by: Engineering Society for Advancing Mobility Land, Sea, Air and Space International (SAE), 400 Commonwealth Drive, Warrendale, P.A., 15096-0001, USA.

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 General requirements

The close tolerance pins and collars covered by this specification shall be of the types, sizes, configurations and materials designated by the part numbers specified on the applicable standards that refer to this specification.

### 5 Requirements for pins in aluminium alloy 7050T73

The requirements for 7050T73 aluminium alloy pins, shear type are given in Table 1. These requirements complement the requirements of all other standards or specifications referenced in the document of the pins and may be overridden only when specially instructed in the definition document.

Inspection tests given in Table 1 and Table 2 are mandatory (except as noted) on each lot as defined in 7.2 for the fastener manufacturer. Tests that are not mandatory for the fastener manufacturer may be applied by the receiving contractor.

**Table 1 — Requirements for pins in aluminium alloy 7050T73**

Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
5.1	General dimensions	The dimensions and any deviations in form and position, measured at ambient temperature, shall be within the limits specified in the standard part drawings and this procurement specification	Conventional measuring methods	According to Table 3	According to Table 5
5.2	Shank diameter	Underfill permissible, shall be within the specified shank diameter range	Standard micrometre 6,35 mm (¼") diameter		
5.3	Shank straightness	Refer to Table 8	Conventional measuring methods		
5.4	Sealant escape groove	Refer to Figure 3 and Table 10			
5.5	Head protrusion (100° heads)	According to standard part drawings	In accordance with EN pin standards		
5.6	Surface texture		Visual examination according to ANSI-B46.1		

## prEN 6052:2020 (E)

Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
5.7	Lubricants		According to applicable specification and visual examination		
5.8	Finish		Visual examination		
5.9	Product identification				
5.10	Delivery	Refer to Clause 8		N/A	
5.11	Shear strength	<p>Table 7 double shear values are applicable for pins having a grip of <math>2 \times</math> nominal diameter or greater for protruding head type and grip of <math>2,5 \times</math> nominal diameter or greater for flush head type. If the pin is too short to perform the shear test, a piece of wire of the same raw material lot heat treated with the fasteners shall be tested. The test wire shall have the same coating as for pins.</p> <p>Minimum shear strength test of fasteners is to be performed on pins or wire without cetyl alcohol lubrication applied.</p>	Test no 13 of NASM1312	According to Table 3	According to Table 6
5.12	Tensile strength	<p>Table 7 values are applicable for pins having a grip of <math>1,5 \times</math> nominal diameter or greater.</p> <p>Qualification and acceptance testing shall be performed with a <math>7^\circ</math> sloped surface (collar side) in minimum and maximum grip with collar according to collar standard.</p>	Test no. 8 of NASM1312		
5.13	Head dishing	<p>After installation in a clearance fit of 0,025 mm, head dishing of flush head pins shall not exceed 0,076 mm (see Figure 6).</p> <p>Testing shall be performed with a <math>7^\circ</math> sloped surface (collar side) in minimum and maximum grip.</p>	Test no. 8 of NASM1312		



Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
5.14	Pin break load	<p>Table 7 values are applicable.</p> <p>Tensile load shall be applied axially at a rate, which breaks the pin at a minimum of 4 s of load application.</p> <p>Test plate countersink for countersunk pins shall have 2° angular misalignment from the hole centreline.</p> <p>Test plate for protruding head pins shall have a 2° slope under the pin head.</p> <p>After evaluation of the pin break loads, head dishing of flush head pins shall not exceed 0,076 mm (see Figure 6).</p> <p>Cracks shall not be allowed in any location of the pin. The presence of cracks shall be determined by fluorescent penetrant inspection according to ASTM-E1417, method B or D sensitivity level 2 or higher.</p> <p>The penetrant materials used shall be according to SAE AMS2644. Examine all surfaces at 10 × to 30 × magnification.</p> <p>Penetrant inspection shall be performed prior to all surface coating and lubricating.</p>	<p>Test no. 8 of NASM1312</p> <p>ASTM-E1417</p>		
5.15	Preload	<p>Table 7 values are applicable to pins having a nominal grip of 1,5 × nominal diameter or greater.</p> <p>Qualification testing shall be performed with a 7° sloped surface (collar side) in minimum and maximum grip with a collar having low strength according to collar standard.</p> <p>Acceptance testing shall be performed with a 7° sloped surface (collar side) in minimum and maximum grip.</p>	Test no. 16 of NASM1312	According to Table 3	According to Table 6

## prEN 6052:2020 (E)

Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
5.16	Fatigue life	Average life 65 000 cycles, minimum life 45 000 cycles, loads according to Table 7.  Tests shall be performed on pins having a grip of 3 × nominal diameter.  Tests shall be performed in maximum grip condition.	Test no. 11 of NASM1312		N/A
5.17	Installation	Pins shall be pulled into 0,076 mm ± 0,005 mm interference fit in 2024T3 aluminium plate in maximum grip.  No premature breakage of the standard installation pintail shall occur. Installation load shall not exceed 90 % of minimum pin break load. Test to be performed using pins with longest grip length.	Use standard pneumatic installation tools and conventional measuring methods.  For all installation tests, there shall be a transition radius of 0,5 mm to 0,7 mm on edge of fastener hole (head side).  Tests shall be performed in maximum grip conditions with a 3° sloped surface (collar side).		N/A
5.18	Test collars	Test collars are specified in Table 7 unless stated otherwise	Refer to Table 7		
5.19	Material	7050-T73 aluminium alloy according to QQ-A-430 and EN 3115, shear strength 283 MPa to 324 MPa.	Verify composition	Each tenth lot from each mill	
			Verify mechanical properties	Each lot	

Clause	Characteristic	Technical requirement	Inspection and test method	Qualification Sampling	Acceptance Sampling
5.20	Discontinuities	<p>Discontinuities shall be permitted only as outlined in Figure 1 and Table 9.</p> <p>Specimens shall be prepared as shown in Figure 2. All surfaces shall be examined at 10 × to 30 × magnification. Indications shall be evaluated by metallurgical examination of cross sections at 50 × to 60 × magnification.</p> <p>Cracks shall not be allowed in any location of the pin.</p> <p>Penetrant inspection shall be performed prior to all surface coating and lubricating or with all coatings removed.</p>	<p>The presence of cracks shall be determined by fluorescent penetrant inspection according to ASTM-E1417, method B or D, sensitivity level 2 or higher.</p> <p>Penetrant materials used according to SAE AMS2644.</p>	According to Table 3	According to Table 6
5.21	Electrical conductivity (EC)	<p>Requirements for EC [% IACS] shall be as follows:</p> <p>EC ≥ 40 %: Lot is acceptable</p> <p>EC ≥ 38 % and &lt; 40 %: SCF test required</p> <p>EC &lt; 38 %: Lot is rejectable</p>	<p>ASTM-B193</p> <p>Test shall be performed on a wire from the same wire lot and heat treatment as the pin or on top of the pin head after smooth and flat machining (<math>R_A = 32\mu\text{m}</math>).</p>		
5.22	Stress corrosion factor (SCF)	<p>Test shall be required if EC ≥ 38 % and &lt; 40 % (see 5.21)</p> <p>SCF shall be &lt; 32 % and shall be calculated as follows:</p> $\text{SCF} = \text{ys} [\text{Pa}] - \text{EC} [\% \text{ IACS}]$ <p>Tensile yield strength shall be measured on a wire from the same wire lot and heat treatment as the pin.</p>	<p>ASTM-E8 (0,2 % offset method)</p>		
5.23	Intergranular corrosion	<p>Intergranular corrosion according to ASTM-G-110</p> <p>Localised intergranular corrosion shall not exceed 0,3 mm in depth. Average depth shall not exceed 0,2 mm.</p>	ASTM-G-110		
5.24	Microstructure	<p>Microstructure shall be free from bursts, voids and overheating</p>			