
Carbon based films — Classification and designations

Films à base de carbone — Classification et désignations

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 20523:2017](https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017)

<https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20523:2017

<https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Abbreviated terms.....	2
5 Deposition.....	2
6 Classification.....	2
6.1 General.....	2
6.2 Main carbon film groups.....	2
6.3 Classification criteria.....	2
6.3.1 General.....	2
6.3.2 Crystallinity.....	3
6.3.3 Ratio of CC sp ² to sp ³ hybridization.....	3
6.3.4 Hydrogen content.....	3
6.3.5 Content of additional elements.....	3
6.4 Coating architecture.....	3
6.4.1 Monolayer.....	3
6.4.2 Multilayer.....	3
6.4.3 Gradient layers.....	3
6.5 Classification table.....	3
7 Polymer-like carbon films.....	5
8 Amorphous carbon films.....	5
9 Diamond films.....	6
10 Graphite films.....	6
Annex A (informative) Deposition methods.....	7
Annex B (informative) Characterization methods.....	8
Bibliography.....	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by ISO/TC 107, *Metallic and other inorganic coatings*.

ISO 20523:2017

<https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017>

Introduction

Carbon based films are applied as a coating to modify the surface properties of parts or to synthesize the carbon material. The applications cover machine elements, tools, optics, electronics, medical engineering, microsystem technology, electrochemistry, acoustics, decoration and many more. Carbon based films exist as many different types, which differ significantly in their properties. It is therefore important to choose the right film type for a given application.

The aim of this document is to provide a consistent classification that covers all carbon based film types. Furthermore, the classified film types are named with a system of consistent designations. This enables both providers and users to compare different carbon based films on common nomenclature.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 20523:2017](#)

<https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 20523:2017

<https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017>

Carbon based films — Classification and designations

1 Scope

This document specifies classification, designations and short names for carbon based films. These are films in which carbon is the predominant constituent part and which are deposited by physical vapour deposition (PVD) or chemical vapour deposition (CVD) process. This includes amorphous carbon-based films, also called diamond-like carbon films (DLC), as well as CVD diamond films, graphite and polymer-like films.

This document is applicable to those films which are produced on an industrial scale. Additional carbon based films are under development.

This document refers to the material of carbon based films. It does not refer to the entire coating that can consist of a main functional layer with additional layers below or on top.

A layer can change in composition and/or material property over its thickness. Such layers are called gradient layers. The definitions in this document refer to non-gradient layers.

A carbon based film can include other elements like hydrogen, metal elements or others. Metal constituents can be included as metal carbides. Films with additional elements are only covered by this document if carbon is the predominant constituent part. Carbon incorporated as carbide, as can be present in metal-containing amorphous carbon films (a-C:Me, a-C:H:Me), does not count to this amount.

This document does not apply to the class of carbon materials such as fullerenes, carbon nanotubes and graphene.

ISO 20523:2017

<https://standards.iteh.ai/catalog/standards/sist/9fa71623-ec02-47b9-a4f6-07dae8522a7b/iso-20523-2017>

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

substrate

workpiece upon which deposition is to take place

3.2

nanocrystalline

polycrystalline form with a crystallite size in the range of 1 nm to 500 nm, measured on the growth side of the film

3.3

microcrystalline

polycrystalline form with a crystallite size in the range of 0,5 µm to 10 µm, measured on the growth side of the film

4 Abbreviated terms

PVD	physical vapour deposition
CVD	chemical vapour deposition

5 Deposition

Many different PVD and CVD methods are used to deposit carbon based films. The properties of a carbon film type may differ depending on the deposition method. A list of common deposition methods is given in [Annex A](#).

6 Classification

6.1 General

The classification of carbon based films is based on the material composition.

6.2 Main carbon film groups

Carbon based films are subdivided into the following main groups according to their chemical bonding state:

- **polymer-like carbon films**, where the carbon atoms are linked in chain formations, with crosslinks between the chains, and which contain a high amount of hydrogen (polymer-like);
- **amorphous carbon films**, where the carbon atoms are in a random, cross-linked arrangement (amorphous);
- **crystalline carbon films**, which are characterized by a regular arrangement of the carbon atoms, such that crystals are formed, subdivided into:
 - **diamond films**, where the carbon atoms are arranged in the diamond crystal lattice, and
 - **graphite films**, where the carbon atoms are arranged in the graphite crystal lattice.

Polymer-like carbon films may also be called plasma-polymer films.

The group of amorphous carbon films are also called diamond-like carbon films (DLC films).

From the main groups, further film types are classified according to the criteria described in [6.3](#).

6.3 Classification criteria

6.3.1 General

For the classification, the following properties and criteria are used:

- crystallinity;
- ratio of sp^2 to sp^3 of CC bonds;
- hydrogen content;
- content of additional elements.

Methods for the characterization of these properties are given in [Annex B](#).

6.3.2 Crystallinity

Carbon based films are non-crystalline (e.g. amorphous, polymer-like) or crystalline. If crystalline, they can vary in relation to their lattice type (diamond lattice, graphite lattice) and the crystallite size (nanocrystalline, microcrystalline).

6.3.3 Ratio of CC sp^2 to sp^3 hybridization

The carbon atoms of the applied carbon film are able to form different hybridization states (sp^3 , sp^2 and sp^1). Depending on the ratio of the different hybridization states, a different ratio of C-C-, C=C- and C \equiv C-bonds is realized. The ratio of CC sp^2 to sp^3 bonds of the carbon film types differs significantly.

6.3.4 Hydrogen content

Hydrogen may be present in carbon based films up to several 10 atomic %.

6.3.5 Content of additional elements

Besides hydrogen, carbon based films may contain additional elements, like metals (e.g. W, Ti) or doping elements (e.g. Si, O, N, F, B), to modify the properties. Films with additional elements are only covered by this document if carbon is the predominant constituent part. Carbon incorporated as carbide, as it may be present in a-C:Me or a-C:H:Me, does not count to this amount.

6.4 Coating architecture

6.4.1 Monolayer

A carbon based film can consist of one single layer. Diamond films, for example, are usually deposited as monolayer with no additional layers below or on top.

6.4.2 Multilayer

If a coating is prepared by subsequent layers of different compositions, it should be designated as "multilayer". All layers shall be taken into account for a full description of a coating. Amorphous carbon films for example, are usually deposited as multilayer coatings.

6.4.3 Gradient layers

A layer may change in composition and/or material property over its thickness. Such layers are called gradient layers. Amorphous carbon films, for example, are often deposited as gradient layers. A gradient composition is not included in the definitions of this document.

6.5 Classification table

[Table 1](#) shows the classification of carbon based films according to the criteria listed above, the film designations and the short names.