



Designation: A579/A579M – 04a(Reapproved 2009)

Standard Specification for Superstrength Alloy Steel Forgings¹

This standard is issued under the fixed designation A579/A579M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers requirements for forged steel shapes for highly stressed structural members requiring yield strengths in excess of 140 ksi [965 MPa].

1.2 This specification is not intended for applications limited by creep deformation.

1.3 Twenty-seven grades are covered by this specification. Selection will depend upon design, service conditions, and mechanical properties required.

1.4 Supplementary requirements are provided for use when additional testing or inspection is desired. These shall apply only when specified individually by the purchaser in the order.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.6 Unless the order specifies the applicable “M” specification designation, the material shall be furnished to the inch-pound units.

2. Referenced Documents

2.1 ASTM Standards:²

- A255 Test Methods for Determining Hardenability of Steel
- A275/A275M Practice for Magnetic Particle Examination of Steel Forgings
- A370 Test Methods and Definitions for Mechanical Testing of Steel Products
- A388/A388M Practice for Ultrasonic Examination of Steel Forgings
- A788/A788M Specification for Steel Forgings, General Requirements

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved April 1, 2009. Published April 2009. Originally approved in 1967. Last previous edition approved in 2004 as A579/A579M – 04a. DOI: 10.1520/A0579_A0579M-04AR09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- E3 Guide for Preparation of Metallographic Specimens
- E21 Test Methods for Elevated Temperature Tension Tests of Metallic Materials
- E45 Test Methods for Determining the Inclusion Content of Steel
- E112 Test Methods for Determining Average Grain Size
- E165 Practice for Liquid Penetrant Examination for General Industry

3. Ordering Information and General Requirements

3.1 In addition to the ordering information required by Specification A788/A788M, the purchaser shall include with the inquiry and order a detailed drawing, sketch, or written description of the forging.

3.2 Material supplied to this specification shall conform to the requirements of Specification A788/A788M, which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

3.3 If the requirements of this specification are in conflict with the requirements of Specification A788/A788M, the requirements of this specification shall prevail.

4. Materials and Manufacture

4.1 The steel shall be made in accordance with the Melting Process Section of Specification A788/A788M. A sufficient discard shall be made to secure freedom from injurious pipe and undue segregation.

4.2 The material shall be forged as close as practical to the specified shape and size.

4.3 The finished product shall be a hot-worked forging as defined by Specification A788/A788M.

4.4 *Heat Treatment Performed by Forging Supplier*—Forgings may be furnished in one of the following conditions as specified in the inquiry and purchase order (some conditions are not applicable to all grades):

- 4.4.1 Stress relieved,
- 4.4.2 Annealed,
- 4.4.3 Solution treated,
- 4.4.4 Solution treated and aged,
- 4.4.5 Normalized,

- 4.4.6 Normalized and tempered, or
4.4.7 Quenched and tempered.

4.5 *Heat Treatment Performed by Purchaser*—When final heat treatment is to be performed by the purchaser after machining or fabrication, or both, a capability heat treatment duplicating the purchaser's final heat treatment must be performed by the supplier on representative samples (see 6.3) to qualify the forgings. The results of these capability tests shall conform to the requirements of Table 1 and Table 2. See also Table 3.

5. Chemical Requirements

5.1 *Heat Analysis*—The heat analysis obtained from sampling in accordance with Specification A788/A788M shall comply with Table 4.

5.2 *Product Analysis*—The product analysis provisions of Specification A788/A788M may be used by the purchaser.

6. Mechanical Properties

6.1 The material shall conform to the mechanical properties specified in Table 1, when ordered to 4.4.4 or 4.4.7. For the other heat treatments specified in 4.4, the provisions of 4.5 apply.

6.2 Tension tests are required for all material ordered to this specification. However, room-temperature Charpy V-notch impact tests are required only for those grades which have minimum impact strength requirements listed in Table 2.

6.3 Tests shall be conducted in accordance with the latest issue of Test Methods and Definitions A370. The largest obtainable tension test specimen as specified in Test Methods and Definitions A370 shall be used. Impact specimens shall be the standard size, Charpy V-notch, as shown in the figure for the Charpy (Simple-Beam) Impact Test of Test Methods and Definitions A370. The use of subsize impact specimens requires prior purchaser approval.

TABLE 1 Minimum Tension Test Requirements

Grade	Yield Strength (0.2 % offset), ksi [MPa]	Tensile Strength, ksi [MPa]	Elongation ^A , %	Reduction of Area ^A , %
Quench and Tempered				
13, 21, 22, 23, 12, 12a	140 [965]	150 [1035]	13	40
13, 21, 22, 23, 11	160 [1100]	175 [1210]	12	36
13, 21, 22, 23, 31	180 [1240] ^B	190 [1310]	10	32
13, 21, 22, 23	200 [1380] ^B	210 [1450]	9	28
22 ^C , 23, 32, 33	225 [1550] ^B	250 [1720]	6	25
Air Hardening				
41	200 [1380] ^B	260 [1790]	9	30
41	225 [1550] ^B	280 [1930]	8	25
Martensitic Stainless				
51, 52, 53	140 [965]	175 [1210]	12	45
52	160 [1100]	220 [1520]	10	40
No. 1 Precipitation Hardening Stainless				
61	140 [965]	165 [1140]	12	50
61	160 [1100]	180 [1240]	10	45
61	180 [1240] ^B	200 [1380]	8	40
No. 2 Precipitation Hardening Stainless				
64	140 [965]	165 [1140]	12	25
64	160 [1100]	185 [1275]	10	25
64	180 [1240] ^B	210 [1450]	10	25
No. 3 Precipitation Hardening Stainless				
62	140 [965]	165 [1140]	6	25
62, 63	160 [1100]	180 [1240]	6	25
63	180 [1240] ^B	200 [1380]	6	25
63	200 [1380] ^B	225 [1550]	5	25
Maraging Steels				
74	160 [1100]	170 [1170]	15	65
75	180 [1240] ^B	190 [1310]	14	60
71	200 [1380] ^B	210 [1450]	12	55
72	250 [1720] ^B	255 [1760]	10	45
73	275 [1895] ^B	280 [1930]	9	40
Miscellaneous				
81	180 [1240] ^D	190 [1310]	13	45
82	200 [1380] ^D	210 [1450]	10	30
83 ^D	225 [1550] ^D	260 [1790]	7	20
83 ^E	250 [1720] ^D	280 [1930]	4	15
84	180 [1240] ^D	185 [1275]	14	45

^A See Note in Table 3.

^B Vacuum melting normally required to achieve list properties.

^C By agreement.

^D Bainitic.

^E Martensitic.