



Designation: E588 – 03(Reapproved 2009)

# Standard Practice for Detection of Large Inclusions in Bearing Quality Steel by the Ultrasonic Method<sup>1</sup>

This standard is issued under the fixed designation E588; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This practice covers a procedure for the rating of rectangular steel sections by immersion ultrasonic techniques. Its purpose is to provide information on the content of large inclusions or clusters of small inclusions for determining the suitability of a steel lot for bearing applications. This practice in no manner defines or establishes limits of acceptability.

1.2 For this document, large inclusions are defined in ultrasonic terms as those having a reflecting area equivalent to or larger than a  $\frac{1}{64}$ -in. diameter flat-bottom hole in a steel reference block of similar properties and thickness. In metallographic terms, large inclusions, defined in this way, are of approximately the same size as the smallest detectable sizes revealed by the macroscopic methods of Test Methods E45. In some cases, inclusions smaller than those described previously can be detected either individually or in clusters, depending on their type, chemical composition, orientation to the ultrasonic beam and distance from the sound entry surface of the specimen.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

E45 Test Methods for Determining the Inclusion Content of Steel

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.28 on Bearing Steels.

Current edition approved April 1, 2009. Published April 2009. Originally approved in 1976. Last previous edition approved in 2003 as E588 – 03. DOI: 10.1520/E0588-03R09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

E214 Practice for Immersed Ultrasonic Testing by the Reflection Method Using Pulsed Longitudinal Waves (Withdrawn 2007)<sup>3</sup>

E428 Practice for Fabrication and Control of Metal, Other than Aluminum, Reference Blocks Used in Ultrasonic Testing

E543 Specification for Agencies Performing Nondestructive Testing

E1316 Terminology for Nondestructive Examinations

### 2.2 ASNT Documents:

SNT-TC-1A Recommended Practice for Personnel Qualification and Certification in Nondestructive Testing<sup>4</sup>

ASNT-CP-189 Standard for Qualification and Certification of Nondestructive Testing Personnel<sup>4</sup>

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this practice, see Terminology E1316.

## 4. Basis of Application

4.1 *Agreements Between Using Parties*— In order for this practice to be effectively used, the following items require agreement between the using parties.

4.1.1 *Evaluation of Nondestructive Testing Agencies* —An agreement is required as to whether the nondestructive testing agency, as defined in Specification E543, must be formally evaluated and qualified to perform the examination. If such an evaluation is specified, a documented procedure such as Specification E543 shall be used as the basis for evaluation.

4.1.2 *Personnel Qualification*—Nondestructive testing (NDT) personnel shall be qualified in accordance with a nationally recognized NDT personnel qualification practice or standard such as ASNT CP-189, SNT-TC-1A, or a similar document. The practice or standard used and its applicable

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from the American Society for Nondestructive Testing, 1711 Arlington Plaza, P.O. Box 28518, Columbus, OH 43228-0518.

\*A Summary of Changes section appears at the end of this standard

revision shall be specified in the contractual agreement between the using parties.

4.1.3 *Search Unit Performance Tests*—Annex A1 defines the minimum manufacturer's specifications for search units to be used with this practice. The extent of testing and verification of these parameters to be performed by the manufacturer shall be specified in the contractual agreement between the using parties.

## 5. Summary of Practice

5.1 The general technique used is immersion ultrasonic testing by the reflection method using pulsed longitudinal waves such as described in Practice E214. Specific additional requirements for sample preparation, equipment operating parameters and calibration, and expression of results are delineated in this procedure. Special focused search units having operating characteristics as defined in Annex A1 are required.

## 6. Significance and Use

6.1 *Comparison with Other Inclusion Rating Methods*—Because the test is performed on a volumetric rather than a surface-examination basis, the ultrasonic method is inherently better able to detect infrequently occurring large inclusions or clusters of small inclusions than eddy current, magnetic particle, microscopical, or macroscopic examination procedures.

6.2 *Limitation of Inclusion Size and Type*—A limitation of the method is that it will not detect all inclusions. Inclusion chemistry, size, shape, location, and distribution may limit the ability of the method to provide indications distinct from those generated by the surrounding metallurgical structure. The recommended practice is only meaningfully applicable to examination of steel wherein the inclusion size and type are within the detection capabilities of the method. For steel wherein inclusion size, dispersion, and chemistry prevent optimum inclusion detection by ultrasonics, microscopical methods detailed in Test Methods E45 may be applied.

## 7. Interference

7.1 *Reflections from Multiple Inclusions*—An ultrasonic indication can represent the reflection from a single inclusion; however, it typically represents the vector summation of reflections from clusters of small inclusions contained within a volume of a few cubic millimetres.

7.2 *Response as a Function of Inclusion Type*—The individual inclusion reflections can have different amplitudes because of different inclusion characteristics. In addition, the individual reflections may have different phase characteristics when arriving at the search unit if the travel distances are different.

## 8. Apparatus

8.1 *Equipment Required*—An equipment system with the following components is needed to conduct this test: ultrasonic test instrument, search unit, a means of recording signals of

various amplitudes, a system reference block, instrument calibration block, and an immersion tank with suitable scanning accessories.

8.2 *Ultrasonic Instrument*—The ultrasonic instrument shall be capable of generating and receiving electrical pulses of 10-MHz frequency at levels compatible with the test requirements. It shall have both an A-scan presentation and an analog or digital output. It shall be the ultrasonic instrument manufacturer's responsibility that instruments supplied for use with this test meet the minimum requirements delineated in this recommended practice.

8.2.1 *Receiver Characteristics*—The center frequency shall be  $10 \pm 0.5$  MHz. The bandpass of the receiver shall be at least 1.3 MHz (3 dB points).

8.2.2 *Dynamic Range*—The dynamic range of the instrument shall permit detection of steel balls with a 16-to-1 diameter ratio at a given sensitivity. Balls shall be placed in water at the focal point of the search unit. Each size ball within this range shall give a significantly different amplitude of indication.

8.2.3 *Stability*—The signal amplitude of a usable full-scale indication shall not vary more than 5 % after 1 h of instrument warm-up, and preferably by less than 2 % (4-h test with air temperature being held to  $\pm 1.2^\circ\text{C}$  over a temperature range of 17.5 to 25.5°C).

8.2.4 *Sweep Length and Linearity*—Sweep length of oscilloscope presentation shall be capable of being adjusted to represent 1 mm = 1.27 mm of steel. A minimum of 80 mm of the sweep display shall be linear to within 5 % of full scale. The signal amplitude of an indication from a target shall not vary more than  $\pm 4$  % over the gated portion of the sweep employed in calibration and testing.

8.2.5 *Repetition Rate*—The repetition rate of the pulser shall not be less than 500 pulses per second.

8.3 *Search Units*—Ultrasonic search units for this test shall be spherically focused immersion-type units. Uniform performance characteristics of search units are critical for obtaining reproducible test measurements. (See Annex A1, which delineates search unit performance characteristics to be met by search unit manufacturers.) Performance characteristics of search units requiring consideration are: the uniformity of focal distance in water, center frequency, frequency spectrum, lens radius, width of field, and beam symmetry.

8.3.1 *Focal Length*—A focused beam of radiated ultrasonic energy is recommended to provide lateral resolution of small defects and to improve testing sensitivity in the region near the focal point. The focal length of a search unit is defined in this discussion as the distance in water, on the search unit axis, between the search unit and the surface of a 1/2-in. or 12-mm diameter ball target at which the highest reflection amplitude indication is obtained. Different focal length transducers may be used to obtain optimum response at selected distances below the test sample surface. (Variation of search unit-to-specimen surface water path would also affect the focal point within the test sample.)

8.3.2 *Search Unit Characteristics*—Search units generally employed have the following frequency and focal length as purchased:

Frequency  
10 ± 0.5 MHz

Focal Length in Water  
8.2 ± 0.3 in. (208.3 ± 7.6 mm)

8.3.3 *Beam Symmetry*—Each search unit should be rotated on its ultrasonic beam axis (not necessarily geometric axis) until a particular circumferential orientation is found which gives a maximum severity, or count, from the system reference block. This search unit orientation shall be identified and employed in subsequent tests. Search units that exhibit variations in indication amplitude in excess of 15 % during rotation shall not be considered satisfactory for the test. There are other methods, such as optimum response over a precision and uniform taut wire, that have been found to be usable.

8.3.4 *Performance*—The performance capabilities of all new search units shall be verified by an actual test on the system reference block. The data obtained for new search units should be compared with that obtained for other search units having the same specifications and tested under identical conditions.

8.4 *Immersion Tank and Accessories*—An immersion tank with associated scanning and indexing facilities shall be used.

8.4.1 *Search Unit Angulation*—The tank shall be provided with a manipulator capable of continuously angulating the search unit in two vertical mutually perpendicular planes permitting the required normalization.

8.4.2 *Scanning and Indexing*—The tank bridge and carriage assemblies shall provide X-Y motion to the search unit. The scanning shall be parallel or perpendicular (depending on the procedure) to the test specimen axis and the indexing shall be perpendicular to the scanning.

8.4.3 *Test Specimen Mounting*—The tank shall be provided with fixturing permitting the mounting of the entry surface of the test specimen parallel to the bridge travel so that the distance between search unit and specimen remains constant within ±<sup>1</sup>/<sub>64</sub> in. (0.4 mm).

8.4.4 *Couplant*:

8.4.4.1 The inspection solution shall consist of tap or distilled water to which a wetting agent has been added to disperse air bubbles. The pH of the water shall be maintained within 7½ to 8½. Rust preventives may also be added. All chemical additives shall be held within concentrations that do not adversely affect test performance. Water temperature must be held between 19.5 and 25.5°C. It is important that excessive thermal gradients do not exist between the search unit and the calibration standards.

8.4.4.2 A means of circulating the immersion inspection solution shall be employed, when necessary, to dissipate thermal gradients.

8.5 *Readout Equipment*—Various types of instrumentation have been employed in conjunction with ultrasonic instruments for many years to determine the number of occurrences of various amplitude indications. These include level counters, pulse counters, integrators, strip chart recorders, B-scan recorders, C-scan recorders, memory oscilloscopes, and computer techniques. With pulse counters, both repetition rate and scanning speed must be held within a 5 % tolerance and, preferably, 2 %.

8.6 *System Reference Block*—A system reference block (defined dimensionally in Section 9.2) is required for initial

adjustments and operational testing of the equipment. This sample should be selected to provide reflection signals at all counting levels. Depth distribution of inclusions in the selected reference block should make its response characteristics relatively insensitive to minor focal length variations between different search units. The reference block should give a minimum change in total counts of 10 % for each 10 % increase or decrease in amplitude setting. A maximum of 30 % change in count for each 10 % change in amplitude setting should not be exceeded. It should be suitably protected from corrosion to assure its longevity.

## 9. Test Specimens

9.1 *General*—Test specimens must be either in the rolled or forged condition. If forged, upset forging is prohibited in order to maintain the rolling direction. Care should be taken not to overheat the forging to avoid spurious ultrasonic indications. Specimen location and frequency shall be as agreed upon between the supplier and the purchaser.

9.2 *Specimen Size and Shape*—Specimens shall have a minimum cross-sectional dimension after preparation of 3½ in. (88.9 mm). The area scanned shall be sufficient to permit testing of a minimum of 25 in.<sup>3</sup> (410 cm<sup>3</sup>) of the specimen. The tested volume equals the scanned area multiplied by the gated depth. If special consideration is given, thinner samples may be tested.

9.3 *Entry Surface Finish*—The test surface through which the sound enters the specimen shall be machined and ground. This finish in any direction over the surface shall be preferably 10 to 80 μin. (0.25 to 2.0 μm). Final material removal may require a dressed grinding wheel to avoid spurious, near-surface indications. All four sides are to be ground.

9.4 *Heat Treatment*—Thermal conditioning of the specimens is required to minimize acoustic anomalies. Typical heat treatment may consist of normalizing or quenching and tempering, depending on steel type, to meet the ultrasonic penetrability requirement of Section 9.5. Certain steels may require special thermal treatment such as a double temper to obtain suitable acoustic properties.

9.5 *Ultrasonic Penetrability*—The ultrasonic penetrability shall be determined to be suitable for the inspection. The penetrability is acceptable if the third back reflection of the specimen is 25 % of full screen height, over the center of the billet specimen, at standard test conditions and test sensitivity.

## 10. Procedure

10.1 *General*:

10.1.1 *Operating Frequency*—The operating frequency for most bearing steels is 10 MHz. Ten megahertz is recommended as the highest practical frequency available within existing manufacturing capabilities to produce search units with uniform performance characteristics. Higher frequencies give better resolution, while lower frequencies give better penetration.

10.1.2 *Normalizing Search Unit*—Normalizing the search unit beam to the entry surface is a precise adjustment and requires extreme care. Normalizing can be accomplished over

billet specimens with parallel ground sides by adjusting for a maximum first far field back reflection in an area where no material discontinuities are present to distort the ultrasonic beam. An alternative method that has been found useful is to maximize the far field reflections from a hardened steel plate with parallel ground sides, such as a 58 to 64 HRC hardness test block, placed on top of the ground billet surface.

10.1.3 *Water Distance*—The water distance between the search unit and entry surface shall not be less than  $1 \pm \frac{1}{16}$  in. (25.4  $\pm$  1.6 mm) for every 4 in. (102 mm) of specimen thickness. In no case should the water distance be less than  $1 \pm \frac{1}{16}$  in.

10.1.4 *Monitoring Gates*—Either single or multiple gates may be employed.

10.1.5 *Scanning of Specimen*—Scanning of the specimen must be perpendicular to the rolling direction with a scan index of 0.050 in. (1.27 mm). Scanning closer than  $\frac{1}{2}$  in. (12.7 mm) to the prepared surface edge should be avoided because of false echoes from the edge. Two adjacent sides are to be inspected. Test specimens must be at room temperature before scanning.

10.1.6 *Scanning Speed*—Permissible scanning speed is a function of counter response and instrument repetition rate. A generally accepted speed is 4 in. (101.6 mm)/s. It shall be limited to that which gives a recorded evaluation of a sample within 5 % of that obtained when the sample is scanned at less than 1 in. (25.4 mm)/s, or one third of normal operating speed, whichever is the slower.

10.1.7 *Sensitivity*—The test sensitivity shall not produce background material indications exceeding an amplitude of one half of the lowest counting level.

10.1.8 *Operational Performance*—Periodically check overall equipment performance by conducting a test on the system reference block specimen. The deviation permitted shall not exceed the variation in counts obtained by altering the electronic gain by  $\pm 10$  %. For practical purposes, the  $\pm 10$  % electronic gain shall be defined as equivalent to the difference in response from ball targets varying by 10 % in diameters.

10.2 *Description of Method*—This method is applicable to the determination of the relative cleanliness of bearing-quality steel. Equipment, calibration, and method of analyzing test results have been made as simple as possible within the limits of having a workable test. An immersed ultrasonic test is conducted with a 10-MHz focused search unit, three-level type counter to indicate test results, steel balls to establish counter levels, an instrument calibration block, and a system reference block specimen. The specimen is scanned in a direction perpendicular to the rolling direction, and counts are recorded only when the search unit passes transversely over either a single inclusion or a cluster of inclusions which give rise to a discrete ultrasonic indication exceeding a counting level.

#### 10.2.1 *Special Equipment and Accessories* :

10.2.1.1 A three-level pulse counter having separate adjustable thresholds for each level shall be used to determine the number of occurrences of various amplitude indications. The input circuits to the counters shall employ sufficient filtering to eliminate counter operation from extraneous high-frequency signals. The equipment shall have sufficient hysteresis to prevent counting spurious variations (jitter).

#### 10.2.2 *Calibration Standards*:

10.2.2.1 Counter calibration requires a set of three ball targets with size ratio of 12:7:4. Highly polished stainless steel ball sets with a surface roughness of 2  $\mu$ m. (.05 mm) Ra maximum and with diameters of  $\frac{3}{4}$  in.,  $\frac{7}{16}$  in., and  $\frac{1}{4}$  in., or 12 mm, 7 mm, and 4 mm, may be employed. (A  $\frac{1}{2}$  in. ball is an acceptable substitute for the  $\frac{7}{16}$  in. ball.)

10.2.2.2 Test instrument calibration is performed with a 10-mm hemispherically shaped hole instrument calibration block described in **Annex A2**. This reference target shall be 1.7 in. (43.2 mm) below the entry surface of the standard.

10.2.2.3 A system reference block specified in **8.6** shall be employed to verify instrument calibration and to cross reference equipment performance between a number of instruments.

#### 10.2.3 *Equipment Calibration Procedures* :

10.2.3.1 Equipment calibration is a two-step procedure that requires counter level calibration followed by ultrasonic test instrument sensitivity calibration.

10.2.3.2 Adjust the three-level counter using a set of highly polished stainless steel balls with a surface roughness of 2  $\mu$ m. (.05  $\mu$ m) Ra maximum and having a diameter ratio of 12:7:4. Position the search unit above the largest ball at a distance for maximum signal amplitude corresponding to the focal distance specified in **8.3.2**. Adjust the test instrument sensitivity to produce a signal at 80 % of full screen height. At this setting, record the signal amplitude and adjust the level-three counter to count. This procedure determines the Level 3 (high) amplitude counting threshold. Without changing the test instrument sensitivity setting, position the search unit at its focal distance over the medium- and small-size balls. Adjust counter thresholds similar to the procedure for Level 3 and record the signal amplitudes for the Level 2 (medium) and Level 1 (low) amplitude counting thresholds.

10.2.3.3 The instrument test sensitivity is established by using a 10 mm sensitivity block as defined in **Annex A2**. Center the transducer over the hemispherically shaped hole of the sensitivity block using a water path distance between 1.1 to 1.7 in. Adjust for maximum signal strength in the XY axes. In the Z axis, adjust the water path distance between 1.1 and 1.7 in. to maximize signal strength. Adjust instrument sensitivity to the sensitivity of the Level 3 threshold (as established in **10.2.3.2**). Increase the instrument sensitivity by 24dB for billet inspection.

10.2.4 *Cross Referencing Between Equipment Users*—If cross referencing of system reference blocks has been performed with other users of the method (as delineated in **Annex A3**), a fine adjustment of sensitivity (not to exceed  $\pm 1.5$  dB ) may be performed to discount variations in search unit response, counter hysteresis, and other instrumentation variables

#### 10.2.5 *General Instructions and Procedures* :

10.2.5.1 Adjust the water path distance so that the search unit face is located  $1 \pm \frac{1}{16}$  in. (25.4  $\pm$  1.6 mm) from the test specimen entry surface. This adjustment may be performed with a rule, reference spacer, or by use of calibrated water path measurements on the test instrument display.