



Designation: D5144 – 08^{ε1}

Standard Guide for Use of Protective Coating Standards in Nuclear Power Plants¹

This standard is issued under the fixed designation D5144; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—The title of Guide D5163 was corrected editorially in April 2009.

INTRODUCTION

Protective coatings (paints) have been used extensively in the nuclear industry to protect the surfaces of facilities and equipment from corrosion and contamination by radioactive nuclides in accordance with ALARA. In the absence of a standard method of selecting, testing, and evaluating coatings, many sites evaluated paints by empirical tests to determine which were useful in their particular operation. Understandably, the methods of testing were not uniform throughout the industry. It has been very difficult, consequently, to compare the results obtained at one site with those obtained at another. Standard tests whereby industrial (nuclear) users of paints systematically prepare specimens and subject them to selected evaluations, thus permitting uniform comparisons, are advantageous, internationally as well as domestically.

The designer of light water-moderated nuclear reactor systems must consider the possibility of a Design Basis Accident (DBA) and the subsequent events which might lead to the release or expulsion of a fraction of the fission-product inventory of the core to the reactor containment facility. Engineered safety features, principally a reactor containment facility, are provided to prevent the release of fission products to the biological environment during and after this improbable event. The design, fabrication, quality assurance, and testing of these engineered safety features ensure reliable operation and safety under all anticipated conditions.

Large areas of the reactor-containment facility are painted with safety-related coatings. If severe delamination, peeling, or flaking causes significant portions of the coating to be discharged into the common water reservoir, the performance of the safety systems could be seriously compromised by the plugging of strainers, flow lines, pumps, spray nozzles, and core coolant channels. Safety-related coatings may also exist outside of the reactor-containment.

This guide is the result of a comprehensive examination of the experience and data that have been developed on protective coatings in the nuclear industry over approximately 40 years. Standards pertaining to nuclear coatings have historically been covered by ANSI N5.12, ANSI N101.2, and ANSI N101.4. Responsibility for updating, rewriting, and issuing appropriate ANSI replacement standards has been transferred to ASTM, specifically ASTM Committee D33, on Protective Coating and Lining Work for Power Generation Facilities.

The objective of this guide is to provide a common basis on which protective coatings for the surfaces of nuclear power generating facilities may be qualified and selected by reproducible evaluation tests. This guide also provides guidance for application and maintenance of protective coatings. Quality assurance in the nuclear industry is a mandatory requirement for all aspects of safety-related nuclear coatings work. Licensees of nuclear power plants are required to determine if coated surfaces are within the scope of 10CFR50.65, “The Maintenance Rule.” Any coated surfaces found to be within the scope of 10CFR50.65 must satisfy the requirements of 10CFR50.65. ASME Section XI, Subsection IWE contains the requirements for periodic evaluation of the reactor-containment steel pressure boundary.

1. Scope

1.1 This guide provides a common basis on which protective coatings for the surfaces of nuclear power generating facilities may be qualified and selected by reproducible evaluation tests. This guide also provides guidance for application and maintenance of protective coatings. Under the environmental operating and accident conditions of nuclear power generation facilities, encompassing pressurized water reactors (PWRs) and boiling water reactors (BWRs), coating performance may be affected by exposure to any one, all, or a combination of the following conditions: ionizing radiation; contamination by radioactive nuclides and subsequent decontamination processes; chemical and water sprays; high-temperature high-pressure steam; and abrasion or wear.

1.2 The content of this guide includes:

	Section
Referenced Documents	2
Terminology	3
Significance and Use	4
Coating Material Testing	5
Thermal Conductivity	5
Surface Preparation, Coating Application, and Inspection for Shop and Field Work	6
Quality Assurance	7
Keywords	8

1.2.1 In addition, this guide addresses technical topics within ANSI N5.12 and ANSI N101.2 that are covered by separate ASTM standards, for example, surface preparation, (shop and field) and coating application, (shop and field).

1.2.2 Applicable sections of this guide and specific acceptance criteria may be incorporated into specifications and other documents where appropriate.²

1.3 The values stated in inch-pound units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:³

C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

¹ This guide is under the jurisdiction of ASTM Committee D33 on Protective Coating and Lining Work for Power Generation Facilities and is the direct responsibility of Subcommittee D33.02 on Service and Material Parameters.

Current edition approved Nov. 15, 2008. Published January 2009. Originally approved in 1991. Last previous edition approved in 2000 as D5144 – 00. DOI: 10.1520/D5144-08E01.

² Certain ASTM standards are available in compilation form (which includes this guide), as *Compilation of ASTM Standards for Use of Protective Coating Standards in Nuclear Power Plants* for expedient reference and usage by personnel involved in nuclear coating work.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D3843 Practice for Quality Assurance for Protective Coatings Applied to Nuclear Facilities
- D3911 Test Method for Evaluating Coatings Used in Light-Water Nuclear Power Plants at Simulated Design Basis Accident (DBA) Conditions
- D3912 Test Method for Chemical Resistance of Coatings and Linings for Use in Nuclear Power Plants
- D4060 Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser
- D4082 Test Method for Effects of Gamma Radiation on Coatings for Use in Nuclear Power Plants
- D4227 Practice for Qualification of Coating Applicators for Application of Coatings to Concrete Surfaces
- D4228 Practice for Qualification of Coating Applicators for Application of Coatings to Steel Surfaces
- D4537 Guide for Establishing Procedures to Qualify and Certify Personnel Performing Coating and Lining Work Inspection in Nuclear Facilities
- D4538 Terminology Relating to Protective Coating and Lining Work for Power Generation Facilities
- D4541 Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers
- D5139 Specification for Sample Preparation for Qualification Testing of Coatings to be Used in Nuclear Power Plants
- D5163 Guide for Establishing a Program for Condition Assessment of Coating Service Level I Coating Systems in Nuclear Power Plants
- D7167 Guide for Establishing Procedures to Monitor the Performance of Safety-Related Coating Service Level III Lining Systems in an Operating Nuclear Power Plant
- D7230 Guide for Evaluating Polymeric Lining Systems for Water Immersion in Coating Service Level III Safety-Related Applications on Metal Substrates
- D7234 Test Method for Pull-Off Adhesion Strength of Coatings on Concrete Using Portable Pull-Off Adhesion Testers
- D7491 Guide for Management of Non-Conforming Coatings in Coating Service Level I Areas of Nuclear Power Plants
- E84 Test Method for Surface Burning Characteristics of Building Materials
- E684 Practice for Approximate Determination of Current Density of Large-Diameter Ion Beams for Sputter Depth Profiling of Solid Surfaces
- E1461 Test Method for Thermal Diffusivity by the Flash Method
- E1530 Test Method for Evaluating the Resistance to Thermal Transmission of Materials by the Guarded Heat Flow Meter Technique

2.2 Other Standards:

- ANSI N5.12 Protective Coatings (Paints) for the Nuclear Industry⁴
- ANSI N101.2 Protective Coatings (Paints) for Light Water Nuclear Reactor Containment Facilities⁴
- ANSI N101.4 Quality Assurance for Protective Coatings

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

- Applied to Nuclear Facilities⁴
ASME Boiler and Pressure Vessel Code (BPVC) Section XI, Rules for Inservice Inspection of Nuclear Power Plant Components, Subsection IWE Requirements for Class MC and Metallic Liners of Class CC Components of Light-Water Cooled Power Plants⁵
EPRI 1003102 (November 2001) Guideline on Nuclear Safety-Related Coatings Revision 1 (formerly TR-109937)⁶
10CFR50 Appendix B: Title 10, Chapter 1, Energy, Part 50, Domestic Licensing of Production and Utilization Facilities, Appendix B, Quality Assurance Criteria for Nuclear Power Plants and Fuel Reprocessing Plants⁷
10CFR50.65 Requirements for Monitoring the Effectiveness of Maintenance at Nuclear Power Plants⁷
Guide 1.54 Regulatory/(1973) Quality Assurance Requirements for Protective Coatings Applied to Water-Cooled Nuclear Power Plants⁷
USNRC Standard Review Plan 6.1.2 Protective Coating Systems (Paints) Organic Materials⁷
USNRC Regulatory Guide 8.8 Information Relevant to Ensuring that Occupational Radiation Exposures At Nuclear Power Stations Will Be As Low As Is Reasonably Achievable⁷

3. Terminology

3.1 *Definitions*—Definitions for use with this guide are shown in Terminology **D4538** or other applicable standards.

4. Significance and Use

4.1 This guide addresses the concerns of Regulation Guide 1.54 and USNRC Standard Review Plan 6.1.2, and the replacement of ANSI Standards N5.12, N101.2, and N101.4. This guide covers coating work on previously coated surfaces as well as bare substrates. This guide applies to all coating work in Coating Service Level I and III areas (that is, safety-related coating work). Applicable sections of this guide may also be used to evaluate and select protective coatings for Coating Service Level II areas where deemed appropriate by the licensee.

4.2 The testing referenced in this guide is particularly appropriate for safety-related coatings inside the reactor-containment. Other test methods may be used for assessing the suitability for service of safety-related coatings outside the reactor-containment. Criteria for qualification and performance monitoring of Coating Service Level III coatings shall be addressed in job specifications. Guidance for selecting and performance monitoring of Coating Service Level III coatings is provided Guides **D7230** and **D7167** respectively, and Sections 4.4 and 4.5 of EPRI 1003102 (formerly TR-109937).

4.3 Users of this guide must ensure that coatings work complies not only with this guide, but also with the licensee's plant-specific quality assurance program and licensing commitments.

4.4 *Safety-Related Coatings:*

4.4.1 The qualification of coatings for Coating Service Levels I and III are different even though they are both safety-related. This guide provides the minimum requirements for qualifying Coating Service Level I coatings and also provides guidance for additional qualification tests that may be used to evaluate Coating Service Level I coatings. This guide also provides guidance concerning selection of Coating Service Level III coatings.

4.4.2 *Coating Service Level I Coatings:*

4.4.2.1 All Coating Service Level I coatings must be resistant to the effects of radiation and must be DBA qualified. The test specimens shall be prepared, irradiated and DBA tested and evaluated in accordance with the requirements of:

- (a) Test Method **D3911** or plant specific requirements as applicable,
- (b) Test Method **D4082**, and
- (c) Specification **D5139**.

4.4.2.2 In addition to the requirements of 4.4.2.1, Coating Service Level I coatings may be evaluated for additional qualities or may require application controls when deemed applicable by the job specifications or licensing commitments. The following documents provide guidance for application, possible additional testing or for the further evaluation of Coating Service Level I coatings when applicable:

- (a) Test Method **C177**,
- (b) Practice **D3843**,
- (c) Test Method **D3912**,
- (d) Test Method **D4060**,
- (e) Practice **D4227**,
- (f) Practice **D4228**,
- (g) Guide **D4537**,
- (h) Test Method **D4541**,
- (i) Test Method **E84**,
- (j) Test Method **E1461**, and
- (k) Test Method **E1530**.

4.4.2.3 Condition assessment and management of Coating Service Level I coatings is also required by the licensee to maintain the coatings following the initial application and subsequent repairs. The following documents provide guidance for the monitoring and management of the Coating Service Level I coatings:

- (a) Guide **D5163** and
- (b) Guide **D7491**.

4.4.3 *Coating Service Level III Coatings:*

4.4.3.1 Coating Service Level III coatings must be evaluated for use in accordance with the requirements of plant licensing commitments and the job specifications. Coating Service Level III coatings may include linings used in areas such as service water systems, essential cooling water heat exchanger heads and emergency diesel generator air intakes. There are *no* specific testing or qualification requirements included in this guide for Coating Service Level III coatings or linings. Testing and evaluation of Coating Service Level III

⁵ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

⁶ Available from EPRI Distribution Center, 207 Coggins Drive, P.O. Box 23205, Pleasant Hills, CA 94523 (510) 934-4212.

⁷ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.