



# SLOVENSKI STANDARD

## SIST-TS CEN/TS 17201:2019+AC:2019

01-februar-2019

Nadomešča:  
SIST-TS CEN/TS 17201:2019

---

**Gradbeni proizvodi - Ocenjevanje sproščanja nevarnih snovi - Vsebnost anorganskih snovi - Metode za analizo po razklopu z zlatotopko (vključno s popravkom AC)**

Construction products- Assessment of release of dangerous substances - Content of inorganic substances - Methods for analysis of aqua regia digests

**iTeh STANDARD PREVIEW**

Bauprodukte - Bewertung der Freisetzung von gefährlichen Stoffen - Gehalt an anorganischen Stoffen - Verfahren zur Analyse von Königswasserauflösungen

[SIST-TS CEN/TS 17201:2019+AC:2019](#)

Produits de construction- Evaluation de l'émission de substances dangereuses - Contenu des substances inorganiques - Méthodes d'analyse des digestats d'eau régale

**Ta slovenski standard je istoveten z: CEN/TS 17201:2018+AC:2018**

---

**ICS:**

13.020.99	Drugi standardi v zvezi z varstvom okolja	Other standards related to environmental protection
91.100.01	Gradbeni materiali na splošno	Construction materials in general

**SIST-TS CEN/TS 17201:2019+AC:2019 en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST-TS CEN/TS 17201:2019+AC:2019](https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019)

<https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019>

TECHNICAL SPECIFICATION  
SPÉCIFICATION TECHNIQUE  
TECHNISCHE SPEZIFIKATION

**CEN/TS 17201:2018+AC**

December 2018

ICS 91.100.01

Supersedes CEN/TS 17201:2018

English Version

**Construction products: Assessment of release of  
dangerous substances - Content of inorganic substances -  
Methods for analysis of aqua regia digests**

Produits de construction: Evaluation de l'émission de  
substances dangereuses - Contenu des substances  
inorganiques - Méthodes d'analyse des digestats d'eau  
régale

Bauprodukte: Bewertung der Freisetzung von  
gefährlichen Stoffen - Gehalt an anorganischen Stoffen  
- Verfahren zur Analyse von  
Königswasserauflösungen

This Technical Specification (CEN/TS) was approved by CEN on 23 March 2018 for provisional application and includes Corrigendum issued by CEN on 19 December 2018.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	3
Introduction .....	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions .....	6
4 Abbreviations .....	8
5 Sample pre-treatment .....	8
6 Selection of suitable analytical test method.....	8
6.1 Table of test methods .....	8
6.2 General validation information .....	8
6.3 Content in mg/kg.....	9
7 Method performance .....	10
8 Expression of results.....	10
9 Test report.....	10
10 Test report.....	10
11 Test performance.....	11
Annex A (informative) Summary of validation results for other matrices.....	12
A.1 General.....	12
A.2 Interlaboratory studies.....	12
A.2.1 Results of the interlaboratory study for EN 13346.....	12
A.2.2 Results of the interlaboratory study for EN 13650.....	14
A.2.3 Results of the interlaboratory study for EN 13657.....	15
A.2.4 Background information in the interlaboratory study for EN 16174.....	17
Annex B (informative) Indicative values for MDL .....	21
Bibliography.....	22

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST-TS CEN/TS 17201:2019+AC:2019

<https://standards.cen.eu/catalog/standards/sist/17201-2019ac/17201-2019ac-2019>

77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019

## European foreword

This document (CEN/TS 17201:2018+AC:2018) has been prepared by Technical Committee CEN/TC 351 “Construction Products - Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 17201:2018.

This document includes the corrigendum 1 which replaces the reference to CEN/TS 17195 with CEN/TS 17196 in Clause 2 and Clause 5.

The start and finish of text introduced or altered by corrigendum is indicated in the text by tags AC AC

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

[SIST-TS CEN/TS 17201:2019+AC:2019](https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019)

<https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019>

**CEN/TS 17201:2018+AC:2018 (E)****Introduction**

Following an extended evaluation of available methods for content analysis in construction products (CEN/TR 16045, [1]) it was concluded that eluate analysis methods are very similar to analytical methods used to determine content after digestion of a solid matrix.

This document has a similar structure as CEN/TS 17195 *Construction products: Assessment of release of dangerous substances – Analysis of inorganic substances in eluates*.

This Technical Specification is part of a modular horizontal approach which was adopted in CEN/TC 351. 'Horizontal' means that the methods can be used for a wide range of materials and products with certain properties. 'Modular' means that a test standard developed in this approach concerns a specific step in assessing a property and not the whole chain of measurement (from sampling to analyses). Beneficial features of this approach are that modules can be replaced by better ones without jeopardizing the standard chain and duplication of work of in different Technical Committees for Products can be avoided as far as possible. Similar standards have been developed for content determination in different types of matrices, see Annex A.

The modules that relate to the standards developed in CEN/TC 351 are specified in CEN/TR 16220 [2], which distinguishes between the modules. This Technical Specification belongs to the analytical step.

The use of modular horizontal standards implies the drawing of test schemes as well. Before executing a test on a certain construction product to determine certain characteristics it is necessary to draw up a protocol in which the adequate modules are selected and together form the basis for the entire test procedure.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST-TS CEN/TS 17201:2019+AC:2019](https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019)

<https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-77a2746aa444/sist-ts-cen-ts-17201-2019ac-2019>

## 1 Scope

This Technical Specification specifies analytical methods for the determination of major, minor and trace elements in aqua regia digests of construction products. It refers to the following 67 elements: Aluminium (Al), antimony (Sb), arsenic (As), barium (Ba), beryllium (Be), bismuth (Bi), boron (B), cadmium (Cd), calcium (Ca), cerium (Ce), cesium (Cs), chromium (Cr), cobalt (Co), copper (Cu), dysprosium (Dy), erbium (Er), europium (Eu), gadolinium (Gd), gallium (Ga), germanium (Ge), gold (Au), hafnium (Hf), holmium (Ho), indium (In), iridium (Ir), iron (Fe), lanthanum (La), lead (Pb), lithium (Li), lutetium (Lu), magnesium (Mg), manganese (Mn), mercury (Hg), molybdenum (Mo), neodymium (Nd), nickel (Ni), palladium (Pd), phosphorus (P), platinum (Pt), potassium (K), praseodymium (Pr), rubidium (Rb), rhenium (Re), rhodium (Rh), ruthenium (Ru), samarium (Sm), scandium (Sc), selenium (Se), silicon (Si), silver (Ag), sodium (Na), strontium (Sr), sulphur (S), tellurium (Te), terbium (Tb), thallium (Tl), thorium (Th), thulium (Tm), tin (Sn), titanium (Ti), tungsten (W), uranium (U), vanadium (V), ytterbium (Yb), yttrium (Y), zinc (Zn), and zirconium (Zr).

The methods in this Technical Specification are applicable to construction products.

NOTE Construction products include e.g. mineral-based products (S); bituminous products (B); metals (M); wood-based products (W); plastics and rubbers (P); sealants and adhesives (A); paints and coatings (C), see also CEN/TR 16045 [1].

The selection of analytical methods to be applied is based on the required sensitivity of the method, which is provided for all combinations of substance and analytical procedure.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 17087:— 1, *Construction products: Assessment of release of dangerous substances — Preparation of test portions from the laboratory sample for analysis of eluates and digests*

AC CEN/TS 17196 AC, *Construction products: Assessment of release of dangerous substances — Digestion by aqua regia for subsequent analysis of inorganic substances*

CEN/TS 17197, *Construction products: Assessment of release of dangerous substances — Analysis of inorganic substances in digests and eluates — Analysis by Inductively Coupled Plasma — Optical Emission Spectrometry (ICP-OES)*

CEN/TS 17200, *Construction products: Assessment of release of dangerous substances — Analysis of inorganic substances in digests and eluates — Analysis by Inductively Coupled Plasma — Mass Spectrometry (ICP-MS)*

EN ISO 5667-3, *Water quality — Sampling — Part 3: Preservation and handling of water samples (ISO 5667-3)*

EN ISO 11969:1996, *Water quality — Determination of arsenic — Atomic absorption spectrometric method (hydride technique) (ISO 11969:1996)*

<sup>1</sup> Under preparation. Stage at the time of publication: prEN 17087:2017.

**CEN/TS 17201:2018+AC:2018 (E)**

EN ISO 12846:2012, *Water quality — Determination of mercury — Method using atomic absorption spectrometry (AAS) with and without enrichment (ISO 12846:2012)*

EN ISO 15586:2003, *Water quality — Determination of trace elements using atomic absorption spectrometry with graphite furnace (ISO 15586:2003)*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025)*

EN ISO 17852:2008, *Water quality — Determination of mercury — Method using atomic fluorescence spectrometry (ISO 17852:2006)*

ISO 17378-1:2014, *Water quality — Determination of arsenic and antimony — Part 1: Method using hydride generation atomic fluorescence spectrometry (HG-AFS)*

ISO 17378-2:2014, *Water quality — Determination of arsenic and antimony — Part 2: Method using hydride generation atomic absorption spectrometry (HG-AAS)*

ISO/TS 13530, *Water quality — Guidance on analytical quality control for chemical and physicochemical water analysis*

ISO/TS 17379-1:2013, *Water quality — Determination of selenium — Part 1: Method using hydride generation atomic fluorescence spectrometry (HG-AFS)*

ISO/TS 17379-2:2013, *Water quality — Determination of selenium — Part 2: Method using hydride generation atomic absorption spectrometry (HG-AAS)*

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

**3 Terms and definitions**

[SIST-TS CEN/TS 17201:2019+AC:2019](https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c-)

<https://standards.iteh.ai/catalog/standards/sist/71989ae7-f676-4174-881c->

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

**3.1****digest**

solution resulting from acid digestion of a sample

[SOURCE: EN 16687:2015, 3.2.8]

**3.2****digestion**

mineralization of the organic matter of a sample and dissolution of its mineral part (as completely as possible) when reacted with a reagent mixture

Note 1 to entry: Usually done with a strong, concentrated acid like aqua regia or nitric acid to dissolve inorganic substances for chemical analysis.

[SOURCE: EN 16687:2015, 3.2.9]

**3.3****laboratory sample**

sample or subsample(s) sent to or received by the laboratory



Note 1 to entry: When the laboratory sample is further prepared by subdividing, mixing, diluting, etc. or by combinations of these operations, the result is the test sample. When no preparation of the laboratory sample is required, the laboratory sample is the test sample. A test portion is removed from the test sample for the performance of the test/ analysis.

Note 2 to entry The laboratory sample is the final sample from the point of view of sample collection but it is the initial sample from the point of view of the laboratory.

[SOURCE: EN 16687:2015, 3.2.1]

### 3.4

#### **method detection limit**

#### **MDL**

smallest analyte concentration that can be detected with a specified analytical method including sample preparation with a defined statistical probability

Note 1 to entry: Usually determined by three times the repeatability standard deviation ( $3 \times S_r$ ) calculated from multiple measurements ( $n > 8$ ) on different days and in different matrix solutions which contain a low analyte concentration.

[SOURCE: EN 16687:2015, 4.1.12]

### 3.5

#### **sample**

portion of material selected from a larger quantity of material

Note 1 to entry The manner of selection of the sample should be described in a sampling plan.

Note 2 to entry: The term “sample” is often accompanied by a prefix (e.g. laboratory sample, test sample) specifying the type of sample and/or the specific step in the sampling process to which the obtained material relates.

[SOURCE: EN 16687:2015, 3.1.5]

### 3.6

#### **test portion**

#### **analytical portion**

amount of the test sample taken for testing/analysis purposes, usually of known weight or volume

EXAMPLE 1 A bag of aggregates is delivered to the laboratory (the laboratory sample). For test purposes a certain amount of the aggregate is dried, the result is the test sample. Afterwards the column for a percolation test is filled with a test portion of dried aggregate.

EXAMPLE 2 A piece of flooring is delivered to the laboratory (the laboratory sample). For the purpose of digestion a certain amount is size reduced, the result is the test sample. From the size-reduced test sample a test portion is taken to execute the digestion. If the digest is to be analyzed afterwards e.g. by ICP-MS, the whole amount of the digest is the laboratory sample again, after any further treatment (e.g. dilution) results the test sample and the amount taken for the analytical procedure the test portion.

[SOURCE: EN 16687:2015, 3.2.3]

### 3.7

#### **test sample**

#### **analytical sample**

sample, prepared from the laboratory sample, from which test portions are removed for testing or for analysis

**CEN/TS 17201:2018+AC:2018 (E)**

[SOURCE: EN 16687:2015, 3.2.2]

**4 Abbreviations**

For the purposes of this document, the following abbreviations apply.

CV-AAS	Cold vapour atomic absorption spectrometry
CV-AFS	Cold vapour atomic fluorescence spectrometry
GF-AAS	Graphite furnace atomic absorption spectrometry
HG-AAS	Hydride generation atomic absorption spectrometry
ICP	Inductively coupled plasma
MDL	Method detection limit (limit of detection)
MS	Mass spectrometry
OES	Optical emission spectrometry

**5 Sample pre-treatment**

The digestion of the construction products is executed according to [\[AC\]](#) CEN/TS 17196 [\[AC\]](#).

The laboratory sample as obtained from sampling as specified in product specific requirements complemented with requirements as set out in CEN/TR 16220 [2], shall be prepared for digestion according to the specifications provided in the aqua regia digestion method [\[AC\]](#) CEN/TS 17196 [\[AC\]](#).

If necessary apply sample pre-treatment as specified in EN 17087:—<sup>2</sup>.

Split the digest in an adequate number of test portions for different chemical analyses and preserve them according to the requirements in EN ISO 5667-3.

**6 Selection of suitable analytical test method****6.1 Table of test methods**

The digest resulting from the aqua regia digestion is analysed for the substances of interest by selecting the appropriate standardized test method listed in Table 1 according to the concentration range of the parameter of interest, regulatory requirements, the expected interferences and the precision needed.

For analytical quality control purposes ISO/TS 13530 and EN ISO/IEC 17025 shall be considered.

**6.2 General validation information**

A selection of the test methods listed in Table 1 will be validated by CEN/TC 351 in an interlaboratory trial for a limited number of construction product matrices. Their suitability for other construction product digests shall be checked in the laboratory performing the analysis.

It is pointed out that the standardized test methods listed in Table 1 have primarily been developed for the analysis of water samples. Most of them were validated by CEN/TC 223, CEN/TC 292 and CEN/TC 308 in interlaboratory trials for a limited number of digests from various matrices. The validation data on these other matrices obtained in the evaluation of the analytical performance of laboratories are given in Annex A.

<sup>2</sup> Under preparation. Stage at the time of publication: prEN 17087:2017.

If the methods referred to in Table 1 are found to be inappropriate by reason of, for example, detection limits, repeatability or interferences, other methods validated for water analysis may be used. Their suitability for construction product eluates shall be checked in the laboratory performing the analysis. The reason for the deviation shall be stated in the test report.

Indicative values for MDL are listed in Table B.1 in Annex B. The values for MDL as listed in Annex B are indicative values in the sense that they are not to be used as sole guideline to select between methods to be applied. An actual MDL will depend on the equipment, matrix properties, interferences, and laboratory experience. Detection limits also depend on the amount of sample processed. If based on better precision for the listed methods another MDL is chosen than the MDL that would result from applying the tabulated values, this shall be mentioned in the test report.

**Table 1 — Substances and test methods for digests**

Parameter	Test method	Method type
<b>Major, minor and trace elements</b>		
Ag, Al, As, B, Ba, Be, Bi, Ca, Cd, Ce, Co, Cr, Cu, Fe, Hg, K, La, Li, Mg, Mn, Mo, Na, Nd, Ni, P, Pb, Pr, Total S, Sb, Sc, Se, Si, Sm, Sn, Sr, Te, Th, Ti, Tl, U, V, W, Zn and Zr	CEN/TS 17197	ICP-OES
Ag, Al, As, Au, Ba, Be, Bi, B, Cd, Ce, Ca, Cr, Co, Cs, Cu, Dy, Er, Eu, Fe, Ga, Gd, Ge, Hf, Hg, Ho, In, Ir, K, La, Li, Lu, Mg, Mo, Mn, Na, Nd, Ni, P, Pb, Pd, Pr, Pt, Rb, Re, Rh, Ru, Total S, Sb, Sc, Se, Si, Sm, Sn, Sr, Tb, Te, Th, Ti, Tl, Tm, U, V, W, Y, Yb, Zn and Zr	CEN/TS 17200	ICP-MS
<b>More sensitive methods</b>		
As	EN ISO 11969:1996	HG-AAS
As, Sb	ISO 17378-1:2014	HG-AFS
As, Sb	ISO 17378-2:2014	HG-AAS
Cd	EN ISO 15586:2003	GF-AAS
Hg	EN ISO 12846:2012	CV-AAS
	EN ISO 17852:2008	CV-AFS
Sb, Se	EN ISO 15586:2003	GF-AAS
Se	ISO/TS 17379-1:2013	HG-AFS
Se	ISO/TS 17379-2:2013	HG-AAS

### 6.3 Content in mg/kg

In Annex B the analytical sensitivity in terms of MDL is given in  $\mu\text{g/l}$ . To convert this value to an indicative value for MDL on content (mg of the substance under consideration per kg of dry solid) a multiplication factor of 500 is used, which is based on the sample mass used and the dilutions of the