



# Standard Test Method for Open Hole Tensile Strength of Polymer Matrix Composite Laminates<sup>1</sup>

This standard is issued under the fixed designation D 5766/D 5766M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope

1.1 This test method determines the open hole tensile strength of polymer matrix composite laminates reinforced by high-modulus fibers. The composite material forms are limited to continuous-fiber or discontinuous-fiber reinforced composites in which the laminate is balanced and symmetric with respect to the test direction. The standard test laminate is of the [45/0/-45/90] $n$ s stacking sequence family, where the sublaminates repeat index  $n$  is adjusted to yield a laminate thickness within the range discussed in 8.2.1. Other laminates may be tested provided the laminate configuration is reported with the results, however, the test method is unsatisfactory for unidirectional tape laminates containing only one ply orientation.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text the inch-pound units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:

- D 792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement<sup>2</sup>
- D 883 Terminology Relating to Plastics<sup>2</sup>
- D 2584 Test Method for Ignition Loss of Cured Reinforced Resins<sup>3</sup>
- D 2734 Test Methods for Void Content of Reinforced Plastics<sup>3</sup>
- D 3039/D 3039M Test Method for Tensile Properties of Polymer Matrix Composite Materials<sup>4</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-30 on High Modulus Fibers and Their Composites and is the direct responsibility of Subcommittee D30.05 on Structural Test Methods.

Current edition approved Aug. 15, 1995. Published October 1995.

<sup>2</sup> Annual Book of ASTM Standards, Vol 08.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 08.02.

<sup>4</sup> Annual Book of ASTM Standards, Vol 15.03.

D 3171 Test Method for Fiber Content of Resin-Matrix Composites by Matrix Digestion<sup>4</sup>

D 3878 Terminology of High-Modulus Reinforcing Fibers and Their Composites<sup>4</sup>

E 6 Terminology Relating to Methods of Mechanical Testing<sup>5</sup>

E 177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods<sup>6</sup>

E 456 Terminology Relating to Quality and Statistics<sup>6</sup>

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method<sup>6</sup>

E 1309 Guide for Identification of Composite Materials in Computerized Material Property Databases<sup>4</sup>

E 1434 Guide for Development of Standard Data Records for Computerization of Mechanical Test Data for High-Modulus Fiber-Reinforced Composite Materials<sup>4</sup>

E 1471 Guide for Identification of Fibers, Fillers and Core Materials in Computerized Material Property Databases<sup>4</sup>

## 3. Terminology

3.1 *Definitions*—Terminology D 3878 defines terms relating to high-modulus fibers and their composites. Terminology D 883 defines terms relating to plastics. Terminology E 6 defines terms relating to mechanical testing. Terminology E 456 and Practice E 177 define terms relating to statistics. In the event of a conflict between terms, Terminology D 3878 shall have precedence over the other standards.

### 3.2 Definitions of Terms Specific to This Standard:

NOTE 1—If the term represents a physical quantity, its analytical dimensions are stated immediately following the term (or letter symbol) in fundamental dimension form, using the following ASTM standard symbol for fundamental dimensions, shown within square brackets: [M] for mass, [L] for length, [T] for time, [θ] for thermodynamic temperature, and [nd] for non-dimensional quantities. Use of these symbols is restricted to analytical dimensions when used with square brackets, as the symbols may have other definitions when used without the brackets.

3.2.1 *balanced laminate, n*—laminate in which all laminae at angles other than 0 degrees or 90 degrees occur only in  $\pm$  pairs, though each ply of a pair is not required to be located adjacent to the other.

3.2.2 *nominal value, n*—a value, existing in name only,

<sup>5</sup> Annual Book of ASTM Standards, Vol 03.01.

<sup>6</sup> Annual Book of ASTM Standards, Vol 14.02.

assigned to a measurable property for the purpose of convenient designation. Tolerances may be applied to a nominal value to define an acceptable range for the property.

3.2.3 *ply orientation*,  $\theta$ ,  $n$ —the angle between a reference direction and the ply principal axis. The angle is expressed in degrees, is never greater than  $90^\circ$ , and is shown as a positive quantity when taken from the reference direction to the ply principal axis, following the right-hand-rule.

3.2.3.1 *Discussion*—The reference direction is usually related to a primary load-carrying direction.

3.2.4 *ply principal axis*,  $n$ —the coordinate axis in the plane of a lamina that is used as the reference direction for that lamina.

3.2.4.1 *Discussion*—The ply principal axis will, in general, be different for each ply of a laminate. The direction of this axis relative to some reference axis is defined by the ply orientation. The convention is to align the ply principal axis with a material feature that is the direction of maximum stiffness (such as the fiber direction for unidirectional tape or the warp direction for fabric reinforced material). Conventions for other laminated material forms have not yet been established.

3.2.5 *symmetric laminate*,  $n$ —is one in which the orientation, form, and material (and warp surface, for satin-type fabrics) for the plies located on one side of the midplane is the mirror image of the stacking sequence on the other side of the midplane.

3.2.6 *warp surface*,  $n$ —the side of a woven fabric, in a satin-type weave pattern, which is dominated by the warp yarns.

### 3.3 Symbols:

3.3.1  $A$ —cross-sectional area of a coupon.

3.3.2  $CV$ —coefficient of variation statistic of a sample population for a given property (in percent).

3.3.3  $D$ —hole diameter.

3.3.4  $h$ —coupon thickness.

3.3.5  $n$ —number of coupons per sample population.

3.3.6  $N$ —number of plies in laminate under test.

3.3.7  $F_x^{OHTu}$ —ultimate tensile strength in the test direction.

3.3.8  $P_x^{\max}$ —maximum load carried by test coupon prior to failure.

3.3.9  $s_{n-1}$ —standard deviation statistic of a sample population for a given property.

3.3.10  $w$ —coupon width.

3.3.11  $x_i$ —test result for an individual coupon from the sample population for a given property.

3.3.12  $\bar{x}$ —mean or average (estimate of mean) of a sample population for a given property.

3.3.13  $\sigma$ —normal stress.

## 4. Summary of Test Method

4.1 A uniaxial tension test of a balanced, symmetric laminate is performed in accordance with Test Method D 3039/D 3039M, although with a centrally located hole and without strain or displacement transducers. Ultimate strength is calculated based on the gross cross-sectional area, disregarding the presence of the hole.

## 5. Significance and Use

5.1 This test method is designed to produce notched tensile

strength data for material specifications, research and development, and quality assurance. Factors that influence the notched tensile strength and should therefore be reported include the following: material, methods of material fabrication, accuracy of lay-up, laminate stacking sequence and overall thickness, specimen geometry, specimen preparation (especially of the hole), specimen conditioning, environment of testing, specimen alignment and gripping, speed of testing, void content, and volume percent reinforcement. Properties that may be derived from this test method include the following:

5.1.1 Open hole (notched) tensile strength.

## 6. Interferences

6.1 *Hole Preparation*—Due to the dominating presence of the notch, and the lack of need to measure the material response, results from this test method are relatively insensitive to parameters that would be of concern in an unnotched tensile property test. However, since the notch dominates the strength, consistent preparation of the hole, without damage to the laminate, is important to meaningful results. Damage due to hole preparation will affect strength results. Some types of damage, such as delaminations, can blunt the stress concentration because of the hole, increasing the load-carrying capacity of the coupon and the calculated strength.

6.2 *Geometry*—Results are affected by the ratio of specimen width to hole diameter; this ratio should be maintained at 6, unless the experiment is investigating the influence of this ratio. Results may also be affected by the ratio of hole diameter to thickness; the preferred ratio is the range of 1.5–3.0 unless the experiment is investigating the influence of this ratio.

6.3 *Other*—Additional sources of potential data scatter in testing of composite materials are described in Test Method D 3039/D 3039M.

## 7. Apparatus

7.1 Apparatus shall be in accordance with Test Method D 3039/D 3039M. However, the procedure herein does not measure material response, so strain or deflection measurement related discussions in Test Method D 3039/D 3039M do not apply. Additionally, a micrometer or gage capable of determining the hole diameter to  $\pm 0.025$  mm [ $\pm 0.001$  in.] is required.

## 8. Sampling and Test Specimens

8.1 *Sampling*—Sampling shall be in accordance with Test Method D 3039/D 3039M.

8.2 *Geometry*—The coupon geometry shall be in accordance with Test Method D 3039/D 3039M, as modified by the following, and illustrated by the schematic of Fig. 1. Any variation of the stacking sequence, specimen width or length, or hole diameter from that specified shall be clearly noted in the report.

8.2.1 *Stacking Sequence*—The normal laminate shall have a balanced and symmetric stacking sequence of  $[45/0/-45/90]_n s$ , where  $n$  is selected to keep the laminate thickness as close as possible to 2.5 mm [0.10 in.], with a permissible range of 2–4 mm [0.080–0.160 in.], inclusive. Laminates containing satin-type weaves shall have symmetric warp surfaces, unless otherwise noted in the report.

8.2.2 *Dimensions*—The width of the specimen is  $36 \pm 1$