



SLOVENSKI STANDARD
oSIST prEN 117:2022

01-december-2022

**Zaščitna sredstva za les - Ugotavljanje toksičnih vrednosti proti Reticulitermes
santonensis (evropskim termitom) (laboratorijska metoda)**

Wood preservatives - Determination of toxic values against Reticulitermes species
(European termites) (Laboratory method)

Holzschutzmittel - Bestimmung der Grenze der Wirksamkeit gegenüber Reticulitermes-
Arten (Europäische Termiten) (Laboratoriumsverfahren)

Produit de préservation du bois - Détermination du seuil d'efficacité contre les termites
européens du genre Reticulitermes (Méthode de laboratoire)

Ta slovenski standard je istoveten z: prEN 117

ICS:

71.100.50 Kemikalije za zaščito lesa Wood-protecting chemicals

oSIST prEN 117:2022

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 117

October 2022

ICS 71.100.50

Will supersede EN 117:2012

English Version

Wood preservatives - Determination of toxic values against Reticulitermes species (European termites) (Laboratory method)

Produit de préservation du bois - Détermination du
seuil d'efficacité contre les termites européens du
genre Reticulitermes (Méthode de laboratoire)

Holzschutzmittel - Bestimmung der Grenze der
Wirksamkeit gegenüber Reticulitermes-Arten
(Europäische Termiten) (Laboratoriumsverfahren)

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 38.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Principle	5
5 Test materials.....	6
5.1 Biological material.....	6
5.2 Products and reagents.....	6
5.3 Apparatus.....	7
6 Sampling.....	8
7 Test specimens.....	8
7.1 Species of wood.....	8
7.2 Wood quality.....	8
7.3 Provision of test specimens.....	8
7.4 Dimensions of test specimens	8
7.5 Number and distribution of test specimens.....	9
8 Procedure.....	9
8.1 Preparation of test specimens.....	9
8.1.1 Conditioning of test specimens prior to treatment	9
8.1.2 Treatment of test specimens.....	9
8.1.3 Drying and conditioning of the test specimens after treatment.....	10
8.2 Exposure of the test specimens to the insects	10
8.2.1 Collecting and selecting the termites.....	10
8.2.2 Instalation of the termites.....	11
8.2.3 Exposure.....	12
8.3 Conditions and duration of test	13
8.3.1 Exposure.....	13
8.3.2 Maintaining of moisture content.....	13
8.4 Examination of the test specimens and colonies.....	14
8.4.1 Assessments.....	14
9 Expression of results.....	15
10 Test report.....	15
Annex A (informative) Example of a test report	17
Annex B (informative) Example of a method of culturing termites.....	19
Annex C (informative) Environmental, health and safety precautions within chemical/biological laboratory	20
Bibliography.....	21

European foreword

This document (prEN 117:2022) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 117:2012.

Significant technical differences between this document and EN 117:2012 are as follows:

- a) the required purity of fine white quartz sand was lowered (5.2.1.1);
- b) the values for the examination of termite attack in rating 2i) and 3i) were slightly changed to close rating gaps (8.4.1.2).

NOTE 1 The species name “*Reticulitermes santonensis*” is officially withdrawn and replaced by *Reticulitermes flavipes*. This document follows the new regulation.

NOTE 2 Test results obtained according to earlier versions of this document and when the tests had started before this version of EN 117 was published are considered as valid.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 117:2022](https://standards.iteh.ai/catalog/standards/sist/c477122d-0a06-4367-9271-8f9ce599cf53/osist-pren-117-2022)

<https://standards.iteh.ai/catalog/standards/sist/c477122d-0a06-4367-9271-8f9ce599cf53/osist-pren-117-2022>

prEN 117:2022 (E)**Introduction**

This document describes a laboratory method of testing which gives a basis for assessment of the effectiveness of a wood preservative against the *Reticulitermes* species of European termites. It allows the determination of the concentration at which the product completely prevents attack by these insects of impregnated wood of a susceptible species.

This laboratory method provides one criterion by which the value of a product can be assessed. In making this assessment the methods by which the preservative can be applied should be taken into account. It is further recommended that results from this should be supplemented by those from other appropriate tests, and above all by comparison with practical experience.

When products which are very active at low concentrations are used it is very important to take suitable precautions to isolate and separate, as far as possible, operations involving chemical products, other products, treated wood, laboratory apparatus and clothing. Suitable precautions should include the use of separate rooms, areas within rooms, extraction facilities and conditioning chambers as well as special training for personnel (see also Annex C for environmental, health and safety precautions).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 117:2022](https://standards.iteh.ai/catalog/standards/sist/c477122d-0a06-4367-9271-8f9ce599cf53/osist-pren-117-2022)

<https://standards.iteh.ai/catalog/standards/sist/c477122d-0a06-4367-9271-8f9ce599cf53/osist-pren-117-2022>

1 Scope

This document specifies a method for the determination of the toxic values of a wood preservative against the *Reticulitermes* species of European termites ¹.

This method is applicable to:

- water-insoluble chemicals which are being studied as active insecticides;
- organic water-dispersible formulations as supplied or as prepared in the laboratory by dilution of concentrates; and
- water-soluble materials, for example salts.

NOTE This method can be used in conjunction with an ageing procedure, for example EN 73 or EN 84.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 3696, *Water for analytical laboratory use - Specification and test methods (ISO 3696)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

representative sample

sample having its physical or chemical characteristics identical to the volumetric average characteristics of the total volume being sampled

3.2

supplier

sponsor of the test (person or company providing the sample of wood preservative to be tested)

4 Principle

Impregnation of several sets of test specimens of susceptible wood with a series of solutions in which the concentration of preservative is ranged in a given progression.

Exposure of these test specimens to specified colonies of *Reticulitermes* and assessment of the attack suffered after exposure under fixed conditions and over a fixed period. In providing biological validation

¹ The method can be applied not only to different species of *Reticulitermes*, but also to other species of the family of the Rhinotermitidae, adapting the conditions of temperature and humidity where necessary to the specific requirements of the species concerned.

prEN 117:2022 (E)

of individual species, it is essential that the locality of origin of each test termite species is given. The description of the locality should at least include the district name.

Comparison of these results with those obtained with untreated and solvent or diluent-treated control test specimens.

Derivation of the toxic values of the product under test.

5 Test materials

5.1 Biological material

Workers, soldiers and nymphs of an identified termite species of *Reticulitermes*.

The termite species and the locality of origin should be stated in the test report and their identification should be proved.

The termites should be obtained from colonies reared as described in Annex B.

5.2 Products and reagents

5.2.1 Substrate for establishing the colonies. A choice of:

5.2.1.1 Fine white quartz sand consisting of grains of crystallized silica, very pure (90 % silica), and free from any organic substances ²

5.2.1.2 A hydrated, laminar, aluminium-iron-magnesium silicate exfoliated to give particles of 1 mm to 3 mm with an apparent density of 80 kg/m³ to 90 kg/m³

Particles of less than 1 mm shall be eliminated by sieving prior to use to ensure the absence of free water and prevent any significant agglomeration of the particles.

5.2.1.3 Rigid polyurethane foam with open pores

NOTE Horticulture foam with mass per unit of volume of 14 kg/m³ and compressive strength ³ of 0,02 N/mm² to 0,03 N/mm² is suitable. It is advisable to cut the foam into sheets 15 mm thick.

5.2.2 Fumigant (if necessary) xylene, technical grade, mixed isomers

5.2.3 Water, complying with grade 3 of EN ISO 3696

5.2.4 Solvent or diluent, a suitable volatile liquid that will dissolve or dilute the preservative but does not leave a residue in the wood which would have a toxic effect on the insect at the end of the conditioning period

5.2.5 Filter paper, ordinary quality, medium-fast grade

² In France Fontainebleau sand, of which more than 97 % of the particles are between 75 µm and 300 µm in size, provides these features.

³ Determined in accordance with EN ISO 844.

5.3 Apparatus

5.3.1 Culturing chamber, with air circulation, controlled at (26 ± 2) °C and at a minimum relative humidity of (70 ± 5) %

5.3.2 Conditioning chamber, well ventilated, controlled at (20 ± 2) °C and relative humidity (65 ± 5) %⁴

5.3.3 Laboratory work area, well ventilated, where treatment of the test specimens is carried out. It is essential to follow safety procedures for handling flammable and toxic materials. Excessive exposure of operators to solvents or their vapours should be avoided.

5.3.4 Testing chamber, protected from light, ventilated and controlled at (26 ± 2) °C and at a minimum relative humidity of (70 ± 5) %

5.3.5 Treatment vessels, of a material that does not react with the preservative under test, for example glass for organic products and polyethylene for salts containing fluorine

5.3.6 Drying vessel(s), capable of holding sets of three test specimens (7.5), provided with a close-fitting cover and containing supports that will give minimum contact with treated test specimens to be placed on them

The vessels and supports shall be of a material that does not react with the preservative under test, for example glass for organic compounds and polyethylene for products containing fluorine.

5.3.7 Weights, to provide ballast for the test specimens

The weights shall not react with any materials with which they come in contact during the test.

5.3.8 Safety equipment and protective clothing, appropriate for the test product and the test solvent, to ensure the safety of the operator

5.3.9 Vacuum vessels, fitted with stopcocks, capable of receiving the treatment

5.3.10 Vacuum pump, fitted with a pressure gauge and capable of maintaining a pressure of 700 Pa

5.3.11 Instruments, adapted for termite manipulation (aspirator, forceps)

5.3.12 Test containers, suitable for holding the test specimens and of material resistant to the product used, and fitted with perforated cover to provide a good exchange of air

Base area	35 cm ² to 60 cm ²
Minimum height	8,5 cm
Volume	500 cm ³ to 1 000 cm ³

5.3.13 Glass rings or rings of other inert materials, ca. 20 mm to ca. 25 mm high, ca. 15 mm to ca. 25 mm in diameter and with a wall thickness of ca. 1 mm to ca. 2 mm

5.3.14 Protective gloves

⁴ The conditioning of test specimens after treatment can be carried out in the laboratory work area (5.3.3) provided that this meets the conditions specified for the conditioning chamber (5.3.2).

prEN 117:2022 (E)

5.3.15 Ordinary laboratory equipment, including a balance capable of weighing to an accuracy of 0,01 g

6 Sampling

The sample of preservative shall be representative of the product to be tested. Samples should be stored and handled in accordance with any written recommendations from the supplier.

NOTE For the sampling of preservatives from bulk supplies, the procedure given in EN 212 will be used.

7 Test specimens**7.1 Species of wood**

The reference species is Scots pine (*Pinus sylvestris* Linnaeus).

Additional tests can be carried out using other species but, if so, this should be stated in the test report.

7.2 Wood quality

The wood shall be free from visible cracks, stain, decay, insect damage and other defects. The wood shall not have been water-stored, floated, chemically treated or steamed. The wood shall originate from trees preferably felled in winter.

NOTE Wood that has been kiln dried at temperatures below 60 °C can be used.

The wood shall be exclusively sapwood containing little resin and having between 2,5 annual rings per 10 mm and eight annual rings per 10 mm. The proportion of latewood in the annual rings shall not exceed 30 % of the whole.

It is recommended to use test specimens of similar growth rate within a single test.

7.3 Provision of test specimens

Prepare planed strips having a cross-section of $(25 \pm 0,5)$ mm \times $(15 \pm 0,5)$ mm removing a minimum of 2 mm from any surfaces exposed during drying. The longitudinal faces shall be parallel to the direction of the grain. The annual rings shall have a contact angle of greater than 10° to the broad faces of the test specimens. Make transverse cuts, neatly to give sharp edges and a fine-sawn finish to the end grain surfaces, to give test specimens $(50 \pm 0,5)$ mm long.

The test specimens shall originate from a minimum of three trees or shall be taken at random from a stock originally of more than 500 test specimens.

7.4 Dimensions of test specimens

The dimensions of each test specimen after reaching equilibrium in the conditioning chamber (5.3.2) shall be $(50 \pm 0,5)$ mm \times $(25 \pm 0,5)$ mm \times $(15 \pm 0,5)$ mm.

For the purposes of calculating the mass of preservative retained per unit volume of wood (8.1.2.2) the nominal volume of each test specimen shall be taken as 18,75 cm³.

Mark each test specimen so that it can be identified throughout the test.

7.5 Number and distribution of test specimens

The test specimens shall be divided as follows:

- a) treated test specimens: these are the test specimens which are impregnated and subject to attack by *Reticulitermes*, use at least five test specimens for each concentration of the product;
- b) untreated control test specimens for checking the virulence of the termite taken for the test: these non-impregnated test specimens are subjected to attack by *Reticulitermes*; they are three in number;
- c) solvent or diluent treated control test specimens subjected to attack by *Reticulitermes*; they are three in number.

8 Procedure

8.1 Preparation of test specimens

8.1.1 Conditioning of test specimens prior to treatment

Allow the test specimens to condition in the conditioning chamber (5.3.2) for a minimum of two weeks.

8.1.2 Treatment of test specimens

8.1.2.1 Preparation of treatment solutions

8.1.2.1.1 Solid preservatives

Water-soluble preservatives: dissolve the preservative in water (5.2.3) to the required concentration.

Non-water-soluble preservatives: dissolve the preservative in an appropriate solvent (5.2.4) to the required concentration.

8.1.2.1.2 Liquid preservatives

If appropriate, use the preservative without further preparation other than any necessary stirring. If it is a concentrate, dilute the preservative with the diluent to the required working concentration, using the procedure specified by the supplier.

Prepare a series of at least five concentrations by mass, distributed evenly about the expected toxic values. A solvent or diluent control, i.e. treatment at concentration = 0, shall also be used. If the approximate toxic values are unknown, the concentrations shall form a widely spaced geometric progression for a first test and a more closely spaced geometric or arithmetic progression for subsequent tests.

All treatment solutions shall be freshly prepared.

8.1.2.2 Impregnation

Carry out impregnation in ascending order of concentration, starting with the solvent control (concentration = 0). The following procedure ensures the required complete impregnation of test specimens by the test solutions. For each concentration weigh each test specimen to the nearest 0,05 g, and then stack the test specimens in one of the treatment vessels (5.3.5) so that as much of their face as possible is exposed (e.g. by piling them crosswise). Ballast the stack of test specimens with weights (5.3.7) to prevent them from floating later when the liquid is admitted.

Place each treatment vessel in one of the vacuum vessels (5.3.9) and reduce the pressure to 700 Pa. Maintain this for 15 min. Observe the proper safety measures for vacuum vessels. After this period, close the stopcock to the vacuum pump (5.3.10) and open the other stopcock to allow the solution of