



# SLOVENSKI STANDARD

## SIST EN 370:2024

01-marec-2024

Nadomešča:  
SIST EN 370:2004

---

**Zaščitna sredstva za les - Ugotavljanje učinkovitosti preventivnega delovanja proti navadnemu trdoglavcu *Anobium punctatum* (De Geer)**

Wood preservatives - Determination of eradicant efficacy in preventing emergence of *Anobium punctatum* (De Geer)

Holzschutzmittel - Bestimmung der auf Schlupfverhinderung beruhenden bekämpfenden Wirksamkeit gegenüber *Anobium punctatum* (De Geer)

Produits de préservation du bois - Détermination de l'efficacité curative contre l'émergence d'*Anobium punctatum* (De Geer)

**Ta slovenski standard je istoveten z: EN 370:2023**

<https://standards.iteh.ai/catalog/standards/sist/177ec6c1-1552-4bb6-8056-11f6f61290bd/sist-en-370-2024>

---

**ICS:**

71.100.50      Kemikalije za zaščito lesa      Wood-protecting chemicals

**SIST EN 370:2024**

**en,fr,de**



EUROPEAN STANDARD

EN 370

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2023

ICS 71.100.50

Supersedes EN 370:1993

English Version

## Wood preservatives - Determination of eradicator efficacy in preventing emergence of *Anobium punctatum* (De Geer)

Produits de préservation du bois - Détermination de  
l'efficacité curative contre l'émergence d'*Anobium*  
*punctatum* (De Geer)

Holzschutzmittel - Bestimmung der auf  
Schlupfverhinderung beruhenden bekämpfenden  
Wirksamkeit gegenüber *Anobium punctatum* (De Geer)

This European Standard was approved by CEN on 6 November 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

# Document Preview

[SIST EN 370:2024](https://standards.iteh.ai/catalog/standards/sist/177ec6c1-f552-4bb6-8056-11f6f61290bd/sist-en-370-2024)

<https://standards.iteh.ai/catalog/standards/sist/177ec6c1-f552-4bb6-8056-11f6f61290bd/sist-en-370-2024>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	4
Introduction .....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions .....	6
4 Principle .....	6
5 Test materials and apparatus.....	7
5.1 Biological material.....	7
5.1.1 <i>Anobium punctatum</i> (De Geer) larvae .....	7
5.1.2 Provision of larvae.....	7
5.1.3 Choice of larvae.....	7
5.2 Products and reagents.....	7
5.3 Apparatus.....	8
6 Sampling.....	8
7 Test specimens.....	8
7.1 Species of wood.....	8
7.2 Quality of wood .....	8
7.3 Provision of test specimens.....	9
7.4 Dimension of test specimens .....	9
7.5 Number of test specimens.....	9
8 Procedure.....	9
8.1 Preparation of the test specimens .....	9
8.1.1 Sealing of the transverse faces .....	9
8.1.2 Treatment of test specimens.....	10
8.2 Exposure of the test specimens to the insects .....	11
8.2.1 Preparation of sub-specimens.....	11
8.2.2 Insertion of larvae.....	11
8.2.3 Conditioning of infested sub-specimens to induce emergence .....	11
8.3 Examination of sub-specimens .....	12
9 Validity of the test .....	12
10 Expression of results.....	12
11 Test report.....	12
Annex A (informative) Example of a test report .....	16
Annex B (informative) Culturing technique for <i>Anobium punctatum</i> .....	18
B.1 Culture wood.....	18
B.1.1 Wood species .....	18
B.1.2 Collection of culture wood.....	18
B.1.3 Cutting of culture wood.....	18
B.1.4 Drying of culture wood.....	18

<b>B.2</b>	<b>Source of beetles .....</b>	<b>18</b>
<b>B.2.1</b>	<b>Collection of beetles.....</b>	<b>18</b>
<b>B.2.2</b>	<b>Quarantine of beetles .....</b>	<b>18</b>
<b>B.3</b>	<b>Infestation of culture wood.....</b>	<b>18</b>
<b>B.3.1</b>	<b>Culture vessels.....</b>	<b>18</b>
<b>B.3.2</b>	<b>Preparation of wood.....</b>	<b>19</b>
<b>B.3.3</b>	<b>Introduction of beetles .....</b>	<b>19</b>
<b>B.4</b>	<b>Culturing conditions.....</b>	<b>19</b>
<b>B.4.1</b>	<b>Normal environment.....</b>	<b>19</b>
<b>B.4.2</b>	<b>Natural pupation induction .....</b>	<b>19</b>
<b>B.4.3</b>	<b>Artificial pupation induction.....</b>	<b>19</b>
<b>B.5</b>	<b>Collection of beetles.....</b>	<b>19</b>
<b>B.6</b>	<b>General culture hygiene .....</b>	<b>19</b>
	<b>Bibliography .....</b>	<b>21</b>

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[SIST EN 370:2024](https://standards.iteh.ai/catalog/standards/sist/177ec6c1-f552-4bb6-8056-11f6f61290bd/sist-en-370-2024)

<https://standards.iteh.ai/catalog/standards/sist/177ec6c1-f552-4bb6-8056-11f6f61290bd/sist-en-370-2024>

## EN 370:2023 (E)

### European foreword

This document (EN 370:2023) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2024, and conflicting national standards shall be withdrawn at the latest by June 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 370:1993.

The main changes compared to the previous edition are listed below:

- a) maximum recommended quantity of test solution application was changed from 250 g/m<sup>2</sup> to 300 ml/m<sup>2</sup> (8.1.2.2);
- b) the count of adults for validity of the test may include those hatching underneath the cover-ups of the end faces (Clause 9).

NOTE Test results obtained according to earlier versions of this document and when the tests had started before this version of EN 370 was published are considered as valid.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## Introduction

This document describes a laboratory method of test which gives a basis for assessment of the eradicator efficacy of a wood preservative, in preventing emergence of *Anobium punctatum*. It determines the lethal effects of an insecticidal product, deposited by surface application, on beetles attempting to emerge through treated wood surfaces.

The method has been developed to assess the efficacy of eradicator formulations based on non-penetrating fluids which act only on emerging adult beetles and not at depth on larvae established in the wood.

The method simulates conditions which can appear in practice where a length of timber infested with *Anobium punctatum* is treated on all the sides from which emergence of beetles is possible.

This laboratory method provides one criterion by which the value of a product can be assessed. In making this assessment, the methods by which the preservative may be applied should be taken into account. It is further recommended that results from this test should be supplemented by those from other appropriate tests, and above all by comparison with practical experience.

When products which are very active at low concentrations are used, it is very important to take suitable precautions to isolate and separate, as far as possible, operations involving chemical products, other products, treated wood, laboratory apparatus and clothing. Suitable precautions should include the use of separate rooms, areas within rooms, extraction facilities and conditioning chambers as well as special training for personnel.

# iTeh Standards (<https://standards.iteh.ai>) Document Preview

[SIST EN 370:2024](https://standards.iteh.ai/catalog/standards/sist/177ec6c1-f552-4bb6-8056-11f6f61290bd/sist-en-370-2024)

<https://standards.iteh.ai/catalog/standards/sist/177ec6c1-f552-4bb6-8056-11f6f61290bd/sist-en-370-2024>

## EN 370:2023 (E)

### 1 Scope

This document specifies a method for the determination of the curative action of a wood preservative against infestation by *Anobium punctatum* (De Geer) when the product is applied as a surface treatment to wood.

This method is applicable to any surface-applied treatment that is intended to prevent emergence of adult beetles but not intended to kill larvae in infested timber.

NOTE 1 This method can be used in conjunction with an ageing procedure, for example EN 73.

NOTE 2 Products intended to kill larvae can be tested by the method described in EN 48.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

EN ISO 835, *Laboratory glassware — Graduated pipettes (ISO 835)*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

#### 3.1

##### **representative sample**

sample having its physical or chemical characteristics identical to the volumetric average characteristics of the total volume being sampled

#### 3.2

##### **supplier**

sponsor of the test

### 4 Principle

Preservative is applied by brush or pipette onto test specimens of a susceptible timber. After drying the test specimens are cut into two sub-specimens and larvae of *Anobium punctatum* are introduced into the freshly-cut end grain surfaces.

After allowing larvae to establish, the untreated faces are sealed and insects are induced to pupate and emerge. The numbers of beetles that emerge and the population that remains within the specimens are compared with those in untreated controls.



## 5 Test materials and apparatus

### 5.1 Biological material

#### 5.1.1 *Anobium punctatum* (De Geer) larvae

The culturing technique, which experience has shown to be suitable, is described in Annex B.

#### 5.1.2 Provision of larvae

Carefully split or crumble infested small branchwood to extract larvae. Examine them under a binocular microscope and destroy any that show injury or mite infestation or that do not respond by movement when touched.

Weigh the larvae and keep those that have a mass between 7 mg and 12 mg, and are in perfect condition. Keep them, for between 12 h and 60 h, separately from one another in glass receptacles in the culturing chamber (5.3.1). Re-examine them and reject any which do not show movement in response to stimulation with a fine brush.

#### 5.1.3 Choice of larvae

Select sets of 12 larvae so that the total mass of each set is between 100 mg and 125 mg.

The numbers of larvae required are shown in Table 1.

**Table 1 — Numbers of larvae**

Number of formulations to be tested	Number of test specimens (100 mm × 50 mm × 30 mm) required		Total number of larvae required
	Untreated controls	Treated specimens	
1	3	3	144
2	3	6	216
3	6	9	360
4	6	12	432

NOTE 1 Each test specimen will later be divided into two sub-specimens (see 8.2).

NOTE 2 Additional larvae can be required to replace larvae which do not establish in the test sub-specimens.

### 5.2 Products and reagents

**5.2.1 Water**, complying with grade 3 of ISO 3696.

**5.2.2 Gelatin**, for sealing the relevant surfaces of specimens to be treated with solutions in which an organic solvent is the continuous phase.

**5.2.3 Paraffin wax**, for sealing the relevant surfaces of specimens to be treated with solutions in which water is the continuous phase.

NOTE Paraffin wax with a setting point of 52 °C to 54 °C has been found to be suitable.

## EN 370:2023 (E)

### 5.3 Apparatus

**5.3.1 Culturing chamber**, with air circulation, controlled at  $(21 \pm 2)$  °C, and at relative humidity  $(75 \pm 5)$  %.

**5.3.2 Laboratory work area**, well ventilated, where treatment of the test specimens is carried out.

CAUTION — It is essential to follow safety procedures for handling flammable and toxic materials. Avoid excessive exposure of operators to solvents or their vapours.

**5.3.3 Testing chamber**, ventilated, controlled at  $(21 \pm 2)$  °C and at relative humidity  $(75 \pm 5)$  %.

#### 5.3.4 Low temperature regime chamber

— Either:

— ventilated and controlled to provide a continuous temperature regime with consecutive cycles of 12 h at  $(6 \pm 1)$  °C and 12 h at  $(13 \pm 1)$  °C; or

— ventilated and controlled at  $(6 \pm 1)$  °C and relative humidity  $(70 \pm 5)$  %.

**5.3.5 Drill, provided with bits capable of drilling smooth cylindrical holes of 2 mm diameter in wood.**

**5.3.6 Plastic** plates of opaque unplasticised PVC, 50 mm × 30 mm × 1 mm.

**5.3.7 Safety equipment and protective clothing**, appropriate for the test product and the test solvent, to ensure the safety of the operator.

**5.3.8 Pipette**, of type specified in EN ISO 835, Class B: graduated pipette with no waiting time. Capacity from 0,5 ml to 25 ml with a maximum permissible error of  $\pm 0,01$  ml.

**5.3.9 Ordinary laboratory equipment**, including a balance capable of weighing to an accuracy of 0,01 g.

## 6 Sampling

The sample of preservative shall be representative of the product to be tested. Samples shall be stored and handled in accordance with any written recommendations from the supplier.

For the sampling of preservatives from bulk supplies, the procedure given in EN 212 should be used.

## 7 Test specimens

### 7.1 Species of wood

The test shall be carried out on *Pinus sylvestris* (Linnaeus), Scots pine.

Additional tests may be done with other species such as European beech (*Fagus sylvatica*) (Linnaeus) but, if so, this should be stated in the test report.

### 7.2 Quality of wood

Use only sound sapwood, straight-grained and without knots and bark.