

SLOVENSKI STANDARD

oSIST prEN ISO 12312-1:2021

01-marec-2021

**Varovanje oči in obraza - Sončna očala in sorodna oprema za varovanje oči - 1.
del: Sončna očala za splošno uporabo (ISO/DIS 12312-1:2021)**

Eye and face protection - Sunglasses and related eyewear - Part 1: Sunglasses for
general use (ISO/DIS 12312-1:2021)

Augen- und Gesichtsschutz - Sonnenbrillen und ähnlicher Augenschutz - Teil 1:
Sonnenbrillen für den allgemeinen Gebrauch (ISO/DIS 12312-1:2021)

Protection des yeux et du visage - Lunettes de soleil et articles de lunetterie associés -
Partie 1: Lunettes de soleil pour usage général (ISO/DIS 12312-1:2021)

<https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35e6d43d987/osist-pr-en-iso-12312-1-2021>

Ta slovenski standard je istoveten z: prEN ISO 12312-1

ICS:

11.040.70	Oftalmološka oprema	Ophthalmic equipment
13.340.20	Varovalna oprema za glavo	Head protective equipment

oSIST prEN ISO 12312-1:2021

en,fr,de

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 12312-1:2021](https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35c6d43d987/osist-pren-iso-12312-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35c6d43d987/osist-pren-iso-12312-1-2021>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 12312-1

ISO/TC 94/SC 6

Secretariat: BSI

Voting begins on:
2021-01-11Voting terminates on:
2021-04-05

Eye and face protection — Sunglasses and related eyewear —

Part 1: Sunglasses for general use

*Protection des yeux et du visage — Lunettes de soleil et articles de lunetterie associés —**Partie 1: Lunettes de soleil pour usage général*

ICS: 13.340.20

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 12312-1:2021](https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35c6d43d987/osist-pren-iso-12312-1-2021)<https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35c6d43d987/osist-pren-iso-12312-1-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 12312-1:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 12312-1:2021](https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35c6d43d987/osist-pren-iso-12312-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/c2af6660-147f-49b8-86ae-a35c6d43d987/osist-pren-iso-12312-1-2021>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Construction and materials	3
4.1 Construction	3
4.2 Filter material and surface quality	3
4.3 Physiological compatibility	3
4.4 Headforms	4
5 Transmittance	4
5.1 Test methods	4
5.2 Transmittance and filter categories	4
5.3 General transmittance requirements	5
5.3.1 Uniformity of luminous transmittance	5
5.3.2 Requirements for road use and driving	6
5.3.3 Wide-angle scatter	6
5.3.4 Additional transmittance requirements for specific filter types	6
5.3.5 Claimed transmittance properties	8
6 Refractive power	9
6.1 Spherical and astigmatic power	9
6.2 Spatial deviation	9
6.3 Prism imbalance (relative prism error)	9
7 Robustness	10
7.1 Minimum robustness of filters	10
7.2 Frame deformation and retention of filters	10
7.3 Impact resistance of sunglasses, strength level 1 (optional specification)	11
7.4 Increased endurance of sunglasses (optional specification)	11
7.5 Resistance to perspiration (optional specification)	11
7.6 Impact resistance of the filter, strength level 2 or 3 (optional specification)	12
8 Resistance to solar radiation	12
9 Resistance to ignition	13
10 Resistance to abrasion (optional specification)	13
11 Protective requirements	13
11.1 Coverage area	13
11.2 Temporal protective requirements	13
12 Information and labelling	14
12.1 Information to be supplied with each pair of sunglasses	14
12.2 Additional information	17
13 Selection of test samples	17
13.1 General	17
13.2 Preparation and conditioning of test samples	17
Annex A (informative) Use of sunglass filters	21
Annex B (informative) Electro-optical filters	23
Annex C (normative) Unmounted filters used as replacement or alternative filters	26
Annex D (informative) Relationship between this European Standard and the essential requirements of Regulation 2016/425 aimed to be covered	31
Bibliography	34

ISO/DIS 12312-1:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 94 *Personal safety – Personal protective equipment*, Subcommittee SC 6, *Eye and face protection*.

This second edition cancels and replaces the first edition (ISO 12312-1:2013), which has been technically revised.

The main changes compared to the previous edition are as follows:

- added a specification for the electro-optical filters;
- replaced the "local variations in refractive power" with the "spatial deviation";
- introduced the activation of photochromic lenses at 5 °C and 35 °C as optional information;
- extended the side protection to children's sunglasses mounting filter category 4 lenses.

A list of all parts in the ISO 12312 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Eye and face protection — Sunglasses and related eyewear —

Part 1: Sunglasses for general use

1 Scope

This part of ISO 12312 is applicable to all afocal (plano power) sunglasses and clip-ons for general use, including road use and driving, intended for protection against solar radiation.

Information on the use of sunglass filters is given in [Annex A](#). Requirements for unmounted filters used as replacement or alternative filters are given in [Annex C](#).

This part of ISO 12312 is not applicable to:

- a) eyewear for protection against radiation from artificial light sources, such as those used in solaria;
- b) eye protectors intended for specific sports (e.g. ski goggles or other types);
- c) sunglasses that have been medically prescribed for attenuating solar radiation;
- d) products intended for direct observation of the sun, such as for viewing a partial or annular solar eclipse;
- e) products intended for occupational eye protection.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4007:2018, *Personal protective equipment — Eye and face protection — Vocabulary*

ISO 8980-5:2005, *Ophthalmic optics — Uncut finished spectacle lenses — Part 5: Minimum requirements for spectacle lens surfaces claimed to be abrasion-resistant*

ISO 12311:2013, *Personal protective equipment — Test methods for sunglasses and related eyewear*

ISO 18526-1:2020, *Eye and face protection — Test methods — Part 1: Geometrical optical properties*

ISO 18526-2:2020, *Eye and face protection — Test methods — Part 2: Physical optical properties*

ISO 18526-4:2020, *Eye and face protection — Test methods — Part 4: Headforms*

ISO 12870:2016, *Ophthalmic optics — Spectacle frames — Requirements and test methods*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4007 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

ISO/DIS 12312-1:2021(E)

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1 related eyewear

eyewear intended for protection in the same wavelength range as solar radiation but not necessarily originated by natural sunlight

3.2 electro-optical sunglare filter electro-optical sunglass filter

filter that varies, by electro-optical means, its luminous transmittance depending upon the irradiance and wavelengths of the radiation to which it is exposed or under manual control

Note 1 to entry: The change may be under fully automatic or fully manual control, or under a combination, for example where the luminous transmittance in the faded and darkened states is set manually, variation between them automatically. The luminous transmittance of the filter therefore adjusts itself within certain limits to the ambient radiant flux.

3.3 reaction time

t_r

«*electro-optical sunglare filter*» response time of an *electro-optical sunglare filter* to darken from its *faded state* towards its *darkened state* when activated or to fade from its *darkened state* towards its *faded state*

Note 1 to entry: The reaction time is the time taken for the filter to change luminous transmittance from τ_{v0} to $\{\tau_{v0} - 0.9 \times (\tau_{v0} - \tau_{v1})\}$ or from τ_{v1} to $\{\tau_{v1} + 0.9 \times (\tau_{v0} - \tau_{v1})\}$.

where

τ_{v0} is the *luminous transmittance* of the *lens* or *filter* in the faded state;

τ_{v1} is the *luminous transmittance* of the *lens* or *filter* in the darkened state.

3.4 absorption ratio AR

«for an *electro-optical sunglare filter*» ratio of the luminous transmittance in the faded state to that in the darkened state

Note 1 to entry: The attenuation ratio, *AR*, is calculated from the following formula:

$$AR = \frac{\tau_{v0}}{\tau_{v1}}$$

where

τ_{v0} is the *luminous transmittance* of the *lens* or *filter* in the faded state;

τ_{v1} is the *luminous transmittance* of the *lens* or *filter* in the darkened state.

3.5 default mode

luminous transmittance state of an electro-optical sunglare filter when the power supply is disconnected or malfunctions

Note 1 to entry: The power supply can be mains electricity, a battery or a photovoltaic cell.

4 Construction and materials

4.1 Construction

When tested in accordance with ISO 12311:2013, Clause 6, areas of the sunglass, including the frame and, if in a rimless or semi-rimless style, the edges of the filters that may come into contact with the wearer during intended use shall be smooth and without sharp projections.

NOTE Manufacturers should restrict the range of screw sizes and threads used in sunglass frames to those specified in ISO 11381:2016 *Optics and optical instruments – Ophthalmic optics – Screw threads*.

4.2 Filter material and surface quality

When tested in accordance with ISO 12311:2013, 6.2, except in a marginal area 5 mm wide, sunglass filters shall have no material or machining defects within an area of 30 mm diameter centred on the reference point that might impair vision, e.g. bubbles, scratches, inclusions, dull spots, pitting, mould marks, notches, reinforced areas, specks, beads, water specks, pocking, gas inclusions, splintering, cracks, polishing defects or undulations. If a 5 mm wide portion around the edge of the test sample intrudes into this circular area, then this intrusion shall be excluded from testing.

4.3 Physiological compatibility

Sunglasses shall be designed manufactured and packaged in such way that, when used under normal conditions they will not compromise the health or safety of the wearer. The risks posed by substances leaking or evaporating from the sunglasses that can come into prolonged contact with the wearer, shall be reduced by the manufacturer to within the limit of any applicable regulatory requirement.

Special attention shall be given to substances that are allergenic, carcinogenic, mutagenic or toxic to reproduction.

NOTE 1 Excessive pressure due to a poor fit on the head, chemical irritation and allergy are known to produce reactions. Rare or idiosyncratic reactions to any material known to occur and the individual wearer is well advised to avoid those types of frame materials.

Substances recommended for cleaning, maintenance or disinfection shall be known to be unlikely to have any adverse effect upon the wearer, when applied in accordance with the instructions given in the information to be supplied by the manufacturer.

Manufacturers/suppliers shall perform an appropriate risk analysis on potentially harmful substances contained in the sunglasses that, when the sunglasses are used under normal conditions, the health (and safety) of the wearer shall not be compromised.

The following are examples of documents that represent the appropriate information.

- a) Specification of the material(s)
- b) Safety data sheets relating to the materials
- c) Information relating to the suitability of the materials for use with food, in medical devices, or other relevant applications
- d) Information relating to toxicological, allergenic, carcinogenic, toxic to reproduction, or mutagenic investigations on the materials.

NOTE 2 Attention is drawn to specific national regulations that restrict chemical substances, e.g. ISO 12870, 4.2.3 for nickel release test methods and requirements.

ISO/DIS 12312-1:2021(E)

4.4 Headforms

Unless the manufacturer specifies the headform(s) in accordance with ISO 18526-4:2020 that is/are compatible with the sunglasses, the test methods where (a) headform(s) is/are required shall use the headform 1-M in accordance with ISO 18526-4:2020 as the default.

5 Transmittance

5.1 Test methods

Transmittance values shall be determined in accordance with ISO 12311:2013, Clause 7. If the direction of measurement is not specified, then it shall be measured normal to the surface of the test sample at the geometrical centre.

5.2 Transmittance and filter categories

Sunglass filters for general use shall be assigned to one of five filter categories based on the luminous transmittance at their reference point.

The range of the luminous transmittance of these five categories is given by the values in [Table 1](#). An overlap of the transmittance values shall be not more than $\pm 2\%$ (absolute) between adjacent categories 0, 1, 2 and 3. There is no overlap in transmittance values between categories 3 and 4.

The maximum deviation for the declared luminous transmittance value shall be $\pm 3\%$ absolute for the transmittance values falling in categories 0 to 3 and $\pm 30\%$ relative to the stated value for the transmittance values falling in category 4.

For gradient-tinted and/or mirrored filters, the maximum deviation for the declared luminous transmittance value shall be double that for uniformly tinted lenses.

When describing the transmittance properties of photochromic filters, two categories for transmittance values are generally used. These two values correspond to the faded state and to the darkened state of the filter.

In the case of gradient-tinted filters, the transmittance value at the reference point shall be used to characterize the luminous transmittance and the category of the filter.

For gradient-tinted filters, the overlap in luminous transmittance allowed between categories shall be double that for uniformly tinted filters.

[Table 1](#) also specifies the UV requirements for sunglass filters for general use and, when the filters are claimed by the manufacturer to protect against IR radiation, the IR requirements.

Table 1 — Transmittance for sunglass filters for general use

Consumer label	Technical label	Requirements			
Usage	Filter category	Ultraviolet spectral range		Visible spectral range	Enhanced infra-red absorption ^a
		Maximum value of solar UV-B transmittance τ_{SUVB} 280 nm to 315 nm	Maximum value of solar UV-A transmittance τ_{SUVA} 315 nm to 380 nm	Range of luminous transmittance τ_v 380 nm to 780 nm	Maximum value of solar IR transmittance τ_{SIR} 780 nm to 2 000 nm
Very limited reduction of sunglare	0	0,05 τ_v	τ_v	$\tau_v > 80 \%$	τ_v
Limited protection from sunglare	1	0,05 τ_v	τ_v	$43 \% < \tau_v \leq 80 \%$	τ_v
Good protection against sunglare	2	1,0 % absolute or 0,05 τ_v , whichever is greater	0,5 τ_v	$18 \% < \tau_v \leq 43 \%$	τ_v
High protection against sunglare	3	1,0 % absolute	0,5 τ_v	$8 \% < \tau_v \leq 18 \%$	τ_v
Very high protection against extreme sunglare, e.g. at sea, over snowfields, on high mountain, or in desert	4	1,0 % absolute	1,0 % absolute or 0,25 τ_v , whichever is greater	$3 \% < \tau_v \leq 8 \%$	τ_v
NOTE The upper limit of UV-A at 380 nm is consistent with that used in ophthalmic optical standards and in ISO 20473, <i>Optics and photonics — Spectral bands</i> .					
^a Only applicable to sunglass filters recommended by the manufacturer as a protection against infrared radiation.					

5.3 General transmittance requirements

5.3.1 Uniformity of luminous transmittance

The relative difference in the luminous transmittance value between any two points of the filter within a circle 30 mm in diameter centred on the reference point shall not be greater than 15 % (relative to the higher value), except for category 4 where it shall not be greater than 20 %. If a 5 mm wide portion around the edge of the test sample intrudes into this circular area, then this intrusion shall be excluded from testing.

The geometric or boxed centre takes the place of the reference point if this is not known.

In the case of mounted gradient filters, this requirement shall be limited to sections parallel to the line connecting the two reference points.

For mounted filters, the relative difference between the luminous transmittance value of the filters at the reference point for the right and left eyes shall not exceed 20 % for gradient-tinted filters and 15 % for all other types (relative to the lighter filter).

Changes of luminous transmittance that are caused by thickness variations due to the design of the filter are permitted. For verification, the test method in ISO 12311:2013, Annex L shall be used.

ISO/DIS 12312-1:2021(E)

5.3.2 Requirements for road use and driving

5.3.2.1 General

Filters suitable for road use and driving shall be of categories 0, 1, 2 or 3 and shall additionally meet the following two requirements.

- a) *Spectral transmittance*. The spectral transmittance of filters suitable for road use and driving for wavelengths between 475 nm and 650 nm shall be not less than $0,2 \tau_v$.
- b) *Detection of signal lights*. The relative visual attenuation quotient Q of filters of categories 0, 1, 2 and 3 suitable for road use and driving shall be not less than 0,80 for red signal light and not less than 0,60 for yellow, green and blue signal lights. The relative visual attenuation quotient for signal light detection Q_{signal} shall be calculated in accordance with ISO 12311:2013, 7.8 (spectral distribution of radiation emitted by incandescent lights).

5.3.2.2 Road use (including driving) in twilight or at night

Sunglass filters with a luminous transmittance of less than 75 % shall not be used in twilight or at night for road use (including driving). In case of photochromic sunglass filters, this requirement applies when tested in accordance with ISO 12311:2013, 7.11.

5.3.3 Wide-angle scatter

When tested in accordance with ISO 12311:2013, 7.9 at the reference point, the wide-angle scatter of the filters in the condition as supplied by the manufacturer shall not exceed the value of 3 %.

5.3.4 Additional transmittance requirements for specific filter types

5.3.4.1 Photochromic filters

The categories of the photochromic filter shall be determined by its luminous transmittance in its faded state, τ_{v0} , and its luminous transmittance in its darkened state, τ_{v1} , achieved after 15 min irradiation according to ISO 12311:2013, 7.11. In both states, the requirements specified in 5.2 and, if applicable, the requirements specified in 5.3.2, shall be met. For photochromic filters, τ_{v0}/τ_{v1} shall be $\geq 1,25$.

Optionally, the luminous transmittance can be measured also at temperatures of 5 °C and 35 °C.

5.3.4.2 Polarizing filters

If the filters in the sunglasses are claimed to be polarizing, when tested in accordance with ISO 12311:2013, 7.10.1, the filters shall be fitted in the frame so that their planes of transmission do not deviate from the vertical, or from the specified direction if different from the vertical, by more than $\pm 5^\circ$. Additionally, any misalignment between the planes of transmission of the left and right filters shall not be greater than 6° .

In the case of clip-ons, the misalignment shall be tested in the position assumed to be taken when mounted on the spectacles or sunglasses.

When tested in accordance with ISO 12311:2013, 7.10.2, the polarization efficiency shall be $> 78 \%$ for filter categories 2, 3, 4 and $> 60 \%$ for filter category 1. Filters of category 0 do not have any useful polarizing effect.

NOTE The polarizing efficiency values of 78% and 60% are approximately equal to polarizing ratio values of 8:1 and 4:1 respectively.

5.3.4.3 Gradient-tinted filters

5.3.4.3.1 General

All parts of a gradient-tinted filter within a 10 mm radius circle centred on the reference point shall comply with the transmittance requirements in [clause 5.2](#) and, for filters suitable for road use and driving, [clauses 5.3.2](#) (except for the filter category which is defined by the transmittance at the reference point). Uniformity of transmission is subject to the requirements of [5.3.1](#).

5.3.4.3.2 Determination of the filter category

The filter category of gradient-tinted filters shall be determined by the luminous transmittance value at the reference point.

The filter category determined at the reference point shall be used to define whether the filters are suitable for road use and driving according to [5.3.2](#).

5.3.4.4 Electro-optical sunglare filter, sunglass filter

5.3.4.4.1 General

The categories of the electro-optical filter shall be determined by its luminous transmittance in its faded state τ_{v0} and its luminous transmittance in its darkened state τ_{v1} achieved after 15 min irradiation in accordance with ISO 12311:2013, 7.11. In both states, the filter shall comply with the requirements specified in [5.2](#), and, if applicable, the requirements specified in [5.3.2](#).

In case of electro-optical filters with manual control, the faded and darkened state have to be set manually as specified by the manufacturer instead of by irradiation.

5.3.4.4.2 Default mode

Electro-optical sunglare filters, when in the default mode, shall comply with all other relevant requirements.

5.3.4.4.3 Reaction time

The reaction time of electro-optical filters to change from the faded (high transmittance) state to the darkened (low transmittance) state, or, from the darkened state to the faded state, shall be measured when changing from (500 ± 50) lx to $50\,000 \pm 5\,000$ lx or vice-versa according to ISO 18526-2:2020, 17.11.

The measurements shall be taken at 5 °C, 23 °C and 35 °C and the results reported (in [12.1](#)).

5.3.4.4.4 Flicker

An inherent technology specific property of an electro-optical filter (image retention), or, external flashing sunlight can, under very rare circumstances, trigger the detection system of an electro-optical filter and provoke flicker. In order to prevent “photosensitive epilepsy”, triggered by flashing light in the frequency range of 3 to 60 Hz, the manufacturer shall provide proof that the electro-optic filter is free from flicker when exposed to direct sunlight that is modulated in the defined frequency range, e.g. by a rotating mechanical shutter. Flicker of an electro-optical filter is defined as the filter continuously switching from the faded to the darkened state and back again.

5.3.4.4.5 Combined uniformity and angular dependence of luminous transmittance

The combined uniformity and angular dependence of the luminous transmittance in the darkened state of electro-optical filters shall comply with the requirements of [Table 2](#) for the angles of incidence between 0° and $\pm 30^\circ$. The darkened state transmittance shall be tested according to ISO 18526-2:2020, clause 17.8 in the as-worn position.