



Designation: D 5772 – 95

An American National Standard



Designation: IP 445/99

## Standard Test Method for Cloud Point of Petroleum Products (Linear Cooling Rate Method)<sup>1</sup>

This standard is issued under the fixed designation D 5772; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

### INTRODUCTION

This test method describes an alternative procedure for the determination of cloud point of petroleum products of Test Method D 2500/IP219 using an automatic apparatus. The temperature results from this test method have been found to be equivalent to Test Method D 2500/IP219. When specification requires Test Method D 2500/IP219, do not substitute this test method or any other method without obtaining comparative data and agreement from the specifier.

### 1. Scope

1.1 This test method describes the determination of the cloud point of petroleum products that are transparent in layers 40 mm in thickness by an automatic instrument using a linear cooling rate.

1.2 This test method covers the range of temperatures from  $-40$  to  $49^{\circ}\text{C}$  with temperature resolution of  $0.1^{\circ}\text{C}$ .

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 2500 Test Method for Cloud Point of Petroleum Products<sup>2</sup>

D 4057 Practice for Manual Sampling of Petroleum and Petroleum Products<sup>3</sup>

D 4177 Practice for Automatic Sampling of Petroleum and Petroleum Products<sup>3</sup>

#### 2.2 IP Standard:

IP219 Test Method for Cloud Point of Petroleum Products<sup>4</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *cloud point,  $n$* — in petroleum products, the temperature of a liquid specimen when a wax crystal structure that is similar in appearance to a cloud is formed upon cooling under prescribed conditions.

3.1.1.1 *Discussion*—The cloud point appears when the temperature of the specimen is low enough to cause wax crystals to precipitate. In homogeneous liquids, the cloud is always noted first at the location in the specimen where the specimen temperature is the lowest. This is typically at the lower portion of the test jar when using the apparatus described in Test Method D 2500.

#### 3.2 Descriptions of Terms Specific to This Standard:

3.2.1 *automatic cloud point,  $n$* —the temperature of a specimen when the appearance of the cloud is determined under the conditions of this test method.

3.2.1.1 *Discussion*—The cloud point in this test method is determined by an automatic instrument using an optical device for detection of the crystal formation. The apparatus and the conditions are different from those established for Test Method D 2500, although, according to interlaboratory examination, the results have been determined to be equivalent to Test Method D 2500.

3.2.2 *D 2500/IP219 equivalent cloud point,  $n$* —the temperature of a specimen, in integers, calculated by rounding the results of this test method to the next lower integer.

3.2.2.1 *Discussion*—This test method produces results with

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-2 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.07 on Flow Properties.

Current edition approved Sept. 10, 1995. Published November 1995.

<sup>2</sup> Annual Book of ASTM Standards, Vol 05.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 05.02.

<sup>4</sup> IP standards are available from the Institute of Petroleum, 61 New Cavendish St. London, England W1M 8AR.

0.1°C resolution. Should the user wish to provide results with a similar format to Test Method D 2500, then this calculation can be performed. Some apparatus can perform this calculation automatically.

#### 4. Summary of Test Method

4.1 After insertion of the specimen into the apparatus and initiation of the program, the specimen is heated and then cooled at a specified rate. The specimen is continuously monitored by an optical light barrier for the crystal structure formation. The temperature when the crystallization of the wax in the specimen is detected by the optical barrier is recorded with a resolution of 0.1°C. The specimen is then heated to the original starting temperature.

#### 5. Significance and Use

5.1 The cloud point of a petroleum product is an index of the lowest temperature of its utility for certain applications. Wax crystals of sufficient quantity can plug filters used in some fuel systems.

5.2 Petroleum blending operations require precise measurement of the cloud point.

5.3 This test method can determine the temperature of the test specimen at which wax crystals have formed sufficiently to be observed as a cloud, with a resolution of 0.1°C.

5.4 This test method provides results that when rounded to the next lower integer are equivalent to Test Method D 2500.

5.5 This test method is more precise than Test Method D 2500.

#### 6. Apparatus

6.1 *Automatic Apparatus*<sup>5</sup>—The automatic cloud point apparatus described in Annex A1 consists of a microprocessor-controlled measuring unit that is capable of heating, cooling, optically observing the appearance of the automatic cloud point, and recording the temperature of the specimen. The apparatus shall be equipped with a digital display, cooling/heating block assembly, optical light barrier assembly, and a test cell of the approximate dimensions listed in Annex A1, and contain a temperature measuring device.

6.2 *Beaker*, glass or plastic (disposable) (50 mL), for containing the sample prior to introduction into the test cell.

6.3 *Circulating Bath*, a refrigeration unit equipped with a circulating pump capable of maintaining a temperature at least 20°C lower than the lowest expected cloud point to be measured.

#### 7. Reagents and Materials

7.1 *Cleaning Solvents*, suitable for cleaning and drying the test cell, such as petroleum naphtha and acetone.

NOTE 1—**Warning:** Flammable. Liquid causes eye burns. Vapor is harmful. May be fatal or cause blindness if swallowed or inhaled.

7.2 *Methyl Alcohol*, anhydrous, for use as cooling medium in circulating bath.

#### 8. Sampling

8.1 Obtain a sample in accordance with Practices D 4057 or D 4177.

8.2 Samples of very viscous materials may be warmed until they are reasonably fluid before they are sampled. However, no sample should be heated more than absolutely necessary.

8.3 The sample shall not be heated above 70°C. When the sample is heated above 70°C, allow the sample to cool below 70°C before filtering or inserting into the apparatus.

8.4 When moisture is present in the sample, remove the moisture by a method such as filtration through dry lint-free filter paper until the oil is perfectly clear. Make such filtration at a temperature at least 14°C above the expected cloud point.

NOTE 2—Moisture will be noticed in the sample as a separate phase or as a haze throughout the entire sample. Generally, a slight haze will not interfere with the detection of the wax cloud.

#### 9. Preparation of Apparatus

9.1 Prepare the instrument for operation in accordance with the manufacturer's instructions.

9.2 Clean and dry the test cell using suitable solvents as prescribed by the manufacturer.

9.3 Prepare the refrigerated circulating bath for operation in accordance with the manufacturer's instructions and allow it to attain a temperature at least 20°C lower than the expected cloud point of the sample.

#### 10. Calibration and Standardization

10.1 Ensure that all of the manufacturer's instructions for calibrating, checking, and operating the apparatus are followed.

10.2 A sample with a mutually agreed upon cloud point can be used to verify performance of the apparatus.

#### 11. Procedure

11.1 Pour at least 20 mL of the sample into the beaker. When necessary, heat the sample in a water bath or oven until it is just sufficiently fluid to pour into the beaker.

11.2 Place the beaker under the entrance of the test cell and start the test in accordance with the manufacturer's instructions.

11.3 When the expected cloud point is known to be above 25°C, preselect a starting temperature which is at least 14°C above the expected cloud point. The highest starting temperature that can be programmed is 70°C.

11.4 When the expected cloud point is known to be at or below 25°C, the test duration can be shortened by preselecting a starting temperature which is at least 14°C above the expected cloud point. The lowest starting temperature that can be programmed is 20°C.

11.5 When the expected cloud point is not known, preselect a starting temperature of 40°C. The apparatus automatically heats the test specimen to approximately 40°C when a starting temperature is not selected. When the expected cloud point is not known and the sample needs to be heated before transferring into the test specimen beaker, preselect a starting temperature of 70°C.

11.6 A portion of the sample is drawn into the test cell. Initially, the specimen is heated to 40°C or to a starting

<sup>5</sup> The following instrument has been found suitable for use in this test method: Herzog Model SC 815 and SC 819 available from Walter Herzog, Lauda, Germany.

temperature preselected by the operator between 20 and 70°C. The flow of the cooling fluid from the circulating bath is then regulated to maintain the rate of cooling of the specimen at  $1 \pm 0.2^\circ\text{C}$  per min (see Note 3). The specimen is continuously monitored by the optical light barrier and the specimen temperature is continuously displayed. At the detection of the automatic cloud point, the temperature the specimen attained, to within  $0.1^\circ\text{C}$  resolution, is held on the digital display until cleared by the operator. The specimen is then heated to  $40^\circ\text{C}$  or to the preselected starting temperature.

NOTE 3—Although the apparatus is capable of faster cooling rates of 2 or  $3^\circ\text{C}/\text{min}$ , the interlaboratory program does not address the equivalency and precision of results using these cooling rates.

11.7 Clean the test cell by flushing solvents through the cell and then dry with clean air according to the manufacturer's instructions.

NOTE 4—Some apparatus is capable of automatic cleaning of the test cell and automatic sample changing.

## 12. Report

12.1 Report the temperature recorded in 11.6 as the automatic cloud point D 5772.

12.2 When specified, round the temperature recorded in 11.6 to the next lower integer and report as the D 2500 equivalent cloud point in accordance with Test Method D 5772.

## 13. Precision and Bias <sup>6</sup>

13.1 *Precision*—The precision of this test method as determined by the statistical examination of the interlaboratory<sup>6</sup> test results is as follows:

13.1.1 *Repeatability*—The difference between successive test results obtained by the same operator using the same apparatus under constant operating conditions on identical test material would in the long run, in the normal and correct operation of this test method, exceed  $0.8^\circ\text{C}$  only in one case in twenty.

13.1.2 *Reproducibility*—The difference between two single and independent test results obtained by different operators working in different laboratories on identical test material would in the long run, in the normal and correct operation of this test method, exceed  $3.7^\circ\text{C}$  only in one case in twenty.

13.2 *Bias*—Since there is no accepted reference material suitable for determining the bias for the procedure in this test method, bias has not been determined.

13.3 *Relative Bias*—The results of the interlaboratory program were examined for bias relative to Test Method D 2500/IP219. Although statistically significant bias was observed, the magnitude was determined to be small enough ( $-0.67^\circ\text{C}$ ) to be of little practical significance.

13.4 The precision statements were derived from a 1990 interlaboratory cooperative test program.<sup>6</sup> Participants analyzed ten sample sets comprised of various distillate fuels and lubricating oils with a temperature range from  $-1$  to  $-37^\circ\text{C}$ . Eight laboratories participated with the automatic apparatus and eight laboratories participated with the manual Test Method D 2500/IP219 test method. Information on the type of samples and their average cloud points are in the research report.<sup>6</sup>

NOTE 5—The precision statements were derived only from samples with temperatures below  $0^\circ\text{C}$ . An interlaboratory test program has been initiated to include the temperatures between 0 and  $+50^\circ\text{C}$ , and will also include some samples below  $-37^\circ\text{C}$ .

## 14. Keywords

14.1 automatic cloud point; cloud point; D 2500 equivalent cloud point; petroleum products

<sup>6</sup> The results of the 1990 interlaboratory cooperative test program are available from ASTM Headquarters. Request ASTM RR: D02-1373.