



Designation: ~~D1730-03~~ Designation: D 1730 – 09

Standard Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting¹

This standard is issued under the fixed designation D 1730; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 These practices cover four types of treatment for preparation of aluminum and aluminum-alloy surfaces for painting, as follows:

- 1.1.1 Type A—Solvent Cleaning.
- 1.1.2 Type B—Chemical Treatments.
- 1.1.3 Type C—Anodic Treatments.
- 1.1.4 Type D—Mechanical Treatments. These four types cover a number of procedures, as described herein.

1.2 Variations in surface treatment produce end conditions which differ, and which do not necessarily yield identical results when paints are applied. Service conditions will dictate the type of surface preparation that should be selected, although the quality produced by any individual method may vary with different alloys.

1.3 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

D 609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products

2.2 Military Standards:

~~MIL-C-5541 Chemical Conversion Coatings on Aluminum and Aluminum Alloys~~ Military Standards:³

MIL-A-8625 Anodic Coatings for Aluminum and Aluminum Alloys

MIL-DTL-5541 Chemical Conversion Coatings on Aluminum and Aluminum Alloys

MIL-M-10578B Metal Conditioner and Rust Remover (Phosphoric Acid Type)

MIL-P-15328bB Coating Compound – Metal Pretreatment Resin Resistant

2.3 Federal Specification:³

TT-C-490 Chemical Conversion Coatings and Pretreatments for Ferrous Surfaces (Base for Organic Coatings)

3. Type A—Solvent Cleaning

3.1 Solvent cleaning does not disturb the natural oxide film on the metal and may prove adequate for some applications, such as ambient indoor or very mild service conditions. Three methods may be employed, as follows:

3.1.1 *Method 1, Manual Swabbing or Dip-Washing*, with a solvent such as mineral spirits or high-flask solvent naphtha. With this method it is extremely difficult to prevent accumulation of contaminants on the swab or in the solvent. This method is only recommended when other treatments are impractical.

3.1.2 *Method 2, Solvent Spray Cleaning*, in accordance with Method A, Procedure 1 of Practice D 609.

3.1.3 *Method 3, Vapor Degreasing*, in special equipment employing trichloroethylene vapor, in accordance with Method A, Procedure 2 of Practice D 609.

¹ These practices are under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.07 on Conversion Coatings on Chromate Conversion Coatings.

Current edition approved Sept. 10, 2003; April 15, 2009. Published Sept. 2003; May 2009. Originally approved in 1960. Last previous edition approved in 1998 as D1730-67(1998); D 1730-03.

² Annual Book of ASTM Standards, Vol 06.01.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098