



SLOVENSKI STANDARD
oSIST prEN 4718:2021
01-junij-2021

Aeronavtika - Polietereeterketon s 55 % neprekinjenih steklenih vlaken (PEEK-GF55) - Zaloga materiala - Specifikacija materialov

Aerospace series - Polyetheretherketone with 55 % continuous glass fibre by volume (PEEK-GF55) - Stock shape material - Material specification

Luft- und Raumfahrt - Polyetheretherketon mit 55 Volumen-% Endlos-Glasfaser (PEEK-GF55) - Halbfabrikat - Materialspezifikation

Série aérospatiale - Polyétheréthercétone avec 55 % de fibre de verre continue par volume (PEEK-GF55) - Demi-produit - Spécification de matériau

[oSIST prEN 4718:2021](https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5817d4bb7b12/osist-pr-en-4718-2021)

[https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-](https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5817d4bb7b12/osist-pr-en-4718-2021)

[5817d4bb7b12/osist-pr-en-4718-2021](https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5817d4bb7b12/osist-pr-en-4718-2021)

Ta slovenski standard je istoveten z: prEN 4718

ICS:

49.025.40 Guma in polimerni materiali Rubber and plastics

oSIST prEN 4718:2021

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 4718:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5fd7ddb7b12/osist-pren-4718-2021>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 4718

April 2021

ICS 49.025.40

English Version

Aerospace series - Polyetheretherketone with 55 % continuous glass fibre by volume (PEEK-GF55) - Stock shape material - Material specification

Série aérospatiale - Polyétheréthercétone avec 55 % de
fibre de verre continue par volume (PEEK-GF55) -
Demi-produit - Spécification de matériau

Luft- und Raumfahrt - Polyetheretherketon mit 55
Volumen-% Endlos-Glasfaser (PEEK-GF55) -
Halbfabrikat - Materialspezifikation

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ASD-STAN.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page
European foreword		3
1	Scope.....	4
2	Normative references.....	4
3	Terms and definitions.....	5
4	Requirements.....	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 4718:2021](https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5fd7ddb7b12/osist-pren-4718-2021)
<https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5fd7ddb7b12/osist-pren-4718-2021>

European foreword

This document (prEN 4718:2021) has been prepared by the Aerospace and Defence Industries Association of Europe — Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this document has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This document is currently submitted to the Enquiry.

This document will supersede EN 4718:2014.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 4718:2021](https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5fd7ddb7b12/osist-pren-4718-2021)

<https://standards.iteh.ai/catalog/standards/sist/69930922-1ffe-432f-8a43-5fd7ddb7b12/osist-pren-4718-2021>

prEN 4718:2021 (E)**1 Scope**

This document specifies the requirements of a thermoplastic composite stock shape material (e.g. tape, rod etc.) consisting of polyetheretherketone with 55 % continuous glass fibres by volume (PEEK – GF55) for aerospace applications, which is presupposed to be used in a further thermal moulding process for forming parts described in prEN 4714 ¹⁾.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2825, *Aerospace series - Burning behaviour of non metallic materials under the influence of radiating heat and flames - Determination of smoke density*

EN 2826, *Aerospace series - Burning behaviour of non metallic materials under the influence of radiating heat and flames - Determination of gas components in the smoke*

EN 3844-1, *Aerospace series - Flammability of non-metallic materials - Part 1: Small burner test, vertical - Determination of the vertical flame propagation*

prEN 4714, *Aerospace series — Screws, bolts and nuts of continuous fibre reinforced PAEK (Polyaryletherketone) composite material — Technical specification* ¹⁾

ISO 75-3, *Plastics — Determination of temperature of deflection under load — Part 3: High-strength thermosetting laminates and long-fibre-reinforced plastics* ²⁾

ISO 175, *Plastics — Methods of test for the determination of the effects of immersion in liquid chemicals*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing* ²⁾

ISO 1172, *Textile-glass-reinforced plastics — Prepregs, moulding compounds and laminates — Determination of the textile-glass and mineral-filler content — Calcination methods*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids* ²⁾

ISO 3597-2, *Textile-glass-reinforced plastics — Determination of mechanical properties on rods made of roving-reinforced resin — Part 2: Determination of flexural strength*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 14125, *Fibre-reinforced plastic composites — Determination of flexural properties* ²⁾

ASTM D2343-17, *Standard Test Methods for Properties of Glass Fiber Strands, Yarns, and Rovings Used in Reinforced Plastics* ³⁾

¹⁾ In preparation at the date of publication of this document.

²⁾ Published by: ISO International Organization for Standardization <http://www.iso.ch/>.

³⁾ Published by: ASTM International (US) American Society for Testing and Materials <http://www.astm.org/>.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Requirements

See Table 1.

Table 1

No.	Properties	Test methods	Specimen directions	Units	Requirements	Test conditions and supplementary instructions	
Material							
Mechanical properties							
1	Flexural strength	ISO 14125 Method A ISO 3597-2	0°	MPa	≥ 850	Test specimen Class III	
			90°		≥ 50		
			0° circular rod		≥ 800	round	
2	Flexural strain at break	ISO 14125 Method A	0°	%	≥ 2	Test specimen Class III	
			90°		≥ 0,6		
3	Flexural modulus	ISO 14125 Method A	0°	GPa	≥ 40	Test specimen Class III	
			90°		≥ 8,4		
Thermal properties							
4	Temperature of deflection under load	ISO 75-3	0°	°C	140	-	
Burning behaviour							
5	Flammability, vertical 12 s	EN 3844-1	-	mm	203 max.	Thickness of specimen: 1,5 mm	
					after flame time		15 max.
					after flame time of drips		5 max.
6	Smoke density flaming mode	EN 2825	-	-	200 max.		
					at 240 s		
7	Concentration of smoke gas components after 4 min flaming mode	EN 2826	-	ppm	100 max.		
					HF	150 max.	
					HCl	150 max.	
					HCN	100 max.	
					SO ₂	100 max.	
NO/NO ₂	100 max.						