



SLOVENSKI STANDARD
oSIST prEN 13523-18:2019
01-julij-2019

Prevlečene kovine, ki se navijajo - Preskusne metode - 18. del: Odpornost proti nastanku madežev

Coil coated metals - Test methods - Part 18: Resistance to staining

Bandbeschichtete Metalle - Prüfverfahren - Teil 18: Beständigkeit gegen Fleckenbildung

Tôles prélaquées - Méthodes d'essai - Partie 18 : Résistance aux taches

Ta slovenski standard je istoveten z: prEN 13523-18

ICS:

25.220.60 Organske prevleke Organic coatings

oSIST prEN 13523-18:2019 **en,fr,de**

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 13523-18

June 2019

ICS 25.220.60

Will supersede EN 13523-18:2002

English Version

Coil coated metals - Test methods - Part 18: Resistance to staining

Tôles prélaquées - Méthodes d'essai - Partie 18 :
Résistance aux taches

Bandbeschichtete Metalle - Prüfverfahren - Teil 18:
Beständigkeit gegen Fleckenbildung

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 139.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Principle	5
5 Apparatus.....	5
6 Substances	6
7 Sampling.....	6
8 Test panels.....	6
9 Procedure.....	6
9.1 General.....	6
9.2 Spot test (covered).....	6
9.3 Spot test (open).....	7
9.4 Immersion test.....	7
10 Expression of results.....	7
11 Precision.....	7
12 Test report.....	8
Bibliography.....	9

European foreword

This document (prEN 13523-18:2019) has been prepared by Technical Committee CEN/TC 139 “Paints and varnishes”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 13523-18:2002.

The main changes are:

- a) the required supplementary information (former Clause 10) has been integrated in the test report;
- b) the text has been editorially revised and the normative references have been updated.

The EN 13523 series, *Coil coated metals — Test methods*, consists of the following parts:

- *Part 0: General introduction*
- *Part 1: Film thickness*
- *Part 2: Gloss*
- *Part 3: Colour difference — Instrumental comparison*
- *Part 4: Pencil hardness*
- *Part 5: Resistance to rapid deformation (impact test)*
- *Part 6: Adhesion after indentation (cupping test)*
- *Part 7: Resistance to cracking on bending (T-bend test)*
- *Part 8: Resistance to salt spray (fog)*
- *Part 9: Resistance to water immersion*
- *Part 10: Resistance to fluorescent UV radiation and water condensation*
- *Part 11: Resistance to solvents (rubbing test)*
- *Part 12: Resistance to scratching*
- *Part 13: Resistance to accelerated ageing by the use of heat*
- *Part 14: Chalking (Helmen method)*
- *Part 15: Metamerism*
- *Part 16: Resistance to abrasion*
- *Part 17: Adhesion of strippable films*
- *Part 18: Resistance to staining*

prEN 13523-18:2019 (E)

- *Part 19: Panel design and method of atmospheric exposure testing*
- *Part 20: Foam adhesion*
- *Part 21: Evaluation of outdoor exposed panels*
- *Part 22: Colour difference — Visual comparison*
- *Part 23: Resistance to humid atmospheres containing sulfur dioxide*
- *Part 24: Resistance to blocking and pressure marking*
- *Part 25: Resistance to humidity*
- *Part 26: Resistance to condensation of water*
- *Part 27: Resistance to humid poultice (Cataplasm test)*
- *Part 29: Resistance to environmental soiling (Dirt pick-up and striping)*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13523-18:2020

<https://standards.iteh.ai/catalog/standards/sist/eb51847c-dcb3-4624-a700-c0549cdd2e03/sist-en-13523-18-2020>

1 Scope

This document specifies test procedures for assessing the effect of chemicals on the characteristics of an organic coating on a metallic substrate. It covers testing by using defined substances and to assess the change in characteristics such as discoloration, change in gloss, blistering, softening, swelling and loss of adhesion. Assessment of other phenomena can be agreed between the interested parties.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13523-0, *Coil coated metals — Test methods — Part 0: General introduction*

EN 23270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing (ISO 3270)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13523-0 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

<https://standards.iteh.ai/catalog/standards/sist/eb51847c-dcb3-4624-a700-c0549cdd2e03/sist-en-13523-18-2020>

4 Principle

A coated test panel or a flat surface on a fabricated article is exposed to an individual substance for an agreed period of time. Three different test procedures can be used:

- Spot test (covered):** The substance is placed on the test panel and immediately covered with a watch glass.
- Spot test (open):** The substance is placed on the test panel and left open to the atmosphere.
- Immersion test:** The test panel is partly immersed in the substance.

5 Apparatus

Ordinary laboratory apparatus and glassware, together with the following:

- 5.1 Watch glass**, of diameter 50 mm.
- 5.2 Pipette**, of capacity 5 ml, graduated in 0,1 ml.
- 5.3 Glass beaker**, of capacity 600 ml, with a suitable cover.
- 5.4 Hotplate**, with thermostatic control.

prEN 13523-18:2019 (E)**6 Substances**

The type of substance, its composition and concentration to be used shall be agreed between the interested parties.

EXAMPLES of possible substances are:

- distilled water (cold);
- distilled water (hot);
- alkaline solution;
- diluted mineral acid;
- acetic acid;
- soap solution;
- detergent solution;
- ethanol, with a volume fraction of 50 %;
- lighter fluid and other volatile reagents;
- fruit;
- oil and fats - butter, margarine, lard, vegetable oils, etc.;
- condiments - mustard, tomato puree, curry, etc.;
- beverages - coffee, tea, cola, etc.;
- lubricating oils and greases;
- shoe polish;
- lipstick;
- marker pens;
- other substances as agreed between the interested parties.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

7 Sampling

Sampling shall be in accordance with EN 13523-0.

8 Test panels

SIST EN 13523-18:2020

<https://standards.iteh.ai/catalog/standards/sist/eb51847c-dcb3-4624-a700-c0549cdd2e03/sist-en-13523-18-2020>

Preparation and conditioning of test panels shall be in accordance with EN 13523-0.

A representative panel shall be selected from the organic coating under test. Spot and direct application techniques may be carried out on the fabricated article coated with the finishing system to be tested, if sufficient flat surface is available. For immersion tests and tests where the finished article is not available, panels shall be prepared after consultation and agreement between the interested parties.

9 Procedure**9.1 General**

The individual procedure (9.2, 9.3 or 9.4) to be used shall be agreed between the interested parties.

9.2 Spot test (covered)

Unless otherwise agreed between the interested parties, carry out the test on a single test panel at ambient temperature. In case of dispute, the ambient temperature shall be defined as (23 ± 2) °C and the relative humidity as (50 ± 5) %, in accordance with EN 23270.

Deposit the agreed substance (see the note in Clause 6) on the horizontal test panel or flat test surface of the fabricated article. For fluid substances, apply approximately 1 ml, using the pipette (5.2). For other substances, apply to an area approximately one half of the watch glass (5.1). Cover immediately with the watch glass.

After the agreed period of time, wipe gently to remove any residues of the substance and examine immediately for any change of the coating characteristics as described in Clause 1.

A typical test period is 24 h. If an intermediate examination is needed, a series of additional spots of the same substance is required. If desired and agreed, the panel may be allowed to recover for a specified time period and then examined for the return of the original properties.

9.3 Spot test (open)

Unless otherwise agreed between the interested parties, carry out the test on a single test panel at ambient temperature. In case of dispute, the ambient temperature shall be defined as (23 ± 2) °C and the relative humidity as (50 ± 5) %, in accordance with EN 23270.

Place a small portion of the agreed substance (see the note in Clause 6) on the test panel or test surface which is in horizontal position. In case of test on fruit, place a freshly cut surface in contact with the test coating.

After the agreed time period, wipe gently to remove any residues of the substance and examine immediately for any change of the characteristics as described in Clause 1.

A typical test period is 24 h. If an intermediate examination is needed, a series of additional spots of the same substance is required. If desired and agreed, the panel may be allowed to recover for a specified time period and then examined for the return of the original properties.

9.4 Immersion test

Immerse a suitably agreed and prepared test panel of dimensions typically 70 mm × 100 mm to half of its length in the agreed substance contained in the glass beaker (5.3) at the test temperature. After the agreed time period, withdraw the panel, wipe gently to remove any residues of the substance, dry with absorbent paper and examine immediately for any change of the characteristics as described in Clause 1.

If desired and agreed, the panel may be allowed to recover before examination. It is normally not necessary to seal the edges of the panel, but if the substance markedly effects the edge condition of the panel, the test should be repeated with the edges sealed, the sealer being agreed between the interested parties.

10 Expression of results

The results shall be expressed as the type of effect observed such as discoloration (staining), change in gloss, blistering, softening, swelling, loss of adhesion or any other phenomena as agreed between the interested parties.

11 Precision

No precision data are currently available.

prEN 13523-18:2019 (E)**12 Test report**

The test report shall contain at least the following information:

- a) all details necessary to identify the product tested;
- b) a reference to this document (i.e. EN 13523-18);
- c) the test procedure employed;
- d) the test temperature in degrees Celsius (to be maintained at ± 5 °C);
- e) the period of time;
- f) the time of recovery, if desired;
- g) the substances used;
- h) the observed changes in characteristics (see Clause 10);
- i) any deviation from the test method specified;
- j) any unusual features (anomalies) observed during the test;
- k) the date of the test.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13523-18:2020

<https://standards.iteh.ai/catalog/standards/sist/eb51847c-dcb3-4624-a700-c0549cdd2e03/sist-en-13523-18-2020>