
Papir, karton, lepenka in vlaknine ter celulozni nanomateriali - Določevanje suhe snovi - Metoda sušenja v sušilniku - 2. del: Materiali v trdni obliki (ISO/DIS 638-2:2020)

Paper, board, pulps and cellulosic nanomaterials - Determination of dry matter content - Oven-drying method - Part 1: Materials in solid form (ISO/DIS 638-1:2020)

Papier, Pappe, Faserstoff und cellulosehaltige Nanomaterialien - Bestimmung des Trockengehaltes - Wärmeschrankverfahren - Teil 1: Materialien in fester Form (ISO/DIS 638-1:2020)

Papiers, cartons et pâtes - Détermination de la teneur en matières sèches - Méthode par séchage à l'étuve - Partie 1: Titre manque (ISO/DIS 638-1:2020)

Ta slovenski standard je istoveten z: prEN ISO 638-1

ICS:

85.040	Vlaknine	Pulps
85.060	Papir, karton in lepenka	Paper and board

oSIST prEN ISO 638-1:2020

en,fr,de

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 638-1:2020](https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020>

DRAFT INTERNATIONAL STANDARD

ISO/DIS 638-1

ISO/TC 6

Secretariat: SCC

Voting begins on:
2020-07-24Voting terminates on:
2020-10-16

Paper, board, pulps and cellulosic nanomaterials — Determination of dry matter content — Oven-drying method —

Part 1: Materials in solid form

ICS: 85.060; 85.040

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 638-1:2020](https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020)<https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 638-1:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	2
4 Principle.....	3
5 Apparatus.....	3
6 Sampling.....	3
7 Preparation of test pieces.....	3
7.1 General.....	3
7.2 Paper and board for recycling.....	3
7.3 Paper, board, pulp and cellulosic nanomaterial in solid form.....	3
8 Procedure.....	4
9 Expression of results.....	5
9.1 Calculation.....	5
10 Test report.....	5
Annex A (informative) Calculation of the moisture content.....	6
Annex B (informative) Precision.....	7
Bibliography.....	11

<https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 638:2008), which has been technically revised.

The main changes compared to the previous edition are as follows:

- Introduction of cellulosic nanomaterials and paper and board for recycling in the scope
- Split of the standard in two parts
- Technical revision of the procedure
- Editorial revision of the document
- Update of clause of precision

Introduction

Determination of dry matter content and moisture content are carried out for different purposes.

This part of International Standard ISO 638 (ISO 638-1) should be used when the dry matter content is needed to calculate the results for chemical analysis or physical testing, or to determine the moisture content of paper and board for recycling. An example of this is where the results of a chemical analysis for cadmium or manganese are required on the basis of the oven-dry mass of the sample.

Part 2 of International Standard ISO 638 (ISO 638-2) [1] is dedicated to the determination of the dry matter content or moisture content of cellulosic nanomaterials in the form of suspensions.

ISO 287 [2] should be used for the purpose of determining the average moisture content and the variation in moisture content (maximum and minimum values) of a lot. In the converting of paper and board, moisture content is important as it can have an effect on processes such as printing and copying. Moisture content can have an effect on curl and dimensional stability.

ISO 4119 [3] should be used in laboratory procedures or is referred to in other International Standards in which the concentration of an aqueous pulp suspension requires determination.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 638-1:2020](https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[oSIST prEN ISO 638-1:2020](https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/2868a5e7-f6ef-4ced-a864-5e4032b27f57/osist-pren-iso-638-1-2020>

Paper, board, pulps and cellulosic nanomaterials — Determination of dry matter content — Oven-drying method —

Part 1: Materials in solid form

1 Scope

This document specifies an oven-drying method for the determination of the dry matter content in paper, board and pulp and cellulosic nanomaterials in solid form, which all may be produced from virgin and /or recycled materials.

It is also applicable to the determination of the dry matter content of paper and board for recycling.

The procedure is applicable to paper, board, and pulp and cellulosic nanomaterials which do not contain any appreciable quantities of materials other than water that are volatile at the temperature of $105\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$. It is used, for example, in the case of pulp, paper, and board and cellulosic nanomaterial samples taken for chemical and physical tests in the laboratory, when a concurrent determination of dry matter content is required.

This method is not applicable to the determination of the dry matter content of slush pulp or to the determination of the saleable mass of pulp lots.

Note 1 ISO 638-2 [1] specifies an oven-drying method for the determination of the dry matter content in suspensions of cellulosic nanomaterials; ISO 287 [2] specifies the determination of the moisture content of a lot of paper and board; ISO 4119 [3] specifies the determination of stock concentration of pulps; ISO 801 (all parts) [4] specifies the determination of the saleable mass in lots.

Note 2 This document determines the total dry matter content of the sample, including any dissolved solids. If only the cellulosic material content free of dissolved solids is desired, dissolved solids should be removed prior to measuring the dry matter content e.g. by washing or dialysis, taking care to retain all cellulosic material; in cases where the sample is filterable without loss of cellulosic solids, ISO 4119 [3] can be used to determine the stock consistency (content of cellulosic material in solid form).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 287:2009, *Paper and board — Determination of moisture content of a lot — Oven-drying method*

ISO 7213, *Pulps — Sampling for testing*

EN 17085, *Paper and board – Sampling procedures for paper and board for recycling*

ISO/TS 20477:2017, *Nanotechnologies — Standard terms and their definition for cellulose nanomaterial*

ISO/TS 80004-1:2015, *Nanotechnologies — Vocabulary — Part 1: Core terms*

ISO/DIS 638-1:2020(E)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 cellulosic nanomaterial CNM

material composed predominantly of cellulose, with any external dimension in the *nanoscale* (3.5), or a material having internal structure or surface structure in the nanoscale, with the internal structure or surface structure composed predominantly of cellulose

Note 1 to entry: The term nanocellulose is an alternative to cellulosic nanomaterial.

Note 2 to entry: Some cellulosic nanomaterials can be composed of chemically modified cellulose.

[SOURCE: ISO/TS 20477:2017, 3.3.1, modified]

3.2 constant mass

mass of the test piece determined at the equilibrium condition after drying until the difference between two successive dryings and weighings, separated in time by at least half the initial drying period, does not exceed 0,1 % mass fraction of the test piece before drying

3.3 dry matter content

ratio of the mass of a test piece, after drying to constant mass at a temperature of $105\text{ °C} \pm 2\text{ °C}$ under specified conditions, to its mass before drying

Note 1 to entry: to entry: The dry matter content is usually expressed as a percentage mass fraction.

3.4 moisture content

content of water in paper or board, i.e. the ratio of the loss of mass of a test piece, when dried at a temperature of $105\text{ °C} \pm 2\text{ °C}$ under specified conditions, to its mass at the time of sampling

Note 1 to entry: to entry: The moisture content is normally expressed as a percentage mass fraction.

[SOURCE: ISO 287:2009, 3.1, modified]

3.5 nanoscale

length range approximately from 1 nm to 100 nm

Note 1 to entry: Properties that are not extrapolations from larger sizes are predominately exhibited in this length range.

[SOURCE: ISO/TS 80004 1:2015, 2.1]

3.6 solid form

form in which water is held immobile within the cell wall, and/or lumen and/or interstices between the cellulosic materials, and/or is adsorbed at the cellulosic material surface, and which behaves as a discrete or separate unit that does not of itself flow (or as a set of such units)