



Designation: ~~C 1280-07~~ Designation: **C 1280 – 09**

Standard Specification for Application of Gypsum Sheathing¹

This standard is issued under the fixed designation C 1280; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the minimum requirements for and methods of application of gypsum sheathing for use as a substrate for exterior wall cladding.

1.2 Details of construction for a specific assembly to achieve the required fire resistance shall be obtained from reports of fire-resistance tests, engineering evaluations, or listings from recognized fire testing laboratories.

1.2.1 This specification shall govern where it is more stringent (size or thickness of framing and size and spacing of fasteners) than the fire-rated construction.

1.3 Where sound control is required for a gypsum sheathing assembly, the details of construction shall be in accordance with the acoustical test report of an assembly that has met the required acoustical value(s).

1.3.1 This specification shall govern where it is more stringent (size or thickness of framing and size and spacing of fasteners) than the sound-rated construction.

1.4 Where resistance to racking loads or shear is required for a gypsum sheathing assembly, the details of construction shall be in accordance with the racking or shear test report of an assembly that has met the required racking or shear value(s).

1.4.1 This specification shall govern where it is more stringent (size or thickness of framing and size and spacing of fasteners) than the racking or shear-tested construction.

~~1.5 The values stated in inch-pound units are to be regarded as the standard. The SI (metric) values given in parentheses are approximate and are provided for information purposes only.~~

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 The text of this standard references footnotes which provide explanatory material. These footnotes shall not be considered as requirements of the standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C 11 Terminology Relating to Gypsum and Related Building Materials and Systems

C 954 Specification for Steel Drill Screws for the Application of Gypsum Panel Products or Metal Plaster Bases to Steel Studs from 0.033 in. (0.84 mm) to 0.112 in. (2.84 mm) in Thickness

C 955 Specification for Load-Bearing (Transverse and Axial) Steel Studs, Runners (Tracks), and Bracing or Bridging for Screw Application of Gypsum Panel Products and Metal Plaster Bases

C 1002 Specification for Steel Self-Piercing Tapping Screws for the Application of Gypsum Panel Products or Metal Plaster Bases to Wood Studs or Steel Studs

C 1007 Specification for Installation of Load Bearing (Transverse and Axial) Steel Studs and Related Accessories

C 1063 Specification for Installation of Lathing and Furring to Receive Interior and Exterior Portland Cement-Based Plaster

C 1396/C 1396M Specification for Gypsum Board

2.2 U.S. Department of Commerce Publication:

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.03 on Specifications for the Application of Gypsum and Other Products in Assemblies.

Current edition approved Nov. 1, 2007; 2009. Published December 2007; May 2009. Originally approved in 1994. Last previous edition approved in 2004; 2007 as C 1280-04; C 1280-07.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

3. Terminology

3.1 *Definitions*: Definitions shall be in accordance with Terminology C 11.

3.2 *Definitions of Terms Specific to This Standard*:

3.2.1 *exterior cladding, n*—a permanent material or system that impedes the transmission of environmental elements to the sheathing.

3.2.2 *fastener, n*—nails, staples, or screws used for application of the sheathing.

3.2.3 *framing member, n*—studs, headers, bracing, and blocking that serve to receive the sheathing.

3.2.4 *horizontal application, n*—a synonym for *perpendicular application*.

3.2.5 *parallel application, n*—gypsum sheathing applied with the edges parallel to the framing members; a synonym for *vertical application*.

3.2.6 *perpendicular application, n*—gypsum sheathing applied with the edges at right angles to the framing members; a synonym for *horizontal application*.

3.2.7 *require, v*—to mandate by a force outside this specification, such as a building code, project specification, contract, or purchase order.

3.2.8 *specified, adj*—pertaining to a mandatory requirement of this specification or a referenced requirement.

3.2.9 *specify, v*—to mandate by an obligation of this standard or a referenced document.

3.2.10 *vertical application, n*—synonym for *parallel application*.

3.2.11 *weather resistive barrier, n*—a temporarily exposed protective membrane that is intended to impede the penetration of environmental elements until the installation of a permanent exterior cladding.

4. Exposure After Installation

4.1 Gypsum sheathing board is a substrate that shall be covered by an exterior cladding or other weather-resistive barrier and is not intended for long-term exposure. It shall not be exposed to the elements for more than 30 days after it has been installed. Gypsum sheathing shall be covered with a weather-resistive barrier within 30 days if the exposure time will be more than 30 days.

NOTE 1—Some building codes require an additional weather-resistive barrier. The exterior face paper of the sheathing shall be dry prior to application of the additional weather-resistive barrier.

5. Materials and Manufacture

5.1 *Gypsum Sheathing*— Specification C 1396/C 1396M.

5.1.1 *Type X (Special Fire-Resistant) Gypsum Sheathing*—Gypsum sheathing that provides a greater degree of fire resistance than regular gypsum sheathing as defined in Specification C 1396/C 1396M.

5.2 *Fasteners*—Fasteners shall be as described in 5.2.1 through 5.2.3. The fastener length shall be not less than that specified in Table 1.

5.2.1 *Nails*—Nails shall be not less than 12-gauge galvanized, 7/16-in. (11.1-mm) diameter head.

5.2.2 *Screws*:

5.2.2.1 Screws for fastening gypsum sheathing to wood framing members, and to steel framing members less than 0.033 in. (0.84 mm) in thickness, shall meet the requirements of Specification C 1002.

5.2.2.2 Screws for fastening gypsum sheathing to steel framing members from 0.033 to 0.112 in. (0.84 to 2.84 mm) in thickness shall meet the requirements of Specification C 954.

5.2.2.3 Trim-head screws shall not be permitted for the attachment of gypsum sheathing.

5.2.2.4 Screws for fastening self-furred metal lath over gypsum sheathing as described in 8.2.7 shall be as specified in Specification C 1063.

³ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

TABLE 1 Minimum Fastener Lengths

| Framing Type | Fastener Type | Sheathing Thickness, in. (mm) | Minimum Fastener Length, in. (mm) | |
|--------------|---------------|-------------------------------|-----------------------------------|------------|
| Wood | nails | 1/2 (12.7) | 1 1/2 (38) | |
| | | 5/8 (15.9) | 1 3/4 (45) | |
| | screws | 1/2 (12.7) | 1 1/4 (32) | |
| | | 5/8 (15.9) | 1 1/4 (32) | |
| | | staples | 1/2 (12.7) | 1 1/2 (38) |
| | | | 5/8 (15.9) | 1 3/4 (45) |
| Steel | screws | 1/2 (12.7) | 1 (25) | |
| | | 5/8 (15.9) | 1 1/4 (32) | |