



SLOVENSKI STANDARD SIST EN ISO 945-1:2019

01-oktober-2019

Nadomešča:
SIST EN ISO 945-1:2018

Mikrostruktura železove litine - 1. del: Razvrščanje grafita z vizualno analizo (ISO 945-1:2019)

Microstructure of cast irons - Part 1: Graphite classification by visual analysis (ISO 945-1:2019)

Mikrostruktur von Gusseisen - Teil 1: Graphitklassifizierung durch visuelle Auswertung (ISO 945-1:2019)

(standards.iteh.ai)

Microstructure des fontes - Partie 1: Classification du graphite par analyse visuelle (ISO 945-1:2019)

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

Ta slovenski standard je istoveten z: EN ISO 945-1:2019

ICS:

77.080.10 Železo Irons

SIST EN ISO 945-1:2019 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 945-1:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

EUROPEAN STANDARD

EN ISO 945-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2019

ICS 77.080.10

Supersedes EN ISO 945-1:2018

English Version

Microstructure of cast irons - Part 1: Graphite classification by visual analysis (ISO 945-1:2019)

Microstructure des fontes - Partie 1: Classification du
graphite par analyse visuelle (ISO 945-1:2019)

Mikrostruktur von Gusseisen - Teil 1:
Graphitklassifizierung durch visuelle Auswertung (ISO
945-1:2019)

This European Standard was approved by CEN on 18 June 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 945-1:2019
<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

European foreword

This document (EN ISO 945-1:2019) has been prepared by Technical Committee ISO/TC 25 "Cast irons and pig irons" in collaboration with Technical Committee CEN/TC 190 "Foundry technology" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2020, and conflicting national standards shall be withdrawn at the latest by January 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 945-1:2018.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 945-1:2019 has been approved by CEN as EN ISO 945-1:2019 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 945-1:2019

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

INTERNATIONAL
STANDARD

ISO
945-1

Third edition
2019-06

Microstructure of cast irons —
Part 1:
Graphite classification by visual
analysis

Microstructure des fontes —

Partie 1: Classification du graphite par analyse visuelle
iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 945-1:2019](https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019)

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>



Reference number
ISO 945-1:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 945-1:2019

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 General	1
4.1 Designation system for classifying graphite in cast irons.....	1
4.2 Form.....	2
4.3 Distribution.....	3
4.4 Size.....	4
4.5 Visual classification of graphite.....	23
5 Sampling and sample preparation	23
5.1 Samples taken from a casting.....	23
5.2 Sample preparation.....	23
6 Procedure for graphite classification	23
6.1 Procedure for visual classification of graphite.....	23
6.2 Evaluation of the analysis results.....	24
7 Reference images	24
7.1 General.....	24
7.2 Reference images for graphite form.....	24
7.3 Reference images for the distribution of graphite (form I).....	24
7.4 Reference images for graphite size.....	24
8 Designation of graphite by form, distribution and size	25
8.1 Designation system.....	25
8.2 Designation of different graphite sizes within a casting.....	25
8.3 Designation of mixed graphite forms, distributions and sizes.....	26
8.4 Designation of unclassified graphite forms.....	26
8.5 Nodule count.....	26
9 Report	27
Annex A (informative) Typical graphite forms in cast-iron materials — Examples of photomicrographs	28
Annex B (informative) Distribution of flake (lamellar) graphite (form I) — Examples of photomicrographs	29
Annex C (informative) Common terminology and main occurrences concerning graphite in cast irons	30
Bibliography	32

ISO 945-1:2019(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 25, *Cast irons and pig irons*.

This third edition cancels and replaces the second edition (ISO 945-1:2017), of which it constitutes a minor revision. The changes compared with the previous edition are as follows:

- [Figures 3](#) and [4](#) have been corrected to a diameter of 120 mm to allow a direct comparison with the microscope display screen;
- [Figures 3](#) and [4](#) have been corrected so that the maximum graphite sizes conform with [Table 1](#).

A list of all parts in the ISO 945 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Microstructure designation is a useful feature that provides a means of classifying the graphite form, distribution and size in cast irons.

Graphite classification by visual analysis is a well-established method which is well recognized within the foundry industry as a means of quickly determining the overall graphite microstructure of a cast iron casting.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 945-1:2019](https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019)

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 945-1:2019

<https://standards.iteh.ai/catalog/standards/sist/6e0113fa-e8f3-4efc-a095-0c8dbf5eda35/sist-en-iso-945-1-2019>

Microstructure of cast irons —

Part 1: Graphite classification by visual analysis

1 Scope

This document specifies a method of classifying the microstructure of graphite in cast irons by comparative visual analysis.

The purpose of this document is to provide information about the method of graphite classification. It is not intended to give information on the suitability of cast-iron types and grades for any particular application.

The particular material grades are specified mainly by mechanical properties and, in the case of austenitic and abrasion resistant cast irons, by their chemical composition. The interpretation of graphite form and size does not allow a statistically valid statement on the fulfilment of the requirements specified in the relevant material standard.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 General

4.1 Designation system for classifying graphite in cast irons

When cast iron materials are examined under a microscope in accordance with this document, the graphite shall be classified by the following:

- a) its form, designated by Roman numbers I to VI (see [Figure 1](#) and [Annex A](#));
- b) its distribution, designated by capital letters A to E (see [Figure 2](#) and [Annex B](#)); the graphite distribution designation is only specified for grey cast irons (form I);
- c) its size, designated by numbers 1 to 8 (see [Figures 3, 4](#) and [5](#) and [Table 1](#)).

NOTE [Figures 1](#) to [5](#) show only the outlines and not the structure of the graphite.