
Vroče izdelani votli konstrukcijski profili iz jekla - 3. del: Tehnični dobavni pogoji za mehansko tehnično uporabo

Hot finished steel structural hollow sections - Part 3: Technical delivery conditions for mechanical engineering purposes

Warmgefertigte Hohlprofile für den Stahlbau - Teil 3: Technische Lieferbedingungen für Anwendungen im Maschinenbau

Profils creux de construction finis à chaud en aciers - Partie 3 : Conditions techniques de livraison pour des applications de construction mécanique

Ta slovenski standard je istoveten z: prEN 10210-3

ICS:

77.140.45	Nelegirana jekla	Non-alloyed steels
77.140.75	Jeklene cevi in cevni profili za posebne namene	Steel pipes and tubes for specific use

oSIST prEN 10210-3:2019**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/9e1e9d42-4fd6-4e43-b450-e16fa3ec5d7e/osist-pren-10210-3-2019>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 10210-3

July 2019

ICS 77.140.75

English Version

Hot finished steel structural hollow sections - Part 3: Technical delivery conditions for mechanical engineering purposes

Profils creux de construction finis à chaud en aciers -
Partie 3 : Conditions techniques de livraison pour des
applications de construction mécanique

Warmgefertigte Hohlprofile für den Stahlbau - Teil 3:
Technische Lieferbedingungen für Anwendungen im
Maschinenbau

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 459/SC 3.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms, definitions and symbols	6
4 Classification and designation.....	8
5 Information to be obtained by the manufacturer	10
6 Manufacturing process.....	11
7 Requirements	12
8 Inspection	17
9 Frequency of testing and preparation of samples and test pieces	20
10 Test methods	22
11 Marking.....	24
Annex A (normative) Structural hollow sections of non-alloy quality steels — Chemical composition and mechanical properties	25
Annex B (normative) Structural hollow sections of normalized/normalized rolled steels — Chemical composition and mechanical properties.....	27
Annex C (normative) Structural hollow sections of thermomechanical formed steels — Chemical composition and mechanical properties.....	30
Annex D (normative) Structural hollow sections of quenched and tempered steels — Chemical composition and mechanical properties.....	35
Annex E (normative) Structural hollow sections of steels with improved atmospheric corrosion resistance — Chemical composition and mechanical properties	40
Annex F (normative) Location of samples and test pieces	42
Annex G (informative) Hot finished hollow section production processes, manufacturing routes and delivery conditions	44
Bibliography.....	46

European foreword

This document (prEN 10210-3:2019) has been prepared by Technical Committee CEN/TC 459 “ECISS - European Committee for Iron and Steel Standardization¹”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This standard consists of the following parts:

- EN 10210-1, Hot finished steel structural hollow sections - Part 1: Technical delivery conditions
- EN 10210-2, Hot finished steel structural hollow sections - Part 2: Tolerances, dimensions and sectional properties
- EN 10210-3, Hot finished steel structural hollow sections - Part 3: Technical delivery conditions for mechanical engineering purposes

It forms part of a series of standards on hollow sections together with EN 10219-1 to -3.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/9e1e9d42-4fd6-4e43-b450-e16fa3ec5d7e/osist-pren-10210-3-2019>

¹ Through its subcommittee SC 3 “Structural steels other than reinforcements” (secretariat: DIN)

1 Scope

This part of this European Standard specifies technical delivery conditions for hot-finished seamless, electric welded and submerged arc welded steel structural hollow sections for mechanical engineering purposes of circular, square, rectangular or elliptical forms.

It applies to hollow sections formed hot, with or without subsequent heat treatment, or formed cold with subsequent heat treatment above 580 °C to obtain equivalent mechanical properties to those obtained in the hot formed product.

NOTE 1 The requirements for tolerances, dimensions and sectional properties are specified in EN 10210-2.

NOTE 2 The attention of users is drawn to the fact that whilst cold formed grades in EN 10219-3 can have equivalent mechanical properties to hot-finished grades in EN 10210-3 the sectional properties of square and rectangular hollow sections in EN 10210-2 and EN 10219-2 are not equivalent.

NOTE 3 A range of material grades is specified in this document and the user are to select the grade most appropriate to the intended use and service conditions. The grades and mechanical properties of the finished hollow sections are generally comparable with those in EN 10025-2, EN 10025-3, EN 10025-4, EN 10025-5 and EN 10025-6.

NOTE 4 The requirements for seamless and welded steel structural hollow sections for use in offshore structures are covered in EN 10225.

NOTE 5 Spiral welded hollow sections are due to be used with caution in construction of dynamic behaviour (fatigue stress) where up to now, there is insufficient knowledge of their performance.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-1, *Welding - Recommendations for welding of metallic materials - Part 1: General guidance for arc welding*

EN 1011-2, *Welding - Recommendations for welding of metallic materials - Part 2: Arc welding of ferritic steels*

EN 10020, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system*

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10168, *Steel products - Inspection documents - List of information and description*

EN 10204, *Metallic products - Types of inspection documents*

EN 10210-2, *Hot finished structural steel hollow sections - Part 2: Tolerances, dimensions and sectional properties*

CEN/TR 10261, *Iron and steel - European standards for the determination of chemical composition*

EN 10266, *Steel tubes, fittings and structural hollow sections - Symbols and definitions of terms for use in product standards*

EN ISO 148-1, *Metallic materials - Charpy pendulum impact test - Part 1: Test method (ISO 148-1)*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 643, *Steels - Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles - Specifications and test methods (ISO 1461)*

EN ISO 4885, *Ferrous materials - Heat treatments - Vocabulary (ISO 4885)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 9606-1, *Qualification testing of welders - Fusion welding - Part 1: Steels (ISO 9606-1)*

EN ISO 9712, *Non-destructive testing - Qualification and certification of NDT personnel (ISO 9712)*

EN ISO 10893-2, *Non-destructive testing of steel tubes - Part 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2)*

EN ISO 10893-3, *Non-destructive testing of steel tubes - Part 3: Automated full peripheral flux leakage testing of seamless and welded (except submerged arc-welded) ferromagnetic steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-3)*

EN ISO 10893-6, *Non-destructive testing of steel tubes - Part 6: Radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-6)*

EN ISO 10893-7, *Non-destructive testing of steel tubes - Part 7: Digital radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-7)*

EN ISO 10893-8, *Non-destructive testing of steel tubes - Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8)*

EN ISO 10893-9, *Non-destructive testing of steel tubes - Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes (ISO 10893-9)*

EN ISO 10893-10, *Non-destructive testing of steel tubes - Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)*

prEN 10210-3:2019 (E)

EN ISO 10893-11, *Non-destructive testing of steel tubes - Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11)*

EN ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 14713-2:2009, *Zinc coatings - Guidelines and recommendations for the protection against corrosion of iron and steel in structures - Part 2: Hot dip galvanizing (ISO 14713-2)*

EN ISO 15607, *Specification and qualification of welding procedures for metallic materials - General rules (ISO 15607)*

EN ISO 15609-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 1: Arc welding (ISO 15609-1)*

EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1)*

ISO 11484, *Steel products - Employer's qualification system for non-destructive testing (NDT) personnel*

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purpose of this document the following terms and definitions apply in addition to or where different from those in EN 10020, EN 10021, EN 10266 and EN ISO 4885.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1.1

hot finished

hollow sections formed hot, with or without subsequent heat treatment, or formed cold with subsequent heat treatment above 580 °C to obtain equivalent metallurgical conditions to those obtained in the hot formed product

3.1.2

cold forming

process where the forming to final shape of the welded hollow section is carried out at ambient temperature

Note 1 to entry: Circular hollow sections produced from normalized strip with a normalized weld seam and with a cold forming ratio of $D/T \geq 20$ may be classified as hot-finished hollow sections.

3.1.3

normalizing rolling

rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after subsequent normalizing

3.1.4**thermomechanical forming**

simultaneously performed forming process and heat treatment in which the final deformation from round to rectangular/square/elliptical hollow sections is carried out in a certain temperature range above 580 °C leading to a material condition with certain properties which cannot be achieved or repeated by heat treatment alone

Note 1 to entry: Thermomechanical rolling leading to the delivery condition M can include processes with an increasing cooling rate with or without tempering including self-tempering but excluding direct quenching and quenching and tempering.

Note 2 to entry: In some publications, the word TMCP (Thermomechanical Control Process) is also used.

3.1.5**steel with improved atmospheric corrosion resistance**

steel in which a certain number of alloying elements has been added in order to increase its resistance to atmospheric corrosion, by forming an auto-protective oxide layer on the base metal under the influence of weather conditions

Note 1 to entry: Steel with improved atmospheric corrosion resistance is often called weathering steel.

Note 2 to entry: Additional information for the use of steel with improved atmospheric corrosion resistance is given in prEN 10210-2:2016, Annex E.

3.1.6**quenching and tempering**

process which consists of the following two steps:

- first quenching, where the steel is heated up above AC3 temperature and then rapidly cooled down in liquids to create a process specific grain structure;
- afterwards tempering, during which the steel is heated up to a certain temperature to adjust the desired properties and cooled down in air afterwards

3.1.7**fine grain steel**

steels with fine grain structure with an equivalent index of ferritic grain size ≥ 6

Note 1 to entry: For the determination of grain sizes except for +QT steels, see EN ISO 643.

3.1.8**hot-dip zinc coating****galvanizing**

application of a zinc coating by immersing the prepared strip or hollow section in a molten bath containing a zinc content of at least 99%

3.2 Symbols

For the purposes of this document, the symbols defined in EN 10266 apply.

4 Classification and designation

4.1 Classification

4.1.1 Within the grades of non-alloy steels given in Annex A, four qualities JR, J0, J2 and K2 are specified. These differ in respect of specified impact requirements, limits on values of various elements, with particular reference to sulphur and phosphorus, and the inspection and testing requirements.

In accordance with the classification system in EN 10020, all steel grades in Annex A are non-alloy quality steels.

4.1.2 Within the grades of steels given in Annex B, C and D seven qualities N, NL, M, ML, Q, QL and QL1 are specified. These differ in respect of the carbon, sulphur and phosphorus content, low temperature impact properties, production process, heat treatment and grain size.

In accordance with the classification system in EN 10020, steel grades S275NH, S275NLH, S355NH and S355NLH are non-alloy quality steels and all other steel grades are alloy special steels.

4.1.3 Within the grades of steels given in Annex E, three qualities J0, J2 and K2 are specified. These differ in respect of specified impact requirements and limits on values of various elements.

In accordance with the classification system in EN 10020, all steel grades in Annex E are alloy special steels.

4.2 Designation

4.2.1 For the products covered by this document the steel names are allocated in accordance with EN 10027-1; the steel numbers are allocated in accordance with EN 10027-2.

4.2.2 The designation of steel hollow sections consists of:

- a) the number of this document (EN 10210-1);
- b) the capital letter S for structural steel;
- c) the indication of the minimum specified yield strength for thicknesses ≤ 16 mm expressed in MPa;
- d) further designations for either:
 - 1) non-alloy structural steels:
 - i) the capital letters JR for the qualities with specified impact properties at room temperature;
 - ii) the characters J0 for the qualities with specified impact properties at 0 °C; and
 - iii) the characters J2 or K2 for the qualities with specified impact properties at -20 °C; or
 - 2) normalized/normalized rolled structural steels:
 - i) capital letter N to indicate normalized or normalized rolled with specified impact properties at -20 °C (see 6.5); and
 - ii) capital letter NL for qualities with specified impact properties at -50 °C; or

- 3) thermomechanical formed structural steels:
 - i) capital letter M to indicate thermomechanical rolled with specified impact properties at $-20\text{ }^{\circ}\text{C}$ (see 6.5); and
 - ii) capital letter ML for qualities with specified impact properties at $-50\text{ }^{\circ}\text{C}$; or
- 4) structural steels in the quenched and tempered condition:
 - i) capital letter Q to indicate the quenched and tempered condition with specified impact properties at $-20\text{ }^{\circ}\text{C}$ (see 6.5); and
 - ii) capital letter QL or QL1 for qualities with specified impact properties at -40 or $-50\text{ }^{\circ}\text{C}$; or
- 5) steels with improved atmospheric corrosion resistance:
 - i) the capital letters JR for the qualities with specified impact properties at room temperature;
 - ii) the characters J0 for the qualities with specified impact properties at $0\text{ }^{\circ}\text{C}$;
 - iii) the characters J2 or K2 for the qualities with specified impact properties at $-20\text{ }^{\circ}\text{C}$ and
 - iv) the letter W (weather) for improved atmospheric corrosion resistance; and
- 6) the capital letter H to indicate hollow sections.

EXAMPLE 1 Hollow section made of structural steel (S) with a specified minimum yield strength for a thickness not greater than 16 mm of 275 MPa, with a minimum impact energy value of 27 J at $0\text{ }^{\circ}\text{C}$ (J0), hollow section (H):

EN 10210-1 — S275J0H

or

EN 10210-1 — 1.0149

EXAMPLE 2 Hollow section made of structural steel (S) with a specified minimum yield strength for a thickness not greater than 16 mm of 355 MPa, normalized condition (N), with a minimum impact energy value of 27 J at $-50\text{ }^{\circ}\text{C}$ (L), hollow section (H):

EN 10210-1 — S355NLH

or

EN 10210-1 — 1.0549

5 Information to be obtained by the manufacturer

5.1 Mandatory information

The following information shall be contained in the order document at the time of enquiry and order:

- a) the quantity (mass or total length);
- b) details of the product form:
 - 1) HFCHS = hot finished circular hollow sections;
 - 2) HFRHS = hot finished square or rectangular hollow sections;
 - 3) HFEHS = hot finished elliptical hollow sections;
- c) the name of the standard for dimensions and tolerances (EN 10210-2);
- d) the dimensions and the type of length, length range or length (see EN 10210-2);
- e) the steel designation (see 4.2).

5.2 Options

A number of options are specified in parts 1 and 2 of this document. Those relevant to this part are listed below with appropriate clause references. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the hollow sections shall be supplied in accordance with the basic specification.

- 1.1 Internal weld bead trimmed (see 6.4.2);
- 1.2 Empty (Option for EN 10219)
- 1.3 Product analysis (see 7.1.1);
- 1.4 Cr, Cu, Mo, Ni, Ti and V cast analysis contents to be reported for non-alloy quality steels (see 7.1.2);
- 1.5 Tensile test in corner region (see 7.2.1);
- 1.6 Impact test in corner region (see 7.2.2).
- 1.7 Verification of impact properties for qualities JR and JO (see 7.2.3);
- 1.8 The product shall have a chemical composition suitable for hot-dip-zinc coating (see 7.3.2);
- 1.9 Weld repairs to the body of structural steel hollow sections are permitted (see 7.4.4);
- 1.10 Full peripheral NDT (non-destructive testing) of circular tubes for imperfections - not possible for elliptical, rectangular, square and SAW (submerged arc welded) hollow sections (see 7.5);
- 1.11 Ultrasonic testing for laminar imperfections (see 7.5);
- 1.12 Inspection certificate 3.1 for steel grades S235JRH, S275JOH, S355JOH of Annex A and S355J0WH of Annex E instead of a test report 2.2 (see 8.1);
- 1.13 Inspection certificate 3.2.